MS9494

FED. SUP CLASS 5306



PART NUMBER	L	K	APPROX WEIGHT LB/100
MS9494-04	.812	.105-.125	8.38
MS9494-05	.875	.105-.125	8.73
MS9494-06	.938	.105-.125	9.08
MS9494-07	1.000	.105-.125	9.43
MS9494-08	1.062	.105-.125	9.77
MS9494-09	1.125	.105-.125	10.12
MS9494-10	1.188	.105-.125	10.47
MS9494-11	1.250	.105-.125	10.81
MS9494-12	1.312	.105-.125	11.16
MS9494-13	1.375	.105-.125	11.51
MS9494-14	1.438	.125-.188	11.86
MS9494-15	1.500	.190-.250	12.20
MS9494-16	1.562	.252-.312	12.54
MS9494-17	1.625	.313-.373	12.89
MS9494-18	1.688	.375-.438	13.24
MS9494-19	1.750	.440-.500	13.59
MS9494-20	1.875	.565-.625	14.28
MS9494-21	2.000	.690-.750	14.97
MS9494-22	2.125	.815-.875	15.67
MS9494-23	2.250	.940-1.000	16.36
MS9494-24	2.375	1.065-1.125	17.05
MS9494-25	2.500	1.190-1.250	17.75
MS9494-26	2.625	1.315-1.375	18.44
MS9494-27	2.750	1.440-1.500	19.13
MS9494-28	2.875	1.565-1.625	19.83
MS9494-29	3.000	1.690-1.750	20.52
MS9494-30	3.125	1.815-1.875	21.22
MS9494-31	3.250	1.940-2.000	21.91
MS9494-32	3.375	2.065-2.125	22.60
MS9494-33	3.500	2.190-2.250	23.30
MS9494-34	3.625	2.315-2.375	23.99
MS9494-35	3.750	2.440-2.500	24.68
MS9494-36	3.875	2.565-2.625	25.38
MS9494-37	4.000	2.690-2.750	26.07
MS9494-38	4.125	2.815-2.875	26.76
MS9494-39	4.250	2.940-3.000	27.46
MS9494-40	4.375	3.065-3.125	28.16
MS9494-41	4.500	3.190-3.250	28.85
MS9494-42	4.625	3.315-3.375	29.54
MS9494-43	4.750	3.440-3.500	30.23
MS9494-44	4.875	3.565-3.625	30.92
MS9494-45	5.000	3.690-3.750	31.62
MS9494-46	5.125	3.815-3.875	32.31
MS9494-47	5.250	3.940-4.000	33.00
MS9494-48	5.375	4.065-4.125	33.70
MS9494-49	5.500	4.190-4.250	34.39
MS9494-50	5.625	4.315-4.375	35.09
MS9494-51	5.750	4.440-4.500	35.78
MS9494-52	5.875	4.565-4.625	36.47
MS9494-53	6.000	4.690-4.750	37.17
MS9494-54	1.812	.302-.362	13.93
MS9494-55	1.938	.628-.688	14.63

(A) 1. SHANK SHALL BE STRAIGHT WITHIN .002 TOTAL PER INCH OF BOLT LENGTH
2. THE CONCENTRICITY OF THREAD PD IS RELATIVE TO THE SHANK SHALL BE WITHIN .006 FIR.
3. THE CONCENTRICITY OF THE SHANK IS RELATIVE TO THE WASHER FACE DIAMETER AND HEXAGON SHALL BE WITHIN .023 FIR.
4. INCOMPLETE THREADS NOT TO ENTER FILLET.
5. MATERIAL: CORROSION AND HEAT RESISTANT STEEL AMS 5731.
6. MANUFACTURING SPECIFICATION: AMS 7477.
7. FULL-BODY CORROSION RESISTANT PASSIVATED PER AMS 2643.
(A) 8. SURFACE ROUGHNESS: USAS B46.1-1962 UNLESS OTHERWISE SPECIFIED SURFACES TO BE 125 MICROINCHES EXCEPT HEXAGON
9. SHEAR CORNER RADII .003-.015 UNLESS OTHERWISE SPECIFIED.
10. DIMENSIONS IN INCHES. UNLESS OTHERWISE SPECIFIED, TOLERANCES: LINEAR DIMENSIONS ± .010, ANGULAR DIMENSIONS ± 5°.
11. DO NOT USE UNMACHINED PART NUMBERS.

AS & AMS ARE SOCIETY OF AUTOMOTIVE ENGINEERS, INC. PUBLICATIONS.
(A) THIS STANDARD WAS DEVELOPED COOPERATIVELY WITH THE MILITARY SERVICES BY THE SAE AEROSPACE PART STANDARDS DIVISION

REVISED (A) 17 Nov 67
APPROVED 5 May 1965

P.A. Navy - AS, MC - 11 Other Cogs Army - AV, MI - AS	(A) BOLT, MACHINE - HEXAGON HEAD, FULL SHANK, AMS 5731, .500-20 UNJF-3A	MILITARY STANDARD MS9494
PROCUREMENT SPECIFICATION	SUPERSEDES.	SHEET 1 OF 1

DD FORM 672-1 (Coordinated)

PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

☆ U. S. GOVERNMENT PRINTING OFFICE: 1970-393-093/5-3734

This military standard is approved by the Department of Defense and is mandatory for all activities. Suggestions for its improvement are welcomed and should be made use of in preparing and revising the document. Review activities: Navy - AS, MC, SH, YD, Air Force - 11, 17, 99, 84. User activities: Navy - OS, SA, CG, MC, Army - AV, MI, AR, MD, Air Force - 71, 82, 85, 99.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:18Z
Check the source to verify that this is the current version before use.