MILITARY SPECIFICATION

SKIN CLOSURE, ADHESIVE, SURGICAL, POROUS

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers sterile, hypo-reactive, pre-packaged strips of microporous adhesive tape containing rayon-reinforcing filaments, suitable for use in place of skin sutures to hold a skin wound together securely, without interfering with healing of body wounds.

1.2 Classification. The skin closures covered by this specification shall be of the following sizes, as specified (see 6.2).

Size I	Skin Closure, Adhesive, Surgical, Porous 12.5 mm x 10.0 cm (1/2 in x 4 in)
Size II	Skin Closure, Adhesive, Surgical, Porous 6.0 mm x 10.0 cm (1/4 in x 4 in)
Size III	Skin Closure, Adhesive, Surgical, Porous 3.0 mm x 7.5 cm (1/8 in x 3 in)
Size IV	Skin Closure, Adhesive, Surgical, Porous 6.0 mm x 7.5 cm (1/4 in x 3 in)

2. APPLICABLE DOCUMENTS

2.1 Specifications and Standards. The following documents of the issue in effect on date of invitation for bids or requests for proposals, form a part of this specification to the extent specified herein.

FSC 6510

Source: https://assist.dla.mil -- Downloaded: 202610-21T10:05Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

Federal

PPP-B-566	Boxes, Folding, Paperboard
PPP-B-585	Box, Wood, Wirebound
PPP-B-601	Box, Wood, Cleated-plywood
PPP-B-621	Box, Wood, Nailed and Lock-corner
PPP-B-636	Boxes, Shipping, Fiberboard
PPP-B-676	Box, Set-up

Military

MIL-L-10547	Liners, Case and Sheet, Overwrap; Waterproof
MIL-S-36586	Sterilization Test Strip Set, Bacterial Spore

STANDARDS

Federal

FED-STD-147	Tape, Packaging, Adhesive and Gummed, Methods of Inspection, Sampling and Testing.

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

(Copies of specifications and standards requested by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING MATERIALS

ASTM-D-726	Resistance of Paper to Passage of Air, Test for
ASTM-D-882	Tensile Properties of Thin Plastic Sheeting, Test for
ASTM-D-1000	Pressure Sensitive Adhesive Coated Tapes Used for Electrical Insulation, Testing

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa., 19103)

UNITED STATES PHARMACOPEIAL CONVENTION PUBLICATION

Pharmacopeia of the United States

(Application for copies should be addressed to the Mack Publishing Company, Easton, Pa., 18042)

3. REQUIREMENTS

3.1 Materials.

3.1.1 Backing. The backing shall consist of a thin, translucent, non-woven rayon fabric containing rayon reinforcing filaments with a high inherent porosity.

3.1.2 Pressure sensitive adhesive. The pressure sensitive adhesive shall be a pure, single component, acrylate type. The adhesive shall contain no rubber, and shall not "ball-up", become opaque or insoluble, or lose its adhesiveness when tested as specified in 4.4.4.

3.1.3 Facing Material. The facing material shall be a smooth, uniform film, paper or other material capable of protecting the adhesive and of resisting breaking, cracking, or tearing when the skin closures are removed. The facing material shall be at least four mils thick. It shall be chemically inert to the adhesive. The facing material shall be cut into rectangular cards as specified in 3.2.2.

3.1.4 Envelope. Each envelope for skin closures shall be made of two rectangular sheets of impervious film such as polyethylene or polyester coated with ethyl vinyl acetate. The films shall be joined to each other by a heat seal which completely surrounds the cards of skin closures and maintains sterility of the contents. Envelopes shall be easily peeled open by hand. Approximate size of the envelope shall be as shown in Table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

Table I. Envelope size

Skin closure size	Film thickness (min.)	Envelope size
I	.05 mm (1.8 mils)	8.3 cm x 17.1 cm (3-1/4 in x 6-3/4 in)
II	.05 mm (1.8 mils)	8.3 cm x 17.1 cm (3-1/4 in x 6-3/4 in)
III	.05 mm (1.8 mils)	5.4 cm x 13.3 cm (2-1/8 in x 5-1/4 in)
IV	.05 mm (1.8 mils)	5.4 cm x 13.3 cm (2-1/8 in x 5-1/4 in)

3.2 Construction.

3.2.1 Skin closures. The skin closures shall be made of the backing specified in 3.1.1 and the adhesive specified in 3.1.2, which is applied to form a coating on one side of the backing. The adhesive coating shall be continuously visible, but the skin closure shall exhibit a porosity as required in 3.2.1.1. The skin closures shall be full width throughout their length and shall be free from any extraneous material covering any portion of the adhesive surface. The skin closure shall be tested in accordance with 4.4.6.

3.2.1.1 Physical properties. The skin closures shall comply with the requirements listed in table II, when tested in accordance with section 4.

Table II. Physical properties

Property	Minimum	Maximum
Adhesion to steel, ounces per 2.54 cm (1 in) of width.	12.0	30.0
Porosity, seconds per 100 cc air.	--	500
Solvent resistance, minutes.	7.0	--
Breaking strength, dry, pounds per inch	10.0	50.0
Thickness, inches.	0.0030	
Ultimate elongation, percent.	5	30

3.2.2 Facing material. The facing material specified in 3.1.3 shall be cleanly cut into rectangular cards with dimensions as specified for each size in 3.2.4. Each rectangular card shall be perforated at least 6.4 mm (1/4 inch) from each end to permit easy removal of a piece of facing material, exposing the ends of all the skin closures on that card.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

3.2.3 Assembly. A number of skin closures as specified in 3.2.4 shall be attached to the specified size card with a visible space between.

3.2.4 Dimensions and number. Dimensions of the skin closures, cards, and the number of skin closures per card shall be as shown in table III.

Table III. Dimensions

Skin closure size	No. skin closures per envelope	Dimensions of skin closure		Overall dimensions of card*	
		Width	Length	Width	Length
I	6	12.5 mm ± 0.8 mm (1/2 in ± 1/32 in)	10.0 cm ± 5.0 mm (4 in ± 3/16 in)	5.0 cm ± 5.0 mm (2 in ± 3/16 in)	10.0 cm ± 5.0 mm (4 in ± 3/16 in)
II	10	6.0 mm ± 0.8 mm (1/4 in ± 1/32 in	10.0 cm ± 5.0 mm (4 in ± 3/16 in)	5.0 cm ± 5.0 mm (2 in ± 3/16 in)	10.0 cm ± 5.0 mm (4 in ± 3/16 in)
III	5	3.2 mm ± 0.8 mm (1/8 in ± 1/32 in)	7.5 cm ± 5.0 mm (3 in ± 3/16 in)	3.2 cm ± 5.0 mm (1-1/4 in ± 3/16 in)	7.5 cm ± 5.0 mm (3 in ± 3/16 in)
IV	3	6.0 mm ± 0.8 mm (1/4 in ± 1/32 in)	7.5 cm ± 5.0 mm (3 in ± 3/16 in)	3.2 cm ± 5.0 mm (1-1/4 in ± 3/16 in)	7.5 cm ± 5.0 mm (3 in ± 3/16 in)

* Skin closures shall not extend beyond the card in any direction.

3.2.5 Envelope. Completed card(s) with skin closures as stated in Table III shall be sealed in an envelope in accordance with 3.1.4.

3.2.6 Sterilization. Sterilization shall be accomplished by the ethylene oxide method to render the skin closures sterile in the envelope. The skin closures shall be sterile when tested with a biological indicator in accordance with 4.4.5.

Source: https://assist.dla.mil -- Downloaded: 20261O-21T10:05Z
Check the source to verify that this is the current version before use.

3.2.6.1 Certificate of sterility. A certificate of sterility stating that samples from each sterilizer lot have been tested and found to be sterile, shall be submitted to the procuring activity. The certificate of sterility shall include:

a. Item identification.
b. National stock number.
c. Contract or purchase order number.
d. Sterility lot or control number.
e. Date of sterilization.
f. Quantity of product in sterilizer lot.
g. Type of sterilization (gas).
h. Form of biological indicator (i.e., inoculated paper spore strip or carrier, inoculated product, or inoculated simulated product).
i. Test organism(s) and population density used.
j. Test medium, incubation temperature, incubation time, and dates of tests.
k. Number of test units.
l. Statement that samples comply with sterility tests.
m. Signature of head of laboratory or a designated qualified alternate.

When inspection is made at destination, the certificate of sterility shall be submitted by the contractor to the Directorate of Medical Materiel, ATTN: DPSC-ATQ, Defense Personnel Support Center, 2800 South 20th Street, Philadelphia, PA, 19101, and a copy forwarded with each shipment to the consignee. When inspection is made at source, certificate of sterility shall be furnished to the cognizant Government Quality Assurance Representative for submission to the procuring activity.

3.2.6.2 Sterility lot. A sterility lot is that single quantity of product subjected to the same manufacturing operation and simultaneously sterilized in the same sterilizer chamber. Each unit package shall be clearly marked with a sterility lot (control) number and date of sterilization as specified in 5.3.1. Each sterility lot shall be traceable to the pertinent manufacturing lot(s).

3.3 Identification marking. One side of each sub-unit package envelope shall be marked to permit ready identification of the size; shall bear the legend "STERILE", the name or registered trademark of the manufacturer, and other requirements of statute. The legend "Sterility Guaranteed Unless Package is Damaged or Opened", shall also be included.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

3.4 Workmanship. Workmanship shall be first class throughout. The skin closures shall conform to the quality of product established by this specification. The occurrence of defects shall not exceed the limits set by the applicable acceptable quality levels. The skin closures shall be free from defects which detract from their appearance or may impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality, supplied by the manufacturer of the components and material, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the NSN, the item identification, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Quality conformance inspection. The examinations and tests required to assure conformance of those items or lots of items to be offered for acceptance are classified as specified in tables V and VI (see 4.2.1 and 4.2.2).

4.2.1 Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels shall be as indicated in table IV. Unit of product for examination purposes shall be the envelope.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

Table IV. Sampling for examination

For visual examination	Inspection level	AQL (Percent defective)
Major defects	S-3	1.0
Minor defects	S-3	4.0

4.2.1.1 Classification of defects. Examination shall be conducted in accordance with the classification of defects specified in table V.

Table V. Categories and defects

Major	
101	Backing material of skin closure not non-woven fabric.
102	Number or size of skin closures incorrect.
103	Skin closures not full width along entire length.
104	No perforated tab at both ends of card.
105	Adhesive area does not cover entire surface of one side.
106	Visible non-adhesive material is adhered to adhesive side.
107	Dirty, not clean appearance.
108	Holes or non-sealed area in envelopes.
109	Reinforcing filaments are not adhered firmly to the skin closure backing.
Minor	
201	Skin closures touch each other on the cards.
202	Any holes or tears in card.
203	Card edges not straight.
204	Marking of envelope incomplete, incorrect, or difficult to read.

Examination shall not be restricted to the classified possible defects listed.

4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and table VI. The unit of product for test purposes shall be the envelope.

4.3 Examination.

4.3.1 Skin closure. The skin closure shall be examined to determine compliance with all requirements contained in this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

4.3.2 Examination of preparation for delivery. An examination shall be made to determine whether the packaging, packing, and marking comply with the requirements of Section 5. Defects shall be scored as specified in table VII. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The Inspection Level shall be S-2 and the acceptable quality level shall be 4.0 defects per hundred units.

Table VII. Examination of preparation for delivery

Examination	Defect
Containers	Not as specified.
Quantity	Quantity in interior packages and shipping containers not as specified.
Packaging and packing materials	Any component missing or damaged.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, tape improperly applied, or containers distorted.
Markings	Omitted, incorrect, illegible, improper size, location, sequence, or method of application.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements. Where possible, the same sample unit shall be used for the determination of two or more tests.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

4.4.1 Components. Skin closure components shall be tested as specified in table VI.

Table VI. Component testing

Component (unit of product)	Characteristic	Requirement	Test procedure	Inspection level	AQL
Adhesive	Component	3.1.2	4.4.4	(2)	(3)
Card	Dimension	3.2.4	(1)	S-2	(3)
	Perforation	3.2.2	(1)	S-2	(3)
Skin closure	Dimension	3.2.4	(1)	S-2	(3)
	Adhesion	3.2.1.1	4.4.2.2	S-2	(3)
	Breaking strength	3.2.1.1	4.4.2.4	S-2	(3)
	Elongation	3.2.1.1	4.4.2.4	S-2	(3)
	Thickness	3.2.1.1	4.4.2.1	S-2	(3)
	Removal from Card	3.2.1.1	4.4.6	S-2	(3)
	Porosity	3.2.1.1	4.4.2.3	S-2	(3)
	Solvent Resistance	3.2.1.1	4.4.3	(2)	(3)
	Sterility	3.2.6 and 3.2.7	4.4.5	(See 4.4.5)	(3)
Sub-unit package	Opening	3.1.4	4.4.7	S-2	(3)

(1) Use scale graduated in 1/32 inch.
(2) Run once per shipment.
(3) Acceptance number shall be zero for all sample sizes.

The samples selected for test shall be removed from their envelopes and conditioned for not less than 24 hours at $73^{\circ} \pm 3.5^{\circ}$ F. and 50 ± 2 percent relative humidity, and shall be tested under these conditions.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

4.4.2 Test methods. The following tests shall be conducted in accordance with the method designated.

4.4.2.1 Thickness. Thickness shall be determined in accordance with Fed. Std. No. 147, Method 36, except make one reading off of each skin closure in the sample package. Report the average of these readings.

4.4.2.2 Adhesion to Steel. Adhesion shall be determined in accordance with Fed. Std. No. 147, Method 10 or ASTM-D-1000 with the following exceptions:

a. Because of the dimensions of the product being tested, specimens are prepared as follows:

(1) Multiple skin closure strips are used for each test as follows:

Size	Skin closure strip size	Quantity
I	12.5 mm (1/2 in)	2
II and IV	6.0 mm (1/4 in)	3
III	3.2 mm (1/8 in)	5

Test one set of multiple skin closure strips for each sample required.

(2) The ends of the multiple strips of test tape nearest the perforation on the facing card shall be taped together with a one inch wide piece of (other suitable) tape. Add an extension of this same tape to provide an extending piece about seven inches in length. The test strips shall be carefully applied to the steel panel, parallel to each other, and the extending tape strip placed in the upper jaw of the test machine.

4.4.2.3 Porosity. Test samples after removal from the facing material. Porosity shall be determined in accordance with ASTM-D-726, Method A, with the following exceptions:

a. Equipment: Adapter plate with two parallel orifices 1/16 inch by 3/4 inch each, and a suitable gasket to insure no leakage between the adapter plate and the upper jaw of the porosity testing apparatus.

b. Apply skin closures, one 12.5 mm (1/2 in), two 6.0 mm (1/4 in), or two 3.2 mm (1/8 in), as applicable, over the orifices.

Source: https://assist.dla.mil -- Downloaded: 202640-21T10:05Z
Check the source to verify that this is the currentversion before use.

c. Use firm, but careful finger pressure to adhere skin closure to plate. (Inspect to insure there is a complete bond on all edges, but that the skin closure is not damaged. If either situation occurs, remove and apply new skin closure.)

d. Insert adapter plate in porosity testing apparatus with the samples up (adhesive down). Tighten porosity testing apparatus clamps firmly with fingers.

e. Time in seconds is the time necessary for transmission of 100 cc of air through the sample.

f. Run two tests per sample and report the average of the two tests.

4.4.2.4 Breaking strength and Elongation. Breaking strength and elongation shall be determined in accordance with Fed. Std. No. 147, Method 30 or ASTM-D-882 Method A using a 1 inch jaw separation and 2 inches per minute cross head speed or ASTM-D-882 Method B using a 1 inch jaw separation at 12 inches per minute with the following exceptions:

a. Multiple skin closure strips are used for each test as follows:

Size	Skin closure strip size	Quantity
I	12.5 mm (1/2 in)	2
II and IV	6.0 mm (1/4 in)	3
III	3.2 mm (1/8 in)	5

Test one set of multiple skin closure strips for each sample required.

b. Tape both ends of the multiple strips so they remain parallel and can be handled.

4.4.3 Solvent resistance.

4.4.3.1 Specimen. Three specimens approximately 7.5 cm (3 in) to 10.0 cm (4 in) long and 12.5 mm ± 0.8 mm (1/2 in + 1/32 in) wide shall be utilized. When testing the 6.0 mm (1/4 in) or 3.2 mm (1/8 in) wide skin closures, each specimen shall consist of two 6.0 mm (1/4 in) wide strips side by side or four 3.2 mm (1/8 in) wide strips side by side to obtain the 12.5 mm (1/2 in) test width.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

4.4.3.2 Apparatus. A stainless steel plate, approximately 3.2 mm (1/8 in) by 2.54 cm (1 in) by 3.5 cm (1-25/64 in), weighing 23 ± 0.5 gm, polished to No. 4 finish shall be utilized. The stainless steel shall be No. 302 or No. 304 AISI designation. Plate may be procured from the Pressure-Sensitive Tape Council, Glenview, Ill.

4.4.3.3 Procedure. At the midpoint of the 3.5 cm (1-25/64 in) side of the plate, adhere 2.54 cm (1 in) of the length of the specimen to the plate with firm finger pressure. The specimen should be at right angles to the 3.5 cm (1-25/64 in) side. Fill a suitable container to a depth of at least 6.4 cm (2-1/2 in) with commercial grade isopropyl alcohol. Suspend the prepared specimen in the alcohol so that the plate is completely immersed, but not touching the bottom of the container. Start a stopwatch at the instant of immersion and stop it when the plate falls to the bottom of the container. Record the average time of three specimens in minutes.

4.4.4 Synthetic adhesive. The method for determining the synthetic non-rubber adhesive shall be as follows: Remove the adhesive from approximately four to six square inches of skin closures with toluene. Dry off the toluene. Divide the adhesive into small portions and add to a beaker containing 50 ml of M.E.K. (methyl ethyl ketone). Heat carefully to boiling on a hot plate in a hood. Caution is essential as both toluene and M.E.K. are highly flammable solvents. The synthetic adhesive will become semi-solid and the mixture will remain water white. A rubber adhesive will "ball-up", become opaque, and not visibly dissolve. After boiling for fifteen minutes, the solic or semi-solid adhesive is removed and dried. A rubber adhesive will be a non-pressure sensitive ball or rubber. The synthetic adhesive will dry to its pressure sensitive form.

4.4.5 Sterility test. The skin closures shall be tested for sterility in accordance with the method specified in the USP for Purified Cotton, Gauze, Surgical Dressings and related material using inoculated product, inoculated simulated product, or paper spore strip (carrier). Product containing a biological indicator shall be marked or labeled so that it clearly differentiates from product intended for distribution. The incubation medium and minimum time in each case shall be soybean casein digest for 7 days for inoculated product, inoculated simulated product, or paper spore strip (carrier). The incubation temperature shall be as indicated in paragraph 4.4.5.1. The minimum number of test units, regardless of lot size, shall be 10, except for inoculated carrier which shall be 30 for Type II Sterilization including inoculated carrier and product test units. From each sterilizer charge, one sub-unit package shall be taken from each of 20 sample unit boxes for sterility testing (sampling).

Source: https://assist.dla.mil -- Downloaded: 202640-21T10:05Z
Check the source to verify that this is the current version before use.

4.4.5.1 Inoculated product or simulated product. For each type of sterilization, the organism used shall be as listed below:

Type of Sterilization	Organism	Incubation Temperature
Gas	B. subtilis var. niger (or globigii)	30° - 35° C

The number of viable cells shall be sufficient to provide assurance that the product has been sterilized.

4.4.5.2 Inoculated carrier. Inoculated carriers (paper spore strips) if used shall be in accordance with MIL-S-36586 except that Bacillus stearothermophilus shall not be used. Other paper carriers shall be inoculated to be of equivalent resistance. The method of incubation and number of test units shall be as indicated in 4.4.5 Sterility test and 4.4.5.1 Inoculated product or simulated product. The method of sterilization will control the organism in the spore strip to be tested for as shown in 4.4.5.1. When an inoculated carrier is chosen, product samples must also be tested as required by the USP.

4.4.5.3 Alternate method. Suppliers conducting sterility tests or designating lots in a manner other than that indicated herein shall submit proof that the alternate method provides equal assurance concerning the sterility of the product. Requests for approval of any alternate method of testing for sterility shall be made to the Contracting Officer, and approval obtained before employment of the alternate method on a government contract.

4.4.5.4 Product testing. Testing for sterility of the product after receipt by the government shall be without a biological indicator and in accordance with the U.S.P.

4.4.6 Removal of the skin closure from the liner. Each skin closure shall be removed by hand, following the manufacturer's instructions. Visual examination shall reveal no delamination of the facing card and no adhesive remaining on the facing card. The skin closure shall comply with 3.2.1.

4.4.7 Package opening. The envelope shall be opened carefully according to the manufacturer's instructions. Tearing of the package, making aseptic removal of the contents impossible, is a reject.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Unit of issue. One box, containing 300, 500, 250 or 150 skin closures as specified in 3.2.4, constitutes one unit of issue.

5.1.1.1 Level A.

5.1.1.1.1 Unit package. Each unit of issue shall be packaged in a box of appropriate size and design. Closure shall be adequate to prevent accidental opening.

5.1.1.1.2 Intermediate package. Four (4) units of issue shall be packaged in a box of appropriate size and design constructed in accordance with PPP-B-566, PPP-B-636, type CF, class domestic or PPP-B-676. Closure shall be adequate to prevent accidental opening.

5.1.2 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the prodct for its intended purpose.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A. Forty eight (48) units of issue of size 1 or size 2, or ninety six (96) units of issue of size 3 or size 4 shall be packed in a box designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, type CF, class weather resistant. Closure and strapping shall be as specified in the appendix of the applicable box specification.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes. Fiberboard box shall be waterproof in accordance with the appendix of PPP-B-636.

5.2.2 Level B. Forty eight (48) units of issue of size 1 or size 2, or ninety six (96) units of issue of size 2 or size 4 shall be packed in a box designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, type CF, class domestic. Closure shall be as specified in the appendix of the applicable box specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Unit package. Each unit package shall be marked in acccordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number, lot control number, and name and address of contractor shall be shown. In addition, information required by the Federal Food, Drug, and Cosmetic Act shall also be shown. In addition, each unit package shall be marked with the method of sterilization (G-Gas, R-Radiation). Marking shall follow the Level of packaging and date of packaging. Example: "A-1/74-G". Final sterilization shall be on or after indicated packaging date.

5.3.2 Intermediate package. Each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Lot (control) number, contract or purchase order number and name of contractor shall be shown. The method of sterilization shall be shown as specified in 5.3.1.

5.3.3 Exterior containers. Exterior container shall be marked in accordance with MIL-STD-129. Lot (control) number shall be shown. The method of sterilization shall be shown as specified in 5.3.1.

6. NOTES

6.1 Intended use. The skin closure covered by this specification is intended to be used in place of skin sutures to hold a skin wound together securely without interfering with healing of the wound margins.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).
(c) Marking requirements (see 5.3).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

6.3 This specification is intended to cover the following items listed in the Federal Supply Catalog:

NSN	Item Identification
6510-00-054-7254	Skin Closure, Adhesive, Surgical, Porous, 12.5 mm x 10.0 cm (1/2 in x 4 in), 300s
6510-00-054-7255	Skin Closure, Adhesive, Surgical, Porous, 6.0 mm x 10.0 cm (1/4 in x 4 in), 500s
6510-00-054-7256	Skin Closure, Adhesive, Surgical, Porous, 3.2 mm x 7.5 cm (1/8 in x 3 in), 250s
6510-00-913-5874	Skin Closure, Adhesive, Surgical, Porous, 6.0 mm x 7.5 cm (1/4 in x 3 in), 150s

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 6510-0602
cs

☆U.S. GOVERNMENT PRINTING OFFICE: 1975-603-757/7

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 4966 WASHINGTON D. C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC-LS
2800 South 20th Street
Philadelphia, PA 19101

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T10:05Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil/online/start/ - 2021T10:05Z
Check the source to verify that this is the current version before use.