A-A-54421
28 June 1991

COMMERCIAL ITEM DESCRIPTION

SKIN CLOSURE, ADHESIVE, SURGICAL, (POROUS)

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Military Specification MIL-S-37164 which is cancelled.

Salient Characteristics:

Shall be sterile, hypo-reactive, pre-packaged strips of micro-porous adhesive tape suitable for use in place of skin sutures to hold a skin wound together securely without interfering with healing of the wound margins. Skin closures shall be sterile when tested in accordance with the USP. The skin closure shall be on a card and the skin closures shall be easily removable from the card. Skin closures shall not extend beyond the card in any direction.

Skin closure shall be of the following sizes and of the following quantities of skin closures in one immediate container (envelope).

SIZE	SKIN CLOSURE WIDTH ± 1/32 (INCH)	SKIN CLOSURE LENGTH ± 3/16 (INCHES)	QUANTITY OF SKIN CLOSURES PER ENVELOPE
1	1/2	4	6
2	1/4	4	10
3	1/8	3	5
4	1/4	3	3

The adhesive and backing shall be joined in such a manner that the skin closures shall have a porosity on a microscopic level. The backing shall be micro-porous, thin, translucent and shall have a high inherent porosity. The backing shall be one of the following:

a. Nonwoven rayon fabric containing either rayon or polyester reinforcing filaments united with an acrylate resin.

AMSC\NA FSC 6510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

b. Expanded network-like polyproplene film.
c. Nonwoven nylon fabric.

The adhesive shall be pressure sensitive, shall be on one side of the skin closures and shall be continuously visible. The adhesive shall be a pure, single component acrylate or acrylic copolymer and shall be hypo-reactive.

The facing material (card) shall be smooth and shall be capable of protecting the adhesive and shall resist breaking, cracking or tearing when the skin closures are removed. The facing material shall have a minimum thickness of four mils and shall be chemically inert to the adhesive. The facing material shall be in the form of rectangular cards. Each rectangular card shall be clean cut and each card shall be perforated at least 1/4 inch from each end to permit easy removal of the skin closures by exposing the ends of all skin closures on each card. There shall be visible spaces between the skin closures on each card.

The skin closures shall comply with the following requirements.:

PROPERTY	MINIMUM	MAXIMUM	TEST METHOD
Adhesion to steel (ounces per inch of width) or as an alternate to steel	6	70	ASTM-D-1000 1/
Adhesion to aluminum (ounces per inch of width)	32	96	ASTM-D-1000 1/
Porosity (seconds per 100 cc of air)	--	500	ASTM-D-726 2/ Method A
Breaking strength, dry (pounds per inch of width)	10	50	ASTM-D-882 Method A 3/ or Method B 4/
Thickness (inch)	0.0030	--	Fed Std No 147 Method 36
Ultimate elongation (percent)	5	100	ASTM-D-882 Method A 3/ or Method B 4/

1/ Multiple skin closures, parallel to each other, shall be used to make up the one inch width.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

2/ Testing shall be performed using the following equipment: adapter plate with two parallel orifices 1/16 by 3/4 inch each and a suitable gasket to insure no leakage. Cover each orifice with a skin closure. Inspect to insure there is a complete bond on all edges and inspect to insure that the skin closures are not damaged. Insert adapter plate in porosity testing apparatus with skin closures up (adhesive down). Tighten porosity testing apparatus firmly. The time in seconds is the time necessary for transmission of 100 cc of air through the sample.

3/ Multiple skin closures, parallel to each other, shall be used to make up the one inch width. Jaw separation 1 inch using a cross head speed of 2 inches per minute.

4/ Multiple skin closures, parallel to each other, shall be used to make up the one inch width. Jaw separation 1 inch using a cross head speed of 12 inches per minute.

For all of the property tests above, skin closures shall be removed from their envelopes and conditioned for at least 24 hours at $73\pm3.5^{\circ}F$ and at 50 ± 2 percent relative humidity and shall be tested under these conditions.

The skin closures shall remain adhered to skin after the skin is wet and skin closures shall be clean and clean-cut.

Manufacturer's instructions for the opening of the immediate container (envelope) and for the use of skin closures shall be supplied in each unit container.

Workmanship. The skin closures and their facing (cards) shall be free from defects which detract from their appearance or impair their serviceability.

Unit. Package (PG).

For Size 1, shall be supplied 6 skin closures on an easily removed backing packaged in a sealed peel-open envelope capable of maintaining sterility of contents unless package is damaged or opened. One package containing 50 sealed envelopes (300 skin closures), as specified, constitutes one unit.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

For Size 2, shall be supplied 10 skin closures on an easily removed backing packaged in a sealed peel-open envelope capable of maintaining sterility of contents unless package is damaged or opened. One package containing 50 sealed envelopes (500 skin closures), as specified, constitutes one unit.

For Size 3, shall be supplied 5 skin closures on an easily removed backing packaged in a sealed peel-open envelope capable of maintaining sterility of contents unless package is damaged or opened. One package containing 50 sealed envelopes (250 skin closure), as specified, constitutes one unit.

For Size 4, shall be supplied 3 skin closures on an easily removed backing packaged in a sealed peel-open envelope capable of maintaining sterility of contents unless packaged is damaged or opened. One package containing 50 sealed envelopes (150 skin closures), as specified, constitutes one unit.

Quality Assurance Provisions

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as specified herein. Unit of product for examination purposes shall be one skin closure. Sampling shall be Inspection level II with an acceptable quality level (AQL) of 2.5 (percent defective).

Examination. Examination shall be conducted to determine compliance with specification requirements.

Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and as specified herein. Unit of product for test purposes shall be one skin closure. Sampling shall be Inspection level S-1 with an AQL of 2.5 (percent defective).

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric Products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerance specified using conversion tables contained in the latest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerance specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

NOTE: The following National Stock Numbers are covered by this document:

NSN	ITEM IDENTIFICATION	SIZE
6510-00-054-7254	SKIN CLOSURE, ADHESIVE, SURGICAL, POROUS, 1/2 by 4 Inches, 300s	1
6510-00-054-7255	SKIN CLOSURE, ADHESIVE, SURGICAL, POROUS, 1/4 by 4 Inches, 500s	2
6510-00-054-7256	SKIN CLOSURE, ADHESIVE, SURGICAL, POROUS, 1/8 by 3 Inches, 250s	3
6510-00-913-5874	SKIN CLOSURE, ADHESIVE, SURGICAL, POROUS, 1/4 by 3 Inches, 150s	4

Ordering data. Inspection/Test dating period, intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

document

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

PREPARING ACTIVITY:
DoD - MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITY:

VA-OSS
PHS
FDA-MPQAS

PGC 05194

Project No. 6510-0793

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:33Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER	2. DOCUMENT DATE (YYMMDD)
	A-A-54421	28 JUNE 1991

3. DOCUMENT TITLE

4. NATURE OF CHANGE (Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial	(2) AUTOVON
Defense Personnel Support Center	(215)737-2870	444-2870
c. ADDRESS (Include Zip Code) ATTN: DPSC-MSE 2800 S. 20th Street Philadelphia, PA 19101	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340	

Source: https://assist.dla.mil -- Downloaded: 2026-02-26T09:33Z
Check the source to verify that this is the current version before use.