MIL-G-17927(NAVY)
AMENDMENT - 1
12 April 1956

MILITARY SPECIFICATION

GASKETS, ASBESTOS-METALLIC COVER, RUBBER CORE

This amendment forms a part of Military Specification MIL-G-17927(NAVY), 29 April 1955, and has been concurred in by all interested bureaus of the Department of the Navy.

Page 1, paragraph 2.1: Delete the reference to Federal Specification ZZ-R-601, and under "NAVY DEPARTMENT" delete the reference to Appendix I.

Page 1, paragraph 2.1: Under "STANDARDS" add:

"FEDERAL
"Fed. Test Method Std. No. 601 - Rubber: Sampling and Testing."

Page 2, paragraph 2.2: Delete the reference to the "American Society for Testing Materials" publication and all matter in regard thereto.

Page 5, paragraph 4.4.1, line 2: Delete "the Direct Determination of Rubber Hydrocarbon of ASTM Method D-297-43T" and substitute "Method 16121 of Test Method Standard No. 601."

Page 6, paragraph 4.4.4, lines 2 and 3: Delete "Specification ZZ-R-601" and substitute "Method 14011 of Test Method Standard No. 601."

Page 6, paragraphs 4.5.1, 4.5.2, and 4.5.3: Delete and substitute:

"4.5.1 Tensile strength, elongation tests. - Methods of tests and test specimens for tensile strength and elongation shall be as specified in Methods 4111 and 4121 of Test Method Standard No. 601.

"4.5.2 Hardness test. - The hardness shall be determined using a plunger of 3.2 millimeter diameter and Method 3051 of Test Method Standard No. 601. Samples of material less than 1/4 inch thick shall be superimposed to a thickness of not less than 1/4 inch nor greater than 1/2 inch before making the hardness determination.

"4.5.3 Delamination tests. - The delamination test shall be in accordance with Method 6311 of Test Method Standard No. 601. A sample of strip rubber, 3 inches long, of the width and thickness furnished for delivery, shall be completely immersed in benzol of the following characteristics:

Specific gravity at 60°F.	0.875 to 0.886
Distillation limits:	
Initial boiling point	168 to 172°F.
95 percent evaporated	174°F. (max.)
Dry	176°F. (max.)
Recovery	98 percent (min.)

After removal from the benzol the strip shall be examined to determine evidence of separation into distinct layers or laminations by attempting to separate the laminations by hand."

Custodian:
Bureau of Ships
Other interest:
Navy - Or

FED. SUP. CLASS
5330

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:46Z
Check the source to verify that this is the current version before use.