MIL-B-43550A(GL)
13 September 1979
SUPERSEDING
MIL-B-43550(GL)
23 October 1967

MILITARY SPECIFICATION

BAG, WATER REPELLENT, SIGNAL EQUIPMENT; BG-102

This specification is approved for use by the US Army Natick Research and Development Command, Department of the Army, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a bag fabricated from heavy weight cotton duck with leather reinforced corners. The bag is provided with inside pockets and an adjustable carrying strap.

2. APPLICABLE DOCUMENTS

* 2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

V-F-106	-	Fasteners, Slide, Interlocking.
V-T-285	-	Thread, Polyester.
FF-R-556	-	Rivets, Solid, Small; Rivets, Split, Small; Rivets, Tubular, Small; and Caps, Rivets; General Purpose.
KK-L-271	-	Leather, Cattlehide, Strap, Vegetable-Tanned.
UU-P-268	-	Paper, Kraft, Untreated, Wrapping.
CCC-C-419	-	Cloth, Duck, Cotton, Unbleached, Plied-Yarns, Army and Numbered.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: US Army Natick Research and Development Command, Natick, MA 01760, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 8465

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:41Z
Check the source to verify that this is the current version before use.

CCC-D-950	-	Dyeing and Aftertreating Processes for Cotton Cloths.
DDD-L-20	-	Label: For Clothing, Equipage and Tentage (General Use).
PPP-B-601	-	Box, Wood, Cleated-Plywood.
PPP-B-636	-	Boxes, Shipping, Fiberboard.

MILITARY

MIL-F-495	-	Finish, Chemical, Black, for Copper Alloy.
MIL-C-496	-	Clips, End, Strap.
MIL-W-530	-	Webbing Textile, Cotton, General Purpose, Natural or in Colors.
MIL-B-543	-	Buckles, Tongueless and Web Strap.
MIL-L-3851	-	Loops, Slide (For Equipage).
MIL-W-43061	-	Wax, Machine Stitching.
MIL-T-43566	-	Tape, Textile, Cotton, General Purpose, Natural or in Colors.

FEDERAL

FED-STD-751	-	Stitches, Seams and Stitchings.

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	-	Marking for Shipment and Storage.
MIL-STD-1188	-	Commercial Packaging of Supplies and Equipment.

DRAWINGS

US ARMY NATICK RESEARCH AND DEVELOPMENT COMMAND

2-3-77	-	Bag, Waterproof, Signal Equipment, BG-102, Illustration, Assembly and Sections.
2-3-78	-	Bag, Waterproof, Signal Equipment; BG-102; Details.

(Copies of specifications, standards and drawings required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:41Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

* 3.1 First article. When specified (see 6.2), the contractor shall furnish a sample for first article inspection and approval (see 4.3 and 6.3).

3.2 Materials and components (see 6.4).

3.2.1 Cloth, duck, cotton. Cloth shall conform to type I, No. 4 hard texture of CCC-C-419 and shall be processed in accordance with type I, class B of CCC-D-950. The color shall be olive drab No. 7.

* 3.2.2 Tape, textile, cotton. Tape shall conform to type I, class 4, 1 inch (25 mm) width of MIL-T-43566, dyed to match olive drab shade No. 7.

3.2.3 Webbing, textile, cotton. Webbing shall conform to type III, class 4, 1 inch (25 mm) and 2 inch (51 mm) widths of MIL-W-530, dyed to match olive drab shade No. 7.

3.2.4 Thread, polyester. Thread shall conform to type I, class 1, subclass B of V-T-285 and shall be dyed to match shade S-1 (Cable No. 66022). The dyed thread shall show fastness to chlorine bleaching equal to or better than the standard sample. If no standard sample is available, the thread shall show good fastness to chlorine bleaching. Thread sizes shall be as follows:

For all stitching except bartacking and stitching on the leather corner reinforcements and leather front pocket reinforcement.	Size FF for needle and bobbin
For bartacking	Size E
For stitching on leather corner reinforcements and leather front pocket reinforcement.	Size 3

3.2.5 Leather. Leather shall be strap leather, 4/64 and 6/64 (plus 1/64 inch or minus 0) (2 mm and 2.3 mm (plus .5 mm or minus 0) thick, russet in color conforming to type I, II or III, class 1, of MK-L-271. No top finish required.

3.2.6 Wax, stitching. Machine stitching wax shall be golden in color, and shall conform to type II of MIL-W-43061.

3.2.7 Buckles, tongueless. Buckles shall conform to type I, style 2, (configuration "A") class 1, size 1 inch (25 mm) of MIL-B-543.

3.2.8 Loops, slide. Slide loops shall conform to class 1, style 2, size 2 inch (51 mm) (construction B) of MIL-L-3851.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:41Z
Check the source to verify that this is the current version before use.

3.2.9 Clips, end. End clips shall conform to type I, class 1 or 2, size 1 inch (25 mm) of MIL-C-496.

3.2.10 Fasteners, slide, interlocking. Slide fasteners shall conform to type I, style 6, single long tab pull of V-F-106. Slide fastener chain shall be fabricated of brass or aluminum. The slide fastener tape shall be dyed to match olive drab shade S (Cable No. 66519), and water repellent and mildew-resistant treated. The color of the tape after treatment will be considered acceptable. The dyed tape shall show good fastness to weathering.

3.2.11 Rivets, tubular with caps. The tubular rivets shall conform to type XII, class 1, grade F, 9/64 inch (4 mm) nominal diameter, 5/16 inch (8 mm) nominal shank of FF-R-556. Caps required for grade F rivets shall conform to type II of FF-R-556. Rivets and caps shall have a black chemical finish in accordance with MIL-F-495.

3.3 Construction. The construction shall conform to the drawings listed in section 2 and as specified herein.

3.3.1 Stitching, machine.

3.3.1.1 Type of stitching. Stitch types, except bartacking, shall conform to FED-STD-751 as follows:

For all stitching except on the leather corner reinforcements, leather front pocket reinforcement and bartacking	-Type 301, 6 to 8 stitches per inch (2-1/2 to 3 stitches/cm)
For stitching on leather corner reinforcements and leather front pocket reinforcement.	-Type 301, 5 to 7 stitches per inch (2 - 3 stitches/cm)
For bartacking	-Bartack, 5/8 inch (16 mm) long with 1/8 inch (3 mm) bight and shall contain 43 stitches

3.3.1.2 Thread breaks. Thread breaks in type 301 stitching shall be overstitched not less than 1 inch (25 mm) at each break. Bartacks shall be free of thread breaks.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:41Z
Check the source to verify that this is the current version before use.

1. Waive any portion of the referenced document(s) or to amend contractual requirements

3.3.1.3 Stitching ends. The ends of type 301 stitching shall be overstitched not less than 1 inch (25 mm), except where ends are turned under in a hem or held down by other stitching. Where stitching is performed automatically, stitch patterns such as box, box with cross-stitch, 3 or more tying, overlapping or backstitches shall be used to secure the ends.

3.3.1.4 Stitching leather. Stitching of the leather shall be performed on a machine capable of using hot stitching wax specified in 3.2.6. The use of a cold liquid wax or prewaxed thread shall not be permitted. All thread ends shall be securely tied and trimmed.

3.3.1.5 Skipped stitches. Two or more consecutively skipped stitches occurring in type 301 stitching shall be overstitched not less than 1 inch (25 mm).

* 3.3.1.6 Thread lubricant. The addition of any lubricant to the polyester thread prior to or during the sewing operation is prohibited.

3.3.2 Attachment of slide fasteners. Care shall be taken to trim all thread ends and maintain specified distances between the edges of fabric attached to the slide fastener tape so that there will be no interference with the operation of the slider. The length of the slide fastener shall be such that after the slide fastener is sewed on, the tape shall not be puckered and the slider shall operate freely.

3.3.3 Setting of end clips. The webbing shall be inserted the full depth of the clips. The clips shall be securely attached without cutting the webbing and the webbing shall lie flat at the point of entrance.

3.3.4 Setting of tubular rivets. Holes shall be formed by rivets when driven into the material and not punched prior to insertion. Rivets shall be securely clinched.

3.4 Marking. All marking shall conform to DOD-L-20.

3.4.1 Special marking. The letters 'US' and the nomenclature shall conform to type IV, class 9 and shall be printed or stenciled in size characters and in the locations shown on Drawing 2-3-78.

3.4.2 Identification marking. Identification marking shall conform to type IV, class 5 in the location shown on Drawing 2-3-78.

* 3.5 Workmanship. Cloth components shall be clear and free of holes, cuts, tears or cloth defects such as multiple floats or broken or missing yarns. Webbing and tape shall not have frayed or scalloped edges. Thread tension shall be maintained so that there will be no loose or tight stitching. Seam allowances shall be maintained with seams secured so that no runoffs, twists, pleats or open seams shall result. Care shall be taken to see that there shall be no skipped stitches or that no needle chews occur. All thread ends shall be trimmed to 1/2 inch (13 mm) or less in length. Leather components shall be clean and free of holes, brand marks, open or healed grubs, open scratches, deep wrinkles or broken grain. Soft, stretchy or spongy leather will not be acceptable. Metal components shall be free of burrs, sharp edges or corroded areas and shall not be broken or malformed.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:41Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.2 Classification of inspection. The inspection requirements specified herein are classified as follows:

1. First article inspection (see 4.3).
2. Quality conformance inspection (see 4.4).

* 4.3 First article inspection. When a first article is required (see 6.2), the bag shall be examined as specified in 4.4.3.1 and 4.4.3.2. The presence of any defect, any dimension not within specified limits or failure of any test shall be cause for rejection of the first article.

* 4.4 Quality conformance inspection. Except as otherwise specified herein, sampling shall be performed in accordance with MIL-STD-105.

4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced specifications, drawings, and standards unless otherwise excluded, amended, modified, or qualified in this specification or applicable purchase document.

4.4.2 In-process inspection. Inspection shall be made to determine that there shall be no lubrication of polyester thread prior to or during sewing operations for compliance with 3.3.1.6 and that holes punched to receive rivets are in compliance with 3.3.4. Whenever nonconformance is noted, correction shall be made to the items affected and the process.

4.4.3 End item examination. The lot shall consist of all completely fabricated bags offered for inspection at one time. The sample unit shall be one completely fabricated bag. The inspection level and acceptable quality levels (AQLs) shall be in accordance with 4.4.3.3.

4.4.3.1 Visual examination. Visual examination shall be made of the completed bag for the defects in table I.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:41Z
Check the source to verify that this is the current version before use.

TABLE I. Classification of defects for visual characteristics

Examine	Defect	Classification Major	Minor A	Minor B
Fabric	Cut, tear or hole	X		
	Broken or missing yarns, multiple floats clearly visible at normal inspection distance (approximately 3 feet (1 m)		X	
Webbing and tape	Edge frayed or scalloped			X
Leather	Open grub hole, brand mark, open scratch, deep wrinkle; broken grain		X	
Hardware	Burr or sharp edge which may cause injury in handling or damage to fabric	X		
	Broken	X		
	Corroded area		X	
	Malformed:			
	-fails to perform intended function	X		
	-but will perform intended function		X	
Seams and stitching	Open seam:			
	-1/2 inch (13 mm) or less			X
	-more than 1/2 inch (13 mm), but not more than 1 inch (25 mm)		X	
	-more than 1 inch (25 mm)	X		
	Run-offs (see open seams)			
	Note: A seam shall be classified as open when one or more stitches joining a seam are broken or when two or more consecutive skipped or run-off stitches occur and are not overstitched.			
	Thread breaks overstitched less than 1 inch (25 mm)			X
	Needle chews resulting in cut, tear or hole (see Cut, tear or hole)			
	Skipped stitches overstitched less than 1 inch (25 mm)			X

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:41Z
Check the source to verify that this is the current version before use.

TABLE I. Classification of defects for visual characteristics (cont'd)

Examine		Defect	Classification Major	Minor A	Minor B
Seams and stitching (cont'd)	Note:	Skipped stitches not overstitched shall be classified as open seams.			
		Mends or darns	X		
Seam type		Wrong seam type	X		
Stitch type		Wrong stitch type	X		
Stitch tension		Loose, resulting in an exposed bobbin or top thread, for more than 6 inches (152 mm)			X
		Tight, as evidenced by puckering on seams, for more than 6 inches (152 mm)			X
Stitches per inch		Less than minimum specified:			
		-one stitch			X
		-two or more stitches		X	
		More than maximum specified:			
		-one stitch			X
		-two or more stitches		X	
	Note:	Variation in the number of stitches per inch, caused by the operator speeding up the machine and pulling the fabric in order to sew over heavy places or heavy seams or in turning corners, shall be classified as follows:			
		a. Within the minor "B" defect classification - no defect			
		b. Within the minor "A" defect classification - minor "B" defect			

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:41Z
Check the source to verify that this is the currentversion before use.

TABLE I. Classification of defects for visual characteristics (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Seams and stitching (cont'd)				
Stitching margin	Larger than specified by more than 3/16 inch (5 mm): -less than 4 inches (102 mm) in length			X
	-4 inches (102 mm) or more in length		X	
Stitching	Overstitched less than 1 inch (25 mm) (except where ends are held down by other stitching, turned under in a hem or where stitching is performed automatically)			X
	Secured with less than three tying overlapping or backstitches when automatic stitching is performed			X
Boxstitching	Incomplete: -one end row of stitching omitted		X	
	-two end rows of stitching omitted	X		
	-any other row of stitching omitted	X		
Components and assembly	Any component part not fabricated of applicable referenced material	X		
	Any component missing	X		
Construction details				
Rivets and caps	Not securely clinched so that they may become disengaged from body, or clinched excessively tight, cutting material	X		
End clips	Improperly clinched; i.e., webbing not flat at point of insertion of clip			X
	Clinched excessively tight, cutting webbing		X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:41Z
Check the source to verify that this is the current version before use.

TABLE I. Classification of defects for visual characteristics (cont'd)

Examine	Defect	Classification Major	Minor A	Minor B
Construction details (cont'd)				
Reinforcements	Improperly applied, causing excessive fullness on reinforcement or reinforced part			X
Slide fastener	Slider jams or fails to interlock chain	X		
	Any tape improperly assembled, causing failure of chain to effect a smooth and secure closure	X		
Handle	Not constructed as specified	X		
Binding	Improperly or loosely applied			X
Marking	Omitted, incorrect, illegible, misplaced or size characters not as specified			X
Cleanness	Grease or oil stains, thread ends not trimmed to 1/2 inch (13 mm) or less throughout			X

4.4.3.2 Dimensional examination. Dimensional examination shall be made of the completely fabricated bag. Any dimension not within the specified tolerances shall be classified as a defect.

4.4.3.3 Inspection levels and AQLs. The inspection levels and AQLs, expressed in terms of defects per 100 units, shall be as follows:

Examination	Inspection level	AQLs
For defects applicable to table I	II	6.5 Major 15.0 Major and minor A defects combined 25.0 Total; major, minor A and B defects combined
For defects applicable to 4.4.3.2	S-3	4.0 (One class)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:41Z
Check the source to verify that this is the current version before use.

* 4.4.4 Packaging inspection. An examination shall be made to determine that preservation, packing and marking comply with section 5 requirements. Defects shall be scored in accordance with table II. The sample unit shall be one shipping container fully packaged with the exception that it need not be closed. Examination for closure defects shall be made on fully packaged shipping containers. The lot shall be the number of shipping containers offered for inspection at one time. The inspection level shall be S-2 with an AQL of 2.5, expressed in terms of defects per 100 units.

TABLE II. Packaging inspection

Examine	Defect
Marking	Omitted; incorrect; illegible, of improper size, location, sequence or method of application
Materials	Any component missing or damaged
Workmanship	Bulged or distorted container Inadequate application of components such as incomplete closure of flaps
Content	Not covered on top and bottom with kraft paper Weight per container more than specified

5. PACKAGING

* 5.1 Preservation. Preservation shall be level A or Commercial as specified (see 6.2).

5.1.1 Level A. Each bag shall be placed in its natural position with the cover strapped shut. The sides and ends shall be pushed inward and the bag pressed downward to its smallest dimension in height. The strap shall be folded and placed on top of the cover, and the bag then tied at each end with cotton tape or twine. The dimensions of the flattened bag shall be approximately 16 inches (406 mm) long by 10 inches (254 mm) by 4 inches)102 mm) deep.

* 5.1.2 Commercial. Bags shall be preserved in accordance with MIL-STD-1188.

* 5.2 Packing. Packing shall be level A, B or Commercial as specified (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 20260-21T21:41Z
Check the source to verify that this is the current version before use.

* 5.2.1 Level A packing. Ten bags, preserved as specified in 5.1, shall be packed on edge 5 by 2 by 1, in a close-fitting fiberboard shipping container conforming to grade V2s, style RSC of PPP-B-636. Multiple quantities exceeding ten bags, preserved as specified in 5.1, shall be packed in a close-fitting plywood box conforming to overseas type, style A of PPP-B-601. Box and skids (when applicable) shall be fabricated in accordance with the load type and gross weight requirements of the plywood box specification. Each fiberboard shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced as specified in the appendix of PPP-B-636.

* 5.2.2 Level B packing. Ten bags, preserved as specified in 5.1, shall be packed on edge 5 by 2 by 1, in a close-fitting fiberboard shipping container conforming to type CF (variety SW) or SF, class domestic, grade 275, style RSC of PPP-B-636. Each container shall have the contents completely covered on the top and bottom with 30-pound minimum basis weight (49 g/m^2) kraft paper conforming to type I, grade B of UU-P-263. Each container shall be closed in accordance with method II as specified in the appendix of PPP-B-636.

5.2.2.1 Weather-resistant containers. When specified (see 6.2), the shipping containers shall be a grade V3c, V3s or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636.

* 5.2.3 Commercial packing. Bags, preserved as specified in 5.1, shall be packed in accordance with MIL-STD-1188.

* 5.3 Marking. In addition to any special marking required by the contract, shipments shall be marked in accordance with the requirements of MIL-STD-129 or MIL-STD-1188, as applicable.

6. NOTES

6.1 Intended use. The bag covered by this specification is used for carrying accessories and hardware of radio sets, antennas, et cetera.

* 6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) When a first article is required (see 3.1, 4.3 and 6.3).
(c) Selection of applicable levels of preservation and packing (see 5.1 and 5.2).
(d) When weather-resistant containers are required for level B shipments (see 5.2.2.1).

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:41Z
Check the source to verify that this is the current version before use.

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of ASPR 7-104.22. The first article should be a preproduction sample. The first article should consist of one finished bag. The contracting officer should include specific instructions in all procurement instruments regarding arrangements for inspection and approval of the first article.

* 6.4 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of the specification (see 3.2).

6.5 Metric equivalents. Metric equivalents, indicated in parentheses throughout this document, are based on practices, conversion factors, and symbols specified in ASTM E 380 Standard for Metric Practice, and are for information only. In each instance, the value stated in US customary units shall be controlling.

6.6 Changes from previous issue. The margins of this specification are marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL

Preparing activity:

Army - GL

Project No. 5820-A720

☆ U.S. GOVERNMENT PRINTING OFFICE: 1979-603-022/3901

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:41Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Natick Research and Development
Laboratories
ATTN: DRDNA-ES (Mr. D. Luppino)
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:41Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:41Z
Check the source to verify that this is the current version before use.