MIL-B-43587C
16 January 1987
SUPERSEDING
MIL-B-43587B
31 May 1978

MILITARY SPECIFICATION

BAGS, CHEMICAL PROTECTIVE CLOTHING OUTFIT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This document covers four types of polyethylene bags for enclosing of chemical protective clothing.

1.2 Classification. The bags shall be of the following types as specified (see 6.2).

Type I	-	For clothing outfit
Type II	-	For glove and sock set
Type III	-	For clothing outfit (Navy)
Type IV	-	For shirt and trouser liners set

2. APPLICABLE DOCUMENTS

* 2.1 Government documents.

2.1.1 Documents. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents shall be those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: U.S. Army Natick Research, Development, and Engineering Center, Natick, MA 01760-5014, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8465

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

A-A-203	-	Paper, Kraft, Untreated
L-P-378	-	Plastic Sheet and Strip, Thin Gauge, Polyolefin
DDD-L-20	-	Label: For Clothing, Equipage, and Tentage (General Use)
PPP-B-636	-	Boxes, Shipping, Fiberboard

MILITARY

MIL-L-35078	-	Loads, Unit: Preparation of Semiperishable Subsistence Items; Clothing, Personal Equipment and Equipage; General Specification for

STANDARDS

FEDERAL

FED-STD-595	-	Colors

MILITARY

MIL-STD-105	-	Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-129	-	Marking for Shipment and Storage
MIL-STD-147	-	Palletized Unit Loads
MIL-STD-731	-	Quality of Wood Members for Containers and Pallets

DRAWINGS

U.S. ARMY NATICK RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER

8-2-204	-	Bag, Chemical Protective Clothing

(Copies of documents required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting officer.)

* 2.2 Other publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DOD adopted shall be those listed in the issue of the DODISS specified in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS shall be the issues of the nongovernment documents which are current on the date of the solicitation.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D 882 - Tensile Properties of Thin Plastic Sheeting
D 3951 - Standard Practice for Commercial Packaging

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

(Technical society and technical association documents are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

* 2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document shall take precedence. Nothing in this document however, shall supersede applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

* 3.1 First article. When specified in the contract or purchase order, a sample shall be subjected to first article inspection (see 4.3, 6.2, and 6.3).

3.2 Materials. (see 6.4).

* 3.2.1 Film. The film used in fabricating all bags shall be polyethylene conforming to type I, class 1, grade B, finish 2 of L-P-378 and shall be 0.0080 inch thick. The color of the film shall approximate color 24087 of FED-STD-595.

3.3 Design and construction. The design of all bags shall be as illustrated in Drawing 8-2-204. Bags shall be constructed from the polyethylene film specified in 3.2.1 and sealed on the two sides. One end of the bag shall be fitted with an interlocking reclosable closure which shall be heat sealed to the bag. Excess material beyond the seals shall be trimmed evenly and shall not exceed 1/4 inch. Access to the reclosable closure shall be by a readily torn membrane strip running parallel to the upper edge of the reclosable closure. The membrane strip shall be identified by a red or black stripe. For details of the closure, see Drawing 8-2-204. The bottom edge of the bag shall be left open to permit insertion of the chemical protective clothing. The seals shall be continuous along the entire length of the sides of the bag, and along the entire length of the interlocking reclosable closure.

3.4 Label. Each bag shall be labeled in accordance with type IV, class 3, of DDD-L-20 except that all printing shall be in capitals and the legend shall be as specified in 3.3.4. The label shall be clearly legible after being subjected to the ink adhesion test in 4.5.1. The label shall be positioned as shown in Drawing 8-2-204.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

3.4.1 Legend.

3.4.1.1 Type I. Each bag shall be marked on the outer surface with the following legend:

CLOTHING OUTFIT, CHEMICAL PROTECTIVE, SIZE _____NSN_____

CONSISTING OF:

1. SET LINERS, SHIRT AND TROUSERS, CHEMICAL PROTECTIVE

3. PAIR SOCKS, CUSHION SOLE, CHEMICAL PROTECTIVE

1. PAIR GLOVES, COTTON, CHEMICAL PROTECTIVE

INSTRUCTIONS FOR USE

ITEMS CONTAINED IN THIS PACKAGE HAVE BEEN IMPREGNATED AND ARE READY FOR WEAR

1. CHECK GARMENT FOR PROPER FIT. TRADE ITEMS AS REQUIRED.

2. IMPREGNATED SOCKS ARE WORN WITH FOLLOWING FIELD FOOTWEAR:

   a. LEATHER COMBAT BOOTS WITH PROTECTIVE TREATMENT ARE USED IN HOT WEATHER AREAS.

   b. INSULATED BOOTS ARE USED IN COLD WEATHER AREAS.

3. THE THREE PAIRS OF SOCKS ARE PROTECTIVE FOR 3 CONTINUOUS DAYS STARTING WITH FIRST DAY OF WEAR. AT END OF THIS PERIOD, SOCKS ARE TO BE REIMPREGNATED BY SAME METHODS USED FOR LINER. REIMPREGNATION OF THREE PAIRS OF SOCKS PROVIDES AN ADDITIONAL 3 DAYS CONTINUOUS PROTECTION.

4. SHIRT AND TROUSER LINERS ARE PROTECTIVE FOR 7 CONTINUOUS DAYS STARTING WITH FIRST DAY OF WEAR. AT THE END OF THIS PERIOD, LINERS MUST BE REIMPREGNATED BY MOBILE LAUNDRY METHOD OR BY USE OF M-13 KIT. THE MOBILE LAUNDRY METHOD PROVIDES AN ADDITIONAL 7 DAYS CONTINUOUS PROTECTION. REIMPREGNATION BY M-13 KIT PROVIDES AN ADDITIONAL 3 DAYS CONTINUOUS PROTECTION.

5. GLOVES ARE PROTECTIVE FOR 3 CONTINUOUS DAYS STARTING WITH FIRST DAY OF WEAR. AT END OF THIS PERIOD, GLOVES ARE TO BE REIMPREGNATED BY SAME METHODS USED FOR THE LINER. REIMPREGNATION PROVIDES AN ADDITIONAL 3 DAYS CONTINUOUS PROTECTION.

6. THIS PACKAGE WITH CHEMICAL PROTECTIVE CLOTHING SHOULD NOT BE EXPOSED TO DIRECT SUNLIGHT FOR EXTENDED PERIODS OF TIME.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

7. TO OPEN BAG INITIALLY, TEAR TOP OF CLOSURE OFF BAG ALONG TOP OR OUTER EDGE AT THE RED OR BLACK LINE. THE BAG MAY THEN BE OPENED BY PULLING THE TWO PLASTIC LIPS APART. THE BAG CAN BE RECLOSED FOR FURTHER USAGE BY PRESSING THE TWO INTERLOCKING LIPS FIRMLY TOGETHER ALONG ENTIRE TOP EDGE OF BAG.

3.4.1.2 Type II. Each bag shall be marked on the outer surface with the following legend:

GLOVES AND SOCKS SET, CHEMICAL PROTECTIVE, SIZE_____NSN_____

CONSISTING OF:

3 PAIR SOCKS, CUSHION SOLE, CHEMICAL PROTECTIVE

1 PAIR GLOVES, COTTON, CHEMICAL PROTECTIVE

PURPOSE:

THE ITEMS IN THIS KIT ARE FOR WEAR WITH THE SUIT, CHEMICAL PROTECTIVE AND CLOTHING OUTFIT, CHEMICAL PROTECTIVE

INSTRUCTION FOR USE:

ITEMS CONTAINED IN THIS KIT HAVE BEEN IMPREGNATED AND ARE READY FOR WEAR

1. CHECK FOR PROPER FIT. TRADE ITEMS AS REQUIRED.

2. THE GLOVES ARE PROTECTIVE FOR 3 CONTINUOUS DAYS STARTING WITH FIRST DAY OF WEAR. AT THE END OF THIS PERIOD THEY ARE TO BE REIMPREGNATED BY MOBILE LAUNDRY METHOD OR BY USE OF M-13 KIT. REIMPREGNATION PROVIDES AN ADDITIONAL 3 DAYS CONTINUOUS PROTECTION.

3. IMPREGNATED SOCKS ARE WORN WITH THE FOLLOWING FOOTWEAR:

   a. LEATHER COMBAT BOOTS WITH PROTECTIVE TREATMENT ARE USED IN HOT WEATHER AREAS.

   b. INSULATED BOOTS ARE USED IN COLD WEATHER AREAS.

4. THE THREE PAIRS OF SOCKS ARE PROTECTIVE FOR 3 CONTINUOUS DAYS STARTING WITH FIRST DAY OF WEAR. AT THE END OF THIS PERIOD, SOCKS ARE TO BE IMPREGNATED IN THE SAME MANNER AS THE GLOVES. REIMPREGNATION OF THREE PAIRS OF SOCKS PROVIDES AN ADDITIONAL 3 DAYS OF CONTINUOUS PROTECTION.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

5. THIS PACKAGE WITH CHEMICAL PROTECTIVE CLOTHING SHOULD NOT BE EXPOSED TO DIRECT SUNLIGHT FOR EXTENDED PERIODS OF TIME.

6. TO OPEN BAG INITIALLY, TEAR TOP OF CLOSURE OFF BAG ALONG TOP OR OUTER EDGE AT THE RED OR BLACK LINE. THE BAG MAY THEN BE OPENED BY PULLING THE TWO PLASTIC LIPS APART. THE BAG CAN BE RECLOSED FOR FURTHER USAGE BY PRESSING THE TWO INTERLOCKING LIPS FIRMLY TOGETHER ALONG ENTIRE TOP EDGE OF BAG.

3.4.1.3 Type III (for Navy application only). Each bag shall be marked on the outer surface with the following legend:

CLOTHING, OUTFIT, CHEMICAL PROTECTIVE, SIZE_____NSN_____

CONSISTING OF:

1 SET LINERS, SHIRT AND TROUSERS, CHEMICAL PROTECTIVE

1 PAIR SOCKS, CUSHION SOLE, CHEMICAL PROTECTIVE

1 PAIR GLOVES, COTTON, CHEMICAL PROTECTIVE

1 HOOD, CHEMICAL AGENT PROTECTIVE (FOR USE WITH NAVY MARK V GAS MASK)

INSTRUCTIONS FOR USE

ITEMS CONTAINED IN THIS PACKAGE HAVE BEEN IMPREGNATED AND ARE READY FOR WEAR

1. CHECK GARMENT FOR PROPER FIT. TRADE ITEMS IF REQUIRED.

2. THIS PACKAGE WITH CHEMICAL PROTECTIVE CLOTHING SHOULD NOT BE EXPOSED TO DIRECT SUNLIGHT FOR EXTENDED PERIODS OF TIME.

3. TO OPEN BAG INITIALLY, TEAR TOP OF CLOSURE OFF BAG ALONG TOP OR OUTER EDGE AT THE RED OR BLACK LINE. THE BAG MAY THEN BE OPENED BY PULLING THE TWO PLASTIC LIPS APART. THE BAG CAN BE RECLOSED FOR FURTHER USAGE BY PRESSING THE TWO INTERLOCKING LIPS FIRMLY TOGETHER ALONG ENTIRE TOP EDGE OF BAG.

3.3.1.4 Type IV. Each bag shall be marked on the outer surface the the following legend:

SHIRT AND TROUSER SET, CHEMICAL PROTECTIVE, SIZE_____NSN_____

CONSISTING OF:

1 SET LINERS, SHIRT AND TROUSERS, CHEMICAL PROTECTIVE, SIZE_____NSN_____

Source: https://assist.dla.mil -- Downloaded: 20261O-21T21:46Z
Check the source to verify that this is the current version before use.

[illegible] and shall conform to type IV [illegible] the location shown

INSTRUCTIONS FOR USE

ITEMS CONTAINED IN THIS PACKAGE HAVE BEEN IMPREGNATED AND ARE READY FOR WEAR

1. CHECK SHIRT AND TROUSER LINERS FOR PROPER FIT.

   TRADE ITEMS AS REQUIRED.

2. THESE SHIRT AND TROUSER LINERS ARE PROTECTIVE FOR 7 CONTINUOUS DAYS STARTING WITH FIRST DAY OF WEAR. AT THE END OF THIS PERIOD, SHIRT AND TROUSERS MUST BE REIMPREGNATED BY MOBILE LAUNDRY METHOD OR BY USE OF M-13 KIT. THE MOBILE LAUNDRY METHOD PROVIDES AN ADDITIONAL 7 DAYS CONTINUOUS PROTECTION. REIMPREGNATION BY M-13 KIT PROVIDES AN ADDITIONAL 3 DAYS CONTINUOUS PROTECTION.

3. THIS PACKAGE WITH CHEMICAL PROTECTIVE CLOTHING SHOULD NOT BE EXPOSED TO DIRECT SUNLIGHT FOR EXTENDED PERIODS OF TIME.

4. TO OPEN BAG INITIALLY, TEAR TOP OF CLOSURE OFF BAG ALONG TOP OR OUTER EDGE AT THE RED OR BLACK LINE. THE BAG MAY THEN BE OPENED BY PULLING THE TWO PLASTIC LIPS APART. THE BAG CAN BE RECLOSED FOR FURTHER USAGE BY PRESSING THE TWO INTERLOCKING LIPS FIRMLY TOGETHER ALONG ENTIRE TOP EDGE OF BAG.

5. WEAR SHIRT AND TROUSER LINERS WITH THE SEPARATE ISSUE GLOVE AND SOCK SET CHEMICAL PROTECTIVE OR WITH THE SEPARATE ISSUE GLOVE SET CHEMICAL PROTECTIVE AND FOOTWEAR COVERS CHEMICAL PROTECTIVE (OVERBOOT).

3.5 Dimensions. All dimensions and tolerances for all types of bags shall be as shown in Drawing 8-2-204.

3.6 Performance.

3.6.1 Seam strength. The breaking strength of the seams shall be not less than 60 percent of the breaking strength of the film when tested as specified in 4.5.2.

3.6.2 Closure strength and seam continuity. The closure for the bag shall not break, tear, or otherwise become unsuitable for the intended use when tested as specified in 4.5.3. The seams shall be continuous along the entire length of the sides of the bag and along the entire length of the interlocking reclosable closure and can be verified by observing whether any leakage occurs when tested as specified in 4.5.3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

* 3.7 Workmanship. The finished bag shall be clean and free from gels, streaks, holes, cracks, blisters, fish eyes, scratches, mottling, particles of foreign matter, and undispersed raw material. Raw edges shall be free of nicks and cuts. The finished bag shall conform to the quality of product established by this document. The occurrence of defects shall not exceed the applicable acceptable quality levels.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this document where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items must meet all requirements of sections 3 and 5. The inspections set forth in this document shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the document shall not relieve the contractor of the responsibility of assuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling in quality conformance does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to acceptance of defective material.

4.1.2 Dimensional requirements. Unless otherwise specified in the contract or purchase order, the contractor is responsible for assuring that all specified dimensions have been met. When dimensions cannot be examined on the end item, inspection shall be made at any point, or at all points, in the manufacturing process necessary to assure compliance with all dimensional requirements.

4.1.3 Certificate of compliance. When certificates of compliance are submitted, the Government reserves the right to check test such items to determine the validity of the certification.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).
b. Quality conformance inspection (see 4.4)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

* 4.3 First article inspection. When a first article is required (see 6.2), it shall be examined for the defects specified in 4.4.2 and 4.4.3. The presence of any defect shall be cause for rejection of the first article.

* 4.4 Quality conformance inspection. Unless otherwise specified, sampling for inspection shall be performed in accordance with MIL-STD-105.

* 4.4.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected in accordance with all the requirements of referenced documents unless otherwise excluded, amended, modified, or qualified in this document or applicable purchase document.

4.4.2 End item visual examination. The end item shall be examined for the defects listed below. The lot size shall be expressed in units of bags. The sample unit shall be one bag. The inspection level shall be I and the acceptable quality level (AQL), expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Material (polyethylene film)	Not approximately color 24087 Not uniform in color, texture, and finish Any gel, streak, hole, crack, blister, fish eye, scratch, fold, undispersed raw material, or mottling Cut, tear, or break Any foreign matter Dirty
Label	Label incomplete, illegible, omitted incorrect, or not proper size Label improperly located
Construction and workmanship	Varies from specified design and construction Closure and heat seal not as shown on Drawing 8-2-204 Any open seam Any pinholes Heat seal seam puckered or distorted Poor heat seal resulting in inadequate fusion Heat seal seam misplaced, out of alignment or not on a straight plane by more than 1/4 inch Excess material not trimmed evenly

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:46Z
Check the source to verify that this is the current version before use.

Examine	Defect
Construction and workmanship (cont'd)	Bag badly creased Any nick or cut in raw edge Interlocking lips of closure cannot be firmly pressed together to close the bag

4.4.3 Dimensional examination. The end item shall be examined for defects in dimensions. Any measurement not in accordance with specified dimensions and tolerances shown in Drawing 8-2-204 shall be scored as a defect. The lot size shall be expressed in units of bags. The sample unit shall be one bag. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 1.5.

4.4.4 End item testing. Each lot of the end item shall be tested for ink adhesion of labels, seam strength, and closure strength in accordance with the test methods specified in 4.5.1, 4.5.2 and 4.5.3. The lot size shall be expressed in units of one completely fabricated bag. The sample unit shall be three bags. Inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 1.5. Each unit shall be tested for all characteristics and each test is applicable to the individual unit. Any failure to meet the test requirements in 3.4, 3.6.1 and 3.6.2 shall be classified as a defect. All test reports shall contain the individual values utilized in expressing the final result.

* 4.4.5 Packaging examination. The fully packaged end items shall be examined for defects listed below. The lot size shall be expressed in units of shipping containers. The sample unit shall be one shipping container fully packaged. The inspection level shall be S-2 and the AQL, expressed in terms of defects per hundred units, shall be 2.5.

Examine	Defect
Markings	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as incomplete closure of container flap, loose strapping, improper taping, or inadequate stapling. Bulged or distorted container.
Content	Kraft paper slip sheet missing or not as specified. Number of bags per container is more or less than required.

Source: https://assist.dla.mil -- Downloaded: 202610-21T21:46Z
Check the source to verify that this is the current version before use.

4.4.6 Palletization examination. The fully packaged and palletized end items shall be examined for the defects listed below. The lot size shall be expressed in units of palletized unit loads. The sample unit shall be one palletized unit load fully packaged. The inspection level shall be S-1 and the AQL, expressed in terms of defects per hundred units, shall be 6.5.

Examine	Defect
Finished dimensions	Length, width, or height exceeds specified maximum requirement.
Palletization	Pallet pattern not as specified. Interlocking of loads not as specified. Load not bonded with required straps as specified.
Weight	Exceeds maximum load limits.
Marking	Omitted; incorrect; illegible; of improper size, location, sequence, or method of application.

* 4.5 Methods of inspection. Unless otherwise specified, test conditions shall be as specified in ASTM D 882.

4.5.1 Ink adhesion (label). The ink adhesion shall be determined according to the procedure in the ink adhesion test of L-P-378, except that the test shall be performed on the label of a finished bag and one determination shall be made per sample unit. The tested area of the label shall then be visually examined for legibility.

* 4.5.2 Seam strength. Strength of the heat sealed seams shall be determined in accordance with ASTM D 882. The specimen shall be 1 inch in width and shall be cut from a finished bag with the seam across the short dimension and equidistant from the ends. The gage marks need not be applied and the elongation need not be measured. The initial separation between grips of the apparatus shall be 2 inches and the specimen shall be placed in grips with the seam equidistant between the grips. The strength of the seams, measured to the nearest 0.1 pound, shall be the average of five determinations per sample unit. The film strength shall be determined by the same method used to determine the seam strength except that the specimen shall be cut from the unseamed section of the bag with the long dimension perpendicular to the seam of the bag and all references to the seam shall not apply. The strength of the film, reported in pounds to the nearest 0.1 pound, shall be the average of five determinations per sample unit. Calculate the seam strength as a percent of the film strength and report to the nearest 1 percent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

4.5.3 Closure strength and seam continuity. Type I or type III bags shall be filled with 5000 mL of water at 70 + 5°F, the closure sealed, and the bag inverted and suspended in air for 15 minutes with the closure at the bottom of the bag. The closure shall then be examined for failure, such as tearing, breaking, or any other defect that would make the closure unsuitable for its intended purpose. A slight leakage of water at the ends of the closure shall not be considered a failure. There shall be no evidence of water leakage along the entire length of the sides of the bag. The procedure for testing the closure strength of type II and type IV bags shall be the same as above except that the volume of water shall be 2000 mL for the type II bag and 3700 mL for the type IV bag.

5. PACKAGING

* 5.1 Packing. Packing shall be level A, B, or Commercial as specified (see 6.2).

5.1.1 Level A packing. Five hundred bags, of one type only, shall be neatly stacked and packed in a snug-fitting fiberboard shipping container conforming to style RSC, grade V2s of PPP-B-636. Each fiberboard container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. In addition, a full size slip sheet of the specified kraft paper shall be placed between each 100 bags. Alternatively, 50 bags of one type only may be tightly rolled together and 10 such rolls packed per shipping container. Each shipping container shall be closed in accordance with method III, waterproofed in accordance with method V, and reinforced in accordance with the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5. Shipping containers shall be arranged in unit loads in accordance with MIL-L-35078 for the type and class of load specified (see 6.2). Strapping shall be limited to nonmetallic strapping, except for type II, class F loads.

5.1.2 Level B packing. Five hundred bags, of one type only, shall be neatly stacked and packed in a snug-fitting fiberboard shipping container conforming to style RSC, type CF (variety SW) or SF, class domestic, grade 275 of PPP-B-636. Each fiberboard container shall have the contents completely covered on the top and bottom with a sheet of 30-pound minimum basis weight kraft paper conforming to A-A-203. In addition, a full size slip sheet of the specified kraft paper shall be placed between each 100 bags. Alternatively, 50 bags of one type only may be tightly rolled together and 10 such rolls packed per shipping container. Each shipping container shall be closed in accordance with method II as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

* 5.1.2.1 Weather-resistant fiberboard containers. When specified (see 6.2), the fiberboard shipping container shall be a grade V3c, V3s, or V4s fiberboard box fabricated in accordance with PPP-B-636 and closed in accordance with method III as specified in the appendix of PPP-B-636, except that the inspection shall be in accordance with 4.4.5.

* 5.1.3 Commercial packing. Bags preserved as specified in 5.1 shall be packed in accordance with ASTM D 3951.

* 5.2 Palletization. When specified (see 6.2), bags packed as specified in 5.1.2 or 5.1.3, shall be palletized on a 4-way entry pallet in accordance with load type Ia of MIL-STD-147. Pallet types shall be type I (4-way entry), type IV, or type V in accordance with MIL-STD-147. Pallets shall be fabricated from wood groups I, II, III, or IV of MIL-STD-731. Each prepared load shall be bonded with primary and secondary straps in accor-dance with bonding means K and L or film bonding means O or P. Pallet patterns shall be in accordance with the appendix of MIL-STD-147. Interlocking of loads shall be effected by reversing the pattern of each course. In the container is of a size which does not conform to any of the patterns specified in MIL-STD-147, the pallet pattern used shall first be approved by the contracting officer.

5.3 Marking. In addition to any special marking required by the contract or purchase order, shipping containers, and palletized unit loads shall be marked in accordance with MIL-STD-129 or ASTM D 3951, as applicable.

6. NOTES

6.1 Intended use. The bags are intended to provide waterproof lightweight protection against rain and moisture for chemical protective clothing. The bags are provided with an interlocking reuseable closure for limited reuse of the bags.

6.2 Ordering data. Acquisition documents should specify the following:

a. Title, number, and date of this document.
b. Type required (see 1.2).
c. When a first article sample is required (see 3.1, 4.3 and 6.3).
d. Selection of applicable levels of packing (see 5.1).
e. When palletization is required (see 5.2).
f. When weather-resistant grade fiberboard shipping containers are required for level B packing (see 5.1.2.1).
g. Type and class of unit load required (see 5.1.1).

6.3 First article. When a first article is required, it shall be inspected and approved under the appropriate provisions of FAR 52.209. The first article should be a preproduction sample. The contracting officer should specify the appropriate type of first article and the number of units to be furnished. The contracting officer should include specific instructions in all acquisition instruments regarding arrangements for selection, inspection, and approval of the first article.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

6.4 Recycled material. It is encouraged that recycled material be used when practical as long as it meets the requirements of this document.

6.5 Source of supply. A source of supply for the bag is Mini-Grip Corp., 225 Route 303, Orangeburg, NY 10962.

6.6 Subject term (key word) listing.

Bag
Chemical protective clothing

6.7 Changes from previous issue. The margins of this document have been marked with an asterisk (*) to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document as written based on the entire content as written, irrespective of the marginal notations and relationship to the last previous issue.

Custodians:

Army - GL
Navy - NU
Air Force - 99

Preparing activity:

Army - GL

Project No. 8465-0924

Review activities:

Army - MD
Navy - MS
Air Force - 82
DLA - CT

User activities:

Navy - AS, MC, YD

U.S. GOVERNMENT PRINTING OFFICE: 1987 - 704-034/70119

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE ARMY

U.S. ARMY NATICK RESEARCH, DEVELOPMENT
and ENGINEERING CENTER
ATTN: STRNC-ES
Natick, MA 01760-5014

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
U.S. Army Natick Research, Development
and Engineering Center
ATTN: STRNC-ES
Natick, MA 01760-5014

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T21:46Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE
MIL-B-43587C	Bags, Chemical Protective Clothing Outfit

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
	☐ USER
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

NATICK OP-1, Feb 86

Source: https://assist.dla.mil -- Downloaded: 202640-21T21:46Z
Check the source to verify that this is the current version before use.