INCH-POUND
MIL-P-24441/20(SH)
23 July 1991

MILITARY SPECIFICATION SHEET

PAINT, EPOXY-POLYAMIDE, GREEN PRIMER, FORMULA 150, TYPE III

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation: MIL-P-24441.

FORMULA. This formula covers green epoxy-polyamide paint designated Navy Formula 150, type III, for interior or exterior use. The paint shall consist of the ingredients specified in the quantities specified.

Component A

Ingredients	Pounds
Thixotrope 1/	---
Polyamide 2/	20
Polyamide adduct 3/	280
Titanium dioxide 4/	100
Magnesium silicate 5/	500
Butyl alcohol 6/	250
Copper phthalocyanine blue 7/	1
Yellow iron oxide 8/	20

Component B

Ingredients	Pounds
Magnesium silicate 5/	100
Thixotrope 9/	---
Epoxy resin 10/	500
Naphtha 11/	249
Aluminum silicate 12/	150

See footnotes on next page.

AMSC N/A
FSC 8010
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:58Z
Check the source to verify that this is the current version before use.

QUANTITATIVE REQUIREMENTS. The paint shall meet the following quantitative requirements and the qualitative requirements of section 3 of the general specification. Components A and B shall be mixed 1:1 by volume for mixed component tests. Tests shall be performed in accordance with the general specification.

Requirements	Component A		Component B		Mixed components	
	Min	Max	Min	Max	Min	Max
Pigment content, percent	51.4	55.4	24.1	28.1	---	---
Volatiles, percent	25.1	27.1	22.6	24.6	---	---
Nonvolatile vehicle, percent	17.5	21.5	47.3	51.3	---	---
Water, percent	---	1.5	---	0.5	---	---
Coarse particles, percent	---	0.3	---	0.3	---	0.5
Consistency, grams	350	500	165	250	190	290
Pounds per gallon (lb/gal)	11.5	11.9	9.7	10.1	10.6	11.0
Set to touch, hours						
(a) at 40°F	---	---	---	---	---	2
(b) at 73°F	---	---	---	---	---	2
Dry-hard, hours						
(a) at 40°F	---	---	---	---	---	24
(b) at 73°F	---	---	---	---	---	6
Fineness of grind, NS	4	---	2	---	2	---
Flash point, °F	99	---	100	---	99	---
Titanium dioxide, percent of pigment	14	---	---	---	---	---
Pot life, hours at 73°F	---	---	---	---	6	---
Sag resistance, mils	---	---	---	---	12	---
Color of dry film to approximate the standard color chip 13/	---	---	---	---	Conform	
Weight per epoxy, vehicle	---	---	175	195	---	---
Contrast ratio, 3 mil dry film	---	---	---	---	0.98	---
Epichlorohydrin content (vehicle), parts per million	---	---	---	2	---	---
VOC, ASTM D 3960, lb/gal 14/	---	---	---	---	---	2.8

1/ Thixotrope to be used is the manufacturer's choice. In the development of the component A, 10 pounds (1.4 gallons) of Dislon NS-30 made by King Industries were used. Manufacturer is responsible for choosing a thixotrope that meets all the requirements herein, including shelf life. Thixotrope is a pigment for calculation purposes.

2/ GENAMID 2000, General Mills Chemicals; UNIREZ 2810, Union Camp; AZAMIDE 600, AZ Products; ANCAMINE 507, Pacific Anchor Chemical Corp.; EPOTUF SF7791, Reichhold Chemical.

3/ VERSAMID 280B75, General Mills Chemicals; UNIREZ 2180B73, Union Camp; AZAMIDE 680B75, AZ Products; ANCAMINE 700B75, Pacific Anchor Chemical Corp.; EPOTUF SF7792, Reichhold Chemical.

4/ Titanium dioxide conforming to ASTM D 476, type IV. In the development of component A, Dupont Tipure R960 was used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:58Z
Check the source to verify that this is the current version before use.

5/ Mistron 400, "Mistron 500", Cyprus Industries.
6/ Butyl alcohol conforming to ASTM D 304.
7/ Sunfast Blue NCNF, Sun Chemical Corp.; Palomar Blue G B-4810, Mobay Chemical Corp.; Monarch Blue G-FR XX-3374 or Irgalite Blue LGLD, Ciba-Geigy Corp.; Cyanine Blue B7000 (352751), BASF Wyandotte Corp.
8/ Pfizer YO3587, Charles Pfizer Chemical Corp.
9/ Thixotrope to be used is the manufacturer's choice. In the development of the component B, 15 pounds (1.8 gallons) of Dislon 6500 made by King Industries were used. Manufacturer is responsible for choosing a thixotrope that meets all the requirements herein, including shelf life. Thixotrope is a pigment for calculation purposes.
10/ EPON 828, Shell Chemical Co.; ARALDITE 6010, Ciba-Geigy Corp.; DER 331, Dow Chemical Co.; AZEPOXY 128, AZ Products; EPO-TUF 37-140, Reichhold Chemical; EPI-REZ 510, Celanese.
11/ Conforming to ASTM D 3734, type I. In the development of component B, AMSCO Super High Flash Naphtha was used.
12/ Huber 70C, J.M. Huber Corp.; Satintone #1, Englehard Mineral and Chemical Co.
13/ Use FED-STD-595 color chip no. 24272. Color shall approximately match the color chip.
14/ For VOC calculations, component A makes approximately 101 gallons and component B makes approximately 102 gallons.

Use of alternate ingredients in this formula must have prior approval of the Naval Sea Systems Command. Approval will be based on review of data demonstrating equivalent physical, chemical and performance characteristics of paint manufactured with the proposed alternate material. Development of the required data package is the responsibility of the proposing agent. Paint incorporating the proposed alternate ingredient shall conform to all the requirements of this military specification sheet and the general specification.

Preparing activity:
Navy - SH
(Project 8010-N239)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:58Z
Check the source to verify that this is the current version before use.

98 ipe film (0.250-inch) galvanized steel plates conforming to MIL-S-24