INCH-POUND
MIL-P-24441/1C(SH)
23 July 1991
SUPERSEDING
MIL-P-24441/1B(SH)
15 May 1986

MILITARY SPECIFICATION SHEET

PAINT, EPOXY-POLYAMIDE, GREEN PRIMER, FORMULA 150, TYPE I

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

The requirements for acquiring the product described herein shall consist of this specification sheet and the issue of the following specification listed in that issue of the Department of Defense Index of Specifications and Standards (DODISS) specified in the solicitation: MIL-P-24441.

FORMULA. This formula covers green epoxy-polyamide paint designated Navy Formula 150, type I, for interior or exterior use. The paint shall consist of the ingredients specified in the quantities specified.

Component A

	Pounds
Thixotrope 1/	---
Polyamide 2/	20
Polyamide adduct 3/	280
Magnesium silicate 4/	500
Titanium dioxide 5/	100
Butyl alcohol 6/	250
Copper phthalocyanine blue 7/	1
Yellow iron oxide 8/	20

Component B

	Pounds
Thixotrope 1/	---
Epoxy resin 9/	500
Magnesium silicate 4/	100
Naphtha 10/	249
Diatomaceous silica 11/	150

See footnotes on next page.

AMSC N/A
FSC 8010
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:55Z
Check the source to verify that this is the current version before use.

QUANTITATIVE REQUIREMENTS. The paint shall meet the following quantitative requirements and the qualitative requirements of section 3 of the general specification. Components A and B shall be mixed 1:1 by volume for mixed components tests. Tests shall be performed in accordance with the general specification.

Requirements	Component A		Component B		Mixed components	
	Min	Max	Min	Max	Min	Max
Pigment content, percent	51.4	55.4	23.8	27.8	---	---
Volatiles, percent	25.1	27.1	22.7	24.7	---	---
Nonvolatile vehicle, percent	17.5	21.5	47.5	51.5	---	---
Water, percent	---	1.5	---	0.5	---	---
Coarse particles, percent	---	0.3	---	0.3	---	0.5
Consistency, grams	235	500	165	250	175	235
Pounds per gallon (lb/gal)	11.5	11.9	9.8	10.2	10.6	11.0
Set-to-touch time, hours at 40°F	---	---	---	---	---	2
Set-to-touch time, hours at 73°F	---	---	---	---	---	2
Dry-hard, hours at 40°F	---	---	---	---	---	24
Dry-hard, hours at 73°F	---	---	---	---	---	6
Fineness of grind, NS	4	---	2	---	2	---
Flash point, °F	99	---	115	---	99	---
Titanium dioxide, percent of pigment	14	---	---	---	---	---
Pot life, hours at 73°F	---	---	---	---	6	---
Sag resistance, mils	---	---	---	---	9	---
Color dry film to approximate the standard color chip 12/	---	---	---	---	Conform	
Weight per epoxy, (vehicle)	---	---	175	195	---	---
Contrast ratio, 3 mils dry film	---	---	---	---	0.98	---
VOC, ASTM D 3960, lb/gal	---	---	---	---	---	2.8

1/ The amount and type of thixotrope shall be selected by the manufacturer to meet all requirements of the general specification and this specification sheet. For VOC calculations: 10.6 lbs and 1.27 gals allocated in each component. Thixotrope is a pigment for calculations.

2/ GENAMID 2000, Henkel Corporation; UNIREZ 2810, Union Camp; AZAMIDE 600, AZ Products; ANCAMINE 507, Pacific Anchor Chemical Corp.; EPOTUF SF7791, Reichhold Chemical; TriChem 9200, Trimont Chemicals.

3/ VERSAMID 280B75, Henkel Corporation; UNIREZ 2180B75, Union Camp; AZAMIDE 680B75, AZ Products; ANCAMINE 700B75, Pacific Anchor Chemical Corp.; EPOTUF SF7792, Reichhold Chemical; TriChem 9280-B-75, Trimont Chemicals.

4/ Pfizer Talc MP 30-36; Cyprus Montana Talc, Mistron 400, "Mistron 500".

5/ DuPont Tipure R960; NL Chemicals TX 2101; Kerr-McGee, Tronox Tr822.

6/ Conforming to ASTM D 304.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:55Z
Check the source to verify that this is the current version before use.

7/ 1. SUNFAST BLUE NCNF
249-0535
Batch D93079
Sun Chemical Corporation
PO Box 2060
Peachtree City, Georgia 30269
(404) 487-4487 Attn: Mr. Alan D. Boles

2. PALOMAR BLUE G B-4810
Batch HB-64220
Mobay Chemical Corporation
Dyes and Pigments Division
PO Box 419
Hawthorne, New Jersey 07507
(201) 942-3232 Attn: Mr. Lee W. Foster

3. MONARCH BLUE G-FR X-3374
Batch 0-15676 PROD
Ciba-Geigy Corporation
Pigments Department
Ardsley, New York 10502
(914) 478-3131 Attn: Mr. Reinhold William Bartsch, Jr.

4. IRGALITE BLUE LGLD
Batch 820608.G
Ciba-Geigy Corporation
(Same as #3)

5. CYANINE BLUE B7000 or BSG
Western Star Color and Chemical Corp.
6377 Drexel Avenue
Los Angeles, CA 90048

6. HELIOGEN BLUE 7101F (352751)
Batch 485-4580
BASF Wyandotte Corporation
Pigments Division
491 Columbia Avenue
Holland, Michigan 49423
(616) 392-2391

8/ Pfizer YO3587.
9/ EPON 828, Shell Chemical Co.; ARALDITE 6010, Ciba-Geigy; DER 331, Dow Chemical Co.; AZEPOXY 128, AZ Products; EPO-TUF 37-140, Reichhold Chemical; EPI-REZ 510, Celanese; TriChem 728, Trimont Chemicals.
10/ Amsco Super High Flash Naphtha.
11/ Celite 281 or 499, Johns-Manville; MICRO-KEN 801 and MICRO-KEN 803.
12/ Use FED-STD-595 color chip no. 24272. Color shall approximately match the color chip.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:55Z
Check the source to verify that this is the current version before use.

Use of alternate ingredients in this formula must have prior approval by the Naval Sea Systems Command. Approval will be based on review of data showing equivalent physical and chemical characteristics to the specified ingredient. It will be necessary to demonstrate that paint made using the ingredient will conform to all requirements of this specification.

Revision letters are not used to denote changes due to the extensiveness of the changes.

Preparing activity:
Navy - SH
(Project 8010-N230)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T21:55Z
Check the source to verify that this is the current version before use.