NOTICE OF CANCELLATION

INCH-POUND

MIL-S-8844D
NOTICE 1
25 April 1994

MILITARY SPECIFICATION

STEEL BAR, REFORGING STOCK, AND
MECHANICAL TUBING, LOW ALLOY, PREMIUM QUALITY

MIL-S-8844D, dated 30 June 1987, with Amendment 1, dated 1 November 1990, is hereby canceled. MIL-S-8844 is superseded by the following AMS specifications as shown below.

MIL-S-8844 Alloy	AMS Specification
4340	AMS 6414F STEEL BARS, FORGINGS, AND TUBING 0.80Cr - 1.8Ni - 0.25Mo (0.38 - 0.43C) (SAE 4340) Vacuum Consumable Electrode Remelted
300M	AMS 6257 STEEL BARS, FORGINGS, AND TUBING 1.6Si - 0.82Cr - 1.8Ni - 0.40Mo - 0.08V (0.40 - 0.44C) Consumable Electrode Vacuum Remelted Normalized and Tempered

(Application for copies of SAE AMS publications should be addressed to the Society of Automotive Engineers, 400 Commonwealth Drive, Warrendale, PA 15096.)

Preparing Activity:
Navy - AS
(Project 9510-0855)

AMSC N/A

FSC 9510

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T11:35Z
Check the source to verify that this is the current version before use.