MILITARY SPECIFICATION

SUPPORT, COVER

This Amendment forms a part of Military Specification MIL-S-70440 (AR), dated 1 September 1983, and is approved for use by the US Army Armament Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 2

2.3: Add the following new paragraph:

"2.3 Other publications. The following document(s) form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

ASTM Method B633 - Electrodeposited Coatings of Zinc on Iron and Steel

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA. 19103)."

3.6: Delete "3.6" and substitute "3.3".

PAGE 3

4.3.1: Delete "Support, Cover (painted)" and substitute "Support, Cover (after surface finishing) (see 6.9)".

PAGE 4

Table 1: Delete "Support, Cover (after painting" and substitute "Support, Cover (after surface finishing) (see 6.9)".

PAGE 6

4.4.2.1: Minor 201: Delete "3.1" and substitute "3.3".

PAGE 7

4.4.2.2: Minor 202: Delete "3.1" and substitute "3.3".

Notes: Add "This paragraph is not applicable when cover supports are zinc plated".

FSC: 1320

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:26Z
Check the source to verify that this is the current version before use.

PAGE 8

4.4.2.3: Delete in its entirety and substitute the new table attached.

Add new paragraphs 4.5.3, 4.5.4 and 4.5.5:

"4.5.3 Zinc plate thickness. Zinc plate thickness shall be determined in accordance with ASTM B633.

4.5.4 Zinc plate corrosion resistance. Two samples per shift shall be selected for this test. The test shall be performed in accordaance with ASTM B633. If any component fails to comply with the specified requirements, the quantity represented by the sample shall be rejected.

4.5.5 Zinc plate corrosion resistance. Two samples per shift shall be selected for this test. The test shall be performed in accordance with ASTM B633 except that post first article testing shall only require 48 hours salt spray immersion. If any component fails to comply with the specified requirements, the quantity represented by the sample shall be rejected."

5.1.1 and 5.1.2: Delete "paint surfaces" and substitute "finished surfaces".

PAGE 10

6.9: Add the following new paragraph:

"6.9 First article testing for alternate finishes. Two alternate surface finishes are allowed for the cover support. When the contractor uses the paint over phosphate finish cover support submission quantities and inspection shall be in accordance with para 4.3.1 and Table I. When the contractor uses the alternate zinc plate finish in lieu of supplying 10 phosphated cover supports and 10 zinc plated cover supports he will supply a quantity of 20 zinc plated parts. After examination for defects 10 of these will be subjected to adhesions tests and 10 to corrosion resistance tests."

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1320-A785)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:26Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF DEFECTS & TESTS

MIL-S-70440 (AR)
AMENDMENT 1

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.3	Support, Cover	1 OF 1	9369960
			NEXT HIGHER ASSEMBLY

CATEGORY	EXAMINATION OR TEST	NO. OF SAMPLE UNITS	AQL OR 100%	REQUIREMENT PARAGRAPH	PARAGRAPH REFERENCE /INSPECTION METHOD
Critical	None defined.				
Major					
101	Salt spray test (for painted parts only)	*		3.1	4.5.2
102	Zinc plate thickness (Note 1)		.40	3.1	4.5.3
103	Zinc plate adhesion (Note 1)	*		3.1	4.5.4
104	Zinc plate corrosion resistance (Note 1)	*		3.1	4.5.5
Minor					
201	Bare spots in coating in excess of .250 inches in length		.65	3.1	Visual
202	Evidence of poor workmanship		.65	3.3	Visual

NOTES:
* See applicable test method paragraph.
1. Applies to zinc plated parts only.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T03:26Z
Check the source to verify that this is the current version before use.