INCH-POUND

MIL-C-29576A
AMENDMENT 1
6 November 1995

MILITARY SPECIFICATION

CYLINDERS, STEEL, COMPRESSED GAS,
NON-SHATTERABLE, WELDED

This amendment forms a part of MIL-C-29576A, dated 2 September 1992, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 2

2.1.1 Under SPECIFICATIONS, MILITARY, delete:

"MIL-C-81302 - Cleaning Compound, Solvent, Trichlorotrifluoroethane"

2.1.1 Under STANDARDS, MILITARY, add

"MIL-STD-1359 - Cleaning Methods and Procedures for Breathing Oxygen Equipment"

PAGE 10

4.7.2.1 Delete paragraph in its entirety and substitute:

"4.7.2.1 Non-volatile residue test.

4.7.2.1.1 Preparation of cylinder. A clean plug shall be placed in the outlet of the cylinder undergoing test. The surface around the plug and the cylinder outlet shall be cleaned with an oxygen-safe cleaning compound, then dried using a clean lint-free cloth.

4.7.2.1.2 Procedure. Non-volatile residue shall be determined in accordance with MIL-STD-1359 and the following:

a. Internal area of the cylinder shall be the basis for determining the quantity of cleaning compound required.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T00:08Z
Check the source to verify that this is the current version before use.

b. The plugged cylinder shall be agitated a minimum of 10 minutes in a manner that completely wets the inner walls with the cleaning compound.

c. Particulate content shall be determined in accordance with 4.7.2.2.

d. Non-volatile residue shall be in conformance with 3.6.2.1."

Custodians:
Army - AV
Navy - AS
Air Force - 99

Review activities:
Air Force - 11, 71
DLA - GS

Preparing Activity:
Navy - AS

(Project 8120-1027)

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T00:08Z
Check the source to verify that this is the current version before use.