MIL-B-36580A
25 August 1978
SUPERSEDING
MIL-B-0036580(DM)
12 June 1969

MILITARY SPECIFICATION

BOTTLE, SCREW CAP, Wide Mouth, Round, Plastic

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

* 1.1 Scope. This specification covers a 4 oz. (120 ml) round, wide mouth, screw cap bottle suitable for collecting water samples for bacteriological analysis. The bottle is fabricated of polypropylene.

2. APPLICABLE DOCUMENTS

* 2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids or request for proposals form a part of this specification to the extent specified herein.

SPECIFICATION

FEDERAL

L-P-394	- Plastic, Molding Material, Polypropylene, Injection And Extrusion.
PPP-B-566	- Boxes, Folding, Paperboard.
PPP-B-636	- Boxes, Fiberboard.
PPP-B-676	- Boxes, Setup.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Headquarters, Defense Personnel Support Center, ATTN: Directorate of Medical Materiel, CODE ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 6640

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:50Z
Check the source to verify that this is the current version before use.

STANDARDS

MILITARY

MIL-STD-105 - Sampling Procedures And Tables For Inspection By Attributes.
MIL-STD-129 - Marking For Shipment And Storage.

(Copies of specifications and standards required by contractors in connection with specific procurement functions should be obtained as directed by the contracting officer).

* 2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply.

U.S. Department of Health, Education and Welfare, Food and Drug Administration (FDA).

Federal Food, Drug, and Cosmetic Act, and applicable regulations promulgated thereunder.

(Application for copies should be addressed to the Food and Drug Administration, Washington, DC 20204).

3. REQUIREMENTS

* 3.1 Material. Polypropylene resin shall be nontoxic in accordance with FDA food additive regulation 121.2501 and shall conform to federal specification L-P-394, type I.

* 3.2 Construction. The bottle components shall be fabricated of polypropylene resin and shall consist of a container and a closure.

3.2.1 Container. Container shall be cylindrical in shape and shall have a threaded neck finish. Threads shall be continuous and shall make at least two complete revolutions around the neck. Bottom shall be so constructed that the bottle is stable when placed on a smooth flat surface.

3.2.2 Closure. Inner diameter shall have threads which mate with the threads on the container. Outside diameter of closure shall have vertical ribs to facilitate removal and tightening of the closure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:50Z
Check the source to verify that this is the current version before use.

* 3.3 Dimensions. Bottle shall have the following dimensions listed in table I.

TABLE I. Dimensions.

	Dimensions in inches
Overall height (container and closure)	4-1/8 ± 1/8
Height of container	4 ± 1/8
Height from bottom of container to shoulder	3-1/2 ± 1/8
Maximum outside diameter of container	1-7/8
Thickness of side walls of container	.020 minimum
Inside diameter of container mouth	1-1/32 minimum

3.4 Resistance to leaking. There shall be no evidence of leaking when tested as specified (see 4.4.1).

* 3.5 Resistance to autoclaving. Bottle components shall not soften, deform, crack, or become opaque when tested as specified. Bottle components shall withstand repeated steam autoclaving without loss of ability to close properly and shall not leak when tested as specified (see 4.4.2).

3.6 Identification markings. Each bottle shall be permanently and legibly marked with the capacity, manufacturer's name or registered trademark.

3.7 Workmanship. Workmanship shall be first class throughout. Bottles shall be free of deformation, cracks, sharp edges, protrusions, crazing, rough surfaces, flash, foreign matter and other defects which detract from their appearance impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:50Z
Check the source to verify that this is the current version before use.

* 4.1.2 Certificates of quality. When available, certificates of quality, supplied by the manufacturer of the polypropylene, listing the specified test method and test results obtained, may be furnished in lieu of actual performance of such testing by the contractor.

4.2 Sampling.

* 4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and table II. Unit of product shall be the assembled bottle.

TABLE II. Sampling for examination.

	Inspection level	AQL (percent defective)
For visual examination		
Major defects	II	2.5
Minor defects	II	4.0
For dimensional examination	S-1	2.5

* 4.2.2 For tests. Sampling for tests shall be conducted in accordance with MIL-STD-105 and table III. Unit of product shall be the bottle.

TABLE III. Sampling for tests.

Characteristic	Requirement	Test	Inspection level	AQL
Leaking	3.4	4.4.1	S-1	See note
Resistance to autoclaving	3.5	4.4.2	S-1	See note

NOTE: Acceptance number shall be zero.

4.3 Examination. The bottles shall be examined to determine compliance with all requirements contained in this specification.

* 4.3.1 Classification of defects. Examination shall be conducted in acccordance with table IV classification of defects. Examination shall not be restricted to the classified possible defects listed.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:50Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of defects.

Categories	Defects
Major	
101	Bottles not stable when placed on smooth flat surface.
102	Bottles not free of deformation.
103	Bottles not free of cracks.
104	Bottles not free of sharp edges.
105	Bottles not free of crazing.
106	Closure missing.
107	Threads on bottle finish and cap not free of breaks and distortion.
108	Closure cannot be secured.
Minor	
201	Identification and capacity marking missing, illegible, or incomplete.
202	Bottles not furnished with screwcap in place.
203	Surface of bottle not smooth.
204	Bottles not free of flash that exceeds 1/64 inches.

* 4.3.2 Dimensional examination. The bottles shall be examined for defects in dimensions. Any dimension not within the tolerance specified shall be considered as a defect.

* 4.3.3 Packaging inspection. The inspection of the unit package, packing and marking for shipment and storage shall be in accordance with quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

* 4.4.1 Leak test. The container shall be filled with water at ambient temperature and the closure shall be hand tightened. The bottle shall be turned upside down for a period of one hour, and examined for evidence of leaking. The bottles used in this test may be used for testing in accordance with 4.4.2.

* 4.4.2 Resistance to autoclaving. The bottles shall be tested for leaking in accordance with 4.4.1, and then emptied. The empty bottles with hand tightened closures shall be autoclaved three times at 250 degree Fahrenheit (15 pounds per square inch) for thirty minutes per autoclaving cycle. Between autoclaving cycles, the bottles shall be cooled at room temperature for 15 minutes and examined for evidence of deterioration. After completion of the autoclaving cycles, the bottles shall be examined for evidence of deterioration and cooled to room temperature. At room temperature, the bottles shall be retested for leaking in accordance with 4.4.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:50Z
Check the source to verify that this is the current version before use.

* 5. PACKAGING

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Unit of issue. One package containing twelve bottles, as specified, constitutes a unit of issue.

5.1.2 Level A.

5.1.2.1 Unit packaging. Bottles shall be clean and dry with closures (caps) secured in place. Twelve bottles shall be further packaged in a box conforming to PPP-B-566 or PPP-B-676. The box shall contain full or shoulder height partitions so arranged that each bottle is contained in an individual cell. Closure of the box shall be as specified in the appendix of the applicable box specification.

5.1.3 Level C. Bottles shall be clean, dry and packaged in a manner that will afford adequate protection against damage during shipment from the supply source to the first receiving activity.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.2).

5.2.1 Level A. Twelve unit packages shall be packed in a shipping container designed for a type 2 load and conforming to PPP-B-636, class weather-resistant. Closure, strapping and waterproofing shall be as specified in the appendix of the box specification.

5.2.2 Level B. Twelve unit packages shall be in a shipping container designed for a type 2 load and conforming to PPP-B-636, class domestic. Closure shall be as specified in the appendix of the box specification.

5.2.3 Level C. The packaged bottles shall be packed in shipping containers in a manner that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier's rules and regulations.

5.3 Marking. Each unit package and shipping container shall be marked as specified in MIL-STD-129.

* 6. NOTES

6.1 Intended use. The item covered by this specification is a Bottle, Screw Cap, Wide Mouth, Round, to be used for collecting water samples for bacteriological analysis.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:50Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Procurement documents should specify the following.

(a) Title, number and date of this specification.
(b) National Stock Number (NSN).
(c) Selection of applicable level of packaging and packing required (see 5.1 and 5.2).

6.3 This specification covers the following item listed in the Federal Supply Catalog.

National Stock Number	Item Identification
6640-00-135-2994	BOTTLE, SCREW CAP, Wide Mouth, Round, 4oz., 12s.

6.4 Changes from previous issue. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the past previous issue.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activity:
DoD - MB

Preparing activity:
Defense Logistics Agency - DM

Project Number 6640-1062

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:50Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-B-36580A BOTTLE, SCREW CAP, Wide Mouth, Round, 4oz. 12s

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*	TELEPHONE NO.
	DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:50Z
Check the source to verify that this is the current version before use.