MILITARY SPECIFICATION

GLOVE, PATIENT EXAMINING and TREATMENT, RUBBER LATEX, NON-STERILE

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers a non-sterile, disposable, impermeable, light-weight seamless rubber latex glove which fits either hand. Glove shall be suitable for medical use in examinations, diagnostic, and therapeutic procedures by physician, nurses, and paramedical personnel.

1.2 Classification. Size of gloves shall be medium-large (see Table I for dimensions).

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.

Military

MIL-L-10547	Liners, Case, and Sheet, Overwrap; Water-Vaporproof or Waterproof, Flexible.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

STANDARDS

Federal

Test Method 601	Rubber, Sampling and Testing.

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment Storage.

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publication. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated the issue in effect on date of invitation for bids or request for proposal shall apply.

THE UNITED STATES PHARMACOPEIAL CONVENTION, INC.
The Pharmacopeia of the United States of America (U.S.P.)

(Applications for copies shall be addressed to the Mack Publishing Company, Easton, Pennsylvania 18042.)

3. REQUIREMENTS

3.1 Material.

3.1.1 Glove. The glove shall be fabricated from natural rubber latex and be free from coloring and fillers. Small amounts of processing additives may be present.

3.1.2 Dusting powder. Gloves shall be uniformly prepowdered with vegetable powder. The minimum amount of powder is preferred. Powder shall be in accordance with the tests, standards, and requirements of the latest revision of the Pharmacopeia of the U.S. (USP) for Absorbable Dusting Powder.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

3.2 Style and design. The patient examining and treatment glove shall be designed to fit either hand. Each glove shall have five fingers and be suitable for performing patient examinations and treatments. The gloves shall be constructed to provide maximum tactility in use, and shall have well-fitting fingers that permit maximum freedom of movement. The palm section shall be of sufficient width to permit comfortable flexing of the hands. The wrists shall be tapered or constricted to conform and adhere to wrist and forearm to minimize "roll down". The gloves shall be packaged in such a manner that they can be readily dispensed.

3.2.1 Dimension. Dimensions shall be in accordance with Table I.

Thickness shall be measured as specified in 4.4.1.

Table I. Dimensions

Characteristic	Inches
Overall length	10 minimum
Flat width at wrist	3-3/8 ± 1/8 *
Flat width of palm at base of thumb	3-13/16
Length of thumb	2-1/4
Length of little finger	2-1/8
Length of middle finger	3-3/16
Length of index finger	2-5/8
Length of ring finger	2-15/16
Flat width of thumb at base	1-7/16
Flat width of thumb 3/4 inch below tip	1-1/4
Flat width of forefinger	1-13/16
Flat width of forefinger 3/4 inch below tip	1-1/8
Flat width of ring finger at base	1-1/4
Flat width of ring finger 3/4 inch below tip	1-1/8
Flat width of middle finger	1-7/16
Flat width of middle finger 3/4 inch below tip	1-3/16
Flat width of little finger at base	1-1/8
Flat width of little finger 3/4 inch below tip	1
Thickness at finger tips	.006 ± .001
Thickness at cuff, 1" below bead	.004 ± .001
Thickness at palm, center	.005 ± .001

* All lengths and flat widths which follow have ± 1/8 inch tolerance.

3.2.2 Physical requirements. The gloves shall comply with the physical requirements contained in Table II. Tests for physical requirements shall be conducted as specified in 4.4.2.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

Table II. Physical Requirements

Characteristics	Values
Tensile strength in pounds per square inch (psi)	4000 min.
Ultimate elongation in percentage	810 min.
Accelerated aging—	
Tensile strength, psi	3000 min.
Ultimate elongation, percentage	650 min.
Specific gravity	0.95 $\pm \frac{.02}{.05}$

3.2.3 Dispensability. The glove shall be able to be removed easily from its package and on removal, the glove shall show no evidence of sticking to other gloves.

3.3 Finish. The gloves shall have a uniform smooth finish free from holes, visible surface or embedded particles, tackiness, bloom, strings, and other imperfections.

3.4 Freedom from pinholes. The glove shall be supplied free of pinholes, and when tested as specified in 4.4.3, the glove shall not leak.

3.5 Workmanship. Workmanship shall be first class throughout. Gloves shall be free from defects which detract from their appearance of impair their serviceability. Gloves shall be packed under sanitary conditions.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and service conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.2 Certificate of quality, for the dusting powder, supplied by the manufacturer of the dusting powder, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the name of the item, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results and the specification requirements.

4.2 Sampling for lot acceptance.

4.2.1 Inspection lot. The inspection lot shall be determined in accordance with MIL-STD-105.

4.2.2 Sampling for examination. A random sample of gloves shall be selected from each lot in accordance with MIL-STD-105. The inspection level and Acceptable Quality Level (AQL) shall be as indicated in Table III below. The unit of product for examination shall be one glove.

Table III. Sampling for Examination

Type defect	Inspection level	AQL (percent defective) *
Major	S-2	1.5
Minor A	S-2	4.0
Minor B	S-2	6.5

* If acceptance number is not exceeded, lot shall be accepted.

If rejection number is equaled or exceeded, inspection at level II may be performed to determine final rejection or acceptance.

4.2.3 Sampling for tests.

4.2.4 Sample unit usage. Where possible, the same sample unit shall be used for the determination of two or more test characteristics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

4.3 Examination. The gloves shall be examined to determine compliance with all requirements contained in this specification and in accordance with MIL-STD-105. Visual examination shall include inflation of the gloves to be examined. This inflation shall be limited to 350 ± 50 percent elongation on any part of the glove. Examination shall be conducted as specified in Tables III and IV. Inspection, however, shall not be restricted to defects listed in Table IV. Any glove in the sample containing one or more defects shall be rejected (defective) and if the number of defective gloves in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

Table IV. Classification of Defects

Categories	Defects
Critical:	None defined
Major	
101	Tears, large holes.
102	Large, open blisters.
103	Large, imbedded, grit-like particles.
104	Excessively thin spots (under 0.003 inch).
105	Tackiness.
106	Pinholes.
Minor A	
201	Fingertips under 0.005 inch or over 0.007 inch.
202	Palm thickness under 0.004 inch or over 0.006 inch.
203	Wrist thickness under 0.004 inch or over 0.005 inch.
204	Short, gloves under 10 inches.
205	Excessive blisters that would interfere with accepted professional use (clusters of small blisters as contrasted with large open blisters.)
206	Snapback, bloom, strings, bleeding, and other imperfections.
207	Excessive amount of dusting powder present.
Minor B	
251	Palm circumference more than 1/4 inch from specified size.
252	Gloves are not free from foreign matter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements. All sample or test specimens intended for accelerated aging tests shall be protected form any unnecessary exposure to strong light prior to the aging. The samples and specimens shall be kept in light-tight containers, except while being inspected, prepared or measured.

4.4.1 Dimensions. Thickness shall be measured in accordance with the test method of Standard No. 601, indicated in Table V.

4.4.2 Physical requirements. Physical requirements test shall be conducted in accordance with the test methods of Standard No. 601, indicated in Table V.

Table V. Test Methods
(Federal Test Method Standard No. 601)

Requirement	Test method no.
Thickness	2011 or 2031
Tensile strength	4111 *
Ultimate elongation	4121 *
Accelerated aging (Oxygen pressure test)	7111 *
Specific gravity	14011 or 14021

* Use dumbbell specimen cut with die III of Figure 4111.

4.4.3 Pinhole test. Gloves shall be filled with 300 milliliters of water and held suspended from the cuff end for 5 minutes. Gloves shall be examined for leaks.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified, (see 6.1).

5.1.1 Unit of issue. One package containing 100 gloves, as specified, constitutes one unit of issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

5.1.2 Packaging quantities. The number of units of issue indicated in Table VI shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table VI. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	Not required	20 units

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package. One hundred gloves shall be packaged in a suitable top opening dispenser type paperboard carton of appropriate size and design. Commercial colors are acceptable on the carton and closure shall be adequate to prevent spilling of contents under normal handling.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing. Packing shall be level A, B or C as specified, (see 6.1).

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for type 2 load, and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, grade V3. Closure and strapping shall be in accordance with appendix of applicable box specification. In addition, each fiberboard box shall be waterproofed in accordance with paragraph 30.4 of PPP-B-636.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-636, class domestic. Closure shall be as specified in the appendix of the box specification.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Unit packages. Each unit package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES.

6.1 Procurement documents should specify the following:

a. Title, number, and date of this specification.

b. Applicable levels of packaging and packing required (see 5.1 and 5.2).

c. Federal stock no.

6.2 This specification is applicable to Federal Supply Catalog item as follows:

Federal Stock No.	Item Identification
6515-462-0832	GLOVE, PATIENT EXAMINING AND TREATMENT: Rubber, Disposable, Medium-large size, 100s.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

6.3 This specification is intended to cover all types that are normally procured to meet military requirements. It does not include all types, sizes or grades as indicated by the title nor all types which are commercially available.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:

Defense Supply Agency - DM

Review activities:
Army - MD
Navy - MS
Air Force - 03

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

☆ U. S. GOVERNMENT PRINTING OFFICE: 1969-393-066/S-2470

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

Fold

Source: https://assist.dla.mil - Downloaded: 2026-03-21T08:52Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document-(s) or serve to amend contractual requirements .

SPECIFICATION
MIL-G-36592 FSN

ORGANIZATION

CITY AND STATE | CONTRACT NUMBER

MATERIAL PROCURED UNDER A
☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?
   ☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)* | DATE

DD FORM 1 JAN 66 1426 REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.