MILITARY SPECIFICATION

GLOVE, PATIENT EXAMINING AND TREATMENT, PLASTIC, NON-STERILE

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers a non-sterile, plastic, disposable, impermeable, light-weight seamless glove of medium size for all wearers, which fits either hand. Glove shall be suitable for medical use in examinations, diagnostic and therapeutic procedures by physicians, nurses and paramedical personnel.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Boxes, Fiberboard.

Military

MIL-L-10547	Liners, Case, And Sheet Overwrap; Water-Vaporproof or Waterproof; Flexible.

FSC 6515

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

STANDARDS

Military

MIL-STD-105	Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129	Marking for Shipment and Storage.

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMERICAN SOCIETY FOR TESTING AND MATERIALS (A.S.T.M.)

D882	Tests for Tensile Properties of Thin Plastic Sheeting.

(Application for copies should be addressed to the American Society For Testing and Materials, 116 Race Street, Philadelphia, Pennsylvania 19103.)

U.S. PHARMACOPEIAL CONVENTION, INC. (U.S.P.)

Pharmacopeia of the United States.

(Application for copies should be addressed to the Mack Publishing Company, Easton, Pennsylvania 18042)

3. REQUIREMENTS

3.1 Material.

3.1.1 Glove. The glove shall be fabricated from virgin translucent polyvinyl chloride.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:52Z
Check the source to verify that this is the currentversion before use.

3.1.2 Dusting Powder. Gloves shall be uniformly prepowdered on the interior only with a minimum of absorbable dusting powder meeting the following requirements: Powder shall be a white, odorless powder and shall be in accordance with the tests, standards, and requirements of the latest revision of the Pharmacopeia of the United States (U.S.P.) for Absorbable Dusting Powder.

3.2 Style and design. The patient examining glove shall be constructed in one piece, free of seams and welts, and shall have a smooth finish. Shall be a five-fingered glove suitable for use on either hand. A small continuous bead shall be formed on the glove circumference at the cuff end to prevent tearing. The glove shall be constructed to provide maximum tactility in use, and have straight or curved, well-fitting fingers that permit maximum freedom of movement. The palm section shall be of sufficient width to permit comfortable flexing of the hands.

3.2.1 Dimensions. The glove shall have the dimensions in inches as indicated in Table I.

Table I. Dimensions

Characteristic	Inches
Overall length	9-3/4 to 11-1/2
Flat width at wrist	3-3/4 to 4-3/4
Flat width at palm at base of thumb	3-7/8 to 4-1/2
Length of thumb	2-1/8 to 2-5/8
Length of little finger	1-7/8 to 2-3/8
Length of middle finger	2-3/4 to 3-1/4
Length of index and ring fingers	2-1/2 to 3
Flat width of thumb at base	1-3/8 to 1-5/8
Flat width of thumb 3/4 inch from tip	1-1/16 to 1-1/2
Flat width of base of index, middle and ring fingers	1 to 1-3/16
Same as line above, 3/4 inch from tips	1-1/8 to 1-3/8
Flat width of base of little finger	1 to 1-3/8
Same as line above, 3/4 inch from tip	1 to 1-3/8
Thickness at finger tips	0.002 to 0.0045
Thickness at remainder of glove (except for area adjacent to cuff bead)	0.004 to 0.008

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:52Z
Check the source to verify that this is the current version before use.

3.2.2 Outer wrapper. Each unit package (50 gloves) shall be made waterproof by placing unit in a sealed plastic bag. The sealed plastic bag may be on the exterior or, as an alternate, on the interior of the unit package. There shall be no evidence of moisture within the plastic bag, when plastic bag of unit package is opened after subjection to leakage test specified in 4.4.3.

3.3 Physical requirements. The gloves shall comply with the physical requirements contained in Table II. Tests for physical requirements shall be conducted as specified in 4.4.1.

Table II. Physical Requirements

Characteristics	Values
Tensile strength - pounds per square inch	1300 min.
Breaking strength - pounds per inch of width	5 min.
Percentage elongation at break	280 min.

3.4 Freedom from pinholes. The glove shall be supplied free of pinholes, and when tested as specified in 4.4.2, the glove shall not leak.

3.5 Finish. The glove shall have a visually dull but smooth-to-the touch exterior, and visually glossy and smooth-to-the-touch interior surface. The glove shall be free from holes, visible ingrained particles, tackiness, bloom, strings, bleeding, and other imperfections.

3.6 Low temperature flexibility. The glove shall not crack at -20° F when tested as specified in 4.4.4.

3.7 High temperature exposure. The glove shall withstand exposure at 165° F for 72 hours without evidence of tackiness, plasticizer exudation, or other deterioration when tested as specified in 4.4.5.

3.8 Workmanship. Workmanship shall be first class throughout. Gloves shall be free from defects which detract from their appearance or may impair their serviceability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties.)

4.1.2 Certificates of quality for the dusting powder, supplied by the manufacturer of the dusting powder, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the name of the dusting powder, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as indicated in Table III. The unit of product for examination shall be one glove.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:52Z
Check the source to verify that this is the currentversion before use.

Table III. Sampling for Examination

Type defect	Inspection level	AQL(percent defective)*
Major	S-3	2.5
Minor	S-2	2.5

* If acceptance number is not exceeded, lot shall be accepted. If rejection number is equaled or exceeded, inspection at level II may be performed to determine final rejection or acceptance.

4.2.2 Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, and in accordance with the Table IV.

Table IV. Sampling for Tests

Characteristic	Unit of Product	Requirement	Test Procedure	Inspection level	AQL(percent defective)
Outer wrapper	Unit package	3.2.2	4.4.3	S-2	4.0
Tensile strength	Glove	3.3	4.4.1	S-3*	2.5
Percentage elongation	Glove	3.3	4.4.1	S-3	2.5
Freedom from pinholes	Glove	3.5	4.4.2	S-3	2.5
Low temperature flexibility	Glove	3.7	4.4.4	S-1	2.5
High temperature exposure	Glove	3.8	4.4.5	S-1	2.5

* Tensile strength shall be run on a minimum of 25 gloves.

4.2.3 Sample unit usage. Where feasible, the same sample unit shall be used for determination of two or more test characteristics.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

4.3 Examination. The gloves shall be examined to determine compliance with all requirements contained in this specification. Examination shall be conducted as specified in Tables II and V, and in accordance with MIL-STD-105. Inspection, however, shall not be restricted to defects listed in Table V. Any glove in the sample containing one or more defects shall be rejected (defective) and if the number of defective gloves in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected (see 4.2.1)

Table V. Classification of Defects

Categories	Defects
Critical:	None defined
Major:	
101	Tears, Large holes.
102	Large open blisters.
103	Imbedded grit-like particles.
104	Excessively thin spots (under 0.002 inch).
105	Tackiness.
106	Pinholes.
107	Gloves adhering to each other.
108	Gloves not having a small continuous bead at the cuff end.
109	Foreign matter present.
Minor:	
201	Fingertips over 0.0045 inch thick.
202	Palm thickness over 0.008 inch.
203	Wrist thickness over 0.008 inch.
204	Short, gloves under 9-3/4 inches.
205	Excessive blisters that would interfere with accepted professional use (cluster of small blisters as contrasted with large open blisters.)
206	Bloom, bleeding, strings, and other imperfections.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

4.4.1 Physical requirements tests shall be conducted in accordance with American Society for Testing and Materials, Method D 882.

4.4.2 Pinhole test. Gloves shall be filled with 300 milliliters of water and held suspended from the cuff end for 5 minutes. Gloves shall be examined for leaks.

4.4.3 Leakage test. (unit package) The finished sealed unit package (comprising 50 gloves shall be held at ambient conditions for at least 4 hours prior to performing the submersion test described herein. The sample shall be immersed in water at a temperature of 35° F $\pm$ 2° F for 1 hour. The sample shall be immersed so that the top surface of the sample is 1 inch below the surface of the water. After removal, the sealed unit package shall be opened and inspected.

4.4.4 Low Temperature flexibility. The glove shall be placed on a wooden rack and exposed in a low temperature cabinet so that it is at a temperature of -20° F for a minimum of $\frac{1}{2}$ hour. It shall then be manipulated with a stick, or other non-conductive rod, to determine if it will flex without cracking.

4.4.5 High temperature exposure. The glove shall be exposed in a mechanical convection oven for 72 hours at 165° F. Upon removal and cooling of the glove, it shall be examined for exudation, tackiness or other deterioration.

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified, (see 6.1).

5.1.1 Unit of issue. One package containing 50 gloves, as specified, constitutes one unit of issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

5.1.2 Packaging quantities. The number of units of issue indicated in Table VI shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table VI Packaging Quantities

Unit package	Intermediate package	Exterior container
1 Unit	Not required	12 Units

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units may be packed in an exterior container or suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package. Fifty gloves shall be packages in a suitable top opening dispenser type paperboard carton of appropriate size and design. Commercial colors are acceptable on the the carton and closure shall be adequate to prevent spilling of contents under normal handling.

5.1.4 Level C. Units shall be packaged in standard commercial container of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.1).

5.2.1 Level A.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

5.2.1.1 Exterior container. Exterior container shall be designed for type 2 load, and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2, or PPP-B-636, class weather-resistant Grade V3. Closure and strapping shall be in accordance with appendix of applicable box specification. In addition, each fiberboard box shall be waterproofed in accordance with paragraph 30.4 of PPP-B-636.

5.2.1.2 Case Liner. Each Level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes.

5.2.2 Level B

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-636, class domestic. Closure shall be as specified in the appendix of the box specification.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Unit packages. Each unit package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

(ASTM) AMERICAN SOCIETY FOR TESTING AND MATERIALS

6. NOTES.

6.1 Ordering data. Procurement documents should specify the following:

(a) Number and date of this specification.
(b) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.2 This specification is intended to cover types which are normally procured to meet Military requirements. It does not include all types, classes or sizes as indicated by the title, nor all types which are commercially available.

6.3 The glove covered by this specification is designated as FSN 6515-477-6722, Glove, Patient Examining and Treatment, Plastic, Non-Sterile. This glove differs from two other patient examining and treatment gloves (covered by other specifications) as indicated by the underlined characteristics:

6515-226-7692, Glove, Patient Examining and Treatment, Plastic, Sterile

6515-462-0832, Glove, Patient Examining and Treatment, Rubber Latex, Non-Sterile.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review Activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency -DM

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:52Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION
MIL-G-36593 FSN

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 68 1426 REPLACES EDITION OF 1 OCT 64, WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 202640-21T08:52Z
Check the source to verify that this is the current version before use.

CAUTION

NOTICE TO BIDDERS/OFFERORS

DO NOT CONDITION OR BASE YOUR BID/OFFER ON ANY CURRENT PROCUREMENT ON THE INFORMATION SUBMITTED ON THIS FORM SINCE ANY CHANGES OR DELETIONS IN THE SPECIFICATIONS MAY RENDER YOUR BID/OFFER NON-RESPONSIVE IN WHICH CASE IT CANNOT BE CONSIDERED FOR AWARD.

Fold

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

DEFENSE SUPPLY AGENCY
OFFICIAL BUSINESS

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

Fold

DPSC FORM 2418
MAR 66

EDITION AUG 66, WILL BE USED UNTIL EXHAUSTED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.