MIL-G-36596A
2 February 1978
SUPERSEDING
MIL-G-36596
15 September 1969

MILITARY SPECIFICATION

GLOVES, SURGEONS', STERILE, DISPOSABLE

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

* 1.1 Scope. This specification covers sterile, disposable, surgeons' natural rubber latex gloves, suitable for use in performing surgical procedures and physical examinations.

2. APPLICABLE DOCUMENTS

* 2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bid or request for proposal form a part of this specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

PPP-B-566 - Boxes, Folding, Paperboard.
PPP-B-636 - Boxes, Shipping, Fiberboard.
PPP-B-676 - Boxes, Setup.

MILITARY

MIL-S-36586 - Sterilization Test Strip Set, Bacterial Spore.

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Defense Personnel Support Center, Directorate of Medical Materiel, DPSC-ATT, 2800 South 20th Street, Philadelphia, PA 19101, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

FSC 6515

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED. TEST METHOD STD. NO. 601 - Rubber: Testing and Sampling

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of specifications, standards, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bid or request for proposal shall apply.

U. S. PHARMACOPEIAL CONVENTION, INC. (USP)

Pharmacopeia of the United States

(Application for copies should be addressed to the Mack Publishing Company, Easton, PA 18042.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

3. REQUIREMENTS

* 3.1 Materials.

3.1.1 Gloves. The gloves shall be fabricated from natural rubber latex, free from coloring and fillers.

* 3.1.2 Dusting powder. Gloves shall be uniformly prepowdered with vegetable powder that shall be biologically absorbable and nontoxic. The minimum amount of powder is preferred. Powder shall be in accordance with the USP for Absorbable Dusting Powder.

Source: https://assist.dla.mil -- Downloaded: 20261O-21T08:52Z
Check the source to verify that this is the current version before use.

3.2 Style and design. The surgeons' gloves shall be supplied as a matching pair (conventional left and right hand), sterile, and suitable for performing physical examinations and surgical procedures. The gloves shall be constructed to facilitate maximum tactility in use, and shall have straight or curved, well-fitting fingers that permit maximum freedom of movement. The palm section shall be of sufficient width to permit comfortable flexing of the hands. The wrists shall be tapered or constricted to conform and adhere to wrist and forearm to minimize "roll down". A bead or band at the wrist of the glove is acceptable. The gloves shall be supplied in a folded inner wrapper which in turn shall be enclosed in an outer wrapper as specified in 3.2.2. The gloves shall be placed flat, prior to folding the inner wrapper over gloves, without rolling or folding, except that the wrist portion shall be folded inside out over the palm. The inner wrapper shall be of sufficient size to permit flat placement of the gloves and shall completely cover and separate both gloves. When a paperboard inner wallet is used, the cuff of the glove shall be folded back over the wrist. The folded cuff may be placed over a pedestal with the glove to the inside. The wallet shall then be folded close over the pedestal. The gloves shall be packaged in such a manner as to permit ready identification of the left and right hand gloves, and permit ready dispensing of the gloves by sterile technique.

* 3.2.1 Dimensions and weight. Dimensions shall be measured as specified in 4.5.1. Dimensions and weight of the gloves shall be as indicated in table I. The gloves shall have the following single thickness:

Finger tip (measured within 1 inch from tip)	0.005 to 0.009 inch
Palm	0.005 to 0.010 inch
Wrist	0.005 to 0.012 inch

TABLE I. Dimensions and weight.

Size	Length 1/ (inches, minimum)	Circumference of palm 2/ (inches, -1/8 + 1/2)	Weight per dozen pair (ounces, minimum)
6	10	6	6
6-1/2	10	6-1/2	6-1/2
7	10	7	7-1/4
7-1/2	10	7-1/2	8
8	10	8	9
8-1/2	10	8-1/2	9-3/4
9	10	9	10-1/2

1/ Measured from the tip of the middle finger to the end of the gauntlet.
2/ Measured at a level between the base of the index finger and the thumb.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

3.2.2 Individual package. The completed, individual package shall consist of a pair of gloves in an inner wrapper or paperboard wallet enclosed in turn in an outer sealed wrapper. The outer wrapper shall maintain the sterility of the inner packaging and its contents. Outer wrapper shall permit ready dispensing of the contents by sterile techniques. Closure of the outer wrapper shall be accomplished by heat or cold sealing. The sealed outer wrapper shall be designed to strip cleanly, without leaving jagged edges of paper extending into the sterilized field more than 5/16 inch, or otherwise contaminating the contents.

* 3.3 Physical requirements. The gloves, after having been sterilized, shall comply with the physical requirements contained in table II. Tests shall be conducted as specified in 4.5.2.

TABLE II. Physical requirements.

Characteristics	Values
Tensile stress at 500 percent elongation	800 pounds per square inch, maximum
Tensile strength	3500 pounds per square inch, minimum
Ultimate elongation	700 percent, minimum
Accelerated aging	
Tensile strength	75 percent of original, minimum
Ultimate elongation	700 percent, minimum
Specific gravity	$0.95 \pm \begin{matrix} .02 \\ .05 \end{matrix}$

3.4 Sterility and maintenance of sterility requirements. The completed individual package, consisting of a pair of gloves enclosed in an inner wrapper, which in turn is enclosed in a sealed outer wrapper, shall be sterilized. The outer wrapper shall then maintain the sterility of its contents. The entire unit shall then comply with the requirements contained in the following paragraphs:

3.4.1 Deterioration. After sterilizing, the prepowdered gloves, inner and outer wrappers, shall show no visual signs of deterioration or other detrimental effects. Discoloration of the wrapper shall not be considered as deterioration. The markings on the gloves (see 3.6.1) shall remain legible and shall not rub off.

* 3.4.2 Freedom from pinholes. The gloves shall be supplied free of pinholes as shown by the absence of leakage when tested as specified in 4.5.5 or 4.5.5.1.

* 3.4.3 Sterility. The entire contents of the outer wrapper shall be sterile. The gloves shall comply with requirements for sterility when tested with a biological indicator as specified in 4.5.3.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:52Z
Check the source to verify that this is the current version before use.

3.4.3.1 Certificate of sterility. A certificate of sterility, stating that samples from each sterilizer lot have been tested and found to be sterile, shall be submitted to the procuring activity. The certificate of sterility shall include:

a. Item identification.
b. National stock number (NSN).
c. Contract or purchase order number.
d. Sterility lot or control number.
e. Date of sterilization.
f. Quantity of product in sterilizer lot.
g. Type of sterilization (gas, radiation, heat, steam, etc.).
h. Form of biological indicator (i.e., inoculated paper spore strip or carrier, inoculated product, or inoculated simulated product).
i. Test organism(s) and population density used.
j. Test medium, incubation temperature, incubation time, and dates of tests.
k. Number of test units.
l. Statement that samples comply with sterility tests.
m. Signature of head of laboratory or a designated qualified alternate.

When inspection is made at destination, the certificate of sterility shall be submitted by the contractor to the Defense Personnel Support Center, Directorate of Medical Materiel, Technical and Quality Assurance Division, ATTN: DPSC-ATQ, 2800 South 20th Street, Philadelphia, PA, 19101, and a copy forwarded with each shipment to the consignee. When inspection is made at source, certificate of sterility shall be furnished to the cognizant Government Quality Assurance Representative for submission to the procuring activity.

3.4.3.2 Sterility lot. A sterility lot is that single quantity of product subjected to the same manufacturing operation and sterilized simultaneously in the same sterilizer chamber. Each unit package shall be clearly marked with a sterility lot (control) number and date of sterilization as specified in 5.3.2. Each sterility lot shall be traceable to the pertinent manufacturing lot(s).

* 3.4.4 Dispensability. The outer wrapper of the sterile, completed unit shall be capable of being opened without endangering the sterility of its contents when tested as specified in 4.5.4.

3.5 Finish. The gloves shall have a uniform smooth finish, free from holes, visible ingrained particles, snapback, tackiness, bloom, strings, bleeding, and other imperfections.

3.6 Identification marking

3.6.1 Gloves. The gloves shall be legibly and permanently marked with the appropriate size. The name or registered trademark of the contractor may be present.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

* 3.6.2 Outer wrapper. The outer wrapper shall be labeled or marked to identify the contents to include the glove size, name of contractor, instructions for opening (see 3.7), and the legend "STERILE". The outer wrapper may be marked with the legend "DISPOSABLE". The outer wrapper shall have the following imprinted on it in letters 1/8 inch or more in height: "Powder should be removed from the gloves after donning by wiping the gloves thoroughly with a sterile wet sponge, sterile wet towel, or other effective method." (see 6.1).

3.7 Instructions. Each outer wrapper shall be marked with instructions describing the proper technique for dispensing the sterile contents from the outer wrapper without compromising the sterility of the contents.

* 3.8 Workmanship. Workmanship shall be first class throughout. Gloves shall be free from defects which detract from their appearance or impair their serviceability. Gloves shall be packed under patently sanitary conditions, and there shall be no indication of soil or any foreign material on them or in the envelope (outer wrapper).

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three (3) years after delivery of the supplies to which such records relate.

* 4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual and auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

* 4.2 Sampling.

* 4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as indicated in table III. The unit of product for examination purposes shall be one glove.

TABLE III. Sampling for examination.

Type defect	Inspection level	AQL (percent defective)
Major	S-4	1.0
Minor	S-4	2.5

* 4.2.2 For tests. Sampling for tests shall be in accordance with MIL-STD-105 and as indicated in table IV. The unit of product for test purposes shall be one glove. Where possible, the same sample unit shall be used for the determination of two or more test characteristics.

TABLE IV. Sampling for tests.

Characteristic	Requirement	Test procedure	Inspection level	AQL (percent defective)
Dispensability	3.2, 3.4.4 and 3.7	4.5.4	S-1	1.0
Dimensions	3.2.1 and Table I	4.5.1	S-1	1.0
Physical	3.3	4.5.2 and Table VI	S-2	1.0
Freedom from pinholes	3.4.2	4.5.5	S-4	1.5
Sterility	3.4.3	4.5.3	S-3	*

* Acceptance number shall be zero.

4.3 Examination. The gloves shall be examined to determine compliance with all requirements contained in this specification. Visual examination shall include inflation of the gloves to be examined. This inflation shall be limited to 350 percent ± 50 percent elongation on any part of the glove. Examination shall be conducted as specified in tables III and IV. Examination, however, shall not be restricted to defects listed in table V. Any glove in the sample containing one or more defects shall be rejected and if the number of defective gloves in any sample exceeds the acceptance number for that sample, the lot represented by the sample shall be rejected.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:52Z
Check the source to verify that this is the currentversion before use.

TABLE V. Classification of defects.

Categories	Defects
Major	
101	Tears, large holes.
102	Large, open blisters.
103	Imbedded particles.
104	Caution notice missing (see 3.6.2).
105	Thin spots (under 0.005 inch thick).
106	Tackiness.
107	No inner wrapper included.
108	Gloves in inner wrapper doubled over upon themselves.
109	Foreign matter present in envelope.
Minor	
201	Short, gloves under 10 inches.
202	Blisters that would interfere with accepted professional use (clusters of small blisters as contrasted with large open blisters).
203	Snapback, bloom, strings, bleeding, or other imperfections.
204	Excessive amount of dusting powder present.

* 4.4 Packaging inspection. The inspection of the unit, intermediate package, packing and marking for shipment and storage shall be in accordance with the quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129.

* 4.5 Tests. Tests shall be conducted to determine compliance with specification requirements. All samples or test specimens intended for accelerated aging tests shall be protected from any unnecessary exposure to strong light prior to the aging. The samples and specimens shall be kept in light-tight containers, except while being inspected, prepared or measured.

* 4.5.1 Dimensions. Dimensions shall be in accordance with the FED. TEST METHOD STD. NO. 601, indicated in table VI.

* 4.5.2 Physical requirements. Physical requirements tests shall be conducted in accordance with the FED. TEST METHOD STD. NO. 601, indicated in table VI.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

TABLE VI. Test methods.

Requirement	Test Method No.
Thickness	2011 or 2031
Tensile stress	4131 1/
Tensile strength	4111 1/
Ultimate elongation	4121 1/
Accelerated aging (Oxygen pressure test)	7111 1/
Specific gravity	14011 or 14021

1/ Use dumbbell specimen cut with die III of Figure 4111.

* 4.5.3 Sterility test. The gloves shall be tested for sterility in accordance with the method specified in the USP using inoculated product, inoculated simulated product, or paper spore strip (carrier). Product containing a biological indicator shall be marked or labeled so that it clearly differentiates from the product intended for distribution. The incubation medium and minimum time in each case shall be soybean casein digest for 7 days for inoculated product, inoculated simulated product, or paper spore strip (carrier). The incubation temperature shall be as indicated in 4.5.3.1. The minimum number of test units, regardless of lot size, shall be ten (10), except for inoculated carrier which shall be twenty (20) for Type I Sterilization and thirty (30) for Type II Sterilization, including inoculated carrier and product test units. The inspection level shall be as indicated in table IV.

* 4.5.3.1 Inoculated product or simulated product. For each type of sterilization, the organism used shall be as listed below:

Type of Sterilization	Organism	Incubation Temperature
Steam	B. stearothermophilus	55° - 65°C
Dry Heat	B. stearothermophilus, or	55° - 65°C
	B. subtilis var. niger (or globigii)	30° - 35°C
Gas	B. subtilis var. niger (or globigii)	30° - 35°C
Radiation	B. pumilus	30° - 35°C

The number of viable cells shall be sufficient to provide assurance that the product has been sterilized.

* 4.5.3.2 Inoculated carrier. Inoculated carriers (paper spore strips), if used, shall be in accordance with MIL-S-36586. Other paper carriers shall be inoculated to be of equivalent resistance. The method of incubation and number of test units shall be as indicated in 4.5.3 and 4.5.3.1. The method of sterilization will control the one organism in the spore strip to be tested for, as shown in 4.5.3.1.

When an inoculated carrier is chosen, product samples must also be tested as required by the USP.

Source: https://assist.dla.mil -- Downloaded: 2026l0-21T08:52Z
Check the source to verify that this is the current version before use.

* 4.5.3.3 Alternate method. Suppliers conducting sterility tests or designating lots in a manner other than that indicated herein shall submit proof that the alternate method provides equal assurance concerning the sterility of the product. However, all sterility tests shall be conducted using biological indicators. Requests for approval of any alternate method of testing for sterility shall be made to the Contracting Officer, and approval obtained before employment of the alternate method on a government contract.

* 4.5.3.4 Product testing. Testing for sterility of the product after receipt by the government shall be without a biological indicator and in accordance with the USP.

* 4.5.4 Dispensability test. The outer wrapper shall be opened, and the gloves removed in accordance with instructions provided (see 3.7).

* 4.5.5 Pinhole test. Gloves shall be inflated with air to a pressure of 20 millimeters of mercury while immersed in water at 70° to 75°F. (21° to 24°C) to observe pinholes. The gloves shall be manipulated so that the hand of the tester does not remain on one spot of the glove and thus obscure possible leakage.

* 4.5.5.1 Alternate pinhole test. Glove shall be inflated with air to a pressure of 12 to 14 mm of mercury. The glove is then sealed at the cuff. Examination shall be made after 15 minutes to determine the absence of a leak as evidenced by partial or complete deflation of glove.

5. PACKAGING

* 5. PACKAGING

5.1 Packaging. Packaging shall be level A or C, as specified (see 6.2).

5.1.1 Unit of issue. One package containing thirty-six (36) pairs of gloves, as specified, constitutes one unit of issue.

5.1.2 Level A.

5.1.2.1 Unit packaging. Each unit, thirty-six pairs of gloves and each pair individually packaged as specified in 3.2.2, shall be packaged in a box conforming to PPP-B-566, PPP-B-636, class domestic or PPP-B-676. Closure shall be as specified in the appendix of the applicable box specification. As an alternate, the unit package may be a dispenser type box of an appropriate size and design fabricated of not less than 0.018 inch board. Closure shall be adequate to prevent spilling of contents under normal handling.

5.1.3 Level C. Each unit, thirty-six pairs of gloves and each pair individually packaged as specified in 3.2.2, shall be packaged in a manner that will afford adequate protection against deterioration and physical damage during shipment from the supply source to the first receiving activity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

5.2 Packing. Packing shall be level A, B or C, as specified (see 6.2).

5.2.1 Level A. Twelve unit packages shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-636, class weather-resistant. Closure, strapping and waterproofing shall be as specified in the appendix of the box specification.

5.2.2 Level B. Twelve unit packages shall be packed in an exterior container designed for a type 2 load and conforming to PPP-B-636, class domestic. Closure shall be as specified in the appendix of the box specification.

5.2.3 Level C. The packaged gloves shall be packed in shipping containers in a manner that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier's rules and regulations.

5.3 Marking.

5.3.1 Individual package. Each individual package shall be marked as specified in 3.6 and 3.7.

5.3.2 Unit package. Each unit package shall be marked in accordance with MIL-STD-129. Sterility lot (control) number, glove size, and name of manufacturer shall be shown. If the manufacturer is not the contractor, the name of contractor shall also be shown. The method of sterilization (G-Gas, R-Radiation, C-Cold, S-Steam, D-Dry Heat sterilization) shall be shown following the level of packaging and date of packaging. Example: "A 1/77-G". Final sterilization shall be on or after indicated packaging date.

5.3.3 Exterior container. Exterior containers shall be marked in accordance with MIL-STD-129. Sterility lot (control) number and method of sterilization as specified in 5.3.2 shall be shown.

6. NOTES

6.1 Dusting powder. There is increasing evidence that granulomatous conditions following operations may have been caused by the introduction of dusting powder into a wound site. For this reason, surgeons follow the practice of removing the powder from the exterior of the gloves after donning and before operating by wiping thoroughly with a sterile wet sponge or sterile wet towel.

* 6.2 Ordering data. Procurement documents shall specify the following:

a. Title, number, and date of this specification.
b. Applicable levels of packaging and packing (see 5.1 and 5.2).
c. Applicable size (see 3.2.1).
d. Applicable NSN.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

* 6.3 This specification covers the following items appearing in the Federal Supply Catalog:

National Stock Number	Item Identification
6515-00-782-6471	GLOVES, SURGEONS', Sterile, Disposable, Size 6, 36 pair
6515-00-782-6472	GLOVES, SURGEONS', Sterile, Disposable, Size 6-1/2, 36 pair
6515-00-782-6473	GLOVES, SURGEONS', Sterile, Disposable, Size 7, 36 pair
6515-00-782-6474	GLOVES, SURGEONS', Sterile, Disposable, Size 7-1/2, 36 pair
6515-00-782-6475	GLOVES, SURGEONS', Sterile, Disposable, Size 8, 36 pair
6515-00-782-6476	GLOVES, SURGEONS', Sterile, Disposable, Size 8-1/2, 36 pair

6.4 Changes. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activity:
DOD-MB

Preparing activity:
DLA-DM

Project No. 6515-2058

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:52Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS: This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.

NOTE: This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-G-36596A GLOVES, SURGEONS', STERILE, DISPOSABLE

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:52Z
Check the source to verify that this is the current version before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

POSTAGE AND FEES PAID

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-21T08:52Z
Check the source to verify that this is the current version before use.