O-C-303D
AMENDMENT 1
August 1, 1986

FEDERAL SPECIFICATION

CHROMIUM TRIOXIDE, TECHNICAL

This amendment which forms a part of Federal Specification O-C-303D, dated August 13, 1985, is approved by the Assistant Administrator, Office of Federal Supply and Services, General Services Administration, for the use of all Federal agencies.

PAGE 1

1.1, line 1: After "flake" add "or crystalline".

PAGE 3

3.1, line 2: Delete "flakes," and substitute "flakes or crystals,".

PAGE 4

3.3: Delete in its entirety and substitute the following:

"3.3 Particle size. No more than 30 percent by weight of flake form chromium trioxide shall pass through a standard 600-micrometer sieve and no more than 25 percent by weight of crystalline form chromium trioxide shall pass through a standard 420-micrometer sieve when tested as specified in 4.2.4.6."

PAGE 7

4.2.4.6, line 2: Delete "600-micrometer".

4.2.4.6, line 3: After "pan." add "Use a 600-micrometer sieve for flake form chromium trioxide or a 420-micrometer sieve for crystalline form trioxide."

FSC 6810

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:13Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians:

Army - EA
Air Force - 68

Review activities:

Army - AR, MD, ME, MI
DLA - GS
Other - DS

User activities:

Army - ER
Navy - AS, OS

CIVIL AGENCY COORDINATING ACTIVITIES:

AGR-APS
GSA-10FCE
VA-OSS

Preparing activity:

Army - EA

Project No. 6810-B554

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T11:13Z
Check the source to verify that this is the current version before use.