COMMERCIAL ITEM DESCRIPTION

COVER, PILLOW

The General Services Administration has authorized the use of this Commercial Item Description as a replacement for Military Specification MIL-C-36185A which is cancelled.

This Commercial Item Description covers a plastic pillow cover.

Salient characteristics:

The pillow cover shall be a plastic cover suitable for use in hospitals to protect pillows from soilage. The cover shall be impervious to moisture, dust, blood, saliva, perspiration, oil, grease, and alcohol. The cover shall not stain or discolor from contact with blood, saliva, oil, grease, or alcohol when tested as specified. The cover shall be supplied in the following two sizes:

Size 1 - 19 inches plus 1/2 inch minus 1/4 inch by 31 inches plus 1/2 inch minus 1/4 inch.

Size 2 - 22-1/4 inches plus or minus 1/4 inch by 29-1/4 inches plus or minus 1/4 inch.

The cover shall be fabricated of nonrigid vinyl plastic material 0.004 inch plus or minus 0.0004 inch thick. The vinyl plastic material shall have a tensile strength of 2200 PSI minimum. The material shall resist boiling and stains, shall be flame retardant and non-toxic. The vinyl plastic shall be joined by heat sealing.

As an alternate, the cover shall be fabricated of nonrigid, high-strength, flame retardant, anti-bacterial, non-toxic, moisture-repellant, vinyl-nylon laminate. The laminate shall have a weight of 6.2 ounces plus or minus 0.6 ounce per square yard and a tensile strength of not less than 65 pounds per linear inch in either direction. The laminate shall be white in color. The vinyl-nylon laminate shall be joined by heat sealing or stitching.

AMSC N/A FSC 7210

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:29Z
Check the source to verify that this is the current version before use.

The pillow cover shall consist of either one or two panels of sheeting. When one panel of sheeting is used, the panel shall be folded along one edge and then heat sealed along the two side edges. When two panels of sheeting are used, one panel shall be superimposed upon the other and the appropriate three sides of the cover shall be heat sealed. As an alternate, pillow covers made of vinyl-nylon laminate may be stitched.

A plastic flap of non-rigid vinyl plastic or vinyl-nylon laminate shall be located near one end of the cover. The flap shall be long enough to permit the open end of the cover to be adequately closed after insertion of a proper size pillow.

All heat seals shall be continuous, uniform, and neatly made and shall not weaken the basic material. The width of each heat seal shall be a minimum of 1/8 inch. The strength of the bond shall be not less than 65 percent of the tensile strength of the sheeting when tested as specified.

All stitched seams shall be stitched with a minimum of 5 stitches per inch using a suitable cotton or synthetic thread. Stitched seams shall have a breaking strength of at least 20 pounds per linear inch for nylon laminate, and not less than 65 percent of the tensile strength of the vinyl plastic sheeting when tested. All seams shall be straight and uniform, and made so that edges of the sheeting are on the inside of the finished cover.

The pillow cover shall be free of cuts, tears, pinholes, or thin areas. The cover shall be free of oil, grease, dirt, or other contamination.

Workmanship. The pillow cover shall be free from defects which detract from its appearance or impair its serviceability.

Unit. Each (EA). One cover, as specified, constitutes one unit.

Quality Assurance Provisions.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:29Z
Check the source to verify that this is the current version before use.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

Sampling for tests. One pillow cover shall be randomly selected for testing from each lot of 200, or less, pillow covers offered to the government. If the pillow cover fails to meet the requirements of this specification, ten more pillow covers shall be selected from the lot for testing. If one or more of the ten pillow covers fails, the lot shall be rejected. Tests shall be conducted in accordance with this document.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more test characteristics. Each unit selected according to the sampling plan shall be tested, and a failure of two or more units, according to the sampling plans, shall be cause for rejection of the entire lot.

Heat sealed seam strength test. The bond strength of the heat sealed seams shall be determined as specified in ASTM D-882, except that tests shall be performed on one seam per cover.

The seam specimen to be tested shall be one inch wide and shall be cut from any point along the seam. For breaking (bonding) strength of the bonded seam, the seam shall be at the center of the specimen and perpendicular to the center line. The free ends of the specimen shall be gripped (one in each jaw) in the testing machine. A bond strength less than 65 percent of the tensile strength of the sheeting shall constitute a failure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:29Z
Check the source to verify that this is the current version before use.

Stitched seam strength test. The seam strength test of the stitched pillow cover shall be performed on one stitched seam per cover. The seam specimen to be tested shall be one inch wide and shall be cut from any point along the seam. For breaking strength of the stitched seam, the seam shall be at the center of the specimen and perpendicular to the center line. The free ends of the specimen shall be gripped (one in each jaw) in the testing machine. A breaking strength of less than 20 pounds per linear inch shall constitute a failure.

Resistance to boiling water test. (vinyl plastic sheeting only). The vinyl plastic pillow cover shall be placed in boiling water for six hours. Failure for the cover to remain free from brittleness or stickiness shall constitute a failure.

Stain resistance to blood or saliva test. Pour 5 ml of blood (human, warm blooded animal, or fowl) or saliva (human) on a specimen of pillow cover sheeting 12 inches square. Spread the blood or saliva to a thin even layer. After drying, the dried specimen shall be allowed to remain in contact with the plastic film for 24 hours. The specimen shall then be washed off with a cloth or sponge using soap and water. Any residual stains or discoloration shall constitute a failure.

Stain resistance to oil or grease test. Pour 5 ml of oil (light mineral oil, USP, or castor oil, USP), or 5 grams of petrolatum, on a specimen of plastic sheeting 12 inches square. Spread the oil or petrolatum to a thin layer. Allow the oil or petrolatum to remain in contact with the plastic film for 24 hours. The specimen shall then be washed off with a cloth or sponge using soap and water. Any residual stains or discoloration shall constitute a failure.

Stain resistance to alcohol test. Pour 5 ml of rubbing isopropyl alcohol or 70 percent ethyl alcohol on a specimen of plastic sheeting 12 inches square. Spread to a thin layer. Permit the alcohol to evaporate at room temperature. Repeat the procedure every half hour for four hours, wash with a cloth or sponge using soap or water. Any residual stains or discoloration shall constitute a failure.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:29Z
Check the source to verify that this is the current version before use.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the latest revision of Federal Standard 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the product is acceptable.

The contracting officer has the option of accepting or rejecting the product.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers' own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Regulatory requirements.

Federal Food, Drug and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug and Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal, State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Public Law 94-580, as amended, and as implemented by Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:29Z
Check the source to verify that this is the current version before use.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

Ordering data. Intermediate/exterior package quantities, labeling, and marking must be specified in the contract and/or order.

NOTES: 1. The following National Stock Numbers are covered by this document:

7210-00-715-9200 (Size 1)

7210-01-023-5026 (Size 2)

2. The Size 2 pillow cover is intended for use with pillow, NSN 7210-00-119-5358.

MILITARY INTERESTS:

Custodians:

Army - MD
Navy - MS
Air Force - 03

PREPARING ACTIVITY:

DoD - MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

Project No. 7210-0283

Location:
CID/COVER/PILLOW/H-13-30

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:29Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1 DOCUMENT NUMBER	2 DOCUMENT TITLE
A-A-54103	COVER, PILLOW

3a. NAME OF SUBMITTING ORGANIZATION	4 TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*

5 PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6 REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:29Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS *In a continuing effort* to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to p s suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, d mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEFENSE LOGISTICS AGENCY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 4966 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEFENSE LOGISTICS AGENCY

Commander
Defense Personnel Support Center
ATTN: DPSC- RSTE
2800 South 20th Street
Philadelphia, Pennsylvania 19101-8419

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:29Z
Check the source to verify that this is the current version before use.