MIL-STD-1393B
20 January 1982
SUPERSEDING
MIL-STD-1393A
29 August 1975

MILITARY STANDARD

PROVISIONS FOR EVALUATING QUALITY

OF

COATED FABRIC RAINCOATS

FSC 8405

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:17Z
Check the source to verify that this is the current version before use.

DEPARTMENT OF DEFENSE

WASHINGTON, D.C. 20301

Provisions for Evaluating Quality of Coated Fabric Raincoats

1. This standard has been approved by the Department of Defense and is mandatory for use by the Departments of the Navy, Marine Corps, Army and Air Force.

2. Beneficial comments (recommendations, additions, and deletions) and any pertinent data which may be of use in improving this document should be addressed to: Officer in Charge, Navy Clothing and Textile Research Facility, 21 Strathmore Road, Natick, MA 01760 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:17Z
Check the source to verify that this is the current version before use.

FORWARD

This standard provides a standardized procedure for evaluating quality of coated fabric raincoats procured by the Department of Defense.

The objectives of this standard are to:

a. Provide standard descriptions for defects.
b. Standardize examination requirements.

Coated Fabric Raincoat specifications that will reference this standard are:

MIL-R-16402 - Raincoat, Man's: Nylon, Rubber Coated; Green
MIL-R-17657 - Raincoat, Man's (Foul Weather)
MIL-R-28975 - Raincoat, Man's: Lightweight, Polyurethane Coated
MIL-R-29103 - Raincoat, Man's, Lightweight, Coated
MIL-R-82190 - Raincoat, Woman's: Nylon, Rubber Coated; Green

Source: https://assist.dla.mil -- Downloaded: 202640-24T00:17Z
Check the source to verify that this is the current version before use.

CONTENTS

Paragraph		Page
1.	SCOPE	1
1.1	Purpose	1
1.2	Application	1
2.	REFERENCE DOCUMENTS	1
2.1	Issue of Documents	1
3.	DEFINITIONS	1
3.1	Fabric Defects	1
3.2	Quality Assurance Terms	1
3.3	Open Seam	1
3.4	Defective Button	2
3.5	Inside-outside	2
3.6	Knots and Slubs	2
4.	GENERAL	
5.	SAMPLE AND INSPECTION PROVISIONS	2
5.1	End Item Examination	2
5.2	Dimensional Examination	3
5.3	Matching Sizes Examination	3
5.4	Packaging Examination	3
5.5	Pinholes Examination	4
6.	INSPECTION	5
6.1	Inspection Procedure	5
6.2	Initiation of Inspection	5
6.3	Continuation of Inspection	5
6.4	Switching Procedures	5
6.4.1	Normal to Tightened	5
6.4.2	Tightened to Normal	5
6.4.3	Normal to Reduced	5
6.4.4	Reduced to Normal	5

TABLES

Number		Page
I	Sampling Provisions for Coated Fabric Raincoats	4
II	Classification of Defects	6

Source: https://assist.dla.mil -- Downloaded: 202610-24T00:17Z
Check the source to verify that this is the current version before use.

1. SCOPE

1.1 Purpose. The purpose of this standard is to provide standardized provisions for evaluating quality of coated fabric raincoats.

1.2 Application. This standard will be made applicable to contracts by references in the appropriate coated fabric raincoat specification.

2. REFERENCE DOCUMENTS

2.1 Issue of documents. The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this standard to the extent specified herein.

STANDARDS

FEDERAL

FED-STD-4 - Glossary of Fabric Imperfections

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes
MIL-STD-109 - Quality Assurance Terms and Definitions
MIL-STD-1487 - Glossary of Cloth Coating Imperfections

(Copies of specifications, standards, drawings and publications required by contractor in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Technical Manual of the American Association of Textile Chemists and Colorists

(Application for copies shall be addressed to the American Association of Textile Chemists and Colorists, P.O. Box 12215, Research Triangle Park, North Carolina 27709.)

3. DEFINITIONS

3.1 Fabric defects. The fabric defect definitions applicable to the standard are described in FED-STD-4 and MIL-STD-1487. All other defect descriptions in this standard are intended to be self-explanatory.

3.2 Quality assurance terms. Definitions of quality assurance terms shall be in accordance with MIL-STD-105 and MIL-STD-109.

3.3 Open seam. The seam shall be classified open when one or more stitches joining a seam are broken or when two or more skipped or runoff stitches occur.

Source: https://assist.dla.mil -- Downloaded: 202640-24T00:17Z
Check the source to verify that this is the current version before use.

3.4 Defective button. A button shall be considered defective when it has a sharp, rough, cracked or split edge; scratches, dents, blemishes, imbedded foreign matter, loose shank, loose shell or is badly shaded.

3.5 Inside-outside. The terms "outside" and "inside" as used in Table II in this standard for defects I, II and IV are defined as follows:

Outside - Any part of the raincoat that is visible when the raincoat is buttoned as normally worn.
Inside - Any part of the raincoat that is not visible when the raincoat is buttoned as normally worn.

The terms "outside" and "inside" as used in Table II in this standard for defects other than I, II and IV are defined as follows:

Outside - Any part, seam or stitching that appears on the outer raincoat. This includes the shoulder loop, sleeve tabs, belts, under the collar (including undercollar) and the back vent.

Inside - Any part, seam or stitching that does not appear on the outer raincoat.

3.6 Knots and slubs. Only knots and slubs that exceed the limits specified in the basic cloth specification shall be scored as defects in evaluating quality of this item.

4. GENERAL

4.1 This standard contains the provisions for end item examination, dimensional examination, pinhole examination, and the packaging examination for raincoats. If there are any inconsistencies between the requirement of the appropriate specification and the provisions of the standard, the specification shall control. This standard assigns to the listed defects, point values of 1, 2 or 3 depending on degree of severity. The higher point values are assigned to those defects having more detrimental effect on the appearance or serviceability of the item.

5. SAMPLE AND INSPECTION PROVISIONS

5.1 End item examination. The raincoats shall be examined and all defects shall be penalized as indicated in Table II of this standard. The sample size shall be as specified in Table I. The sample unit shall be one finished raincoat. The lot shall be unacceptable if:

a. The point value for 3 and 2 point defects exceeds the applicable maximum acceptable point value
b. The point value for total (3, 2 and 1 point) defects exceeds the applicable maximum acceptable point value

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:17Z
Check the source to verify that this is the current version before use.

5.2 Dimensional examination. The appropriate number of raincoats, determined from the table below, shall be examined for conformance to the dimensional requirements cited in the table of measurements of the appropriate raincoat specification. When a measurement deviates from a dimension and tolerance specified, the raincoat shall be penalized one point. The lot shall be unacceptable if the total point value exceeds the applicable point values specified below. Each size raincoat present in the lot shall be represented in the sample selected for this examination.

Lot size	Sample size	Point limit value
Up thru 500	8	0
501 thru 3200	13	1
3201 thru 35,000	20	2
35,001 and up	32	3

5.3 Matching sizes examination. The raincoats with liners, selected for the dimensional examination (see 5.2), shall be examined for defects in matching sizes, i.e., any raincoat with liner not of the same size shall be scored one point. The lot shall be unacceptable if the total point value resulting from this examination exceeds one point.

5.4 Packaging examination. An examination shall be made to determine that the packaging, packing and marking requirements are in compliance with Section 5 of the appropriate specification. Defects listed below shall be scored one point. The sample size for this examination shall be five shipping containers fully prepared for delivery with the exception that they need not be closed. Defects of closure listed below shall be examined on shipping containers fully prepared for delivery. The lot shall be unacceptable if one or more points are scored for this examination.

Examine	Defect
Marking (exterior and interior)	Omitted; incorrect, illegible; of improper size, location, sequence or method of application.
Materials	Any component missing, damaged, or not as specified.
Workmanship	Inadequate application of components, such as: incomplete closure of container flaps, loose strapping, improper taping, inadequate stapling. Bulged or distored container.
Content	Number of packages per shipping container is more or less than required. Number of raincoats per package is more or less than required. 1/ Size shown on one or more raincoats not as specified on shipping container. 1/

1/ For this defect, one package from each shipping container in the sample shall be examined.

Source: https://assist.dla.mil -- Downloaded: 202640-24T00:17Z
Check the source to verify that this is the current version before use.

5.5 Pinholes examination. The raincoats selected for dimensional examination (see 5.2), shall be given a through-light inspection for pinholes. The through-lighting inspection shall be performed in accordance with MIL-STD-1487. The lot shall be unacceptable if the total point value resulting from this examination exceeds 1 point.

Table I - Sampling Provisions for Coated Fabric Raincoats

	Lot size	Sample size	Maximum acceptable point values	
			3 & 2 point defects	3, 2 & 1 point defects
Normal Inspection	Up thru 90	20	5 points	9 points
	91 thru 150	32	9 points	15 points
	151 thru 280	50	16 points	24 points
	281 thru 500	80	23 points	35 points
	501 thru 1200	125	34 points	50 points
	1201 thru 3200	200	49 points	73 points
	3201 thru 10,000	315	72 points	115 points
	10,001 thru 35,000	500	104 points	146 points
	35,001 and over	800	151 points	225 points
Tightened Inspection	Up thru 90	20	2 points	4 points
	91 thru 150	32	4 points	8 points
	151 thru 280	50	7 points	14 points
	281 thru 500	80	18 points	28 points
	501 thru 1200	125	30 points	45 points
	1201 thru 3200	200	45 points	64 points
	3201 thru 10,000	315	65 points	103 points
	10,001 thru 35,000	500	75 points	116 points
	35,001 and over	800	143 points	213 points
Reduced Inspection	Up thru 280	13	1-3 points 1/	5 points
	281 thru 500	20	4-7 points 1/	9 points
	501 thru 1200	32	9-15 points 1/	15 points
	1201 thru 3200	50	16-19 points 1/	24 points
	3201 thru 10,000	80	23-29 points 1/	35 points
	10,001 thru 35,000	125	34-40 points 1/	50 points
	35,001 and over	200	49-55 points 1/	173 points

1/ If the first value is exceeded, but the second value has not been reached, accept the lot and reinstate normal inspection (see 6.4.4b). The second value is the maximum acceptable point value.

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:17Z
Check the source to verify that this is the current version before use.

6. INSPECTION

6.1 Inspection procedure. Inspection shall be as specified in MIL-STD-105, except where otherwise indicated in this document.

6.2 Initiation of inspection. Normal inspection will be used at the start of inspection unless otherwise directed by the procurement quality assurance element administrating the contract.

6.3 Continuation of inspection. Normal, tightened or reduced inspection shall continue unchanged on successive lots except where switching procedures in 6.4 require change.

6.4 Switching procedures.

6.4.1 Normal to tightened. When normal inspection is in effect, tightened inspection shall be instituted when two out of five consecutive lots have been rejected on original inspection (i.e., ignoring resubmitted lots for this procedure).

6.4.2 Tightened to normal. When tightened inspection is in effect, normal inspection shall be instituted when five consecutive lots have been considered acceptable on original inspection.

6.4.3 Normal to reduced. When normal inspection is in effect, reduced inspection shall be instituted providing that all of the following conditions are satisfied:

a. The preceding 10 lots have been on normal inspection and none have been rejected on original inspection; and
b. The total number of points for 3 and 2 point defects in the samples from the preceding 10 lots is equal to or less than sixty percent of the total maximum acceptable point values for 3 and 2 point defects from the preceding 10 lots; and
c. The total number of points for 3, 2 and 1 point defects in the sample from the preceding 10 lots is equal to or less than seven-five percent of the total maximum acceptable point values for 3, 2 and 1 point defects from the preceding 10 lots: and
d. Production is at a steady rate; and
e. Reduced inspection is considered desirable by the procuring agency.

6.4.4 Reduced to normal. When reduced inspection is in effect, normal inspection shall be instituted if any of the following occur on original inspection:

a. A lot is rejected; or
b. A lot is considered acceptable but exceeds the applicable first value (see 1/ to Table I); or
c. Production becomes irregular or delayed; or
d. Other conditions warrant that normal inspection be instituted.

Source: https://assist.dla.mil -- Downloaded: 202610-24T00:17Z
Check the source to verify that this is the current version before use.

Table II - Classification of Defects

	Point Value
A. GENERAL DEFECTS	
I. MATERIAL DEFECTS AND WORKMANSHIP DAMAGES	
a. Any hole, cut, tear, smash, mend, patch, burn, scorched area or open place:	
1. On outside	3
2. On inside and liner (longest dimension in any direction):	
(a) - up to 1/4 inch, inclusive	1
(b) - more than 1/4 inch	2
b. Any loose yarn, snagged thread, misweave, coarse yarn, area of no dye penetration, dye streak, missing yarn, broken yarn, thin place, shade bar or woven in waste more than 1/4 inch (largest dimension in any direction):	
1. On outside	2
2. On inside and liner	1
c. Any permanent fold, pleat or crease in cloth (including when caught in seaming or stitching);	
1. On outside	3
2. On inside and liner	1
d. Any coating scuff	1
e. Any blister, pick-off in coating or coating flaky	3
f. Coating uneven, lumpy, abraded or thin	1
g. Coating tacky or contains imbedded foreign matter	2
h. Any needle chew	
1. Up to 1/4 inch inclusive	2
2. More than 1/4 inch	3
i. Any knot or slub (see 3.6) on outside only	2
j. Area of coated surfaces permanently adhered	3
II SHADED PARTS	
a. On outside:	
1. Any shading between parts (except parts which may be cut from ends)	3
2. Variation in shade within a part (except parts which may be cut from ends)	3
3. Part cut from ends not approximating shade of garment	1
b. On inside:	
Any lining or liner part badly shaded	1

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:17Z
Check the source to verify that this is the current version before use.

	Point Value
III PRESSING (if performed)	
1. Pressing causing the coating to become soft, tacky, stiff or visibly degraded	1
2. Wrinkles pressed into coat	1
IV CLEANNESS	
a. Any spot or stain:	
1. On outside (longest dimension in any direction):	
a. -up to 1/2 inch inclusive	1
b. -more than 1/2 inch up to 1 inch inclusive	2
c. -more than 1 inch	3
2. On inside and liner	
b. Any shade or size marking exposed or visible on outside	1
c. Thread ends - on inside:	
1. More than three but not more than six trimmed to less than 1/2 inch	1
2. More than six not trimmed to less than 1/2 inch	2
d. Two or more shade or size tickets not removed	1
e. Dusting medium on outside	1
f. Dusting medium on inside on other than cemented/sealed seams, strapping or repaired areas	1
g. Seam sealant on any area other than were specified	1
V COMPONENTS AND ASSEMBLY	
a. Any component part or operation omitted (unless otherwise classified herein)	3
b. Any component not as specified	3
c. Any component part tight, twisted, distored, pleated or full (unless otherwise classified herein)	2
d. Any operation not as specified (unless otherwise classified herein)	2
e. The edge of any component part required to be forced out having folds of more than 1/8 inch (unless otherwise classified herein)	2
VI CUTTING	
a. Any component part not cut in accordance with specified pattern, directional lines on patterns or not in accordance with specification requirements	3
b. Twill line of any outside part not running in specified direction	3

Source: https://assist.dla.mil -- Downloaded: 202610-24T00:17Z
Check the source to verify that this is the current version before use.

	Point Value
VII SEAMS AND STITCHING	
A. Sewn seams	
(a) Accuracy of seaming:	
1. Any seam puckered 1/	1
2. Any seam irregular, pleated or wavy	2
3. Any part of raincoat caught in any unrelated operation or stitching	2
4. Tacking exposed on outside	1
5. End of stitching when not caught in another seam or stitching not finished as specified	1
6. Stitching overlapping end of thread break less than 1/2 inch	1
7. End of a continuous line of stitching overlapped less than 1/2 inch	1
8. Not specified color thread used on outside	2

1/ Seams shall be examined at a distance of 3 feet for evidence of puckering. When puckering appears over more than 1/2 the length of the seam, and is equal to a rating of 3 or less when compared to the seam appearance limits of AATCC Test Method 88B, the seam shall be scored as a puckered seam.

(b) Gage of stitching and seam allowance:	
1. Edge, top or raised stitching sewn too close to edge resulting in damage to cloth	3
2. Seam allowance not as specified by 1/16 inch or more (score only when condition exists on more than 1/2 the length of the seam)	1
3. Irregular or not within range specified or varies more than 1/16 inch when no range is specified (score only when condition exists on more than 1/2 the length of the seam)	1
(c) Open seam	
1. On outside (including undercollar):	
(a) -more than 3/4 inch	3
(b) -more than 3/8 inch up to 3/4 inch inclusive	2
(c) -up to 3/8 inch inclusive	1
2. On inside (except when covered by sealant):	
(a) -more than 2 inches	2
(b) -up to 2 inches inclusive	1

Source: https://assist.dla.mil -- Downloaded: 202640-24T00:17Z
Check the source to verify that this is the currentversion before use.

	Point Value
(d) Raw edge:	
1. On outside:	
(a) -up to 3/8 inch inclusive	1
(b) -more than 3/8 inch up to 3/4 inch inclusive	2
(c) -more than 3/4 inch	3
b. On inside:	
(a) -1/4 inch up to 1 3/4 inch inclusive	1
(b) -more than 1 3/4 inches	2
(e) Seam and stitch type:	
1. Not specified seam or stitch type	3
2. Any line of stitching omitted or insecure	2
3. Any line of stitching not beginning or ending where specified (unless otherwise classified herein)	1
4. Looper thread of 401 stitch type on outside	3
(f) Stitch tension:	
1. Loose tension resulting in a loose seam	3
2. Loosely exposed loops of lower or top thread on edge, top or raised stitching	2
3. Tight tension (stitches break when normal strain is applied in the direction of the seam or stitching)	3
(g) Stitches per inch (score only when condition exists on more than 1/2 the length of seam):	
1. -more than the maximum specified	1
2. -less than the minimum specified	
(a) -by one or two stitches	1
(b) -by three or more stitches	2
(h) Runoff, skipped or broken stitch:	
1. Joining seam - use (Open seam) classification	-
2. Edge, top or raised stitching (more than 1/4 inch)	1
(i) Backtack, tack or tacking	
1. Missing, insecure, misplaced, not serving intended purpose or not specified size or type	1
2. Loose stitch tension	1
(j) Direction of lap of seams:	
Direction of lap of seam not as specified	1
(k) Needle perforations more than 1/2 inch in length	1

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:17Z
Check the source to verify that this is the current version before use.

	Point Value
B. Cemented Seams	
(a) Any seam poorly rolled resulting in puckers or wrinkles:	
1. Forming open channel(s)	
(a) Depth up to 1/2 seam width inclusive	2
(b) Depth more than 1/2 seam width	3
2. Forming closed channel(s)	1
(b) Any loose or unaffixed edge	
1. Length	
(a) Up to 1/4 inch inclusive	2
(b) More than 1/4 inch	3
2. Depth	
(a) Up to 1/8 inch inclusive	2
(b) More than 1/8 inch	3
(c) Overlap less than 1/2 inch or more than 3/4 inch	1
(d) Direction of lap of seam other than specified	1
(e) Cement line not visible	2
VIII REPAIRS ON COATED FABRIC	
a. More than specified number of repaired scuffs, pinholes, needle holes or pick-offs	1
b. Dimensions of repaired area of scuffs, pinholes, needle holes or pick-offs exceeds specified dimension	2
c. The repair compound cracks, flakes or lifts at the edge when subjected to a light hand scrubbing action	3
IX SEALED SEAMS	
a. Any stitched seam required to be sealed:	
1. Not sealed	3
2. Sealed improperly, i.e., sealant not under the turned edge of the seam or does not completely cover the stitching	3
b. Any sealed seam not dusted	3
c. Sealant cracks or flakes when creased	3
d. Sealant tacky	2
e. Any seam badly twisted, pleated or puckered when caused by improperly performed seam sealing operation	2

Source: https://assist.dla.mil -- Downloaded: 202640-24T00:17Z
Check the source to verify that this is the currentversion before use.

	Point Value
X STRAPPING	
a. Omitted or misplaced	3
b. Poorly rolled resulting in puckers or wrinkles:	
1. Forming open channnel(s)	
(a) Depth up to 1/2 seam width inclusive	2
(b) Depth more than 1/2 seam width	3
2. Forming closed channel(s)	1
c. Any loose or unaffixed edge:	
1. Length	
(a) Up to 1/4 inch inclusive	2
(b) More than 1/4 inch	3
2. Depth	
(a) Up to 1/8 inch inclusive	2
(b) More than 1/8 inch	3
XI SNAP FASTENERS	
a. Not style, size or finish specified	1
b. Any part of assembly omitted, mismated, misplaced, broken or otherwise defective	3
c. One or more not securely attached or clinched too tightly resulting in cutting of the fabric	3
d. Not properly aligned:	
1. Pulling, twisting or bulging when garment is in closed position	2
2. Front edge of right front is less than 1/4 inch or more than 3/8 inch from the inside edge of the storm fly when in closed position	2
XII BARTACKS, TACKS OR TACKING	
a. Any missing or misplaced	3
b. Any added	2
c. Loose stitching or 2 or more broken stitches	2
d. Stitches less than number specified	1

Source: https://assist.dla.mil -- Downloaded: 202610-24T00:17Z
Check the source to verify that this is the current version before use.

	Point Value
XIII BUTTONHOLES	
a. Any omitted, added or misplaced	3
b. Not specified type	2
c. Ragged edge, incomplete stitching, stitching not securely caught in fabric, bulky appearance or stitches not uniform	2
d. Loose stitching or 2 or more broken stitches	2
e. Stitches less than number specified by:	
1. One to three stitches	1
2. Four or more stitches	2
XIV BUTTON	
a. Any omitted, broken or defective	1
b. Any misplaced, loose; not attached as specified, or insecurely sewn	1
c. Tacking stitches omitted or insecure (hand sewn)	1
d. Shank wrapping omitted or loosely wrapped	1
e. Stitching on button not locked at end of cycle (tug at loose end of the thread when accessible to determine whether it will ravel)	1
XV EYELETS	
a. Any omitted, malformed, damaged or misplaced	2
b. Any not securely attached	1
c. Not type, size or finish specified	1
d. Any eyelet not completely cut out	1
XVI EYELET STAY REINFORCEMENT	
a. Missing	2
b. Misplaced by 1/2 inch or more in any direction	2
c. Not securely attached	1
B. DETAILED DEFECTS (RAINCOAT BUTTONED ON FORM OR HANGER)	
XVII COLLAR AND SLEEVE ADJUSTMENT TAB OR ASSEMBLY	
a. Any assembly or tab omitted or misplaced	3
b. Any loose or unaffixed edge:	
1. Up to 1/4 inch inclusive in length or depth	1
2. More than 1/4 inch in length or depth	2
c. Edge of tab not parallel to bottom edge of sleeve by more than 1/4 inch	2
d. Finished width or length not as specified	1

Source: https://assist.dla.mil -- Downloaded: 2026-10-24T00:17Z
Check the source to verify that this is the current version before use.

	Point Value
XVIII BELT	
a. Twisted	2
b. Width less than 2 1/8 inches or more than 2 3/8 inches	1
c. Irregular in width by more than 1/8 inch	1
XIX VENT	
a. Triangular stitching at top of vent pleated omitted or not as specified	1
b. Boxstitching missing, misplaced or not size specified	1
c. Left vent not overlapping right	1
d. Uneven in length 1/4 inch or more	1
XX HANGER LOOP AND YOKE HINGE LOOP	
a. Omitted or not securely stitched	1
b. Finished width or length not as specified	1
c. Misplaced, i.e., off center by more than 1/2 inch	1
XXI COLLAR	
a. Not uniform in size or shape - any point varying:	
1. More than 1/2 inch with corresponding point on matching part	3
2. More than 3/8 inch up to 1/2 inch inclusive with corresponding point on matching part	2
3. 1/4 to 3/8 inch inclusive	1
b. Collar uneven in width by:	
1. More than 1/4 inch up to 3/8 inch inclusive	2
2. More than 3/8 inch	3
c. Twisted, not smooth and flat, short or tight causing collar to turn out	3
d. Collar off center by 1/4 inch or more 1/	2
e. Collar tight causing puckers or pleats at neckline	2
f. Edge of collar not properly forced out, i.e., having a fold or more than 1/8 inch in depth	2
g. Collar stand tight causing puckers on undercollar or topcollar	1
h. Collar stand full causing bulging or twists	1
i. Top collar tight causing collar to curl	2
j. Quilting not as specified	1
k. Finished width of collar stand at center back not as specified	2
l. End(s) poorly shaped	2

1/ Center of collar is determined by aligning the two shoulder seams at junction of collar.

Source: https://assist.dla.mil -- Downloaded: 202640-24T00:17Z
Check the source to verify that this is the currentversion before use.

	Point Value
XXII SHOULDER LOOP/STRAP	
a. Not uniform in size or shape - any point varying:	
1. More than 3/8 inch with corresponding point on matching part	3
2. 1/4 inch up to 3/8 inch (inclusive) with corresponding point on matching part	2
b. Not positioned as specified or attached crookedly	2
c. Width or length not as specified	1
d. Button misplaced causing distortion on loop or shoulder	2
XXIII FRONT	
a. Spacing between two or more buttonholes unequal by 1/4 inch or more	1
b. Two or more buttonholes out of vertical alignment by:	
1. 3/16 inch to 3/8 inch	1
2. More than 3/8 inch	2
c. Any button out of alignment with the corresponding buttonhole	2
d. Front edge not folded straight; irregular, or uneven	1
e. Width of lapel step not as specified, or width of step uneven by more than 1/4 inch	2
f. Uneven in length (when buttoned or snapped):	
1. 1/4 inch or more at the top	1
2. 3/8 inch or more at the top	2
g. Storm tab extending beyond edge of left front	2
h. Left and right lapel varying by:	
1. More than 1/4 inch up to 1/2 inch inclusive	2
2. More than 1/2 inch	3
i. Front excessively full, tight or twisted:	
1. At lapel	3
2. Below lapel	2
j. Top edge of storm tab not stitched or bartacked to facing	1
k. Front facing short, tight or twisted causing fullness or twist on front	3
l. Facing too long causing bottom corner of front to curl up	3
m. Stitching forming fly front not specified distance from front edge	2
n. Fly stitching tapering to a curve at bottom not as specified	1
o. Any button out of horizontal or vertical alignment by:	
1. 3/16 inch to 3/8 inch	1
2. More than 3/8 inch	2

Source: https://assist.dla.mil -- Downloaded: 202610-24T00:17Z
Check the source to verify that this is the current version before use.

	Point Value
p. Any dart not properly tapered causing distortion or bulge(s)	2
q. Darts uneven in length by more than 1/2 inch	1
XXIV HEM	
a. Twisted or pleated	2
b. Puckered	1
c. Width of hem not as specified	1
XXV POCKET	
a. Welt twisted, tight or full, not permitting pocket to lie smooth	2
b. Stitching of welt to raincoat not through hanging pocket	2
c. Front of hanging pocket not stitched under facing	2
d. Back edge of welt short causing puckers on front or too loose causing welt to gap	1
e. Interlining omitted	1
f. Poorly shaped or not uniform in shape or size	1
g. Irregular in width by more than 3/16 inch	1
h. Corner of welt not finished as specified	1
i. Other than specified	2
j. Pocket opening:	
1. Tape omitted	2
2. End not caught in welt stitching	1
3. Tight or twisted causing fullness or twist on the outside of welt	1
k. Finished length or width of pocket welt not as specified	1
l. Pockets out of alignment by:	
1. 1/4 inch up to 1/2 inch inclusive	1
2. More than 1/2 inch up to 3/4 inch inclusive	2
3. More than 3/4 inch	3
m. Pocket notch exposed:	
1. On outside	3
2. On inside	1
n. Pocket flap not tacked to welt at each bottom corner of welt	2
o. V-strip omitted or misplaced	3
XXVI SLEEVE TAB (SEWN)	
a. Any tab omitted or misplaced	3
b. Bottom edge of tab not parallel to the bottom edge of the sleeve by more than 1/4 inch	2
c. Finished width or length not as specified	1

Source: https://assist.dla.mil -- Downloaded: 2026-04-24T00:17Z
Check the source to verify that this is the current version before use.

	Point Value
XXVII FASTENER TAPE	
a. Not width or length specified	2
b. Not color specified	1
c. Not type and class specified	1
XXVIII SLEEVE	
a. Sleeve fullness at armholes misplaced	2
b. Armhole or shoulder seam tape omitted or not positioned as specified	2
c. Sleeve tight at armholes, causing puckers or pleat	2
d. Raise stitching omitted	1
e. Sleeve lining visible below sleeve bottom	2
XXIX BACK YOKE AND NETTING BACK	
a. Excessive fullness	2
b. Tight or twisted	2
XXX LINING	
a. Twisted, tight or short	3
b. Too long causing lining to sag at bottom	2
c. Bottom edge or hem not finished as specified	1
d. Underfly exposed beyond front edge	2
XXXI PLEAT	
a. Omitted or not specified type	3
b. Not positioned as specified	2
c. Bulge at tapered end	1
XXXII LABEL	
a. Missing, incorrect, or illegible:	
1. Size label, instruction or combination label	3
2. Identification label	1
b. Not attached as specified or misplaced	1
XXXIII FACING TAB	
a. Stitching at top edge of tab omitted or insecure	1
b. Length or width of tab more or less than specified	1
c. Pointed end exposed beyond front edge of front	1
d. Omitted or misplaced	2

Source: https://assist.dla.mil -- Downloaded: 202610-24T00:17Z
Check the source to verify that this is the current version before use.

	Point Value
XXXIV SLEEVE ADJUSTMENT TAB ASSEMBLY (CEMENTED)	
a. Any tab assembly omitted; or misplaced	3
b. Any loose or unaffixed edge:	
1. Up to 1/4 inch inclusive in length or depth	1
2. More than 1/4 inch in length or depth	2
c. Bottom edge of tab not parallel to the bottom edge of the sleeve by more than 1/4 inch	2
d. Finished width or length not as specified	1
XXXV LINER	
a. Fronts uneven in length by:	
1. More than 1/2 inch but less than 1 inch	2
2. More than 1 inch	3
b. Quarter-lining twisted, tight or excessively full	2
c. Bound pocket opening length:	
1. Less than 5 1/2 inches	2
2. More than 6 1/2 inches	1
d. Ends of binding:	
1. Not turned under	1
2. Overlapped less than 1/2 inch	1
OR	
Not turned to the underside of binding and securely caught in stitching	1

Custodians:

Navy - NU
Army - GL

Review activities:
Navy - MC
DLA - CT

Preparing activity:

Navy - NU

Project No. 8405-0713

Source: https://assist.dla.mil -- Downloaded: 202610-24T00:17Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12503 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Officer in Charge
Navy Clothing & Textile Research Facility
(Code 50)
21 Strathmore Road
Natick, MA 01760

Source: https://assist.dla.mil -- Downloaded: 202610-24T00:17Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)*: _____

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

DD FORM 82 MAR 1426 PREVIOUS EDITION IS OBSOLETE.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

Source: https://assist.dla.mil -- Downloaded: 202610-24T00:17Z
Check the source to verify that this is the current version before use.