This document has been approved for public release and sale; its distribution is unlimited.

MIL-S-21953B(SHIPS)
6 April 1970
SUPERSEDING
MIL-S-21953A(SHIPS)
12 June 1962
(See 6.4)

MILITARY SPECIFICATION

SEALING KIT FOR PRESERVATION OF ENDS OF DISCONNECTED CABLES

1. SCOPE

1.1 This specification covers a sealing kit used to supply heat sealed polyethylene boots on disconnected and unused ends of electrical cables to serve as a guard against the entry of moisture, tools used in preparing cable ends for sealing, and the consumable materials used in making end seals.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

J-C-175 - Cable Assembly, Power, Electrical, (3-Wire, 3-Prong, Grounding Plug Connector for 125 Volt Equipment).
QQ-C-576 - Copper Flat Products with Slit, Slit and Edge Rolled, Sheared, Sawed, or Machined Edges, (Plate, Bar, Sheet, and Strip).
QQ-R-175 - Resistance Wire.
QQ-S-698 - Steel, Sheet and Strip, Low-Carbon.
GGG-K-481 - Knives; Craftsman's (Hawkbill, Shoe, Chipping), Putty and Scraping.
GGG-P-471 - Pliers.
GGG-P-611 - Pot, Melting, Electric, Portable.
GGG-S-121 - Screwdriver and Screw Starter, Hand.
GGG-S-665 - Stripper, Cable, Hand; and Stripper, Wire, Hand.

MILITARY

MIL-I-631 - Insulation, Electrical, Synthetic-Resin Composition, Nonrigid.
MIL-E-917 - Electric Power Equipment, Basic Requirements (Naval Shipboard Use).

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

UNIFORM CLASSIFICATION COMMITTEE
Uniform Freight Classification Rules

(Application for copies should be addressed to the Uniform Classification Committee, 202 Union Station, 516 West Jackson Boulevard, Chicago, Illinois 60606.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)
A415-64 - Hot Rolled Carbon Steel Sheets, Commercial Quality.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal agencies.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:49Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

3.1 General requirements. Materials procured under this specification shall be used to insulate conductor ends of cables, including any attached lugs or wire terminals, and to seal the ends of the cables by applying a plastic boot over the conductor ends extending back from the cable end to cover at least 3 inches of the cable jacket. The boot shall be heat bonded to the jacket, with the protective armor cut away or pushed back to clear the boot. Copper foil shall be used to transmit heat between the mold and the boot and also as a temporary seal to make a tight enclosure between the mold and the boot. Equipment furnished for this purpose shall be portable, for sealing cable ends in place onboard ship, or wherever power service is available at 115 volts, 60 hertz (Hz), single phase, 1000 watts.

3.2 Melting pot. The melting pot shall be in accordance with GGG-P-611, except as specified in 3.2.1 through 3.2.6.

3.2.1 The melting pot shall be for melting polyethylene plastic (see 3.6) used for hot-dipping conductor ends of cable and thermostatically controlled for holding contents at the proper temperature for dipping during a working day and in an ambient temperature between 20 and 100°F.

3.2.2 The heating element shall consist of a resistance wire embedded in a refractory material, preferably magnesium oxide, which shall be firmly held in place by an outer metal sheath. The resistance wire shall be composition D or E of QQ-R-175 and shall be firmly fixed by the refractory material and shall not become grounded to the sheath when subjected to bending or vibration and exposure to moisture. The element shall be for use on 115-volt, 60 Hz, single-phase service and its rating plus the rating of the bonding heater (see 3.3) shall not exceed 1000 watts.

3.2.3 The cup or pot shall be cylindrical, with tapered sides and generous fillet at bottom to facilitate cleaning, and shall have volume of approximately 8 fluid ounces.

3.2.4 The pot shall have legs permitting it to stand on any horizontal surface, but shall be small and light enough to allow it to be lifted in one hand to the cable end while the wire ends are separated and dipped with the other hand.

3.2.5 The pot shall completely liquify its rated capacity within 1/2 hour at 68°F. ambient.

3.2.6 Cable assembly and grounding shall consist of a 10-foot, assembly in accordance with type I of J-C-175.

3.3 Bonding heater.

3.3.1 The heater shall be a portable hand held, thermostatically controlled device for applying heat to bond a plastic boot to a cable jacket over a length of approximately 1-1/4 inches at the neck of the boot. The heater shall have a hinged portion to allow it to be opened to clear mold parts as specified in 3.10.

3.3.2 The heating element shall consist of resistance wire embedded in a refractory material, preferably magnesium oxide, which shall be firmly held in place by an outer metal sheath. The resistance wire shall be composition D or E of QQ-R-175 and shall be firmly fixed by the refractory material and shall not become grounded to the sheath when subjected to bending or vibration and exposure to moisture. The element shall be for use on 115-volt, 60-Hz, single-phase service. Its rating plus the rating of the heating pot (see 3.2), shall not exceed 1000 watts.

3.3.3 The heater shall be supplied equipped with adapters, if required, to transfer heat from heating elements to the various diameters of bonding molds. The adapters shall be of a metal having a high thermal conductivity. Heaters shall develop the proper amount of thermostatically controlled heat, when transferred through accessory parts to the surface of a boot, to make a tight bond of boot to cable jacket in ambient temperature of 20° to 100°F., and when sealing boots to cable jacket up to 2 inches in diameter.

3.3.4 The cable assembly and grounding shall consist of a 10-foot, assembly in accordance with type I of J-C-175.

3.4 Tool set. The set shall consist of type and quantity as required to change and tighten removable parts of the bonding heater. Tools shall be provided in a tool roll for

Source: https://assist.dla.mil -- Downloaded: 202640-19T10:49Z
Check the source to verify that this is the current version before use.

carrying with other equipment in the equipment chest. Tools supplied shall conform to the following (where applicable):

Tool	Applicable document
Screwdriver	GGG-S-121
Pliers	GGG-P-471
Knife, linoleum	GGG-K-481
Stripper, cable, hand	GGG-S-665

3.5 Equipment chest.

3.5.1 The chest shall be for stowing and carrying a complete kit of cable end sealing equipment specified in 3.2, 3.3, 3.4, 3.6, 3.7, 3.8, 3.9, 3.10 and 3.11. The quantity of the consumable equipment to be stowed shall be that required for use during a normal 8 hour day by one man. Material shall be in accordance with the requirements referenced herein. Materials not covered by the referenced specifications shall be of the best commercial quality and shall be suitable for the purpose intended.

3.5.2 The sheet steel used in the chest construction shall conform to QQ-S-698 or ASTM-A-415-64.

3.5.3 The thickness of steel used in the chest construction shall be not less than 22 gauge (0.0284 inch).

3.5.4 Seams shall be spot welded, seam welded, or lock seamed.

3.5.5 The box and cover shall be joined by a continuous hinge. The hinge pin shall be made of corrosion-resistant steel, brass, or bronze, and shall be permanently fixed to prevent removal.

3.5.6 Each chest shall be provided with a heavy duty plated catch for holding the cover closed. The catch shall withstand the test specified in 4.5.8.

3.5.7 Each chest shall be provided with a handle which shall be either formed sheet steel or cast aluminum and shall be convenient to grip. The handle shall be either riveted or welded in place and shall be capable of lifting the box with not less than 100 pounds distributed within the box without permanent distortion.

3.5.8 The completed box shall be painted in accordance with MIL-E-917.

3.5.9 The chest shall be provided with interior compartments or racks to allow orderly stowage of each item of kit. The thickness of steel used shall be not less than 24 gauge (0.0225 inch).

3.6 Dipping plastic. The dipping plastic shall be a hot-dip polyethylene material for coating ends of wires when in a melted state. It shall adher to lug terminals, conductors and conductor insulation to form a watertight insulated coating but shall be capable of being peeled off with a knife or fingernail. The plastic shall be supplied in blocks to fit the melting pot.

3.7 Plastic boot. The plastic boot shall be a polyvinyl chloride tube with inside diameter sufficient to slide over an impervious jacket of cable. The boot shall be long enough to reach past the conductors with attached lugs or terminals, and one end shall be closed. The boot shall have a uniform wall thickness of 1/16 inch. Boots shall be supplied in inside diameters from 3/8 inch to 2 inches by 1/8 inch increments and in lengths from 12 inches to 36 inches by 6-inch increments as specified (see 6.1). The material shall conform to type F, form U, grade a, class I of MIL-I-631. It shall also be properly formulated with plasticizers, stabilizers, or other ingredients necessary for weather resistance and for proper sealing to various cable jacket materials (see 4.5.9).

3.8 Foil seal. Copper foil seals shall be provided to wrap boot under mold. Seals shall be cut to size from 0.002 inch copper sheet conforming to QQ-C-576. Copper sheet shall be hot rolled and annealed temper.

3.8.1 The copper sheet shall be furnished in strips 4 by 2-1/2 inches, 4 by 4 inches or 4 by 6-1/2 inches, as specified (see 6.1).

3.9 Cyclohexanone. Cyclohexanone shall be used for cleaning cable jacket in preparing for sealing to boots. The solvent shall be furnished in a pint can with a brush soldered to the lid.

Source: https://assist.dla.mil -- Downloaded: 202610-19T10:49Z
Check the source to verify that this is the current version before use.

3.10 Split bonding mold. The split molds shall be for applying bonding heat through the foil seal (see 3.8) to a band approximately 1-1/4 inches wide at the neck of the plastic boot and shall press the plastic tightly against the cable jacket. Split molds shall be of corrosion-resistant metal or of a material given a corrosion-resistant treatment, with low thermal coefficient plastic end rings to facilitate handling and shall incorporate a stepped diameter to overhang the end of the boot in use and prevent it from creeping under heat and pressure. All split molds shall fit the heater, (see 3.3), and the applicable boot; (see 3.7). The split molds shall be furnished in 1/4, 3/8, 1/2, 5/8, 3/4, 7/8, 1, 1-1/8, 1-1/4, 1-3/8, 1-1/2, 1-5/8, 1-3/4, 1-7/8, and 2-inch inside diameters, as specified (see 6.1).

3.11 Technical manuals. Technical manuals shall consist of the manufacturer's commercial instruction for use of the kit. Preliminary manuals submitted to the command or agency concerned for approval shall include all proposed sections complete.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Test reporting. Test results shall be recorded by the supplier on test forms prepared by the supplier and approved by the Defense Contract Administration Service (DCAS). Provision shall be made for recording of all required data. Each test report form shall be identified by the number of this specification and by the particular test requirement paragraph number and its title.

4.1.2 Test reports. All test data shall be approved by the DCAS prior to the shipment of the equipment. After approval, one file copy of all test data shall be forwarded to the command or agency concerned. The data shall be bound into a 9 by 11-1/2 inch binder. The cover and title page shall give sufficient information to identify the equipment. A table of contents shall be included and list each test. No special test format will be required. However, each test shall be prefaced by the name of the test and applicable test paragraph as indicated in tables III and IV. The data submitted shall be copies of the actual data taken on the test floor and not retyped data. The forms used shall allow sufficient columns to make instrument corrections and necessary calculations. The DCAS shall sign the cover sheet of the test report and note thereon the number of test sheets verified.

4.2 Lot. All sealing kits presented at one time shall be considered a lot for purposes of quality conformance inspection.

4.3 Sampling for quality conformance inspection.

4.3.1 Sampling for group A inspection. A random sample of sealing kits shall be selected as specified in table I from each lot and shall be subjected to group A inspection specified in 4.4.1. Any sealing kit in the sample which fails in any examination or test shall be rejected and if the number of defective kits in the sample exceeds the acceptance number for that sample the lot represented by that sample shall be subjected to rejection.

Table I - Sampling for group A inspection
AQL (approx.) = 1.5 percent defective.

Number of sealing kits in lot	Number of sealing kits in sample	Number of sealing kits nonconforming on any group A inspection	
		Acceptance number	Rejection number
15 and under	7 or all for lots of less than 7	0	1
16 to 40	10	0	1
41 to 110	15	0	1
111 to 300	25	1	2
301 to 500	35	1	2
501 and over	50	2	3

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:49Z
Check the source to verify that this is the current version before use.

4.3.2 Sampling for group B tests. A random sample of sealing kits shall be selected from each lot in accordance with table II, and shall be subjected to each of the group B tests specified in 4.4.2. Any kit in the sample which fails in any test shall be rejected and if the number of defective kits in the sample exceeds the acceptance number for that sample, the lot represented by that sample shall be rejected.

Table II - Sampling for group B tests.

Number of sealing kits in lot	Number of sealing kits in sample	Number of sealing kits nonconforming on any group B test	
		Acceptance number	Rejection number
15 and under	3 or all for lots of less than 3	0	1
16 to 40	5	0	1
41 to 110	7	0	1
111 to 300	10	0	1
301 to 500	15	1	2
501 and over	25	2	3

4.3.3 Sampling for group C tests. A random sample of plastic boot, solvent, foil seal and dipping plastic shall be selected from each lot offered for tests in accordance with 4.5.9 and 4.5.10. Three sets shall comprise the sample, one set for each of the three test assemblies required in 4.5.9 and 4.5.10. If any sample fails in any test the lot represented by the sample shall be subject to rejection.

4.4 Quality conformance inspection.

4.4.1 Group A inspection. Each of the samples selected in accordance with 4.3.1 shall be subjected to the applicable examination and test shown in table III. The results of the examination and test shall be compared with the requirements of this specification.

Table III - Group A inspection.

Inspection	Applicable paragraph
Visual and dimensional examination	4.5.2
Dielectric strength	4.5.3

4.4.2 Group B tests. Each of the samples selected in accordance with 4.3.2 shall be subjected to the tests shown in table IV. The results of each test shall be compared with the requirements of this specification.

Table IV - Group B tests.

Tests	Applicable paragraph
Melting time	4.5.4
Heat transfer	4.5.5
Power input	4.5.6
Cable assembly	4.5.7
Chest handle	4.5.8

4.5 Test procedures.

4.5.1 Material tests. While it is not the intention of this specification, in general, to require that all material used in the construction of the sealing kits be tested in accordance with the applicable specification, such tests shall be required when considered necessary to ascertain that the quality of a material used is at least equal to the material specified herein and covered by the specifications listed in section 2.

4.5.2 Visual and dimensional examination. Each sample melting pot, bonding heater, bonding mold, tool set, equipment chest, plastic boot, dipping plastic and foil seal selected in accordance with 4.3.1 shall be subjected to a visual and dimensional examination to ascertain that the detail and character of workmanship conform to the requirements of this specification (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 202640-19T10:49Z
Check the source to verify that this is the currentversion before use.

4.5.3 Dielectric strength. Each sample melting pot or bonding heater selected in accordance with 4.3.1 shall be subjected to the dielectric strength test specified in GGG-P-611.

4.5.4 Melting time. Each sample melting pot selected in accordance with 4.3.2 shall be tested to determine that the melting time conforms with the requirements of this specification. During a 2 hour test at rated voltage, the thermostat shall control the pot temperature to maintain the dipping plastic in the melted state for the coating process (see 3.6).

4.5.5 Heat transfer. Each sample bonding heater shall be tested with the largest and smallest mold to determine that the heat transfer for bonding of boot to cable jacket is satisfactory.

4.5.6 Power input. Each sample melting pot and bonding heater shall be tested to determine that the power input conforms with the requirements of this specification.

4.5.7 Cable assembly. Each sample melting pot or bonding heater including its cable assembly shall be subjected to the "Test procedures" specified in J-C-175.

4.5.8 Chest handle. Each equipment chest shall be tested by loading the chest with 100 pounds of material distributed among the drawers and lifted 10 times. Handle and box shall then be examined for any permanent distortion which would affect the serviceability of the chest.

4.5.9 Effective seal. The plastic boot, dipping plastic and solvent shall be assembled into a cable end seal and tested to determine the effectiveness of cable end sealing required by this specification. The cable shall be cut off 6 inches from the seal in the direction away from the boot seal and the cut end sealed in any effective manner. This sample shall then be immersed in water to a depth of at least 4 inches above the upper part of the sample. The sample shall then be rotated so that the entire surface of the sample has been examined. Each part of the surface shall be examined for at least 1 minute and total elapsed time of test shall be not less than 3 minutes. An assembly shall be tested for each of the following three types of cable jackets:

Polyvinyl chloride.
Polychloroprene.
Blend of polyvinyl chloride and nitrile rubber.

4.5.9.1 Interpretation of results. Observation of evolution of air bubbles shall be made at each position of the sample. Bubbles which appear on the surface of the package but are not released are not to be construed as indication of failure. A steady stream or a recurring succession of bubbles from any surface or seam shall be cause for rejection.

4.5.10 Effective conductor end insulation. Each of the samples tested in 4.5.9 shall be tested to determine the effectiveness of the dipping plastic. The cut end of the cable opposite the boot seal shall be opened and the conductors subjected for a period of 1 minute to a dielectric test potential of 1880 volts, 60 Hz alternating current, applied between conductors. Each sample shall then be opened and the dipping plastic examined for ease of removal as required by 3.6.

5. PREPARATION FOR DELIVERY

(The preparation for delivery requirements specified herein apply only for direct Government procurements. For the extent of applicability of the preparation for delivery requirements of referenced documents listed in section 2, see 6.3.)

5.1 Domestic shipment and early equipment installation.

5.1.1 Sealing kit.

5.1.1.1 Preservation and packaging. Preservation and packaging which may be the supplier's commercial practice, shall be sufficient to afford adequate protection against corrosion, deterioration and physical damage during shipment from the supply source to the using activity and until early installation.

5.1.1.2 Packing. Packing shall be accomplished in a manner which will insure acceptance by common carrier at the lowest rate and will afford protection against physical or mechanical damage during direct shipment from the supply source to the using activity for early installation. The shipping containers or method of packing shall conform to the Uniform Freight Classification Rules or other carrier regulations, as applicable to the mode of transportation and may conform to the supplier's commercial practice.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:49Z
Check the source to verify that this is the current version before use.

5.1.1.3 Marking. Shipment marking information shall be provided on interior packages and exterior shipping containers in accordance with the contractor's commercial practice. The information shall include nomenclature, Federal stock number or manufacturer's part number, contract or order number, contractor's name and destination.

5.2 Domestic shipment and storage or overseas shipment. The requirements and levels of packaging, packing and marking for shipment shall be as specified (see 6.1).

(5.2.1 The following provides various levels for protection during domestic shipment and storage or overseas shipment, which may be required when procurement is made.

5.2.1.1 Preservation and packaging.

5.2.1.1.1 Level A. Sealing equipment and consumable material shall be preserved and packaged as follows:

5.2.1.1.1.1 Sealing equipment.

5.2.1.1.1.1.1 Melting pot and bonding heater. The melting pot and the bonding heater shall be individually packaged, in accordance with method IA of MIL-P-116. Contact preservatives will not be required.

5.2.1.1.1.1.2 Tool set. The tools shall be individually packaged in accordance with mentod I of MIL-P-116. Contact preservative shall conform to type P-2. Tools shall be placed in the roll and the roll secured by tie strings or other suitable means.

5.2.1.1.1.2 Consumable material.

5.2.1.1.1.2.1 Dipping plastic. Each block of plastic shall be wrapped and secured with pressure sensitive tape or other suitable means.

5.2.1.1.1.2.2 Bonding molds, foil seals and plastic tubes. Material of like size and description shall be packaged in accordance with method III of MIL-P-116.

5.2.1.1.1.2.3 Cyclohexanone. Cyclohexanone shall be furnished in 1-pint cans conforming to type V, class 4 of PPP-C-96. Exterior plan B coating and side seam striping shall be required. Each closure shall be provided with an inner seal and brush (see 3.9).

5.2.1.1.1.3 Equipment chest. Sealing equipment and consumable material, packaged as specified in 5.2.1.1.1.1 and 5.2.1.1.1.2, shall be placed in the compartments or rack provided within the chest. Indexing and cushioning shall be provided to prevent damage to material from movement during handling and shipment. Chests shall be closed and individually packaged in fiber boxes conforming to PPP-B-636. Box closure shall be as specified in the appendix to the box specification.

5.2.1.1.1.3.1 Index list. An index list, completely itemizing the contents of the chest, shall be placed on the inside of the box. The list shall be enclosed in a waterproof bag or shall be so treated as to be resistant to water, oil and fading.

5.2.1.1.2 Level C. Sealing equipment, consumable material and the equipment chest shall be packaged in accordance with the manufacturer's commercial practice.

5.2.1.2 Packing.

5.2.1.2.1 Level A. Kits, packaged as specified, shall be packed in weather-resistant type, wood cleated fiberboard, nailed wood, fiber, wirebound wood, wood cleated veneer paper overlaid, or wood cleated plywood boxes conforming to PPP-B-591, PPP-B-621, PPP-B-636, class 3, PPP-B-585, PPP-B-576 or PPP-B-601, respectively, at the option of the supplier. Shipping containers shall have case liners conforming to MIL-L-10547. Case liners for boxes conforming to PPP-B-636 may be omitted provided all joints and corners of the boxes are sealed with minimum 1-1/2 inch wide tape conforming to PPP-T-76. Boxes shall be closed and strapped in accordance with the applicable box specification or appendix thereto, except fiber boxes may be banded with tape conforming to type IV of PPP-T-97 and the appendix thereto. The gross weight of wood or wood cleated boxes shall not exceed 200 pounds: fiber boxes shall not exceed the weight limitations of the applicable box specification. Fiber boxes (see 5.2.1.1.1.3) conforming to PPP-B-636, closed, sealed and banded as specified herein, and used as the shipping container need not be overpacked.

Source: https://assist.dla.mil -- Downloaded: 202640-19T10:49Z
Check the source to verify that this is the currentversion before use.

5.2.1.2.2 Level B. Kits, packaged as specified, shall be packaged in domestic type wood cleated fiberboard, nailed wood, wirebound wood, cleated plywood or wood cleated veneer paper overlaid boxes or class 2 fiber boxes conforming to PPP-B-591, PPP-B-621, PPP-B-585, PPP-B-601, PPP-B-576 or PPP-B-636, respectively, at the option of the supplier. Box closure shall be as specified in the applicable box specification or appendix thereto. The gross weight of wood or wood cleated boxes shall not exceed 200 pounds; fiber boxes shall not exceed the weight limitations of the applicable box specification. Fiber boxes (see 5.2.1.1.1.3) conforming to PPP-B-636, closed as specified herein, and used as the shipping container need not be overpacked.

5.2.1.2.3 Level C. Kits, packaged as specified, shall be packed in containers which will insure acceptance by common carrier and safe delivery at destination. Shipping containers shall comply with the Uniform Freight Classification Rules or other regulations as applicable to the mode of transportation.

5.2.1.3 Marking. In addition to any special marking required by the contract or order or herein, interior and exterior shipping containers shall be marked in accordance with MIL-STD-129.

5.2.1.3.1 Special marking. The 1-pint cans of cyclohexanone shall be labelled as follows:

"CAUTION! VAPOR HARMFUL
Keep away from heat and open flame.
Use only with adequate ventilation.
Avoid prolonged breathing of vapor.
Avoid prolonged or repeated contact with skin.")

6. NOTES

6.1 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Diameter and length of plastic boot required (see 3.7).
(c) Size of copper sheet required (see 3.8.1).
(d) Size of split molds required (see 3.10).
(e) Preservation, packaging, packing and marking requirements other than those required by 5.1 (see 5.2).

6.2 Where a manufacturer's sealing kit of the same manufacture has passed all tests on a previous submission, only the examination of 4.5.2 will be required.

6.3 Sub-contracted material and parts. The preparation for delivery requirements of referenced documents listed in section 2 do not apply when material and parts are procured by the supplier for incorporation into the equipment and lose their separate identity when equipment is shipped.

6.4 CHANGES FROM PREVIOUS ISSUE. THE OUTSIDE MARGINS OF THIS DOCUMENT HAVE BEEN MARKED "#" TO INDICATE WHERE CHANGES (DELETIONS, ADDITIONS, ETC.) FROM THE PREVIOUS ISSUE HAVE BEEN MADE. THIS HAS BEEN DONE AS A CONVENIENCE ONLY AND THE GOVERNMENT ASSUMES NO LIABILITY WHATSOEVER FOR ANY INACCURACIES IN THESE NOTATIONS. BIDDERS AND CONTRACTORS ARE CAUTIONED TO EVALUATE THE REQUIREMENTS OF THIS DOCUMENT BASED ON THE ENTIRE CONTENT AS WRITTEN IRRESPECTIVE OF THE MARGINAL NOTATIONS AND RELATIONSHIP TO THE LAST PREVIOUS ISSUE.

Preparing activity:
Navy - SH
(Project 5975-N398)

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T10:49Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 119-R004

INSTRUCTIONS

This sheet is to be filled out by personnel either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity *(as indicated on reverse hereof)*.

SPECIFICATION

ORGANIZATION *(Of submitter)*	CITY AND STATE

CONTRACT NO.	QUANTITY OF ITEMS PROCURED	DOLLAR AMOUNT
		$

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES.

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO IF "YES", IN WHAT WAY?

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity)*	DATE

DD FORM 1 APR 63 1426 REPLACES NAVSHIPS FORM 4663, WHICH IS OBSOLETE 0101-807-2000

Source: https://assist.dla.mil -- Downloaded: 202610-19T10:49Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE NAVY
Naval Ship Engineering Center
Center Building
Prince George's Center
Hyattsville, Maryland 20782

POSTAGE AND FEES PAID
NAVY DEPARTMENT

OFFICIAL BUSINESS

Commander, Naval Ship Engineering Center
DOD Standardization Program & Documents Branch
Center Building
Prince George's Center
Hyattsville, Maryland 20782

FOLD

Source: https://assist.dla.mil -- Downloaded: 202610-19T10:49Z
Check the source to verify that this is the current version before use.