MIL-STD-775(SHIPS)
15 November 1962

MILITARY STANDARD

X-RAY STANDARDS FOR WELDING ELECTRODE QUALIFICATION TEST WELDS

FSC MISC

DEFENSE FILE COPY
DO NOT DESTROY

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:39Z
Check the source to verify that this is the current version before use.

DEPARTMENT OF THE NAVY

BUREAU OF SHIPS

WASHINGTON 25, D.C.

X-Ray Standards for Welding
Electrode Qualification Test Welds

MIL-STD-775(SHIPS)

1. This standard has been approved by the Bureau of Ships, and is mandatory for use by activities under the cognizance of the Bureau of Ships effective 15 November 1962.

2. Recommended corrections, additions, or deletions should be addressed to the Chief, Bureau of Ships Department of the Navy, Washington 25, D. C.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:39Z
Check the source to verify that this is the current version before use.

CONTENTS

Paragraph		Page
1.	SCOPE	1
2.	REFERENCED DOCUMENTS	1
3.	REQUIREMENTS	1
4.	NOTES	1

FIGURES

Figure		Page
1.	Thickness range - 1/8 inch to and including 1/4 inch thick	3
2.	Thickness range - over 1/4 inch to and including 1/2 inch thick	4
3.	Thickness range - over 1/2 inch to and including 1 inch thick	5
4.	Thickness range - over 1 inch to and including 2 inches thick	6
5.	Thickness range - over 1 inch to and including 2 inches thick	7

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:39Z
Check the source to verify that this is the current version before use.

formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Copies of this standard for Military use may be obtained as indicated in the foreword to, or the general provisions of, the Index of Military Specifications and Standards.

Both the title and the identifying number should be stipulated when requesting copies of Military Standards.

Preparing activity:
Navy - Ships
(Project MISC-N005Sh)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:39Z
Check the source to verify that this is the current version before use.

T=1/8 "TO AND INCLUDING 1/4" THICK




Figure 1

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:39Z
Check the source to verify that this is the current version before use.





Figure 2

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:39Z
Check the source to verify that this is the current version before use.


T = OVER 1/2" TO AND INCLUDING 1" THICK

ASSORTED – RANDOMLY DISPERSED




ALL SIZES TO 1/16" IN DIAMETER
MAXIMUM NUMBER OF INDICATIONS IN 6" = 15

LARGE – RANDOMLY DISPERSED




3/64" TO 1/16" MAXIMUM IN DIAMETER
MAXIMUM NUMBER OF INDICATIONS IN 6" = 8

MEDIUM – RANDOMLY DISPERSED



1/32" TO 3/64" IN DIAMETER
MAXIMUM NUMBER OF INDICATIONS IN 6" = 15

FINE – RANDOMLY DISPERSED



UP TO 1/32" IN DIAMETER
MAXIMUM NUMBER OF INDICATIONS IN 6" = 20


SH7274

Figure 3

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:39Z
Check the source to verify that this is the current version before use.


T = OVER 1" TO AND INCLUDING 2" THICK

ASSORTED – RANDOMLY DISPERSED



ALL SIZES TO 3/32" IN DIAMETER
MAXIMUM NUMBER OF TOTAL INDICATIONS IN 6" = 15

LARGE – RANDOMLY SPACED



1/16" TO 3/32" MAXIMUM IN DIAMETER
MAXIMUM NUMBER OF INDICATIONS IN 6" = 8


SH 7275

Figure 4

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:39Z
Check the source to verify that this is the current version before use.


T=OVER 1" TO AND INCLUDING 2" THICK

MEDIUM-RANDOMLY DISPERSED



3/64" TO 1/16" IN DIAMETER
MAXIMUM NUMBER OF INDICATIONS IN 6"= 15

FINE-RANDOMLY DISPERSED



UP TO 3/64" IN DIAMETER
MAXIMUM NUMBER OF INDICATIONS IN 6"= 20

SH7276

Figure 5

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T22:39Z
Check the source to verify that this is the current version before use.