INCH-POUND

MIL-D-45441D (AR)
AMENDMENT 3
3 June 1994
SUPERSEDING
AMENDMENT 2
01 April 1992

MILITARY SPECIFICATION

DETONATOR STAB, M61, PARTS FOR,
AND LOADING, ASSEMBLING AND PACKING

This Amendment forms a part of Military Specification MIL-D-45441D (PA) dated 5 April 1974 and is approved for use by the US Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of Department of Defense.

PAGE 8

4.3.2.3, Major Defect 102: Delete the word "concentricity" and substitute the words "true position".

PAGE 12

4.4.1: Delete in its entirety and substitute the following:

"4.4.1 Determination of moisture content of lead azide. A tared dried aluminum dish 2 inches in diameter shall be covered with a sheet of polytetrafluoroethylene (PTFE) 2-1/2 inches square and sufficiently flat to form a tight cover. An accurately weighed portion of approximately 2 grams shall be transferred to the moisture dish while both the cover and dish are on the balance pan. The dish and contents shall be transferred to an oven and dried at 95 +/- 5 degrees C for 2 hours. The cover shall be placed in a desiccator during the drying period. After drying, the dish shall be quickly transferred to the desiccator and allowed to cool to room temperature. The PTFE cover shall be placed on the dish and the assembly weighed. The loss in weight shall be calculated to percentage of moisture in the lead azide as follows:

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T03:00Z
Check the source to verify that this is the current version before use.

$$\text{Percentage of moisture} = \frac{100(A - B)}{A}$$

Where:

A = weight of specimen before drying
B = weight of specimen after drying.

4.4.1.1 Determination of moisture content of lead azide, alternate method. The procedure is the same as paragraph 4.4.1 with the following exception. The sample shall be dried in a vacuum oven at a temperature of 95 +/- 5 degrees C and a pressure of 80 +/- 10 mm mercury for 45 minutes.

4.4.1.2 Determination of moisture content of primer mixture. Transfer an accurately weighed portion of approximately 1 gram of the primer mixture to a tared aluminum weighing dish provided with a polytetrafluoroethylene (PTFE) cover while both the dish and cover are on the balance pan. Place the dish and contents with the cover removed, in an oven maintained at 60 +/- 5 degrees C for 2 hours. The cover shall be placed in a desiccator during the drying period. After drying, transfer the dish and contents quickly to a desiccator and cool to room temperature. Replace the PTFE cover and weigh. Calculate the loss in weight of the dish, the cover, and the contents to percent moisture in the sample.

4.4.1.2.1 Determination of moisture content of primer mixture, alternate method. The procedure is the same as paragraph 4.4.1.2 with the following exception. The sample shall be dried in a vacuum oven at a temperature of 60 +/- 5 degrees C and a pressure of 80 +/- 10 mm of mercury for 45 minutes."

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T03:00Z
Check the source to verify that this is the current version before use.

* Add the following paragraph:

"5.4 Performance oriented packaging (POP). The exterior pack cited above shall meet all of the POP test requirements in accordance with Code of Federal Regulations Title 49 (49 CFR). A POP test report shall be generated in accordance with DI-PACK-81059 following the tests. POP testing may be waived if an acceptable analogy in accordance with 49 CFR, to another pack which has successfully completed the testing, can be made. An analogy must also be documented in accordance with DI-PACK-81059. When completed, either POP test report must be kept on file by the contractor and must also be submitted to the U.S. Army Research, Development and Engineering Center, ATTN: SMCAR-AEP, Picatinny Arsenal, NJ 07806-5000. (Note: If a POP test report is prepared against an acceptable analogy, the analogy POP test must also be submitted to SMCAR-AEP). The POP marking to be applied to the exterior pack shall be as specified by the government after review and acceptance of the submitted POP test reports."

NOTE: The margins of this amendment are marked with an asterisk or vertical line to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1375-0001)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T03:00Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T03:00Z
Check the source to verify that this is the current version before use.