
MS9633

FED SUP CLASS 5306



PART NUMBER	L	K	APPROX WEIGHT LB/100
MS9633-03	.312	.072- .092	.44
MS9633-04	.375	.072- .092	.46
MS9633-05	.438	.072- .092	.48
MS9633-06	.500	.072- .092	.51
MS9633-07	.562	.072- .092	.53
MS9633-08	.625	.072- .092	.55
MS9633-09	.688	.072- .092	.58
MS9633-10	.750	.072- .120	.60
MS9633-11	.812	.122- .182	.62
MS9633-12	.875	.185- .245	.64
MS9633-13	.938	.248- .308	.67
MS9633-14	1.000	.310- .370	.69
MS9633-15	1.062	.372- .432	.71
MS9633-16	1.125	.435- .495	.73
MS9633-17	1.188	.498- .558	.76
MS9633-18	1.250	.560- .620	.78
MS9633-19	1.312	.622- .682	.80
MS9633-20	1.375	.685- .745	.83
MS9633-21	1.438	.748- .808	.85
MS9633-22	1.500	.810- .870	.87
MS9633-23	1.562	.872- .932	.89
MS9633-24	1.625	.935- .995	.92
MS9633-25	1.688	.998-1.058	.94

PART NUMBER	L	K	APPROX WEIGHT LB/100
MS9633-26	1.750	1.060-1.120	.96
MS9633-27	1.812	1.122-1.182	.99
MS9633-28	1.875	1.185-1.245	1.01
MS9633-29	1.938	1.248-1.308	1.03
MS9633-30	2.000	1.310-1.370	1.05
MS9633-31	2.125	1.435-1.495	1.10
MS9633-32	2.250	1.560-1.620	1.15
MS9633-33	2.375	1.685-1.745	1.20
MS9633-34	2.500	1.810-1.870	1.24
MS9633-35	2.625	1.935-1.995	1.29
MS9633-36	2.750	2.060-2.120	1.33
MS9633-37	2.875	2.185-2.245	1.37
MS9633-38	3.000	2.310-2.370	1.42
MS9633-39	3.125	2.435-2.495	1.47
MS9633-40	3.250	2.560-2.620	1.51
MS9633-41	3.375	2.685-2.745	1.56
MS9633-42	3.500	2.810-2.870	1.60
MS9633-43	3.625	2.935-2.995	1.65
MS9633-44	3.750	3.060-3.120	1.70
MS9633-45	3.875	3.185-3.245	1.74

1. SHANK SHALL BE STRAIGHT WITHIN .003 TOTAL PER INCH OF BOLT LENGTH.
2. THE CONCENTRICITY OF THREAD PD IN RELATION TO THE SHANK SHALL BE WITHIN .006 FIR.
3. THE CONCENTRICITY OF THE SHANK IN RELATION TO THE WASHER FACE DIAMETER AND HEXAGON SHALL BE WITHIN .011 FIR.
4. INCOMPLETE THREADS NOT TO ENTER FILLET.
5. MATERIAL TITANIUM AMS 4967.
6. HARDNESS: ROCKWELL C36-42.
7. MANUFACTURING SPECIFICATION AMS 7461, EXCEPT MATERIAL AS NOTED.
8. FLUORESCENT PENETRANT INSPECTION PER AMS 2645.
9. SURFACE TEXTURE. USAS B46.1-1962. UNLESS OTHERWISE SPECIFIED, SURFACES TO BE 125 MICROINCHES EXCEPT UPSET HEAD.
10. BREAK SHARP EDGES .003-.015 UNLESS OTHERWISE SPECIFIED.
11. DIMENSIONS IN INCHES. UNLESS OTHERWISE SPECIFIED, TOLERANCES: LINEAR DIMENSIONS ± .010, ANGULAR DIMENSIONS ± 5°.
12. DO NOT USE UNASSIGNED PART NUMBERS.

AS & AMS ARE SOCIETY OF AUTOMOTIVE ENGINEERS, INC. PUBLICATIONS.
THIS STANDARD WAS DEVELOPED COOPERATIVELY WITH THE MILITARY SERVICES BY THE SAE AEROSPACE PART STANDARDS DIVISION.

APPROVED 3 MAR 70 REVISED

PA USAF-11 Other Cust NAVY-AS	INTERNATIONAL INTEREST ASCC AIR STD 17/2	TITLE BOLT, MACHINE - HEXAGON HEAD, PD SHANK, TITANIUM AMS 4967, .190-32 UNJF-3A	MILITARY STANDARD MS9633
PROCUREMENT SPECIFICATION NONE		SUPERSEDES:	SHEET 1 OF 1

DD FORM 672.1 PREVIOUS EDITIONS OF THIS FORM ARE OBSOLETE

Review activities: USAF-82

This military standard is approved by the Department of Defense and is mandatory on all activities. Selection for all new engineering and design applications and for repetitive use shall be made from this document

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T13:21Z
Check the source to verify that this is the current version before use.