RR-P-35C
July 30, 1971
SUPERSEDING
Fed. Spec. RR-P-35b
May 16, 1966

FEDERAL SPECIFICATION

PAILS, UTILITY METAL (ZINC-COATED)

s specification was approved by the Commissioner, Federal Supply Service, eral Services Administration, for the use of all Federal agencies.

SCOPE AND CLASSIFICATION

Scope. This specification covers zinc-coated metal utility pails bail and without pouring lip.

Classification.

.1 Types and capacities. Metal pails covered by this specification be of the following types and capacities, as specified (see 6.2):

Type I	-	Lightweight
Capacity	-	10 Quarts
Capacity	-	12 Quarts
Capacity	-	14 Quarts
Type II	-	Heavyweight
Capacity	-	14 Quarts

APPLICABLE DOCUMENTS

The following documents, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification e extent specified herein:

Federal Specifications:

QQ-S-698	-	Steel, Sheet and Strip, Low-Carbon.
QQ-W-461	-	Wire, Steel, Carbon, (Round, Bare and Coated).
QQ-Z-325	-	Zinc Coating, Electrodeposited, Requirements For.
PPP-P-130	-	Pails and Cans, Packaging and Packing Of.

Federal Standard:

FED-STD-123	-	Marking for Domestic Shipment (Civil Agencies).

FSC 7240

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

(Single copies of this specification and other Federal Specifications required by activities outside the Federal Government for bidding purposes are available without charge from Business Service Centers, at the General Services Administration Regional Offices in Boston, New York, Washington, DC, Atlanta, Chicago, Kansas City, MO, Ft. Worth, Denver, San Francisco, Los Angele and Seattle, WA.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

Military Standards:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless a specific issue is indicated, the issue in effect on date of invitation for bids or request for proposal shall apply:

American Society for Testing and Materials (ASTM) Standards:

A90 - Method of Test for Weight of Coating on Zinc-Coated (Galvanized) Iron or Steel Articles.
B117 - Method of Salt Spray (Fog) Testing.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

U.S. Department of Health, Education and Welfare

Federal Food, Drug and Cosmetic Act and Regulations Promulgated Thereunder

(Application for copies should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402.)

(Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups, and using Federal agencies.)

3. REQUIREMENTS

3.1 First article. When specified, the supplier shall furnish a sample for first article inspection and approval (see 4.2, 6.2, and 6.3).

3.1.1 Certification. When the use of a seaming compound is necessary to enable a given product to meet the provisions of this specification, the supplier shall submit satisfactory evidence to the contracting officer or his authorized representative that the seaming compound and all substances incorporated therein meet the requirements of Federal Food, Drug, and Cosmetic Act; Food Additive Resulting from Contact with Containers or Equipment and Food Additives Otherwise Affecting Food (Code for Federal Requirements for Contact with Food). Acceptable evidence of meeting the requirements of this document shall be a certified report of compliance acceptable to the procuring activity and submitted prior to approval of the first article if one is submitted or prior to approval of the first shipment, if no first article is required.

3.2 Standard product. The metal pails delivered under this specification shall be the manufacturer's standard commercial product, except for any changes necessary to comply with this specification.

3.3 Design. Each completely fabricated and finished pail shall be watertight. There shall be no binding or catching which will prevent the bail from swinging freely in the ears.

3.4 Materials. Materials shall conform to the referenced specifications and requirements specified herein. Where materials are not definitely specified, they shall be of the quality normally used for the purpose in commercial practice, provided the completed item complies with all applicable provisions of this specification.

3.4.1 Steel, carbon, sheet or strip, bare (black) or zinc-coated.

3.4.1.1 Bare. Bare sheet or strip carbon steel shall conform to hot-rolled or cold-rolled commercial quality of QQ-S-698 and of thickness specified in tables I and II.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

TABLE I. Type I pails; capacities and dimensions

Brimful capacity (minimum)	Inside diameter				Overall height 1/		Body and bottom metal thickness (commercial 2/ tolerance applicable)
	Top		Bottom				
	Minimum	Maximum	Minimum	Maximum	Minimum	Maximum	
Quarts	Inches	Inches	Inches	Inches	Inches	Inches	Inch
10	10	11-1/4	8	9	8-3/4	10-1/4	0.0097 (min)
12	10-7/16	11-1/2	8	9	9-3/8	10-3/8	.0179 (nominal)
14	11	12-1/4	8-1/2	10	9-7/8	11	.0179 (nominal)

1/ Exclusive of ears and bail.

2/ Before galvanizing.

TABLE II. Type II pail; capacity and dimensions

Brimful capacity (minimum)	Inside diameter				Overall height 1/		Metal thickness (nominal) 2/	
	Top		Bottom					
	Minimum	Maximum	Minimum	Maximum	Minimum	Maximum	Body	bottom
Quarts	Inches	Inches	Inches	Inches	Inches	Inches	Inch	Inch
14	11	12-1/4	8-1/2	10	9-7/8	11	0.0239	0.0299

1/ Exclusive of bail.

2/ Before galvanizing.

3.4.1.2 Zinc-coated. Zinc-coated sheet or strip carbon steel shall comply with the steel composition in 3.4.1.1 and have a finished continuous zinc coating not less than 2 ounces per square foot total deposit (both surfaces) or not less than 0.0018 inch thick each surface when tested as specified in 4.4.2.

3.4.2 Wire.

3.4.2.1 Wire, steel zinc-coated. Zinc-coated carbon steel wire shall conform to steel numbers 1010-1020, finish 5, class 1 of QQ-W-461.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

3.4.2.2 Wire, steel reinforcing. Reinforcing wire shall be commercial bright steel.

3.4.3 Rivets, steel, flathead, tinners, bare (black) or zinc-coated finished.

3.4.3.1 Bare. The bare steel rivets shall be commercial type normally used for securing bail ears.

3.4.3.2 Zinc-coated. The zinc-coated steel rivets shall be as specified in 3.4.3.1 with a coating to type I, class 2 of QQ-Z-325.

3.4.4 Seaming compound. The seaming compound shall not flow, crack, or become brittle when tested as specified in 4.4.4.

3.5 Construction. Construction of all components and assemblies of the pail shall be as specified herein. The pails shall be made from either bare carbon sheet or strip steel (see 3.4.1.1), or zinc-coated sheet or strip steel (see 3.4.1.2). Pails made from steel specified in 3.4.1.1 shall be coated by the molten bath process. The formed bails specified in 3.6.5 shall be attached to the pail after coating. Pails fabricated from zinc-coated sheet steel specified in 3.4.1.2 shall have all components except the steel reinforcing wire specified in 3.4.2.2 (see 3.6.2.1) galvanized prior to assembly and shall have the side seam(s) and the bottom chime seam compound lined with sealing compound specified in 3.4.4. The seaming compound shall be applied to the open seam prior to closing the seams. All pails shall not leak when tested as specified in 4.4.1.

3.5.1 Type I pails, lightweight. The type I pails shall conform to the requirements specified in table I.

3.5.2 Type II pail, heavyweight. Type II pail shall conform to the requirements specified in table II.

3.6 Details of components.

3.6.1 Body. Body of the pails shall be fabricated of steel specified in 3.4.1 and shall conform to either the one-piece or two-piece method as specified in 3.6.1.1 and 3.6.1.2, respectively. The top edge for 12 and 14 quart pails, shall be reinforced by beading over a minimum of 0.225 inch diameter wire specified in 3.4.2.2 to form a tightly rolled bead completely around the top of the body with not more than 1/16 inch opening between bead edge and wall. There shall be not more than 3/4 inch between the two ends of the reinforcing wire at the top of the body. The top edge of the body of the type I, 10 quart capacity pail shall be reinforced with a minimum of 0.117 inch diameter wire.

3.6.1.1 One-piece body method. One-piece body method shall consist of forming a single piece of steel with the vertical ends joined together by a lock seam.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

3.6.1.2 Two-piece body method. Two-piece body method shall consist of forming two pieces of steel with the vertical ends joined together by two locked seams located diametrically opposite each other.

3.6.2 Ears. Two metal ears shall be provided on the outside of the pail at points diametrically opposite. Ears shall be so formed to permit the bail specified in 3.6.5 to move freely without binding or catching. On the one or two-piece body pails (see 3.6.1.1 and 3.6.1.2) the centerline of the ears shall be directly over the centerlines of the vertical seams, as applicable. Each ear shall be securely held in place with welding or a minimum of two rivets.

3.6.2.1 Type I, 10-quart capacity pail. Ears for the type I, 10-quart capacity pail shall be forged or stamped type and fabricated of a minimum of 20 gage (0.0359 inch nominal thickness) steel specified in 3.4.1. The ears shall be so located that the axis about which the bail swings shall be not more than 1-3/4 inches below nor more than 1 inch above the top of the pail. In lieu of ears, the top beading wire may be looped to serve as ears, provided a reinforcing clip fabricated of minimum of 20 gage steel specified in 3.4.1.2 is fastened at each loop. Alternatively, the top beading wire shall be galvanized as specified in 3.4.2.1 and the reinforcing clips shall not be required.

3.6.2.2 Type I, 12- and 14-quart capacity and type II pails. Ears for type I, 12- and 14-quart capacity and type II pails shall be butterfly type and formed so that the fold shall bend back on itself. Ears shall be fabricated of a minimum of 16 gage (0.0598 inch nominal thickness) steel specified in 3.4.1. Ears shall be located vertically so that the axis about which the bail swings shall be not less than 1 inch nor more than 1-3/4 inches below the top of the pail. Type I, 12- and 14-quart capacity pail ears may be of the forged or stamped type in lieu of the butterfly type.

3.6.3 Bottoms. Bottoms for all pails shall be fabricated of steel specified in 3.4.1 and shall be of one piece construction. The bottom shall be lock seamed to the sides of the body. The sides of the body shall extend below the bottom for a distance of not less than 1/4 inch nor more than 1 inch.

3.6.3.1 Type II pail. In addition to the requirements specified in 3.6.3, the bottom for the type II pail shall be either convex or concave in shape in accordance with the manufacturer's standard practice. At the option of the manufacturer, the bottom may be reinforced with 2 cross straps specified in 3.6.4. The straps shall rest against the underside of the bottom of the pail. When bottom straps are used, bottom of pail may be supplied with 0.0239 inch steel specified in 3.4.1.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

3.6.4 Strap. Strap, when used, shall be nominal 1-1/2 inches wide and shall be fabricated of a minimum of 11 gage (0.1196 inch nominal thickness) steel specified in 3.4.1.

3.6.5 Bails. Bails for all pails shall be fabricated of minimum of 0.313 inch diameter wire specified in 3.4.2.1. The ends of the bail shall be formed into loops to engage the ears specified in 3.6.2.1 and 3.6.2.2, as applicable. The loops shall be of such shape and size as to permit the bail to move freely in the ears without binding or catching. When ears are located so that the axis (see 3.6.2.1) is above the top of the pail, the bail shall be bent into a semicircle having a diameter not less than the top of the pail and the bail shall rest on the top of the pail. When ears are located so that the axis (see 3.6.2.1 and 3.6.2.2) is below the top of the pail, the bail shall be bent into a semicircle having a diameter not less than 1 inch greater than the top of the pail. When the bail rests against the sides of the pail, the bail shall clear the top edge of the pail. In lieu of the 0.313 inch diameter wire, the bail for the type I, 10-quart capacity pail may be fabricated of a minimum of 0.171 inch diameter wire.

3.7 Finish. Components of the pail, and the completed pail fabricated from steel specified in 3.4.1.1, excluding prefinished wire bails, shall be cleaned and loose scale or rust removed prior to being completely coated with zinc by the hot dip process. The weight of the coating shall be not less than 2 ounces per square foot (both surfaces) when tested as specified in 4.4.2.1, or thickness of coating shall be not less than 0.0018 inch thick (each surface) when tested as specified in 4.4.2.2. Components of the pail, the complete pail fabricated from steel specified in 3.4.1.2, and the prefinished wire bales and handles shall be cleaned. All pails shall have no exposed inside or outside surface area of no zinc or damaged finish except cut edges of zinc-coated steel sheet or strip specified in 3.4.1.2. The coating on all pails shall adhere and not peel when tested as specified in 4.4.3. There shall be no visible red rust on any surface of the pail when tested in accordance with 4.4.5. There shall be no visible crashes or flaking of the finish due to forming. Organic coating shall not be used to cover exposed areas.

3.8 Marking for identification. Pails shall be permanently and distinctly marked with the name or trademark of such known character as to make the source of manufacture easily determined in accordance with manufacturer's standard practice.

3.9 Workmanship. The finished pails, including welding, shall be complete, sound, smooth and free from burn through area, porosity, crack, fracture, and excess flux deposit. The pails shall be clean and free from

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

any rough or sharp edges, burrs or sliver, oil and grease, rust, flux, dirt, lumps, blisters, gritty areas, acid or black spots, dross, or areas of no coating except on cut edges. Rivets shall be thoroughly driven with heads flush against surface and the ends securely set.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

4.2 First article inspection. When a preproduction sample is required, it shall be examined for defects in table IV, dimensions specified, and tested in accordance with 4.4.1 through 4.4.5. The presence of any visual defects or any dimension not meeting specified requirements or failure to meet the test requirements shall be cause for rejection of the preproduction sample.

4.3 Inspection. Sampling for inspection shall be performed in accordance with MIL-STD-105, except where otherwise indicated hereinafter.

4.3.1 Component and material inspection. In accordance with 4.1, components and materials shall be inspected and tested in accordance with all the requirements of referenced specifications and standards to the extent specified herein, or, if none, in accordance with this specification.

4.3.1.1 Seaming compound. The seaming compound shall be tested in accorance with 4.4.4.1 and 4.4.4.2. The sample shall be 2 ounces of the seaming compound for each test. The test shall be conducted on each lot of seaming compound offered at one time. Failure to meet the requirements of 3.4.4. shall be cause for rejection of the lot.

4.3.2 In-process inspection.

4.3.2.1 In-process examination. Examination shall be made during the manufacturing process for the requirements specified in table III to establish that no deviation is made from the indicated requirements. Whenever a nonconformance is noted, correction shall be made to the affected items and the process.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

TABLE III. In-process examination

Requirement	Requirement paragraph
Application of seaming compound prior to closing of seam (when applicable).	3.5
Cleaning and removing of loose scale and rust prior to zinc-coating of the pails.	3.7

4.3.2.2 Intermediate test. Prior to fabrication, zinc-coated sheet or strip shall be tested in accordance with 4.4.2.1 or 4.4.2.2 at the option of the supplier. The sample unit shall be one sheet or strip of zinc-coated steel. Any nonconformance with the requirements of 3.4.1.2 should be cause for rejection of the sheet or strip and the lot.

4.3.3 End item inspection. The lot shall be all the pails of one type and capacity offered for inspection at one time. The sample unit for this inspection shall be one completely fabricated pail.

4.3.3.1 Visual examination. Examination shall be made of the pails for the defects in table IV. The inspection level shall be II with an acceptable quality level (AQL) of 4.0 for major defects and 10.0 for total defects, expressed in terms of defects per hundred units.

TABLE IV. Classification of defects

Examine	Defect	Classification Major	Minor
Finish zinc-coating (except bail)	Not zinc-coated	X	
	Coating not smooth, adherent, and continuous		X
	Lump, blister, gritty area, uncoated spot, acid or black spot, dross, or flux		X
	Rust, area of no coating, except on cut edges	X	

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of defects (con.)

Examine	Defect	Classification Major	Minor
General	Nicks, gouges, scratches, or abrasions noticeable at a distance not less than five feet		X
	Pail not clean, evidence of oil, grease or dirt		X
	Rough or sharp edge, burr, or sliver	X	
Construction and workmanship	Component missing	X	
	Bail not attached to ear	X	
	Rivet or weld missing (as applicable)		X
	Rivet head not flush against surface		X
	End of rivet not securely set but can not be removed by hand		X
Welding	Not complete, sound or smooth (when applicable)		X
	Evidence of burn through area, porosity, crack, fracture, or excess flux deposit		X
Body	More than two seams	X	
	Top edge not reinforced with beading over wire	X	
	Vertical ends of body not joined together by a lock seam	X	
	Two locked seams not located diametrically opposite each other (as applicable)		X
Ear	Not on outside of pail		X
	Not at points diametrically opposite	X	
	Malformed, i.e. causing interference of the free movement of bail with catching or binding		X
	Centerline of ear not directly over centerline of body seam (when applicable)		X
	Not specified type		X
	Reinforced clip missing (as applicable to wire loop when serving as ear)		X
	Butterfly type not formed as specified, i.e. fold not bent back on itself (except for type I, 10-quart capacity pail)		X

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

TABLE IV. Classification of defects (con.)

Examine	Defect	Classification Major	Minor
Construction and workmanship (cont'd)			
Bottom	More than one-piece construction	X	
	Not lock seamed to the sides of the body	X	
(applicable to type II pail)	Not concave or convex in shape or straps missing when applicable		X
Bail	Ends not looped		X
	Not engaging the ear	X	
	Malformed, i.e. causing interference of the free movement in ear with binding or catching		X
	Does not rest on top of the pail (applicable to pails having pivot above the top of the pail)		X
	Does not clear the top of pail (applicable to pails having pivot below the top of the pail)		X
Marking	Missing, illegible, or incomplete		X

4.3.3.2 Dimensional examination. Examination shall be made of the pails for defects in dimensions. Any dimension not within specified tolerances shall be classified as a defect. The inspection level shall be S-2 with an AQL of 4.0, expressed in terms of defects per hundred units.

4.3.3.3 End item testing. Testing of the completely finished pails shall be performed in accordance with table V for characteristics shown therein. Any non-conformance shall constitute a defect. The inspection level shall be S-2 with and AQL of 4.0, expressed in terms of defects per hundred units.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:08Z
Check the source to verify that this is the current version before use.

TABLE V. Testing

Characteristic	Requirement paragraph	Test procedure	Sample unit	Inspection
Leakage	3.5	4.4.1	One pail	Pass or fail
Zinc-coating: 1/				
Weight	3.7	4.4.2.1	One pail	Pass or fail
Thickness	3.7	4.4.2.2	One pail	Pass or fail
Adhesion	3.7	4.4.3	One pail	Pass or fail
Salt spray test	3.7	4.4.5	One pail	Pass or fail

1/ Zinc-coating shall be tested by either the weight or thickness method. Hot dip process only.

4.3.3.4 Standard compliance. Proof of compliance with the requirements of 3.4.4 shall be submitted to the Government representative.

4.3.4 Examination of preparation for delivery. Examination of preparation for delivery shall be in accordance with PPP-P-130.

4.4 Tests.

4.4.1 Leakage. The pail to be tested shall be filled with water to within one half inch of top of pail and allowed to stand for 24 hours. Examination shall then be made to determine compliance with 3.5. Any nonconformance shall constitute failure of the test.

4.4.2 Weight or thickness of zinc-coating.

4.4.2.1 Weight. The weight of the zinc-coating shall be determined to the nearest 0.01 oz. in accordance with ASTM A90.

4.4.2.2 Thickness. The thickness of the zinc-coating shall be checked to the nearest 0.001 inch with a magnetic type gage in accordance with the industry's commercial practice. Readings shall be taken on one surface of the sheet or pail, as applicable, and on the opposite surface of the next sheet or pail tested, alternately, throughout the testing of the samples.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:08Z
Check the source to verify that this is the current version before use.

4.4.3 Adhesion of zinc-coating. From a height of 2 feet, drop a 1/2 pound steel ball on each pail selected for the test. Examine test area of pail for compliance with 3.7. Any nonconformance shall constitute failure of the test.

4.4.4 Seaming compound test.

4.4.4.1 High temperature test. The seaming compound shall be spread and dried as a thin film on tin plate and exposed to a forced hot air oven at +212°F. for 40 hours. Failure to meet the requirements of 3.4.4 shall constitute failure of the test.

4.4.4.2 Low temperature test. The seaming compound shall be spread and dried as a thin film on a tin plate and exposed to a temperature of -40°F. for 24 hours. The tin plate shall be bent back on itself so that the coating is on the outer surface. Failure of the seaming compound to meet the requirements of 3.4.4 shall constitute a failure of the test.

4.4.5 Salt spray test. Pails shall be subjected to a 96 hour salt spray test in accordance with ASTM B117-64. No areas or edges of the pail shall be covered or protected during this test.

5. PREPARATION FOR DELIVERY

5.1 Packing. Packing shall be in accordance with the level A, B, or C requirements of PPP-P-130, as specified (see 6.2).

5.2 Marking.

5.2.1 Civil agencies. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with FED-STD-123.

5.2.2 Military activities. In addition to any special marking required by the contract or order, shipments shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The pails covered by this specification are for general carrying use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

6.2 Ordering data. Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

(a) Title, number, and date of this specification.
(b) Type and capacity of pail required (see 1.2).
(c) When a first article is required (see 3.1, 4.2, and 6.3).
(d) Selection of applicable level of packing (see 5.1).

6.3 First article. When a first article is required it shall be inspected and approved under the appropriate provisions of ASPR 7-104.55. The first article should be a preproduction sample of the specified type pail. The first article should consist of one unit. The contracting officer should include specific instructions in all procurement instruments regarding arrangements for inspection and approval of the first article.

MILITARY CUSTODIANS:

Army - GL
Air Force - 84

Review activity:

Army - MD

User activities:

Navy - MC, YD

Preparing activity:

Army - GL

CIVIL AGENCIES INTEREST:

AGR
HEW
JUS-FPI
VA
COM
GSA

Project No. 7240-0157

Orders for this publication are to be placed with General Services Administration, acting as an agent for the Superintendent of Documents. See section 2 of this specification to obtain extra copies and other documents referenced herein. Price 15 cents each.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION

Pails, Utility Metal (Zinc-Coated) RR-P-35C

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

Source: https://assist.dla.mil -- Downloaded: 202640-26T12:08Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY
U. S. Army Natick Laboratories
Natick, Massachusetts 01760

POSTAGE AND FEES PAID
DEPARTMENT OF THE ARMY

U.S.MAIL

OFFICIAL BUSINESS

Commanding General
U. S. Army Natick Laboratories
ATTN: AMXRES-EQS
Natick, Massachusetts 01760

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:08Z
Check the source to verify that this is the current version before use.