RR-P-375B
AMENDMENT-2
September 8, 1972
SUPERSEDING
Int. Amendment-1
December 16, 1971

FEDERAL SPECIFICATION

PITCHERS, VACUUM OR INSULATED: FILLER, GLASS (REPLACEABLE)

This amendment, which forms a part of Federal Specification RR-P-375B, dated April 1, 1971, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 2

2.1, under Federal Specification.- Add in proper sequence:

"L-P-393 - Plastic Molding Material, Polycarbonate, Injection and Extrusion."

"L-P-394 - Plastic Molding Material, (Propylene Plastics, Injection and Extrusion)."

"L-P-1183 - Plastic Molding Material, Acrylonitrile-Butadiene-Styrene (ABS) Rigid."

PAGE 3

2.1, under Military Specification.- Delete "MIL-M-22544-Molding Plastic, Acrylonitrile-Butadiene-Styrene, Rigid."

Add "MIL-P-46120 - Plastic Molding and Extrusion Material, Polysulfone."

2.2.- Delete "American Society for Testing and Materials (ASTM) Specification.

D-2146 - Polypropylene Moulding and Extrusion Material (Tentative).

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103)".

PAGE 4

2.2, under "Uniform Classification Committee, Agent".- Delete "Room 202 Union Station, 516 W. Jackson Blvd." and substitute "Room 1106, 222 South Riverside Plaza".

FSC 7350

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:09Z
Check the source to verify that this is the current version before use.

PAGE 4 (con.)

3.3.2.- Delete "condition A".

PAGE 5

3.3.3.2.- Delete "MIL-M-22544" and substitute "L-P-1183".

3.3.3.6.- Delete "-00400 of ASTM D2146" and substitute "of L-P-394".

Add new paragraphs as follows:

3.3.3.7 Polysulfone.- Polysulfone shall conform to Type I, Class 1 of MIL-P-46120.

3.3.3.8 Polycarbonate.- Polycarbonate molding material shall conform to Form 1, of L-P-393.

3.4.1, second sentence.- Delete and substitute: "At the option of the manufacturer the type I, grade B pitcher may also have a plastic filler shield conforming to 3.4.4.1.6. The vacuum insulated replaceable glass filler shall be securely held in the body by a rubber retainer at the neck and a shock absorber at the bottom except that in pitchers having plastic filler shields, the replaceable glass filler shall be held in place by the filler shields or by the filler shields with a plastic or rubber gasket and a shock absorber at the bottom.

PAGE 6

3.4.2, third sentence.- Delete and substitute: "The temperature of water between 175 F - 180 F in the pitcher shall not drop more than 30 F in 30 minutes in an ambient temperature of 70 F $\pm$ 2 F when tested as specified in 4.4.1.3."

3.4.4.1.2.1, last line.- Delete "or 3.3.3.4" and substitute "3.3.3.4, or 3.3.3.8."

PAGE 7

3.4.4.1.4 Add the following:

"(f) Polycarbonate specified in 3.3.3.8."

Add new paragraph as follows:

3.4.4.1.6 Plastic filler shield, type I, grade B.- Plastic filler shields, when used in type I, grade B pitchers shall be fabricated of the

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:09Z
Check the source to verify that this is the current version before use.

PAGE 7 (cont'd)

polysulfone specified in 3.3.3.7, the polycarbonate specified in 3.3.3.8, or the polypropylene specified in 3.3.3.6. The shield shall fit down inside the replaceable glass filler and conform to the capacity requirements specified in 3.4.1. The plastic filler shield shall be removable to permit replacement of the glass filler.

PAGE 11

Table I, after Type I, grade A, defects.- Add "Type I, grade B, Plastic filler shield, when used, not removable." Classify as "Major Defect".

PAGE 12

4.3.6, line 3.- Delete the second sentence and substitute: "Defects shall be as indicated in table III."

PAGE 13

4.3.6.2, line 3.- Delete the second sentence and substitute: "Defects shall be as indicated in table IV."

PAGE 14

4.4.1.3 Delete and substitute:

4.4.1.3 Type II.- The type II insulated pitchers shall be preheated with water between 203 F and 207 F for a period of three minutes. The pitcher shall then be emptied and refilled with water at a temperature between 175 F and 180 F and the lid closed. The pitcher shall then remain in an ambient temperature of 70 ± 2 F for not less than 30 minutes. The water temperature shall then be measured to determine compliance with the heat retention requirements of 3.4.2. Any noncompliance with specified heat retention requirements shall constitute failure of this test.

MILITARY CUSTODIANS:

Army - GL
Navy - SA
Air Force - 84

Review activities:

Army - MD
Navy - MS

User activity:

Navy - MC

Preparing activity:

Army - GL

Project No. 7350-0127

Civil Agency Coordinating Activities:

GSA-FSS
VA-DMS

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:09Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:09Z
Check the source to verify that this is the current version before use.