[METRIC]
A-A-2121A
March 20 1995
Superseding
A-A-2121
August 8, 1983

COMMERCIAL ITEM DESCRIPTION

COVER, PAINT ROLLER

The General Services Administration has authorized this use of this commercial item description, for all federal agencies.

1. Scope. This commercial item description covers paint roller covers. The size (or length) of the paint roller cover shall be as specified in the contract or order.

2. Salient characteristics:

2.1 Type 1, Animal Fibers and Animal/Synthetic Fiber Type.

Class A - Sheepskin (for use with oil base paints on rough surfaces.)
Class B - Woven mohair/viscose blend (for use with oil base paints on smooth surfaces.)

2.2 Type 2, Synthetic

Class A - Knitted polyester (for use with latex and oil base paints.)
Class B - Woven acrylic/modacrylic blend (for use with latex paints.)
Class C - Woven polyester (for use with latex paints.)

2.3. Covers shall consist of a pile on a backing as specified for the applicable type and class. When immersed in mineral spirits (type 1 and 2) or water (type 2) for one hour, the backing material, cement or core shall not show evidence of solubility to such an extent that the ends of the covers separate more than 1.6 mm (1/16 inch). The cover shall not slip off the cage with an end-wise pull of less than 27 N (6 pounds). For pile heights 3.2 mm (1/8 inch) up to and including 22 mm (7/8 inch), the pile shall be beveled 45°. For pile heights 25.4 mm (1-inch) and greater, the bevel shall be not less than 30° nor more than 45° from the end plane to the core. The sheepskin or fabric cover shall be attached to the core by adhesive bonding which shall include end gluing. Staples used in the manufacturing process, for fastening the sheepskin or fabric to the core, shall be removed. The assembled roller cover shall have a minimum bonding strength of 33 N (7.5 pounds) per linear inch (except that Type 1, Class A shall be 22 N [5 pounds] per linear inch minimum.) All roller covers shall be of the sewed-stocking type.

2.4 Type 1, Class A covers shall be of tanned sheepskin with pile heights of 16 mm (5/8 inch), 25.4 mm (1-inch), or
32 mm (1-1/4 inch) +/- 4.8 mm (3/16 inch). The sheepskin shall be of a uniform color without bare spots, cuts, holes or hard spots.

2.5 Type 1, Class B covers shall be made of a woven pile fabric with the pile being a blend of mohair and viscose fibers. The pile yarn shall be woven with a "W" bind weave with 212 tufts per square inch +/- 5 %. The backing fabric shall be woven with 55 ends (warp) and 46 picks (filling) per inch +/- 5 %. The backing fabric shall be coated with a heat-cured synthetic coating. Pile thickness, backing yarn size, pile yarn content and weight of fabric shall be as specified in Table 1.

Beneficial comments, recommendations, additions, deletions, clarification, etc., and any data which may improve this document, should be sent to: GSA, Paints and Chemicals Commodity Center, 400 15th Street, S.W., Auburn, WA 98001.

DISTRIBUTION STATEMENT: Approved for public release.
Distribution is unlimited.

FSC 8020

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:19Z
Check the source to verify that this is the current version before use.

Table 1. ROLLER COVERS, TYPE 1, CLASS B

Thickness mm, (inch)	Pile Tolerance mm, (inch)	Backing Yarn Cotton or Polyester Size Warp	Filling	Pile Yarn Content	Fabric Weight/ Square Yard including backing, grams, (ounces), min.	
5 (13/64)	+/- 0.8 (1/32)	20/2	10/1	40 % Mohair 60 % Viscose	606	(19.5)
6 (1/4)	+/- 0.8 (1/32)	20/2	10/1	40 % Mohair 60 % Viscose	684	(22)

2.6 Type 2, Class A roller covers shall be knotted, crimped polyester on a 100 percent polyester backing. The backing shall be knit with not less than 10 wales, and not less than 21 courses nor more than 25 courses per inch. The fabric shall be back coated with a heat-cured synthetic coating. Pile height, polyester size, denier of pile and weight per square yard shall be in accordance with Table 2.

Table 2. ROLLER COVER, TYPE 2, CLASS A

Height mm, (inch)	Pile Tolerance mm (inch)	Backing Material Polyester, Size Warp Max	Filling Min	Pile Denier	Fabric Weight/ Square Yard including backing, kg., (ounces), min.	
9.5 (3/8)	+/- 0.8 (1/32)	10/1	14/1	100 % - #6	0.9	(29)
16 (5/8)	+/- 1.6 (1/16)	10/1	14/1	75 % - #6 25 % - # 15	1.02	(33)
22 (7/8)	+/- 1.6 (1/16)	10/1	14/1	75 % - #6 25 % - # 15	1.15	(37)
25.4 (1)	+/- 2 (3/32)	10/1	14/1	75 % - #6 25 % - # 15	1.31	(42)
32 (1-1/4)	+/- 2 (3/32)	10/1	14/1	75 % - #6 25 % - # 15	1.43	(46)

2.7 Type 2, Class B roller cover shall be made of a woven pile fabric with the pile being a blend of acrylic and modacrylic fibers. The pile yarn shall be woven with a "W" bind weave. The 6 mm (0.225 inch) pile thickness shall have 111 tufts per square inch +/- 5 % and the backing fabric shall be woven with 52 ends and 48 picks per 25.4 mm (1-inch) +/- 5 %. The backing fabric shall be coated with a heat cured synthetic coating. Pile thickness, backing yarn size, pile yarn content and weight of fabric shall be as specified in Table 3.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:19Z
Check the source to verify that this is the current version before use.

TABLE 3. ROLLER COVERS, TYPE 2, CLASS B

Pile Thickness mm, (inch)	Pile Tolerance mm,(inch)	Backing Yarn Cotton or Polyester Size Warp	Backing Yarn Cotton or Polyester Size Filling	Pile Yarn Content	Fabric Weight/ Square Yard Including backing, kg.,	Fabric Weight/ Square Yard Including backing, (ounces), min.
5.8 (29/128)	+/- 0.8 (1/32)	20/2	10/1	65 % Acrylic 35 % Modacrylic	0.5	(17-1/4)
9.5 (0.375)	+/- 0.8 (1/32)	20/2	10/1	65 % Acrylic 35 % Modacrylic	0.7	(24-1/4)

2.8 Type 2, Class C roller covers shall be made of a woven pile fabric with the pile being 100 % polyester fiber. The pile yarn shall be woven with a "W" bind weave with 184 tufts per 6.5 cm^2 (1-$inch^2$). The backing fabric shall be woven with 55 ends (warp) and 40 picks (filling) per 6.5 cm^2 (1-$inch^2$) +/- 5 %. The backing fabric shall be coated with a heat-cured synthetic coating. Pile thickness, backing yarn size and weight of fabric shall be specified in Table 4.

TABLE 4. ROLLER COVERS, TYPE 2, CLASS C

Pile Thickness mm, (inch)	Pile Tolerance mm,(inch)	Backing Yarn Cotton or Polyester Size Warp	Backing Yarn Cotton or Polyester Size Filling	Pile Yarn Content	Fabric Weight/ Square Yard Including backing, kg., (ounces), min.
5 (13/64)	+/- 0.8 (1/32)	20/2	10/1	100 % Polyester	0.51 (16.5)
6.3 (1/4)	+/- 0.8 (1/32)	20/2	10/1	100 % Polyester	0.54 (17.25)

3. Certification. The contractor shall certify that the product offered meets the salient characteristics of this description, and that the product conforms to the producer's own drawings, specifications, standards and quality assurance practices and is the same product offered for sale in the commercial marketplace. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

4. Regulatory requirements. The offeror/contractor is encouraged to use recovered materials in accordance with Public Law 94-580 to the maximum extent practicable.

5. Preservation, packaging, packing, labeling, and marking. Preservation, packaging, packing, labeling, and marking shall be as specified in the contract or order.

PREPARING ACTIVITY

GSA - FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:19Z
Check the source to verify that this is the current version before use.