
MIL-W-16878/6B(NAVY)
10 August 1981
SUPERSEDING
MIL-W-16878/6A(NAVY)(IN PART)
5 July 1961
(See supersession data herein)

MILITARY SPECIFICATION SHEET

WIRE, ELECTRICAL, POLYTETRAFLUOROETHYLENE (PTFE) INSULATED, 200°C, 250 VOLTS, EXTRUDED INSULATION

This specification sheet is approved for use by the Naval Sea Systems Command, Department of the Navy, and is available for use by all Departments and Agencies of the Department of Defense.

The complete requirements for acquiring the wire described herein shall consist of this document and the latest issue of MIL-W-16878.



SH 11875

FIGURE 1. Construction.

TABLE I. Construction details.

Wire size	Stranding	Conductor		Conductor diameter (nominal) (inch)	Finished wire Diameter (inch)	
		Material 2/ 3/	Coating		Min	Max
32	7 X 40	Copper	Silver	0.010	0.020	0.024
32	7 X 40	H.S.C.A.	Silver	.010	.020	.024
32	7 X 40	C.C. Steel	Silver	.010	.020	.024
30	1 X 30	Copper	Silver	.0100	.020	.024
30	1 X 30	H.S.C.A.	Silver	.0100	.020	.024
30	1 X 30	C.C. Steel	Silver	.0100	.020	.024

See footnotes at end of table

FSC 6145

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:27Z
Check the source to verify that this is the current version before use.

TABLE I. Construction details.- Continued

Wire size	Stranding	Conductor		Conductor diameter (nominal) (inch)	Finished wire	
		Material 2/ 3/	Coating		Diameter (inch)	
					Min	Max
30	7 X 38	Copper	Silver	0.012	0.022	0.026
30	7 X 38	H.S.C.A.	Silver	.012	.022	.026
28	1 X 28	Copper	Silver	.0126	.023	.027
28	1 X 28	H.S.C.A.	Silver	.0126	.023	.027
28	1 X 28	C.C. Steel	Silver	.0126	.023	.027
28	7 X 36	Copper	Silver	.015	.025	.029
28	7 X 36	H.S.C.A.	Silver	.015	.025	.029
26	1 X 26	Copper	Silver	.0159	.026	.030
26	1 X 26	H.S.C.A.	Silver	.0159	.026	.030
26	1 X 26	C.C. Steel	Silver	.0159	.026	.030
26	7 X 34	Copper	Silver	.019	.029	.033
26	7 X 34	H.S.C.A.	Silver	.019	.029	.033
26	19 X 38	Copper	Silver	.020	.029	.033
26	19 X 38	H.S.C.A.	Silver	.020	.029	.033
24	1 X 24	Copper	Silver	.0201	.030	.034
24	1 X 24	H.S.C.A.	Silver	.0201	.030	.034
1/ 24	1 X 24	C.C. Steel	Silver	.0201	.030	.034
24	7 X 32	Copper	Silver	.024	.034	.038
24	7 X 32	H.S.C.A.	Silver	.024	.034	.038
24	19 X 36	Copper	Silver	.025	.034	.038
24	19 X 36	H.S.C.A.	Silver	.025	.034	.038
22	1 X 22	Copper	Silver	.0254	.035	.040
22	1 X 22	H.S.C.A.	Silver	.0254	.035	.040
1/ 22	1 X 22	C.C. Steel	Silver	.0254	.035	.040
22	7 X 30	Copper	Silver	.030	.040	.044
22	7 X 30	H.S.C.A.	Silver	.030	.040	.044
22	19 X 34	Copper	Silver	.032	.040	.044
22	19 X 34	H.S.C.A.	Silver	.032	.040	.044
20	1 X 20	Copper	Silver	.0320	.042	.046
20	1 X 20	H.S.C.A.	Silver	.0320	.042	.046
20	7 X 28	Copper	Silver	.038	.048	.052
20	7 X 28	H.S.C.A.	Silver	.038	.048	.052
20	19 X 32	Copper	Silver	.040	.048	.052
20	19 X 32	H.S.C.A.	Silver	.040	.048	.052

1/ Inactive for new design.
2/ H.S.C.A. stands for high strength copper alloy.
3/ C.C. Steel stands for copper clad steel

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:27Z
Check the source to verify that this is the current version before use.

REQUIREMENTS:

Visual and mechanical inspection: Applicable.
Spark test: 2.5 kilovolts (kV).
Impulse dielectric test: 4.0 kV.
Tank test: 1.5 kV.
Dielectric withstanding voltage: 1.5 kV.
Insulation resistance: $IR = K \log_{10} D/d$

Where: IR = Minimum insulation resistance in megohms per 1000 feet at 20°C.
K = 50,000
D = Maximum average diameter of finished wire
d = Conductor diameter

Cold bend: Condition 4 hours at minus 65°C ± 1°C (see table II).

TABLE II. Cold bend mandrel sizes.

Wire size	Cold bend mandrel (maximum diameter) (inches)
32 through 20	1

Concentricity: 70 percent (minimum).
Surface resistance: 5 megohms (minimum).
Wrap back: Applicable.
Heat resistance: Condition at 290°C.
Flammability: Not applicable
Soldering: Applicable.
Heating aging: Not applicable.
Insulation tensile strength: 3000 pounds force per square inch (minimum).
Insulation elongation: 150 percent (minimum).
Stripe durability: Applicable.
Fungus resistance: Applicable.
Maximum direct current resistance of finished wire: See table I of MIL-W-16878.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:27Z
Check the source to verify that this is the current version before use.

TABLE III. Put-up tabulation. 1/

AWG size	Percentage of order	Length (ft) one continuous length	Max. no. of lengths (per spool or reel)	
			500 ft	1000 ft
32 to 22	25	Under 75	4	6
	25	75 - 300		
	50	301 or more		
20 to 16	Unacceptable	Under 75	5	7
	20	75 - 100		
	50	101 - 300		
	30	301 or more		
14 to 10	Unacceptable	Under 50	5	6
	40	50 - 100		
	50	101 - 300		
	10	301 or more		

1/ Each spool or reel shall be marked accordingly with the length in feet and location of each piece.

Military part number (see MIL-W-16878):

M16878/ 6 B C B 905

- M16878/: Military designation
- 6: Specification sheet
- B: Conductor material
- C: Conductor size
- B: Conductor stranding
- 905: Color code

Supersession data: The wire covered by this specification sheet supersedes MIL-W-16878/6A(NAVY), type ET, 200°C rated, extruded without jacket.

Review activities:
Navy - AS, EC

User activities:
Navy -OS, MC

Preparing activity:
Navy - SH
(Project 6145-N300-6)

Source: https://assist.dla.mil -4 Downloaded: 2026-10-18T09:27Z
Check the source to verify that this is the current version before use.

INSTRUCTIONS: In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. If block 7 is filled out, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

NOTE: This form may not be used to request copies of documents, nor to request waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document*(s)* or to amend contractual requirements.

(Fold along this line)

(Fold along this line)

DEPARTMENT OF THE NAVY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12503 WASHINGTON D C

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE NAVY

Commander
Naval Sea Systems Command (SEA 55z3)
DOD Standardization Program and Documents
Division
Department of the Navy
Washington, DC 20362

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T09:27Z
Check the source to verify that this is the current version before use.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

(See Instructions – Reverse Side)

1. DOCUMENT NUMBER	2. DOCUMENT TITLE

3a. NAME OF SUBMITTING ORGANIZATION	4. TYPE OF ORGANIZATION *(Mark one)*
	☐ VENDOR
b. ADDRESS *(Street, City, State, ZIP Code)*	☐ USER
	☐ MANUFACTURER
	☐ OTHER *(Specify)* _____

5. PROBLEM AREAS

a. Paragraph Number and Wording

b. Recommended Wording

c. Reason/Rationale for Recommendation

6. REMARKS

7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional	b. WORK TELEPHONE NUMBER *(Incl Area Code)* – Optional
c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional	8. DATE OF SUBMISSION *(YYMMDD)*

Source: https://assist.dla.mil - Downloaded: 2026-10-18T09:27:28
Check the source to verify that this is the current version before use.