INCH-POUND

MIL-S-50204C (AR)
21 December 1993
SUPERSEDING
MIL-S-50204B (PA)
30 June 1975

MILITARY SPECIFICATION

SUPPORTS, MOLDED, PLASTIC (FOR USE IN AMMUNITION CONTAINERS)

This specification is approved for use by the U.S. Army Armament, Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements, examinations and tests for supports molded from high density polyethylene for use in ammunition containers (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards, and handbooks. The following specifications, standards, and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

SPECIFICATIONS

FEDERAL

L-P-390 - Plastic, Molding and Extrusion Material, Polyethylene and Copolymers (Low, Medium, and High Density)

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document, should be addressed to Commander, U.S. Army ARDEC, ATTN SMCAR-BAC-S, Picatinny Arsenal, New Jersey 07806-5000 by using the Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 8140

DISTRIBUTION STATEMENT A. Approved for public release, distribution is unlimited

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

MILITARY

MIL-P-116 - Preservation, Methods of
MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specification for

STANDARDS

FEDERAL

FED-STD-595 - Colors

MILITARY

MIL-STD-109 - Quality Assurance Terms and Definitions
MIL-STD-129 - Marking for Shipment and Storage
MIL-STD-1167 - Ammunition Data Card
MIL-STD-1168 - Ammunition Lot Numbering
MIL-STD-1169 - Packaging, Packing and Marking for Shipping of Inert Ammunition Components

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from DODSSP - Customer Service, Standardization Documents Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

DRAWINGS (see 6.3)

U.S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER (ARDEC)

9216180 - Support Assembly

(Copies of other Government documents, drawings, and publications required by contractors in connection with specific acquisition functions should be obtained from the contracting activity or as directed by the contracting activity.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

AMERICAN SOCIETY FOR TESTING AND MATERIALS

ASTM-B117	- Salt Spray (Fog) Testing, Method of (DoD adopted)
ASTM-D1238	- Flow Rates of Thermoplastics by Extrusion Plastometer, Test Method for
ASTM-D1505	- Density of Plastics by the Density Gradient Technique, Test for (DoD adopted)
ASTM-D3951	- Commercial Packaging, Practice for (DoD adopted)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.)

2.3 Order of precedence. In the event of a conflict between the text of this document and references cited herein the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained. (See contract provisions for additional precedence criteria.)

3. REQUIREMENTS

3.1 Material. The resin used in the manufacture of the supports shall be colored or natural polyethylene, as specified herein. In addition, the supports shall be manufactured in accordance with the applicable drawings, L-P-390 and other applicable specifications.

3.2 Color. Color of supports, unless otherwise specified, shall approximate color number 14036, 14052, 14056, 14062, 14064, 14077, 16081 or 16099, as specified in FED-STD-595. If the color is specified in the applicable support drawing, then the color shall be as specified in the applicable support drawing.

3.3 Thermal stress cracking resistance. The supports, exposed for 100 hours at 71 degrees Centigrade, shall not crack, split, warp or break when subjected to thermal stress, cracking resistance.

3.4 First article inspection. When specified in the contract or purchase order (see 6.2), a sample shall be subjected to first article inspection in accordance with the technical provisions herein (see 4.3).

3.5 Workmanship. All parts shall be fabricated and finished in a thorough, workmanlike manner. They shall be free of burrs, surface defects, flash, air bubbles, blisters, dirt, twists, and scrap. The cleaning method shall not be injurious to any of the parts, nor shall the parts be contaminated by the cleaning agent.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) as specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in this specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of Sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 General provisions. Unless otherwise specified herein, the provisions of MIL-A-48078 apply and form a part of this specification. Reference shall be made to MIL-STD-109 to define quality assurance terms used herein.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3)

b. Quality conformance inspection (see 4.4)

4.3 First article inspection.

4.3.1 Submission. The contractor shall submit a first article sample as designated by the Contracting Officer for evaluation in accordance with provisions of 4.3.2. The first article sample shall consist of the assemblies and components listed in Table I in the quantities indicated.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

4.3.2 Inspections to be performed. As determined by the Government, the first article assemblies, components and test specimens may be subjected to any or all of the examinations and tests specified in this detail specification (see Table I) and be inspected for compliance with any or all requirements of the applicable drawings, including packaging requirements.

4.3.3 Rejection. If any assembly, component or test specimen fails to comply with any of the applicable requirements, the first article sample shall be rejected. The Government reserves the right to terminate inspection upon any failure of an assembly, component or test specimen to comply with any of the requirements.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
--	Assemblies and Components (see Notes 1 and 2)	1 OF 1	See Below

NEXT HIGHER ASSEMBLY: -1

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
	Support (Assembly, Nose, Tube or Projectile) (Applicable Dwg.)			
	a. Examination for defects	15 (see note 3)	3.1	4.4.2.1
	b. Melt index test	5	3.1	4.5.1
	c. Density test	5	3.1	4.5.2
	d. Thermal stress cracking	20	3.3	4.5.3
	Stop, Packing, Flanged (as applicable) (Dwg. 9216180)			
	a. Examination for defects	15 (see note 4)	3.1	4.4.2.2
	b. Salt spray test	8	3.1	4.5.4
	Packaging, Packing and Marking			
	Examination for defects	5	5	4.4.2.3

NOTES

1. The samples for the molded parts shall be taken after the molds have stabilized.
2. Delay time in dimension examinations-No attempt shall be made to determine compliance with dimension and tolerance requirements of the supports for a minimum period of 48 hours after molded.
3. After the examination for defects is performed, these samples may be included in the samples needed to perform the melt index, density and thermal stress cracking tests.
4. After the examination for defects is performed, samples for the salt spray test may be selected from this sample quantity.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

4.4 Quality conformance inspection.

4.4.1 Inspection lot formation. The term "inspection lot" is defined as a homogeneous collection of units of product from which a representative sample is drawn or which is inspected 100 percent to determine conformance with applicable requirements. Units of product selected for inspection shall represent only the inspection lot from which they are drawn and shall not be construed to represent any prior or subsequent quantities presented for inspection. Homogeneity shall be considered to exist provided the inspection lot has been produced by one manufacturer, in one unchanged process, using the same materials and methods, in accordance with the same drawings, same drawing revisions, same specifications and same specification revisions. All material submitted for inspection in accordance with this specification shall comply with the homogeneity criteria specified herein, regardless of the type of inspection procedure which is being applied to determine conformance with requirements. In addition, lots of molded plastic supports shall contain:

a. Material from not more than one lot from one manufacturer.

b. Material of one color designation.

c. Components from the same manufacturer.

4.4.2 Examinations and tests.

a. Classification of characteristics. Quality conformance examinations and tests are specified in the following Classification of Characteristics paragraphs. The contractor's quality program or detailed inspection system shall provide assurance of compliance of all characteristics with the applicable drawing and specification requirements utilizing, as a minimum, the conformance criteria specified. When cited herein, attributes sampling inspection shall be conducted in accordance with Table II below, using the inspection levels stated in the Classification of Characteristics paragraphs.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

TABLE II. Attributes sampling inspection.

Lot Size	Inspection Levels III	IV	V
2 to 8	*	*	5
9 to 15	*	13	5
16 to 25	*	13	5
26 to 50	32	13	5
51 to 90	32	13	12
91 to 150	32	13	12
151 to 280	32	30	14
281 to 500	32	30	17
501 to 1200	74	35	20
1201 to 3200	74	43	24
3201 to 10000	87	50	30
10001 to 35000	109	61	36
35001 to 15000	124	74	40
150001 to 500000	156	91	40
500001 and over	187	102	40

Numbers under inspection levels indicate sample size; asterisks (*) indicate one hundred percent inspection. If sample size exceeds lot size, perform one hundred percent inspection. Accept on zero and reject on one or more for all inspection levels.

b. Alternative quality conformance provisions. Unless otherwise specified herein or provided for in the contract, alternative quality conformance procedures, methods, or equipment, such as statistical process control, tool control, other types of sampling procedures, etc., may be used by the contractor when they provide, as a minimum, the level of quality assurance required by the provisions specified herein. Prior to applying such alternative procedures, methods, or equipment, the contractor shall describe them in a written proposal submitted to the Government for evaluation (see 6.4). When required, the contractor shall demonstrate that the effectiveness of each proposed alternative is equal to or better than the specified quality conformance provisions herein. In cases of dispute as to whether the contractor's proposed alternative(s) provides equivalent assurance, the provisions of this specification shall apply. All approved alternative provisions shall be specifically incorporated into the contractor's quality program or detailed inspection system, as applicable.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.1	Support (Assembly, Nose, Tube, or Projectile) (see Notes 1 and 2)	1 OF 2	As applicable
			NEXT HIGHER ASSEMBLY

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Melt index test	3, 0-1	3.1	4.5.1
102	Density test	3, 0-1	3.1	4.5.2
103	Thermal stress cracking resistance test	20, 0-1	3.3	4.5.3
104	Large outside diameter (as applicable)	Note 3	3.1	Gage
105	Distance accross the shoulders (as applicable)	Note 3	3.1	Gage
106	Large inside diameter, functional (as applicable)	Note 3	3.1	Gage
107	Profile of nose cavity or fuze well (as applicable)	Note 3	3.1	Gage
108	Small outside diameter (as applicable)	Note 3	3.1	Gage
109	Inside diameter of tube (as applicable)	Note 3	3.1	Gage
110	Total height	Note 3	3.1	Gage
111	Crack, split or hole	Level III	3.1	Visual
112	Sprue above flush (as applicable	Level III	3.1	Visual
113	Depth of nose cavity or fuze well (as applicable)	Note 3	3.1	Gage
114	Wall thickness (as applicable)	Note 3	3.1	Gage
115	Thickness of base (as applicable)	Note 3	3.1	Gage

NOTES

1. The samples shall be taken after the molds have stabilized.
2. Delay time in dimension examination - No attempt shall be made to determine compliance with dimension and tolerance requirements of the supports for a nimimum period of 48 hours after molding.
3. See 4.5.6 for qualification and production control of molded parts.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.1	Support (Assembly, Nose, Tube or Projectile) (see Notes 1 and 2)	2 OF 2	As applicable
			NEXT HIGHER ASSEMBLY

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Minor				
201	Color	5, 0-1	3.2	4.5.5
202	Small inside (as applicable)	Note 3	3.1	Gage
203	Height of tube flange (as applicable)	Note 3	3.1	Gage
204	Depth of slot (as applicable)	Note 3	3.1	Gage
205	Width of slot (as applicable)	Note 3	3.1	Gage
206	Distance between ribs (as applicable)	Note 3	3.1	Gage
207	Location of slots (as applicable)	Note 3	3.1	Gage
208	Evidence of poor workmanship (as applicable)	Note 3	3.1	Gage

NOTES

1. The samples shall be taken after the molds have stabilized.
2. Delay time in dimension examinations - No attempt shall be made to determine compliance with dimension and tolerance requirements of the supports for a minimum period of 48 hours after molding.
3. See 4.5.6 for qualifications and production control of molded parts.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

QUALITY CONFORMANCE INSPECTION

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET	DRAWING NUMBER
4.4.2.2	Stop, Packing, Flanged (as applicable) Prior to assembly	1 OF 1	9216180
			NEXT HIGHER ASSEMBLY

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101	Salt spray test	5, 0-1	3.1	4.5.4
102	Outside diameter	Level III	3.1	Gage
103	Inside diameter	Level III	3.1	Gage
104	Thickness of metal	3, 0-1	3.1	Gage
Minor				
201	Diameter over curls	Level IV	3.1	Gage
202	Total height	Level IV	3.1	Gage
203	Location of hole	Level IV	3.1	Gage
204	Evidence of poor workmanship	Level V	3.5	Visual

NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

CLASSIFICATION OF CHARACTERISTICS

PARAGRAPH	TITLE	SHEET 1 OF 1	DRAWING NUMBER
4.4.2.3	Packaging, packing and marking		Not applicable
			NEXT HIGHER ASSEMBLY

CLASSIFICATION	EXAMINATION OR TEST	CONFORMANCE CRITERIA	REQUIREMENT PARAGRAPH	INSPECTION METHOD REFERENCE
Critical	None defined			
Major				
101.	Marking missing, incorrect or illegible	Level III	5	Visual
102.	Material incorrect or missing	Level III	5	Visual
Minor				
201	Evidence of poor workmanship	Level III	5	Visual

NOTES

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

4.4.3 Inspection equipment. The inspection equipment required to perform the inspections specified herein is identified in the "Inspection Method Reference" column of the Classification of Characteristics listing starting with 4.4.2.1. Contractor inspection equipment designs shall be submitted for Government approval as specified in the contract. Designs which provide variable measurements instead of attributes data are preferred in order to facilitate the use of statistical process control. See MIL-A-48078 and 6.5 herein.

4.5 Methods of inspection. (see 6.6)

4.5.1 Melt index. Determine the melt index of the samples in accordance with ASTM-D1238.

4.5.2 Density. Determine the density of the samples in accordance with ASTM-D1505. Do not anneal or otherwise treat the specimens so as to change the crystallinity (see 6.7).

4.5.3 Thermal stress cracking resistance. Subject the supports to 100 hours at 71 degrees Centigrade, plus or minus one degree Centrigrade. Immediately following the 100 hours time period, visually examine each support while warm for evidence of cracks, splits, warping or other deformations.

4.5.4 Salt spray test. Test the packing stops in accordance with ASTM-B117 (see 6.8). The test shall be conducted using a five (5) percent solution for a duration of ninety six (96) hours.

4.5.5 Color. Examine the specimen, on all sides, using daylight illumination as to determine compliance with the applicable requirement.

4.5.6 Dimensional control of molded plastic parts. To qualify a new or reworked cavity for use in production, a sample of three (3) parts (as molded) from each mold cavity shall be fully inspected dimensionally after a curing time of 48 hours. This is done in place of normal sampling associated with the classification of characteristics. The molded parts shall carry the individual cavity identification. As a control of each cavity during production, the above quantity of parts from each cavity shall be inspected for at least the characteristics listed in 4.4.2.1 as applicable after continuous production of 8 hours. Of the three (3) samples, one (1) sample shall be the last part produced. If any defective parts are found during qualification of the cavity, the cavity producing the defective part will not be used in production. If any defective parts are found when inspection is performed for the control of the cavity, the cavity producing the defective part shall be removed from production. Further, that portion of production since the last control check shall be

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

returned to the contractor for appropriate action, in accordance with the provisions of the contract. All cavities removed from production because of some fault, may, after reworking, be returned to production providing they pass the qualification test above. The contractor may request a change of inspection frequency providing he presents objective evidence to the contracting officer to substantiate the request. Contractor designs of gages and test equipment required to perform the inspections listed herein shall be forwarded to the technical agency specified in contract for approval prior to manufacture of equipment. The noted sub-paragraphs identify those items and minimum inspection subject to the requirements of this paragraph.

4.5.7 Inspection of packaging. The inspection of packaging for shipment and storage shall be in accordance with section 5.

5. PACKAGING

5.1 Preservation. Preservation shall be Level A or C, as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Cleaning. The item shall be cleaned in accordance with process C-1 of MIL-P-116, if required.

5.1.1.2 Drying. The item shall be dried in accordance with MIL-P-116, if required.

5.1.1.3 Preservative application. Not applicable

5.1.1.4 Unit and intermediate packs. Not applicable

5.1.2 Level C. Not applicable

5.2 Packing. Packing shall be Level A, B, or C, as specified (see 6.2). For Levels A, B and C, supports suitably protected from damage or contamination shall be packed in accordance with MIL-STD-1169. Sufficient filler material shall be added to ensure a tight pack and arrival at the destination. Instead of Level C packing, commercial packing in accordance with ASTM D3951 may be used as an acceptable alternate.

5.3 Marking. Marking shall be in accordance with MIL-STD-129 and as follows: Unless otherwise specified, intermdiate (when provided), and exterior packs shall, as a minimum, be marked as follows by any means which provides legibility and durability: Commercial packing shall be in accordance with ASTM-D3951.

a. Seller's name and address

b. Lot no. (per MIL-STD-1168)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

c. Quantity per carton

d. Noun nomenclature

e. Carton ..... of ..... cartons

f. Army drawings and revisions part no.

g. Contract no.

h. Carton/package wt.

5.4 General.

5.4.1 Unitization. Not applicable

5.4.2 Packaging inspection. The inspection of these packaging and unitization requirements shall be in accordance with 4.4.1 and 4.5.7.

5.4.3 Shipping. When supports from more than one lot are shipped at the same time, each lot shall be kept separate and the division between lots clearly indicated to prevent mixing of lots in shipment. Ammunition data cards in accordance with MIL-STD-1167 shall be included.

5.4.4 Reuse of packing material. Reuse of all packing material is permissible and recommended when considered economically feasible by the procuring activity and the material is in reusable condition.

5.4.5 Advance packing technology. Contractors are encouraged to use advanced packing technology and innovative methods of materials for the purpose of effecting packaging economics providing materials meet the required specifications.

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The supports covered by this specification are intended for use in supporting various types of projectiles in ammunition containers.

6.2 Acquisition requirements. Acquisition documents must specify the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

a. Title, number and date of this specification.

b. Issue of DODISS to be cited in the solicitation and, if required, the specific issue of individual documents referenced (see 2.1.1 and 2.2).

c. Requirements for submission of first article sample.

d. Certified material test report (CMTR) for each lot shipment of product.

e. Packaging requirements

6.3 Drawings. Drawings listed in Section 2 of this specification under the heading U.S. Army Armament, Development and Engineering Center (ARDEC) may also include drawings prepared by, and identified as, U.S. Army Armament, Research and Development Command (ARRADCOM), Frankford Arsenal, Rock Island Arsenal or Picatinny Arsenal drawings. Technical data originally prepared by these activities is now under cognizance of ARDEC.

6.4 Submission of alternative quality conformance provisions. All proposed alternative quality conformance provisions will be submitted to the Government for evaluation/approval as directed by the contracting activity.

6.5 Submission of contractor inspection equipment designs for approval. Submit copies of designs, as required, to: Commander, U.S. Army ARDEC, ATTN: SMCAR-QAR-I, Picatinny Arsenal, New Jersey 07806-5000. This address will be specified on the Contract Data Requirements List, DD Form 1423 in the contract.

6.6 Equivalent test methods. Prior approval of the Contracting Officer is required for use of equivalent test methods. A description of the proposed method should be submitted through the Contracting Officer to: Commander, U.S. Army ARDEC, ATTN: SMCAR-QAR-Q, Picatinny Arsenal, New Jersey 07806-5000. This description should include, but not be limited to, the accuracy and precison of the method, test data demonstrating the accuracy and precision and drawings of any special equipment required.

6.7 Density specimen. Saw speed in excess of 500 to 600 linear feet per minute has been found to be unsatisfactory, as excess speed can melt the material and greatly change the density.

6.8 Salt spray testing. Salt spray testing applies only to metal components (e.g., packing steps) utilized in the fabrication of molded supports.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

6.9 Temperature. Temperatures for continuous use or storage of the molded supports should not exceed 176 degrees Fahrenheit.

6.10 Subject term (key word) listing.

Packing
Projectiles
Polyethylene, High Density

6.11 Changes from previous issue. Marginal notations are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 8140-A960)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER: MIL-S-50204C (AR)	2. DOCUMENT DATE (YYMMDD): 931221

3. DOCUMENT TITLE: SUPPORTS, MOLDED, PLASTIC (FOR USE IN AMMUNITION CONTAINERS

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets if needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON

7. PREPARING ACTIVITY

a. NAME	b. TELEPHONE (Include Area Code)
U.S ARMY ARDEC STANDARDIZATION OFFICE	(1) Commercial: 201-724-6675 (2) AUTOVON: DSN-880-6675
c. ADDRESS (Include Zip Code): ATTN. SMCAR-BAC-S PICATINNY ARSENAL, NJ 07806-5000	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

DD Form 1426, OCT 89 — *Previous editions are obsolete.* — 198/290

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:17Z
Check the source to verify that this is the current version before use.