SS-B-750b
NOVEMBER 23, 1960

SUPERSEDING
Int. Fed. Spec. SS–B–00750a (GSA–FSS)
August 15, 1959 and
Fed. Spec. SS–B–750
May 25, 1956

FEDERAL SPECIFICATION

BUILDING BOARD, ASBESTOS-CEMENT, CORRUGATED

This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

1. SCOPE AND CLASSIFICATION

1.1 Scope.—These specifications and methods of test cover corrugated asbestos-cement sheets designed for the following purposes:

(*a*) To provide the weather-exposed surfaces of roofs, walls, and other elements of buildings and structures, and

(*b*) For decorative and other purposes.

1.2 Classification.

1.2.1 *Types.* — Corrugated sheets supplied under these specifications are of the following types as to thickness, weight, and intended use:

1.2.1.1 *Type A (standard).* — Approximately 3/8 inch thick, weighing approximately 3¾ to 4 pounds per square foot, designed as a structural roofing and siding sheet and suitable for use over sheathing or for direct application on girts and purlins. For structural roofing, span between purlins must not exceed 4 feet 6 inches center to center; and for siding span, between girts must not exceed 5 feet 6 inches center to center.

1.2.1.2 *Type B (lightweight).*—Approximately 3/16 inch thick, weighing approximately 1¾ to 2 pounds per square foot, and designed as a roofing and siding sheet for use over sheathing or for direct application on girts and purlins. For roofing span between purlins must not exceed 2 feet 6 inches center to center; and for siding span between girts must not exceed 3 feet 6 inches. Type B sheets must not be substituted for type A sheets where the spans are in excess of the maximum permitted in this paragraph.

2. APPLICABLE SPECIFICATIONS, STANDARDS, AND OTHER PUBLICATIONS

2.1 Specifications and standards.—The following specifications and standards, of the issues in effect on date of invitation for bids, form a part of this specification:

Federal Specifications:

PPP–B–566 — Boxes, Folding, Paperboard.
PPP–B–585—Boxes, Wood, Wirebound.
PPP–B–591—Boxes, Fiberboard, Wood-Cleated.
PPP–B–601—Boxes, Wood, Cleated-Plywood.
PPP–B–621—Boxes, Wood, Nailed and Lock-Corner.
PPP–B–636—Box, Fiberboard.
PPP–T–60 — Tape, Pressure Sensitive Adhesive, Waterproof—For Packaging and Sealing.

Federal Standards:

Fed. Std. 102—Preservation, Packaging, and Packing Levels.
Fed. Std. 123 — Marking for Domestic Shipment (Civilian Agencies).

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

FSC 5640

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications, Standards, and Handbooks and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington 25, D. C.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, Seattle, and Washington, D. C.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications, Standards, and Handbooks from established distribution points in their agencies.)

Military Specifications:

MIL–C–132—Crates, Open, Wood; Maximum Capacity 2500 Pounds.

MIL–C–3774 — Crates, Open, Wood (2500 to 10,000 Pounds).

MIL–L–10547 — Liners, Case, Waterproof.

Military Standards:

MIL–STD–105 — Sampling Procedures and Tables for Inspection by Attributes.

MIL–STD–129—Marking for Shipment and Storage.

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. — The following documents, of the issues in effect on date of invitation for bids, form a part of this specification:

Uniform Freight Classification Rules.

(Copies may be obtained from the Official Classification Committee, 1 Park Avenue at 33rd Street, New York 16, New York.)

National Motor Freight Classification Rules.

(Copies may be obtained from the American Trucking Associations Inc., 1424 16th Street, NW., Washington, D. C.)

3. REQUIREMENTS

3.1 Material.—Corrugated asbestos-cement sheets and supplementary shapes, except for filler strips, shall be composed of a combination of asbestos fiber and portland cement or portland blast-furnace slag cement, and not more than 1 percent by weight of organic fiber, with or without the addition of inert mineral pigments, mineral fillers, coatings, or a curing agent formed under pressure and cured to meet the physical requirements of these specifications.

3.2 Finish.—The exposed surface of the sheet shall be relatively smooth.

3.3 Color.—Color may be natural cement gray, or as agreed between the purchaser and the seller.

3.4 Corrugations.—Asbestos-cement sheets of both types A and B shall have a pitch of 4.2 inches from center to center.

3.5 Dimensions.

3.5.1 *Width.*—Sheets of both types A and B shall be 42 inches wide having 10 complete corrugations.

3.5.2 *Thickness.*—The face-to-face or overall thickness between two planes contacting the crests of corrugations on opposite sides of the sheet, and the thickness of the section of the sheet, across corrugations, shall be as in table I.

3.5.3 *Length.*—Corrugated asbestos-cement sheets of both types A and B shall be furnished in lengths up to and including 12 feet, as specified.

3.5.4 *Tolerance.* — The permissible variation in length and width shall be plus or minus ¼ inch.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

TABLE I.—*Thickness*

Type	Overall thickness (accepted)		Cross section-minimum thickness across corrugations	
	Min.	Max.	Crest & vale	Midway between crest & vale
	Inches	*Inches*	*Inch*	*Inch*
A	1 23/64	1 9/16	11/32	9/32
B	1 3/16	1 25/64	11/64	9/64

3.6 Weight.—The weight may be estimated approximately as follows:

Type A.—3¾ to 4 lb. per sq. ft.

Type B.—1¾ to 2 lb. per sq. ft.

3.7 Water absorption.—The average water absorption of the dried test specimens from the lot being tested shall not exceed 25 percent by weight for both types A and B, when tested in accordance with 4.4.4.2.

3.8 Flexural strength. — The minimum average breaking load of the dried test specimens from the lot being tested shall be as follows, when tested in accordance with 4.4.3.2:

Type A.—500 lb. per ft. of width.

Type B.—200 lb. per ft. of width.

3.9 Fasteners. — Noncorrodible, nonstaining fasteners of suitable size and type for securing corrugated asbestos-cement sheets and supplementary pieces to metal or wood supporting members of all sizes and types should be specified by the purchaser or recommended by the manufacturer of the sheets, and complete information regarding the supporting structure must be supplied by the purchaser. (6.5.5)

3.10 Workmanship.—The surface of the sheet to be exposed shall be free from defects that impair appearance or serviceability. Sheets shall be whole and clean.

4. SAMPLING, INSPECTION, AND TEST PROCEDURES

4.1 Unless otherwise specified herein, the supplier is responsible for the performance of all inspection requirements prior to submission for Government inspection and acceptance. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. Inspection records of the examinations and tests shall be kept complete and available to the Government as specified in the contract or order.

4.2 Sampling. — Sampling for inspection shall be in accordance with Military Standard MIL–STD–105, level L5.

4.3 Examination.—Samples selected in accordance with 4.2 shall be examined for conformance to the requirements of this specification not requiring tests. AQL shall be 2.5 percent defective.

4.4 Tests.

4.4.1 *Preparation of test specimens.* — A test specimen 36 ± ⅛ inch in length and 12.6 ± 1/16 inch in width shall be cut from the interior of each sheet in such a manner that no edge of the specimen shall be less than 4.2 inches from the original edges of the sheet. The length direction shall be parallel to the corrugations of the sheet. Each specimen shall be a complete symmetrical unit with the long edges cut in the bottoms of valleys. Cracked or other damaged specimens shall not be tested, but substitute specimens shall be provided.

4.4.2 *Dimensional measurements.*

4.4.2.1 *Definition of dimensions.*—For the purpose of this specification, dimensions are the length, width on a plane, and thickness of corrugated asbestos-cement sheets as measured under specified conditions. Dimensions are expressed in inches, or feet and inches.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

4.4.2.2 *Thickness measurement.*—Measure the thickness of each specimen at the crest and valley and at the flank (midway between crest and valley) by a micrometer having ball-anvil and ball-spindle ends approximately ⅛ to ¼ inch in diameter, or an anvil and spindle, each with a 30-degree taper and a 1/64-inch flat at their end. Place the anvil or spindle of the ball shaped or the tapered flat end shaped micrometers between the projections on the back of the sheet so as to measure the flat plane surface. The thickness of the crest and valley shall be the average of four measurements two of which are on the crest (one at each end) and two of which are in the valley (one at each end). The thickness at the flank shall be the average of four measurements, two at each end of the test specimen.

4.4.3 *Flexural-strength test.*

4.4.3.1 *Definition of flexural-strength test.*—For the purpose of this specification, flexural strength is the average breaking load, in pounds, of dried test specimens, loaded as simple beams, with the load applied at the center and tested by the procedure prescribed in 4.4.3.2.

4.4.3.2 *Procedure.*—Dry each specimen to constant weight in a ventilated oven at a temperature of 212° to 220°F., and cool to room temperature in a dessicator-type cabinet. Record the dry weight of each cooled specimen. Determine the flexural strength of each specimen by placing the specimen on supports which cannot exert longitudinal constraint (rocker-type bearing edges, rollers, etc., with a ⅛-inch minimum and ½-inch maximum radius) and applying the load at mid-span through a similar edge bearing against finished surface of the specimen. The test span shall be 30 inches ± 1/16 inch and the load line and supports shall be parallel. Increase the load applied at a uniform rate such as will result in failure of the specimen in 1 to 2 minutes. The error in the load reading shall not exceed 1 percent of the maximum load. Take the flexural strength as the average maximum load, in pounds, for all the specimens tested, calculated to a width of one foot (3.8).

4.4.4 *Water absorption test.*

4.4.4.1 *Definition of water absorption test.*—For the purpose of this specification, water absorption is the increase in weight of the test specimen expressed as a percentage of its dry weight, after immersion in water for a specified period of time as prescribed in 4.4.4.2.

4.4.4.2 *Procedure.*—Weigh a broken half of each of the specimens that have been used in the flexural strength test and submerge them for 24 hours ± ½ hour in clean water at 60° to 80°F. Then remove each specimen from the water, wipe with a damp cloth, and weigh separately on a scale accurate to 0.5 percent. Report the water absorption as the average value for all the specimens tested. Calculate the water absorption value for each specimen as follows (3.7):

$$\text{Water absorption, percent by weight} = \frac{\text{saturated weight} - \text{dry weight}}{\text{dry weight}} \times 100$$

4.5 **Rejection.**—If the sample fails to conform to any one of the requirements of this specification, a second sample from the same lot shall be prepared and tested. The results of the retest shall be averaged with the results of the original test to determine compliance with this specification. Failure to conform to any of the requirements of this specification, upon retest as prescribed above, shall constitute grounds for rejection. If more than 2 percent of the units in the lots are broken on delivery, the lot shall be rejected. In case of rejection, the seller shall have the right to reinspect the rejected shipment and resubmit the lot after removal of the portion of the shipment not conforming to the specified requirements, provided this is done within 20 days after receipt of notice of the specific cause for rejection.

4.6 **Inspection of preparation for delivery.**—The packing and marking of the corru-

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

gated sheets, siding and fasteners shall be examined to determine compliance with the requirements of section 5 of this specification. Examination of packing and marking not covered by referenced specifications shall be in accordance with Military Standard MIL–STD–105, AQL shall be 4.0 percent defective.

4.6.1 *Classification of defects.*—(For packing and marking not covered by referenced specifications.)

1. Closure of shipping containers incorrect.
2. Case liner missing when required.
3. Case liner not sealed as specified.
4. Strapping missing.
5. Strapping not specified, type and class incorrectly applied.
6. Gross weight of shipping container exceeds limit specified.
7. Marking missing, illegible or incorrect.

5. PREPARATION FOR DELIVERY

5.1 For civil agency procurement, the levels of preservation, packaging, and packing used are defined in Federal Standard No. 102.

5.2 Packaging.

5.2.1 *Level A.*

5.2.1.1 Corrugated building board and siding shall be packaged according to standard commercial practice.

5.2.1.2 Fasteners shall be packaged 10 pounds to a box conforming to Federal Specification PPP–B–566 (style 1, type A, class a) closed in accordance with the appendix thereto.

5.2.2 *Level C.*—Material shall be packaged according to standard commercial practice.

5.3 Packing.—Packing shall be level A, B, or C as specified (see 6.1).

5.3.1 *Level A.*

5.3.1.1 Corrugated building board and siding shall be uniformly packed in unsheathed crated conforming to Military Specification MIL–C–132, or Military Specification MIL–C–3774. Flat steel strapping shall be type 1, class B.

5.3.1.2 Fasteners packaged as specified in 5.2.1.2 shall be packed 100 pounds to a box conforming to Federal Specifications PPP–B–585, PPP–B–591, PPP–B–601, PPP–B–621, and PPP–B–636. Containers shall be provided with case liners conforming to Military Specification MIL–L–10547 and sealed in accordance with the appendix thereto. Case liners may be omitted for fiber containers conforming to Federal Specification PPP–B–636 provided all seams including manufacturer's joints are sealed with tape conforming to Federal Specification PPP–T–60. The gross weight of wood and wood cleated fiberboard containers shall not exceed 200 pounds. Fiber containers shall not exceed the weight limitations of the box specification.

5.3.2 *Level B.*

5.3.2.1 The corrugated sheets, siding and fasteners shall be packed as specified for level A, except that the boxes shall be domestic type or class as applicable and case liners shall not be required.

5.3.3 *Level C.*

5.3.3.1 The corrugated sheets, siding and fasteners shall be packed to insure carrier acceptance and safe delivery to destination at lowest rates in containers complying with Uniform Freight Classification Rules, National Motor Freight Classification Rules, or with other carrier rules and regulations as applicable to the mode of transportation.

5.4 Marking.

5.4.1 *Civil agencies.*—Marking shall be in accordance with Federal Standard No. 123.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

5.4.2 *Military procurement.* — Marking shall be in accordance with Military Standard MIL–STD–129.

6. NOTES

6.1 **Ordering data.** — Purchasers should exercise any desired options offered herein and should specify the following:

(*a*) Type (see 1.2.1).
(*b*) Length (see 3.5.3).
(*c*) Number of sheets of each length (see 6.2).
(*d*) Kind and amount of supplementary shapes, including the linear footage of corner and ridge rolls and of filler strips if required (see 6.5).
(*e*) Kind and quantity of fasteners and whether for wood or steel framing (see 3.9).
(*f*) Level of packing required (5.1).
(*g*) Whether application will be by the staggered joint or straight joint (sometimes called the cut corner method) method.

6.2 **Commercial quantities.** — Corrugated asbestos-cement roofing and siding is marketed on a basis of the following:

(1) Per sheet depending on length.
(2) Supplementary and finishing pieces, accessories, fasteners and cements may be quoted as "extras".

6.3 Manufacturer's lists should be consulted by purchasers to avoid, where possible, the drafting of requirements that would unduly restrict competition.

6.4 **Efflorescence.** — Efflorescence, that sometimes appears on asbestos-cement sheets, is not a defect and should not result in a permanent change in color.

6.5 The following supplementary shapes, finishing pieces, and accessories are available when specified.

6.5.1 Ridge roll is manufactured in two types as follows:

(*1*) Half-pound sections of asbestos-cement about 7 to 8 inches in diameter by 4 to 12 feet in length, weighing approximately 2½ to 3¾ pounds per lineal foot. Battens are furnished to fit ridge roll.
(*2*) Two-piece adjustable-pitch asbestos-cement of several designs.

6.5.2 Corner angles or corner rolls, outside or inside types, with or without overlapping bell ends, of asbestos-cement. The angle wings of these units are about 6 to 8 inches in length at 90 degrees with about a 2 to 3 inches radius corner, and are 4 to 12 feet in length. Weight is approximately 2¾ to 3½ pounds per lineal foot.

6.5.3 Asbestos-cement louvre blades of both "S" and "corrugated" types and jointing battens.

6.5.4 Filler or closure strips of various types for closing flat surfaces or straight edges to corrugations.

6.5.5 The purchaser should specify fasteners of suitable size and type for securing asbestos-cement sheets and supplementary pieces to metal or wood supporting members of all sizes and types. Complete information regarding the supporting structure must be supplied by the purchaser (see 3.9).

6.6 This specification conforms to ASTM Specification C221–58T.

6.7 It is believed that this specification adequately describes the characteristics necessary to secure the desired material, and that normally no samples will be necessary prior to award to determine compliance with this specification. If, for any particular purpose samples with bids are necessary they should be specifically asked for in the invitation for bids, and the particular purpose to be served by the bid sample should be definitely stated,

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

the specification to apply in all other respects. Samples, if requested, shall be three corrugations (12.6 inches) wide by 12 inches.

6.8 Federal specifications do not include all types, classes, grades, sizes, etc., of the commodities indicated by the titles of the specifications, or which are commercially available, but are intended to cover the types, etc., which are suitable for Federal Government requirements.

6.9 Transportation description.—Transportation description applicable to this item is:

Asbestos Siding
Carload minimum weight 40,000 pounds.
Truckload minimum weight 20,000 pounds.

Notice. — When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded, by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

MILITARY INTERESTS:
Army—E
Navy—Y S
Air Force.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.