TT-L-57C
AMENDMENT-1
June 23, 1977

FEDERAL SPECIFICATION

LACQUER, RUBBING, CLEAR, (FOR WOOD FURNITURE)

This amendment, which forms a part of Federal Specification TT-L-57C, dated October 10, 1972, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 1

Under Federal Specifications: Change "TT-P-143" to "PPP-P-1892".

PAGE 2

Under American Society for Testing and Materials (ASTM) Standards: Add

D 1545 - Test for Viscosity of Transparent Liquids by Bubble Time Method.
D 1644 - Tests for Nonvolatile Content of Varnishes.

PAGE 3

Table I, At end of table add: Under characteristics, "Lead, percent nonvolatile", under minimum "__"; and under maximum "0.06".

Paragraph 4.3 and table II. Delete and substitute:

4.3 The varnish shall be tested as indicated in table II and hereinafter specified.

TABLE II. Index

Characteristics	Requirement Reference	Applicable Tests: Fed. Test Method Std. No. 141	Applicable Tests: ASTM Method	Applicable Tests: Paragraph Reference
Nonvolatile matter	Table I	----	D 1644	--------
Viscosity	Table I	----	D 1545	--------
Dry to rub	Table I	----	------	4.3.5
Benzol	Table I	5091	------	--------
Condition in container	3.2.1	----	------	4.3.1
Storage stability	3.2.2	----	------	4.3.2
Color	3.2.3	----	------	4.3.3
Working properties	3.2.4	----	------	4.3.4
Rubbing properties	3.2.5	----	------	4.3.5
Self-lifting	3.2.6	----	------	4.3.6
Resistance to alcohol	3.2.7.1	----	------	4.3.7.1
Resistance to naphtha	3.2.7.2	----	------	4.3.7.2
Resistance to boiling water	3.2.7.3	----	------	4.3.7.3
Cold check	3.2.7.4	----	------	4.3.7.4
Print resistance	3.2.7.5	----	------	4.3.8
Ultra-voilet light	3.2.7.6	----	------	4.3.9
Adhesion and toughness	3.2.8	----	------	4.3.10
Lead content	Table I	----	------	4.3.11

FSC 8010

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:15Z
Check the source to verify that this is the current version before use.

Add new paragraphs:

4.3.11 Lead content.

4.3.11.1 Sample preparation. Using a 0.006-inch film applicator and a mechanical applicator plate, duplicate drawdowns for each sample of well-mixed paint shall be made on a standard paint penetration chart and dried for 24 hours. The drawdown shall be at least 10 inches long on the sealed portion of the penetration chart. The drawdown shall be cut into discs of appropriate size to fit the sample holder of a fluorescence X-ray spectrometer.

4.3.11.2 Procedure. Lead content shall be determined using an X-ray fluorescence spectrometer capable of determining lead content at a minimum level of 0.03 percent by weight of the total nonvolatile. The settings for a wavelength dispersive fluorescence spectrometer shall be as follows: (1)

Element	Analytical Line	Angle	Crystal	Detection	Collimeter	X-ray tube (MO)
Pb	L	33.93	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Pb (backgrd I)		33.00	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Pb (backgrd II)		35.50	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Mo	K	20.33	LiF(200)	Flow S.C.	Fine	60Kv 45Ma

Pulse height selection shall be used in all measurements, and counting time shall be 100 seconds. Place the sample disc in the wavelength dispersive unit. Measure the count rates of lead, lead background, and the Molybdenum Compton scattered background from the X-ray tube.

4.3.11.3 Calculation.

$$R = \frac{I_{Pb} - \frac{I_{Pb\ (Background\ I)} + I_{Pb\ (Background\ II)}}{2}}{I_{Mo}}$$

where I equals gross intensity. These results shall be compared to those obtained using a 0.06 percent lead standard made up from the same type of paint sample, and evaluated for compliance with table I.

(1) Energy dispersive fluorescence spectrometers shall be set up according to the manufacturer's manual.

Paragraphs 5.1 and 5.1.1, change "TT-P-143" to "PPP-P-1892".

Source: https://assist.dla.mil -- Downloaded: 20260-26T12:15Z
Check the source to verify that this is the current version before use.