TT-P-55b
April 27, 1965
SUPERSEDING
Int. Fed. Spec. TT-P-0055a (Army-CE)
May 21, 1958

FEDERAL SPECIFICATION

# PAINT, POLYVINYL ACETATE EMULSION, EXTERIOR

*This specification was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.*

## 1. SCOPE AND CLASSIFICATION

**1.1 Scope.** This specification covers polyvinyl acetate emulsion paints for application to exterior masonry surfaces.

**1.2 Classification.** Paint shall be of the following types, as specified (see 6.2):

Type I—Polyvinyl acetate homopolymer.
Type II—Polyvinyl acetate copolymer.

## 2. APPLICABLE SPECIFICATIONS AND STANDARDS

**2.1** The following specifications and standards, of the issues in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

*Federal Specifications*:

SS-C-192—Cement, Portland.
SS-S-346—Siding (Shingles, Clapboards, and Sheets) Asbestos-Cement.
TT-D-301—Dibutyl Phthalate: Plasticizer (For Use in Organic Coatings).
TT-P-143—Paints, Varnish, Lacquer and Related Materials; Packaging, Packing, and Marking of.
TT-P-442—Pigment, Titanium Dioxide, (For Protective Coatings).

*Federal Standards*:

Fed. Test Method Std. No. 141—Paint, Varnish, Lacquer, and Related Materials; Methods of Inspection, Sampling, and Testing.
Fed. Std. No. 595—Colors.

(Activities outside the Federal Government may obtain copies of Federal Specifications, Standards, and Handbooks as outlined under General Information in the Index of Federal Specifications and Standards and at the prices indicated in the Index. The Index, which includes cumulative monthly supplements as issued, is for sale on a subscription basis by the Superintendent of Documents, U. S. Government Printing Office, Washington, D. C. 20402.

(Single copies of this specification and other product specifications required by activities outside the Federal Government for bidding purposes are available without charge at the General Services Administration Regional Offices in Boston, New York, Washington, D. C., Atlanta, Chicago, Kansas City, Mo., Dallas, Denver, San Francisco, Los Angeles, and Seattle, Wash.

(Federal Government activities may obtain copies of Federal Specifications, Standards, and Handbooks and the Index of Federal Specifications and Standards from established distribution points in their agencies.)

*Military Specification*:

MIL-M-15176—Mica (Extender Pigment).

(Copies of Military Specifications and Standards required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

## 3. REQUIREMENTS

**3.1 Material.** Material shall be as specified herein. Material not definitely specified shall be selected by the supplier and shall be subject to all the provisions of this specification. The paint shall be free from mate-

U.S. GOVERNMENT PRINTING OFFICE: 1967—703-023/4334



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

rial which will be toxic to personnel under normal conditions of use.

3.2 Composition.

3.2.1 *Vehicle.* For type I, the vehicle shall consist of a water dispersion of polyvinyl acetate resin, together with dibutyl phthalate conforming to TT-D-301, and minimum amounts of additives such as emulsifiers, pigment-dispersants, antifoaming agents, thickeners, coalescing agents, and preservative. For type II, the vehicle shall consist of a water dispersion of vinyl acetate copolymerized with a plasticizing monomer, together with minimum amounts of additives.

3.2.2 *Pigment.* For white paint, the opaque portion of the pigment shall consist of a minimum of 2.5 pounds per gallon of titanium dioxide pigment specified in table I. For tints and medium colors, the opaque portion of the pigment shall consist of titanium dioxide pigment conforming to TT-P-442, type III, grade A, and tinting pigments as required (see 6.4). The extender portion of the pigment shall consist of mica conforming to MIL-M-15176, type I, together with compatible pigments.

TABLE I. *Quantitative requirements of the pigment for white paint*

| Material | Requirement | |
|---|---|---|
| | Minimum | Maximum |
| Anatase titanium dioxide pigment, (TT-P-442, type I), percent by weight of total titanium dioxide pigment. | — | 10 |
| Rutile titanium dioxide pigment, (TT-P-442, type III, grade A), percent by weight of total titanium dioxide pigment. | 90 | — |

3.3 Quantitative requirements. The paint shall conform to the quantitative requirements specified in table II.

TABLE II. *Quantitative requirements of the paint*

| Characteristic | Requirement | |
|---|---|---|
| | Minimum | Maximum |
| Total solids, percent by weight of paint | 50 | — |
| Pigment, percent by weight of paint: | | |
| Type I | — | 30 |
| Type II | — | 32 |
| Mica, pounds per gallon of paint | 0.3 | — |
| Weight per gallon of paint, pounds | 11.0 | — |
| Fineness of grind | 4-1/2 | — |
| Viscosity, Krebs units | 68 | 82 |
| Drying time: | | |
| Set-to-touch, hours | — | 1/4 |
| Dry-through, hours | — | 1 |
| Wet abrasion resistance, oscillations (double strokes): | | |
| Type I | 500 | — |
| Type II | 1000 | — |
| Daylight directional reflectance (0.005-inch wet film thickness), percent, for white paint | 87 | — |
| Dry opacity (0.005-inch wet film thickness), contrast ratio: | | |
| For white paint | 0.98 | — |
| For tints and medium colors | 0.99 | — |

Note: For some tints and medium shades it may be necessary to deviate from the total solids and percentage pigment requirements. Such deviation shall not exceed 4 percent of the allowable figure.

3.4 Qualitative requirements.

3.4.1 *Color.* Paints shall be of the color specified (see 6.2) and shall match the appropriate color chip of Fed. Std. No. 595.

3.4.2 *Condition in container.* The paint shall mix readily with a minimum of foaming to a homogeneous state, free from lumps and coarse particles. In a freshly opened package, there shall be no rusting of the container and no disagreeable odor.



Source: https://assist.dla.mil -- Downloaded: 202610-26T12:14Z
Check the source to verify that this is the current version before use.

3.4.3 *Stability.*

3.4.3.1 *Freeze-thaw stability.* When tested as specified in 4.3.5, the paint shall show no coagulation or flocculation and no decrease in wet abrasion resistance.

3.4.3.2 *Heat stability.* When tested as specified in 4.3.6, the paint shall show no coagulation, flocculation, or discoloration, and shall not exceed the maximum viscosity requirement (see table II).

3.4.3.3 *Storage stability.* After a 30-day storage in a three-quarters filled, closed container, the paint shall show no skinning, livering, curdling, or caking and shall show no settling that cannot be readily remixed to a homogeneous state.

3.4.4 *Application properties.* (See 4.3.7)

3.4.4.1 *Brushing.* The paint shall brush easily and have good flowing, leveling, and spreading characteristics.

3.4.4.2 *Recoating.* When the painted surface is recoated, no film irregularity shall be observed after 1 hour of air drying under standard laboratory, air-drying conditions. There shall be no picking or rolling up of the previous coat.

3.4.5 *Appearance.* The paint shall dry to a uniform, smooth appearance. There shall be no streaking or flashing.

3.4.6 *Accelerated weathering resistance.*

3.4.6.1 *White paint.* When tested as specified in 4.3.8, the paint film shall show no more than very slight chalking and no other film defect. The film shall not darken more than four units as determined from the daylight directional reflectance. The yellowness factor shall be not more than 0.08.

3.4.6.2 *Tints and medium colors.* When tested as specified in 4.3.8, the paint film shall show no chalking and no other film defect. Color change equivalent to a lightness index difference, $\Delta L$, shall not exceed the values shown in table III.

TABLE III. *Permissible color change for tints and medium colors*

| Color number (Fed. Std. No. 595) | Maximum color change (Lightness index difference, $\Delta$ L) |
|---|---|
| 30227 | 2.0 |
| 30252 | 1.0 |
| 30324 | 1.0 |
| 32648 | 1.0 |
| 33613 | 1.0 |
| 33617 | 1.0 |
| 33690 | 1.0 |
| 33711 | 1.5 |
| 33722 | 1.5 |
| 34277 | 1.0 |
| 34424 | 1.0 |
| 34516 | 1.0 |
| 34554 | 2.5 |
| 34672 | 3.0 |
| 35237 | 2.0 |
| 35231 | 1.5 |
| 36307 | 2.5 |
| 36440 | 1.0 |
| 36521 | 1.5 |
| 36595 | 1.5 |

3.4.7 *Fungus resistance.* When tested as specified in 4.3.9, the paint shall show no fungus growth within the area bounded by the guide lines on the test specimen.

## 4. SAMPLING, INSPECTION, AND TEST PROCEDURES

**4.1 Responsibility for inspection.** Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

**4.2 Quality conformance inspection.**

4.2.1 *Sampling.* Sampling shall be in accordance with Fed. Test Method Std. No. 141, methods 1011, 1021, and 1031.1.

4.2.2 *Tests.* Samples selected in accordance with 4.2.1 shall be tested as specified



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

in 4.3. Failure to pass any test shall be cause for rejection of the lot which the sample represents.

**4.3 Test procedure.**

**4.3.1** *Tests in accordance with Fed. Test Method Std. No.* 141. The following tests specified in table IV shall be in accordance with Fed. Test Method Std. No. 141, method as specified. Nonconformance to the applicable requirements shall constitute failure of this test.

TABLE IV. *Tests and methods*

| Test | Test method | Requirements |
|---|---|---|
| Condition in container | 3011 | 3.4.2 |
| Weight per gallon | 4184 | table II |
| Pigment content[1] | 4021 | table II |
| Volatile and nonvolatile content | 4041 | table II |
| Drying time | 4061 | table II |
| Dry opacity | 4121 | table II |
| Storage stability | 4141 and 4142 | 3.4.3.3 |
| Color | 4250 | 3.4.1 |
| Daylight directional reflectance[2] | 6121 | table II |
| Viscosity | 4281 | table II |
| Fineness of grind | 4411 | table II |
| Yellowness and yellowing | 6131 | 3.4.6.1 |
| Wet abrasion resistance[3] | 6142 | table II |
| Color change | 6122 | 3.4.6.2 |
| Analysis of titanium dioxide pigment | 7081 | table I |

[1] Extract twice with water, then twice with acetone, and finally with extraction mixture "C" until the vehicle is completely removed.

[2] Apply the paint to a substrate having a minimum reflectance of 80 percent.

[3] Use the unreduced paint for the draw down. Air dry the paint for 72 hours and test. Run one panel for the minimum number of strokes required. Run one panel for 2,400 strokes or to failure (the point at which the first film rupture is noted) whichever occurs first. Use the same panel for determining washability before and after the freeze-thaw stability test specified in 4.3.5.

**4.3.2** *Vehicle.* Strip a portion of the dried coating, weighing 0.5 gram (g.) or less, from the pan used for the total solids determination and place in the bottom of a large (7-inch) test tube. Heat over a flame, slowly at first, until the entire sample is reduced to ash. Cool, transfer the distillate on the wall of the test tube to a flat salt plate by means of absorbent cotton and identify the type of resin from the infrared absorption spectrum. If necessary, the film thickness of the pyrolyzate sample can be increased by repeated applications. Identification is made by comparison to spectra obtained from the pyrolyzates of known materials. Nonconformance to 3.2.1 shall constitute failure of this test.

**4.3.3** *Titanium dioxide.* Determine the amount of titanium dioxide in the pigment, the pigment content of the paint, and the weight per gallon of the paint as specified in table IV. Calculate the pounds of titanium dioxide per gallon of white paint as follows:

Titanium dioxide in pounds per gallon of white paint = A × B × C

where A = percentage of titanium dioxide in pigment, by weight

B = percentage of pigment in paint, by weight

C = weight of paint in pounds per gallon

Less than 2.5 pounds of titanium dioxide pigment per gallon of paint and an amount of titanium dioxide, by analysis, of less than 93.5 percent of the titanium dioxide pigment required shall constitute failure of this test.

**4.3.4** *Mica.* Weigh out about 0.5 g. of the extracted pigment, and mix well with 0.5 g. ammonium chloride and 3 g. calcium carbonate. Transfer to a platinum crucible, placing about 0.5 g. of calcium carbonate in the bottom of the crucible and a similar amount over the top of the mixture. Heat gently over a low flame for about 15 minutes to volatilize ammonium chloride. Then raise the temperature until the lower three quarters of the crucible is dull red. Hold this temperature for about 1 hour. Cool, take up with about 50 cc. of water, and heat over a water bath adding water to replace that lost by evaporation. Break up any lumps with a small pestle. Decant the clear liquid through a filter paper, and wash four times by decanta-



Source: https://assist.dla.mil -- Downloaded: 202610-26T12:14Z
Check the source to verify that this is the current version before use.

tion. Then transfer the residue to the filter. Wash until silver nitrate shows only a very faint turbidity. To the filtrate, add ammonium hydroxide and ammonium carbonate, and heat to boiling. Filter and digest the precipitate with ammonium hydroxide and ammonium carbonate. Filter and allow the filtrate to collect with the previous filtrate, then evaporate to dryness in a platinum or porcelain dish. Remove ammonium salts by gentle ignition in moving flame. After the residue cools, dissolve it in a little water and add a few drops of ammonia and ammonium oxalate. Let stand overnight. Filter, evaporate to dryness, ignite gently, and allow to cool. Then moisten the residue with hydrochloric acid, evaporate again to dryness, ignite gently, and weigh. (The increase in weight is potassium chloride plus sodium chloride.) Dissolve in water. (Ignite and weigh any insoluble residue, deducting this from the mixed chlorides.) Dilute the solution, and add hydrochloroplatinic acid in amount equal to 0.3 ml. more than would be necessary if all chlorides were present as sodium chloride. Evaporate to a syrupy consistency. Cool and treat with a few ml. of 80 percent ethyl alcohol. Stir and decant through a weighed Gooch crucible. Treat again with 80 percent alcohol and decant. Repeat washings and decantation until the alcohol leaving the Gooch crucible is colorless and the precipitate appears golden yellow. Transfer the precipitate to the Gooch crucible, wash with 80 percent alcohol six times, and dry at plus 130°C. to constant weight as potassium chloroplatinate. Calculate as follows:

$$\frac{\text{Weight of potassium chloroplatinate} \times 0.9376 \times 100}{\text{Weight of sample}} = \text{percent of potassium oxide}$$

Percent of $K_2O \times 8.45$ = percent mica

Mica content in pounds per gallon = $A \times B \times C$

where A = percentage of mica in pigment, by weight

B = percentage of pigment in paint, by weight

C = weight per gallon of paint, lb.

Less than 0.3 pound of mica per gallon of paint shall constitute failure of this test.

4.3.5 *Freeze-thaw stability.* Add 1-3/4 ounces of the paint to a 2-ounce screw-cap container. Close the container, invert, and place in a cold chamber maintained at a temperature of 0°F. Remove the container after 16 hours of conditioning at 0°F., and condition at room temperature for 8 hours. Repeat this procedure four more times. At the completion of five freeze-thaw cycles, mix the paint thoroughly with gentle stirring, and examine for smoothness and uniformity. Perform the wet abrasion test specified in table IV, using the same panels (recleaned) that were used to determine the original wet abrasion resistance. Nonconformance to 3.4.3.1 shall constitute failure of this test.

4.3.6 *Heat stability.* Add 1-3/4 ounces of the paint to a 2-ounce screw-cap container, close the container, seal with tape, and place in an oven maintained at plus 120°F. for 1 week. When the paint is cooled to room temperature, mix the paint thoroughly with gentle stirring and examine for excessive thickening, discoloration, and freedom from lumps and coarse particles. Nonconformance to 3.4.3.2 shall constitute failure of this test.

4.3.7 *Application properties and appearance.* Conduct the test under standard laboratory air-drying conditions. Apply the paint with a 2-inch nylon brush to the unglazed side of an asbestos-cement shingle conforming to SS-S-346 at a rate of approximately 300 square feet per gallon. The total area of the shingle shall be not less than 2 square feet. Rinse the brush with water, and remove the excess water by shaking the brush vigorously. Apply the paint by brushing across the panel using back-and-forth strokes and leveling up the coat with light cross strokes using the tip of the brush. During application, note the working properties of the paint. After 1 hour of air drying, apply the second coat in the same manner as the first coat. During application, examine the paint film for picking and rolling up of the first coat. After 24 hours,



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

examine the dried film for smoothness and uniformity. Nonconformance to 3.4.4.1, 3.4.4.2, and 3.4.5 shall constitute failure of this test.

4.3.8 *Accelerated weathering resistance.* Prepare test panels by applying the paint by brushing at a spreading rate of 300 square feet per gallon to both sides and edges of panels cut to appropriate size from asbestos-cement shingles conforming to SS-S-346, type I. Apply two coats allowing 24 hours drying between coats and 72 hours before testing. Expose test panel (use the painted, unglazed side of the panels as the test surface) for 300 hours to accelerated weathering in accordance with Fed. Test Method Std. No. 141, method 6151. For white paint, determine the daylight directional reflectance before and after 300 hours of accelerated weathering. For tints and medium colors, determine the values of directional reflectance with the amber, green, and blue filters before and after 300 hours of accelerated weathering. After accelerated weathering, examine the panels for chalking and other film defects. Determine the extent of change in reflectance and yellowness for white paint and the color change for tints and medium colors. Compare the results with 3.4.6. In localities where iron staining by the water spray of the accelerated weathering unit occurs, conduct the tests for darkening, yellowing, and color change without the water spray. Nonconformance to the requirements specified in 3.4.6 shall constitute failure of this test.

4.3.9 *Fungus resistance.* The fungus resistance of the paint shall be determined as follows.

4.3.9.1 *Test organism.* The test organism used in this test shall be aspergillus oryzae, ATTC No. 10196 (see 6.5). Cultures of this organism shall be carefully maintained on a potato-dextrose agar medium and promptly renewed if there is evidence of contamination. The stock cultures may be kept for not more than 4 months in a refrigerator at approximately 3° to 10°C. (37.4° to 50°F.). Subcultures incubated at 28° to 30°C. (82.4° to 86°F.) for 10 to 14 days shall be used in preparing the inoculum.

4.3.9.2 *Culture medium.* The culture medium shall have the following composition:

| | | |
|---|---|---|
| $NaNO_3$ | 3.0 | g. |
| $K_2HPO_4$ | 1.0 | g. |
| $MgSO_4 \cdot 7H_2O$ | 0.5 | g. |
| KCl | 0.25 | g. |
| Sucrose | 30.0 | g. |
| Agar | 15.0 | g. |
| Distilled water to make | 1,000 | ml. |

The pH shall be 5.5 to 6.5; if otherwise, adjust to that range with HCl or NaOH. After the above ingredients are mixed, they shall be sterilized by autoclaving for 15 minutes at 15 p.s.i. (121°C.). Under sterile conditions, the medium shall be poured into 10-cm. petri dishes, about 30 ml. per dish, and allowed to harden.

4.3.9.3 *Inoculum.* To a subculture (10 to 14 days old) of the test organism in a ripe fruiting condition, add about 10 ml. of sterile distilled water containing about 0.005 percent of a nontoxic wetting agent. Force the spores into suspension with a sterile camel's hair brush (or other suitable means) and dilute to 100 ml. with sterile distilled water.

4.3.9.4 *Preparation of test specimens.* Apply two brush coats of paint to each side of a sheet of No. 30 Whatman filter paper, or equal, allowing 24 hours drying time between coats; brush the filter paper uniformly in all directions to assure a uniform covering of the paper. After drying, cut the paper into 1-1/4-inch squares, and draw guide lines on one side of the sheet with black waterproof ink 1/8 inch from each edge of the squares. Completely immerse three test specimen squares in slowly running tap water for 24 hours after which they are air dried. The leaching tank shall be large enough to hold an amount of water weighing not less than 50 times the weight of the specimens. The water shall not fall directly on the specimens, and shall flow at a rate of 5 to 10 liters per hour. The pH



Source: https://assist.dla.mil -- Downloaded: 202610-26T12:14Z
Check the source to verify that this is the current version before use.

of the water shall be in the range of 6.0 to 8.0.

4.3.9.5 *Inoculation.* Under aseptic conditions, place leached specimen squares, with guide lines showing, firmly on the center of the solidified agar medium contained in the 10-cm. petri dish. With a sterile pipette or other suitable means, distribute 1.0 to 1.5 ml. of inoculum over the surface of the specimen and surrounding agar medium.

4.3.9.6 *Incubation.* The period of incubation shall be 7 days at a temperature of 28° to 30°C. (82.4° to 86°F.), and 85 to 90 percent relative humidity.

4.3.9.7 *Controls.* Two petri dishes containing only the solidified agar medium specified in 4.3.9.2 shall be inoculated with the test organism to determine the viability of the inoculum. At the end of the incubation period, the controls shall be well covered with the fungus growth.

4.3.9.8 *Results.* When the incubation period is completed, examine the test specimens visually. Evidence of fungus growth within the area bounded by the guide lines on the specimen square shall constitute failure of this test. Growth on the specimen up to but not crossing the guide lines shall be disregarded. There shall be no evidence of the growth of bacteria or other fungus organisms. When contaminating micro-organisms are present, the tests shall be repeated.

4.4 Inspection of preparation for delivery. The packaging, packing, and marking of the containers shall be examined and tested in accordance with TT-P-143.

## 5. PREPARATION FOR DELIVERY

5.1 Packaging, packing, and marking. The paint shall be packaged, packed, and marked in accordance with TT-P-143. The level of packaging shall be level A, B, or C and the level of packing shall be level A, B, or C, as specified (see 6.2). The paint shall be furnished in the size of container specified (see 6.2).

5.1.1 *Additional marking.* In addition to the marking requirements specified in 5.1, each container shall be marked with the following instructions:

"*Surface preparation.* No unusual preparation is required on new work, except cinder block which should be grouted. On previously painted surfaces, all loose, powdery, or flaking material; heavy chalking; and dirt should be removed by sand blasting. If sand blasting cannot be accomplished, as much loose material as possible should be removed by wire brushing and the surface shall be sealed with a surface conditioner such as low-solids, alkali-resistant varnish of good penetrating properties. The surface conditioner must be thoroughly dry before application of the paint. When a fill or grout coat is necessary the following formula should be used:

*Polyvinyl Acetate Fill Coat*

| | |
|---|---|
| White portland cement | 16.5 pounds |
| Aggregate | 33.5 pounds |
| Mixing liquid (polyvinyl acetate) | 0.75 gallon |
| Exterior polyvinyl acetate emulsion paint | 1.0 gallon |
| Potable water | 1.5 gallons maximum |

"The white portland cement shall conform to type I or II of Federal Specification SS-C-192.

"The aggregate shall be washed silica sand with 100 percent passing a No. 20 sieve, 30 percent passing a No. 70 sieve, and 100 percent being retained on a No. 100 sieve.

"The mixing liquid shall be the same polyvinyl acetate resin emulsion used in formulating the exterior polyvinyl acetate emulsion paint and shall consist of 92.6 percent by weight vinyl polymer (55 percent solids), 3.7 percent by weight carbitol acetate, and 3.7 percent by weight potable water.

"The exterior polyvinyl acetate emulsion paint shall conform to Federal Specification TT-P-55.

"The fill coat shall be mixed as follows:



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

"Cement and aggregate shall be dry-mixed so that uniform distribution and intermixing are obtained. One-half gallon of water and the mixing liquid shall be premixed, stirred until uniform, and added gradually to the cement-aggregate mixture with constant stirring until smooth. To avoid excessive foaming and air entrapment, the mixture should not be agitated too vigorously. Add the exterior emulsion paint to the cement-aggregate-mixing liquid-water slurry and stir until uniform. Add additional water to obtain a blend having a thick creamy consistency. Blending mixing liquid or emulsion paint with any other component shall be done with caution. Too rapid agitation will cause air entrapment and foaming. When either of these conditions is present, the blend shall not be applied until it is free of entrapped air foam."

6. NOTES

6.1 **Intended use.** The polyvinyl acetate emulsion paint is intended for application to exterior concrete, stucco, and masonry surfaces which have been properly prepared. White paint is not suitable for use as a tint base.

6.2 **Ordering data.** Purchasers should exercise any desired options offered herein and procurement documents should specify the following:

(*a*) Title, number, and date of this specification.
(*b*) Type required (see 1.2).
(*c*) Color required (see 3.4.1).
(*d*) Level of packaging and packing required (see 5.1).
(*e*) Size of container required (see 5.1).

6.3 **Basis of purchase.** The paint should be purchased by volume, the unit being a gallon of 231 cubic inches at plus 60°F.

6.4 **Suitable tinting pigments.** Suitable tinting pigments include the following: red, brown, and black iron oxides, chromium oxide, phthalocyanine green, phthalocyanine blue, nickel azo yellow, and hansa yellow.

6.5 **Test organism.** The organism used in the fungus test specified in 4.3.7.1 may be obtained from the American Type Culture Collection, 2030 M Street, N.W., Washington 6, D.C.

6.6 **Transportation description.** Transportation descriptions and minimum weights applicable to this commodity are:

*Rail*:

Paints, not otherwise indexed by name, liquid.
Carload minimum weight 36,000 pounds.

*Motor*:

Paints, not otherwise indexed, liquid.
Truckload minimum weight 36,000 pounds, subject to Rule 115, National Motor Freight Classification.

CUSTODIANS:
Army—MO(ERDL)
Navy—YD

*Review activities*:
Army—MO, MR, MD, MU
Navy—YD

*User activities*:
Army—MI, EL, GL
Navy—MC

CIVIL INTEREST:
District of Columbia
Veterans Administration
Commerce

Preparing activity:
Army—MO(ERDL)

Copies of this specification may be purchased for 5 cents each.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

**INSTRUCTIONS:** In a continuing effort to make our standardization documents better, the DoD provides this form for use in submitting comments and suggestions for improvements. All users of military standardization documents are invited to provide suggestions. This form may be detached, folded along the lines indicated, taped along the loose edge *(DO NOT STAPLE)*, and mailed. In block 5, be as specific as possible about particular problem areas such as wording which required interpretation, was too rigid, restrictive, loose, ambiguous, or was incompatible, and give proposed wording changes which would alleviate the problems. Enter in block 6 any remarks not related to a specific paragraph of the document. *If block 7 is filled out*, an acknowledgement will be mailed to you within 30 days to let you know that your comments were received and are being considered.

*NOTE:* This form may not be used to request copies of documents, *nor to request* waivers, deviations, or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced *document(s) or* to amend contractual requirements.

*(Fold along this line)*

*(Fold along this line)*

DEPARTMENT OF THE ARMY

NO POSTAGE NECESSARY IF MAILED IN THE UNITED STATES

*OFFICIAL BUSINESS*
PENALTY FOR PRIVATE USE $300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.
POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

Commander
US Army Mobility Equipment Research & Development
Command
ATTN: DRDME-DS
Fort Belvoir, VA 22060

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.

(TO DETACH THIS FORM, CUT ALONG THIS LINE.)

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

*(See Instructions – Reverse Side)*

| 1. DOCUMENT NUMBER | 2. DOCUMENT TITLE |
|---|---|
| | |

| 3a. NAME OF SUBMITTING ORGANIZATION | 4. TYPE OF ORGANIZATION *(Mark one)* |
|---|---|
| | ☐ VENDOR<br>☐ USER<br>☐ MANUFACTURER<br>☐ OTHER *(Specify)*: |
| b. ADDRESS *(Street, City, State, ZIP Code)* | |

5. PROBLEM AREAS

a. Paragraph Number and Wording:

b. Recommended Wording:

c. Reason/Rationale for Recommendation:

6. REMARKS

| 7a. NAME OF SUBMITTER *(Last, First, MI)* – Optional | b. WORK TELEPHONE NUMBER *(Include Area Code)* – Optional |
|---|---|
| c. MAILING ADDRESS *(Street, City, State, ZIP Code)* – Optional | 8. DATE OF SUBMISSION *(YYMMDD)* |

DD FORM 1426

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T12:14Z
Check the source to verify that this is the current version before use.