FEDERAL SPECIFICATION

PAINT, RUBBER: FOR SWIMMING POOLS AND OTHER CONCRETE AND MASONRY SURFACES

This amendment, which forms a part of Federal Specification TT-P-95C, dated December 8, 1975, was approved by the Commissioner, Federal Supply Service, General Services Administration, for the use of all Federal agencies.

PAGE 2

Under American Society for Testing and Materials (ASTM) Standards: delete

D 3335 - Test for Low Concentrations of Lead in Paint by Atomic Absorption Spectroscopy.

PAGE 3

Table I. Last line - under maximum, change "0.5" to "0.06".

PAGE 4

Table III. Last line, under ASTM method, delete "D 3335 1/" and delete footnote.

PAGE 8

Paragraph 4.4.14. Delete in its entirety and substitute:

4.4.14 Lead content.

4.4.14.1 Sample preparation. Using a 0.006-inch film applicator and a mechanical applicator plate, duplicate drawdowns for each sample of well-mixed paint shall be made on a standard paint penetration chart and dried for 24 hours. The drawdown shall be at least 10 inches long on the sealed portion of the penetration chart. The drawdown shall be cut into discs of appropriate size to fit the sample holder of a fluorescence X-ray spectrometer.

4.4.14.2 Procedure. Lead content shall be determined using an X-ray fluorescence spectrometer capable of determining lead content at a minimum level of 0.03 percent by weight of the total nonvolatile. The settings for a wavelength, dispersive fluorescence spectrometer shall be as follows:(1)

Element	Analytical Line	Angle	Crystal	Detection	Collimeter	X-ray tube (MO)
Pb	L	33.93	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Pb (backgrd I)		33.00	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Pb (backgrd II)		35.50	LiF(200)	Flow S.C.	Fine	60Kv 45Ma
Mo	K	20.33	LiF(200)	Flow S.C.	Fine	60Kv 45Ma

Pulse height selection shall be used in all measurements and counting time shall be 100 seconds. Place the sample disc in the wavelength dispersive unit. Measure the count rates of lead, lead background and the Molybdenum Compton scattered background from the X-ray tube.

(1) Energy dispersive fluorescence spectrometers shall be set up according to the manufacturer's manual.

Source: https://assist.dla.mil -- Downloaded: 20260-26T12:15Z
Check the source to verify that this is the current version before use.

4.4.14.3 Calculation.

$$R = \frac{I_{Pb} - \frac{I_{Pb\ (Background\ I)} + I_{Pb\ (Background\ II)}}{2}}{I_{Mo}}$$

where I equals gross intensity. These results shall be compared with those obtained by a 0.06 percent lead standard made up from the same type of paint sample and evaluated for compliance with table I.

Source: https://assist.dla.mil -- Downloaded: 202610-26T12:15Z
Check the source to verify that this is the current version before use.