MILITARY SPECIFICATION

TAPE, TEXTILE: NYLON, ELASTIC, ONE-INCH

1. SCOPE

*1.1 This specification covers requirements for one type of flat braided nylon elastic tape.

2. APPLICABLE DOCUMENTS

***2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.**

SPECIFICATIONS

MILITARY

MIL-W-43334	**- Webbing And Tape, Textile, Packaging And Packing Of.**

STANDARDS

FEDERAL

FED-STD-191	**- Textile Test Methods.**
FED-STD-601	**- Rubber: Sampling And Testing.**

MILITARY

MIL-STD-105	**- Sampling Procedures And Tables For Inspection By Attributes.**

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

***2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.**

Rules and Regulations Under the Textile Fiber Products Identification Act

(Copies may be obtained from the Federal Trade Commission, Washington, D. C. 20580.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:48Z
Check the source to verify that this is the current version before use.

3. REQUIREMENTS

*3.1 Sample. Samples are furnished solely for guidance and information to the supplier (see 6.3). Variation from this specification may appear in the sample, in which case the specification shall govern.

*3.2 First article. Unless otherwise specified (see 6.2), before production is commenced, a finished tape shall be submitted, or made available, to the contracting officer or his authorized representative for approval. The approval of the first article authorizes the commencement of production, but does not relieve the supplier of responsibility for compliance with all provisions of this specification. The first article shall be manufactured by the supplier at the same facilities to be used for the manufacture of the production item.

*3.3 Materials. The tape shall be made of 200/34 or 210/34 denier nylon yarns and 37-gage extruded natural rounded rubber of a quality and grade to meet the requirements of this specification (see Section 4, Table II for required test).

*3.4 Design and construction. The tape shall be made on a carrier braider and the finished tape shall conform to the requirements specified in Table I when tested as specified in Section 4, Table IV.

Table I. Physical requirements

Characteristic	Requirements
Width-inches	**1** +1/16, −1/32
Weight-ounces per linear yard	**0.5 minimum**
Carriers (total)	**65 minimum**
Ends per carrier	**2 minimum**
Picks per inch	69 ±5
Total ends (rubber core)	**32 minimum**
Weave	**2/2**
Color (unless otherwise specified)	**OG No. 106**
Colorfastness to:	
- wet (dry) cleaning	**Good**
- crocking	**Good**
- light	**Good**
- perspiration	**Good**

***3.4.1 Ultimate elongation and rupture of rubber strands. The tape shall have an ultimate elongation of not more than 130 percent with no evidence of rupture of the rubber strands.**

*3.5 Length of roll. Unless otherwise specified (see 6.2), the webbing shall be furnished in rolls in a continuous length of not less than 36 yards.

***3.6 Identification tickets. Each roll of tape shall have an identification ticket attached to the roll in accordance with MIL-W-43334.**

***3.7 Fiber identification. Each roll of tape shall be labeled, ticketed or invoiced for fiber content in accordance with the Textile Fiber Products Identification Act.**

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:48Z
Check the source to verify that this is the current version before use.

* 3.8 Workmanship. The finished elastic tape shall conform to the quality and grade of product established by this specification. The occurrence of defects shall not exceed the levels set by the applicable acceptable quality levels (AQL).

4. QUALITY ASSURANCE PROVISIONS

*4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure suppliers and services conform to prescribed requirements.

*4.1.1 Certificate of compliance. Where certificates of compliance are submitted, the Government reserves the right to check test such item to determine the validity of the certification.

*4.2 Inspection. Inspection shall be in accordance with the provisions set forth in MIL-STD-105, except where otherwise indicated herein.

*4.2.1 First article inspection. The first article submitted in accordance with 3.2 shall be visually inspected for appearance and color. The first article shall be tested for physical and chemical properties specified in Section 3 in accordance with the methods specified in 4.3.

*4.2.2 Testing of components. Components listed in Table II shall be tested for the characteristics specified herein in accordance with the referenced test methods of FED-STD-191. The sample unit shall be one cone, tube, or spool each. The lot shall be unacceptable if one or more units fail to meet any requirement specified herein. The sample size shall be as follows:

Lot size (yards)	Sample size
800 or less	2
801 up to and including 22,000	3
22,001 and over	5

Table II - Testing of components

Characteristic	Req. para.	Test method
Nylon yarn:		
Material identification	3.3	1/
Denier	3.3	4021
Rubber Yarn:		
Material identification	3.3	1/
Gage	3.3	4.3.2

1/ The supplier shall submit a certificate of compliance for the characteristics listed. The certificate shall be accompanied by actual test, inspection, or other verifiable quality data.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:48Z
Check the source to verify that this is the current version before use.

*4.2.3 Examination of the end item. The tape shall be examined to determine conformance with requirements of this specification. The defects found during the examination of the end item shall be classified in accordance with 4.2.3.1, 4.2.3.2 and 4.2.3.3.

*4.2.3.1 Yard-by-yard examination. The yardage specified in Table III shall be inspected for visual defects as follows. All defects listed shall be counted regardless of their proximity to each other. A continuous defect shall be counted as one defect for each yard or fraction thereof in which it occurs. The sample unit for this examination shall be 1 yard. The AQL for this examination shall be 0.4 major and 1.5 total defects (major and minor combined) per 100 units. The sample size shall be based upon inspection level II of MIL-STD-105. The lot size shall be expressed in units of 1 yard each. The number of rolls from which the sample is to be selected shall be in accordance with Table III. The sample yardage to be examined shall consist of an approximately equal number of yards from each of the rolls selected.

Defects	Classification Major	Minor
Abrasion mark, bruise - resulting in rupture of **individual yarns or plies, distortion in the orientation of threads, dimensional distortion, areas noticeably thinner than adjoining unaffected areas.**	X	
Braiding loose or tight causing distortions; uneven tension resulting in thick and thin places clearly visible.		X
Broken or missing end - two or more.	X	
Broken or missing picks - two or more within a linear inch, regardless of the size of missing portion.	X	
Cut, hole or tear - any cut, hole or tear.	X	
Coarse filling - yarn larger in diameter than in adjoining unaffected area, or resulting in noticeably increased stiffness or thickness of tape.	X	
Crease, edges folded or rolled - tape twisted or **distorted, will not lay flat upon application of manual pressures.**		X
Edges beaded or corded - noticeable **increase in thickness or misformed edges.**		X
Slub or slug, gout - more than twice the thickness **of normal yarn.**		X
Spot, stain, streak - any **spot, stain, streak or dye spot, clearly visible.**		X

Source: https://assist.dla.mil --Downloaded: 2026-10-18T10:48Z
Check the source to verify that this is the current version before use.

Defects	Classification Major	Minor
Wavy or ridgy tape - clearly visible, will not flatten under manual pressure (resulting from uneven tension).	X	
Weak place - any.	X	

Table III - Sample size

Lot Size in yards	Sample size in rolls	Number of defects acceptable
Up to 1,200 1/	3	0
1,201 to 3200	5	0
3,200 to 10,000	8	0
10,001 to 35,000	13	0
35,001 to 150,000	20	1
150,001 and up	32	2

1/ If a lot contains fewer than 3 rolls, each roll shall be examined.

4.2.3.2 Overall examination. Each defect listed below shall be counted no more than once in each roll examined. The sample unit for this examination shall be one roll. The sample size for this examination and the number of defects acceptable shall be as shown in Table III.

Not cleaned throughout.
Objectionable odor.
Off-shade or uneven in color.

*4.2.3.3 Examination of length. The sample unit for this examination shall be one roll. The number of rolls selected as the sample for this examination and the acceptable number shall be in accordance with Table III. The lot size shall be expressed in units of 1 yard each. Each roll in the sample shall be examined for the following defects:

Gross length less than specified minimum length.
Gross length more than 2 yards less than gross length marked on roll.

The lot shall be unacceptable if the total of the actual gross lengths of the rolls examined in the sample is less than the total of the gross lengths marked on the roll.

*4.2.4 Examination of preparation for delivery requirements. An examination shall be made to determine compliance with packaging, packing and marking requirements of Section 5 of this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:48Z
Check the source to verify that this is the current version before use.

*4.3 Testing of the end item. The methods of testing specified in Table IV shall be in accordance with FED-STD-191. When the data in the "results reported as" column are not specified in the table, they shall be as required by the referenced test method. The physical and chemical values specified in Section 3 apply to the average of the determinations made on a sample unit for test purposes as specified in the applicable test methods. The lot shall be unacceptable if one or more units fail to meet any requirement specified herein. The lot size shall be expressed in units of 1 linear yard. The sample unit for testing shall be 3 yards (see 4.2.2 for sample size).

Table IV - Test Methods

Characteristic	Req. para.	Test method	Results reported as
Weight - oz/lin yd	3.4	5040	---
Carriers (total)	3.4	Visual	Pass or fail
Ends per carrier	3.4	Visual	Pass or fail
Picks per inch	3.4	Visual	Pass or fail
Total ends (rubber core)	3.4	Visual	Pass or fail
Weave	3.4	Visual	Pass or fail
Colorfastness to:			
Wet (dry) cleaning	3.4	5622	---
Crocking	3.4	5650	
Light	3.4	5660 1/	
Perspiration	3.4	5680	
Ultimate Elongation and rupture of rubber strands	3.4.1	4.3.1	Pass or Fail

1/ Except that the specimen shall be exposed for 40 standard fading hours.

*4.3.1 Ultimate elongation test. The test for ultimate elongation shall be in accordance with Method 4121 of FED-STD-601. Determination of the rupture of rubber strands shall be made during the test for ultimate elongation.

*4.3.2 Gage of rubber. The gage of rubber shall be determined by counting the actual number of strands, laid side by side, contained in 1 inch. The gage is equivalent to the actual number of the rubber strands contained in 1 inch.

5. PREPARATION FOR DELIVERY

*5.1 Packaging and packing. Packaging and packing shall be the level of shipment specified in the contract or order in accordance with MIL-W-43334 (see 6.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:48Z
Check the source to verify that this is the current version before use.

5.2 Marking. In addition to any special markings required by the contract or order, shipments shall be marked in accordance with MIL-W-43334. The item identification nomenclature to be marked on rolls and shipping containers shall be: Tape, Textile: Nylon, Elastic, One Inch Width, OG-106.

6. NOTES

*6.1 Intended use. The tape is intended for use on Marine Corps body armor vest and body armor lower torso. Specifically, the tape is used for joining lower front and back insert pockets of vest; and for joining front and back parts of lower torso at the crotch.

*6.2 Ordering data. Purchasers should exercise any desired options offered herein, and procurement documents should specify the following:

*6.2.1 Procurement requirements:

(a) Title, number and date of this specification.
(b) Whether first article is required (see 3.2).
(c) Length of roll desired (see 3.5) if other than specified.
(d) Selection of applicable levels of packaging and packing (see 5.1).

*6.2.2 Contract data requirements. Data conforming to Data Item Description R-01, R-02, R-04, T-01, T-02, T-03 and T-04 will usually be required for delivery in connection with this specification. When so required, such data will be specified for delivery on a DD Form 1423 included in the contract.

*6.3 Sample and shade sample. For information regarding the availability of sample tape, and of standard shades specified, address inquiry to the procuring activity issuing the invitation for bids.

*6.4 First article. Examinations, tests and approval shall be as specified by the contracting officer (see 3.2).

*6.5 Marginal notations. The margins of this specification are marked with an asterisk to indicate where changes (additions, modification, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship of the last previous issue.

Preparing activity
Navy - MC
Project No. 8315-N159

Source: https://assist.dla.mil -- Downloaded: 2026-10-18T10:48Z
Check the source to verify that this is the current version before use.