INCH-POUND

MIL-D-50420A (AR)
AMENDMENT 2
9 April 1992
SUPERSEDING
AMENDMENT 1
1 May 1986

MILITARY SPECIFICATION

DETONATOR, STAB, M98 (T83E1)
PARTS FOR, AND LOADING, ASSEMBLING AND PACKING

This Amendment forms a part of Military Specification MIL-D-50420A (MU), dated 31 December 1971, and is approved for use by the US Army Armament Munitions and Chemical Command, and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

Add the following preamble underneath the title: "This Specification is approved for use by the US Army Armament, Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense."

Page 1 and the following pages: Change "MIL-D-50420A (MU)" wherever it appears, to "MIL-D-50420A (AR)".

PAGE 4

4.3.2.4, Assembly (see dwg 9243921): Add the following to the list of Critical defects:

"3. Exposed explosive.....Visual 04013"

PAGE 11

AMSC N/A FSC 1375

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T20:24Z
Check the source to verify that this is the current version before use.

* 4.4.1.1: Delete in its entirety and substitute:

"4.4.1.1 Primer mixture NOL #130 (See 4.3.3.1). - Transfer an accurately weighed portion of approximately one gram of the primer mixture to a tared aluminum weighing dish provided with a teflon cover while both the dish and the are on the balance pan. Place the dish and contents with the cover removed, in an oven maintained at 60 degrees ± 5 degrees C for 2 hours. The cover shall be placed in a desiccator during the drying period. After drying, transfer the dish and contents quickly to a desiccator and cool in room temperature. Replace the plastic cover and weigh. Calculate the loss in weight of the dish, cover and contents to percent moisture in the sample.

4.4.1.1.1 'Moisture content, alternate method (See 4.3.3.1). The procedure is the same as paragraph 4.4.1.1 with the following exception. The sample shall be dried in a vacuum oven at a temperature of 60 ± 5 degrees C and a pressure of 80 ± 10 mm of mercury for 45 minutes."

* 4.4.1.2: Delete in its entirety and substitute:

"4.4.1.2 Determination of moisture content of lead azide (See 4.3.3.1). - A tared dried aluminum dish 2 inches in diameter shall be covered with a sheet of teflon 2 1/2 inches square and sufficiently flat to form a tight cover. An accurately weighed portion of approximately two grams shall be transferred to the moisture dish while both the cover and dish are on the balance pan. The dish and contents shall be transferred to an oven and dried at 95 degrees C plus or minus (±) 5 degrees C for 2 hours. The cover shall be placed in a desiccator during the drying period. After drying, the dish shall be quickly transferred to the desiccator and allowed to cool to room temperature. The teflon cover shall be placed on the dish and the assembly weighed. The loss in weight shall be calculated to percentage of moisture in the lead azide as follows:

$$\text{Percentage of moisture} = \frac{A-B}{A} \times 100$$

Where:
A = the weight of the specimen before drying.
B = the weight of the specimen after drying.

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:24Z
Check the source to verify that this is the current version before use.

4.4.1.2.1 Determination of moisture content of lead azide, alternate method (see 4.3.3.1). - The procedure is the same as paragraph 4.4.1.2 with the following exception. The sample shall be dried in a vacuum oven at a temperature of 95 ± 5 degrees C and a pressure of 80 ± 10 mm of mercury for 45 minutes."

PAGE 18

6.5: Delete in its entirety and substitute:

"6.5 Ammunition Data cards. When required by DD Form 1423 as part of the contract, ammunition data cards shall be prepared for each lot in accordance with Data Item Description DI-MISC-80043".

NOTE: The margins of this amendment are marked with an asterisk or vertical line to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian
Army-AR

Preparing activity:
Army-AR

(Project 1375-A484)

Source: https://assist.dla.mil -- Downloaded: 202610-22T20:24Z
Check the source to verify that this is the current version before use.