A-A-54308
16 September 1991

COMMERCIAL ITEM DESCRIPTION

# BONE PLATE

The General Services Administration has authorized the use of this commercial item description as a replacement for Military Specification MIL-B-36636A, which is cancelled.

This commercial item description covers one-piece, curved bone plates suitable for implantation into the human body for orthopedic repair.

Salient characteristics:

General. The bone plates shall be of the following sizes with the indicated number of holes and lengths:

| Size | No. of holes | Length in inches | (mm) |
|---|---|---|---|
| 1 | 4 | 2.25 | 57.1 |
| 2 | 4 | 2.8 | 71.1 |
| 3 | 6 | 3.3 | 85.1 |
| 4 | 6 | 3.9 | 99.0 |
| 4 | 4 | 3.9 | 99.0 |
| 5 | 6 | 4.7 | 119.3 |
| 6 | 6 | 5.5 | 139.7 |
| 7 | 6 | 6.3 | 160.0 |
| 8 | 8 | 7.1 | 180.3 |
| 9 | 8 | 7.9 | 200.6 |

The bone plates shall possess countersunk holes capable of accepting standard bone screws possessing a cruciate oval head in accordance with ASTM Designation F543.

Material. The bone plates shall be fabricated from cold drawn corrosion-resistant steel, conforming to the composition specified in ASTM Designation F138, Grade 2. Grain size of the raw material shall be five or finer.

Hardness. The bone plates shall have a Rockwell Hardness C scale (HRC) of 30 to 39 when tested in accordance with ASTM Designation E18 or E92 whichever is applicable. Conversion of hardness values shall be in accordance with ASTM Designation E140.

AMSC N/A FSC 6515

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:32Z
Check the source to verify that this is the current version before use.

Style, design and dimensions. The bone plates shall be in accordance with Defense Personnel Support Center (DPSC) Drawing No. 1826 for style, design and dimensions.

Surface preparation. Description of surface characteristics and methods of surface preparation shall be in accordance with ASTM Designation F86.

Finish. The completed bone plate shall have a bright, smooth finish, properly passivated.

Corrosion properties. Bone plates shall show no evidence of corrosion when subjected to the following tests:

Intergranular corrosion. The intergranular corrosion susceptibility tested specified in ASTM Designation F138.

Saline. Bone plates shall be completely immersed into Normal Saline Solution (USP), and while immersed, placed into an oven at a temperature of $37^{0}$ +\- $1^{0}$ C for a period of seven days, removed from the oven and examined for corrosion while still immersed.

Boil. Bone plates shall be scrubbed with soap and water, rinsed thoroughly in distilled water, and dried. After cleaning, the instrument shall be boiled in distilled water in a beaker for 30 minutes, and allowed to remain submerged for an additional 24 hours.

Workmanship. The bone plate shall be free from defect which detract from their appearance or impair their serviceability.

Unit. Each (EA). One bone plate of the size and millimeter specified, constitutes one unit.

QUALITY ASSURANCE PROVISIONS.

Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except otherwise specified in the contract or purchase order, the contractor may use his own or any facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:32Z
Check the source to verify that this is the current version before use.

Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government upon request, at any time, or from time to time, during the performance of the contract and for a period of three years after delivery of the supplies to which such records relate.

Inspection. Inspection, as used herein, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means and chemical properties) of the item.

Tests. Tests shall be conducted to determine compliance with specification requirements. Where feasible, the same sample shall be used for the determination of two or more text characteristics.

Contractor certification. The contractor shall certify that the product offered meets the salient characteristics of this description and conforms to the producers'own drawings, specifications, standards, and quality assurance practices. The Government reserves the right to require proof of such conformance prior to first delivery and thereafter as may be otherwise provided for under the provisions of the contract.

Metric products. Products manufactured to metric dimensions will be considered on an equal basis with those manufactured using inch-pound units, providing they fall within the tolerances specified using conversion tables contained in the lastest revision of Federal Standard No. 376, and all other requirements of this document are met.

If a product is manufactured to metric dimensions and those dimensions exceed the tolerances specified in the inch/pound units, a request should be made to the contracting officer to determine if the products is acceptable.

The contracting officer has the option of accepting or rejecting the product.



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:32Z
Check the source to verify that this is the current version before use.

Regulatory requirements.

Federal Food, Drug, and Cosmetic Act. If the product covered by this document has been determined by the U.S. Food and Drug Administration to be under its jurisdiction , the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of the Federal Food, Drug Cosmetic Act, as amended, and regulations promulgated thereunder. In addition, the offeror/contractor shall comply, and be responsible for compliance by its subcontractors/suppliers, with the requirements of all other applicable Federal State, and local statutes, ordinances, and regulations.

Recovered materials. The offeror/contractor is encouraged to use recovered material in accordance with Federal Acquisition Regulation Subpart 23.4 to the maximum extent practical.

Preservation, packaging, packing, labeling, and marking. Unless otherwise specified, preservation, packaging, and packing shall be to a degree of protection to preclude damage to containers and/or contents thereof under normal shipping conditions, handling, etc., involving shipment from the supply source to the receiving activity, plus reshipment from receiving activity, and shall conform to applicable carrier's rules and regulations. Intermediate and exterior package quantities and labeling and marking shall be as specified in the contract and/or order.

Ordering data (Intermediate/exterior package quantities and labeling and marking must be specified in the contract and/or order).

NOTE: The following National Stock Numbers and their respective sizes and Item Identified are covered by this document:

| NSN | SIZE | ITEM IDENTIFICATION |
|---|---|---|
| 6515-00-355-9005 | 1 | BONE PLATE, 2.25 inches (5.71 cm) |
| 6515-00-355-9010 | 2 | BONE PLATE, 2.8 inches (7.11 cm) |
| 6515-00-355-9015 | 3 | BONE PLATE, 3.35 inches (8.51 cm) |
| 6515-00-355-9020 | 4 | BONE PLATE, 3.9 inches (9.9 cm) |
| 6515-00-355-9025 | 4 | BONE PLATE, 3.9 inches (9.9 cm) |
| 6515-00-355-9030 | 5 | BONE PLATE, 4.7 inches (11.9 cm) |
| 6515-00-355-9035 | 6 | BONE PLATE, 5.5 inches (13.97 cm) |
| 6515-00-355-9040 | 7 | BONE PLATE, 6.3 inches (16.00 cm) |
| 6515-00-355-9045 | 8 | BONE PLATE, 7.1 inches (18.03 cm) |
| 6515-00-355-9050 | 9 | BONE PLATE, 7.9 inches (20.06 cm) |



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:32Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

Custodians:

Army-MD
Navy-MS
Air Force-03

PREPARING ACTIVITY:

DoD-MB

Agent:

DLA-DM

CIVIL AGENCY COORDINATING ACTIVITIES:

VA-OSS
PHS
FDA-MPQAS

PGC 05304

Project No. 6515-4730
Location: AA54308.doc Carson Disk 1



Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:32Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

## INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

| I RECOMMEND A CHANGE: | 1. DOCUMENT NUMBER | 2. DOCUMENT DATE (YYMMDD) |
|---|---|---|
| | A-A-54308 | 16 September 1991 |

3. DOCUMENT TITLE

BONE PLATE

4. NATURE OF CHANGE (*Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.*)

5. REASON FOR RECOMMENDATION

6. SUBMITTER

| a. NAME (Last, First, Middle Initial) | b. ORGANIZATION | |
|---|---|---|
| c. ADDRESS (Include Zip Code) | d. TELEPHONE (Include Area Code)<br>(1) Commercial<br>(2) AUTOVON<br>(If applicable) | 7. DATE SUBMITTED (YYMMDD) |

8. PREPARING ACTIVITY

| a. NAME | b. TELEPHONE (Include Area Code) | |
|---|---|---|
| Defense Personnel Support Center<br>ATTN: DPSC-MSE | (1) Commercial<br>(215) 737-2870 | (2) AUTOVON<br>444-2870 |
| c. ADDRESS (Include Zip Code)<br>2800 South 20th Street<br>Philadelphia, PA 19145 | IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT<br>Defense Quality and Standardization Office<br>5203 Leesburg Pike Suite 1403, Falls Church VA 22041-3466<br>Telephone (703) 756 2340 AUTOVON 289-2340 | |

DD Form 1426, OCT 89 — *Previous editions are obsolete* — 198/290

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T09:32Z
Check the source to verify that this is the current version before use.