MILITARY SPECIFICATION

MIL-I-5458
30 March 1976
SUPERSEDING
MIL-I-5458A
25 October 1960

INSULATION SHEET, ELECTRICAL, PAPER, PRESSBOARD

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the requirements for paper, pressboard, electrical insulation sheet. The insulation is class O insulation with a continuous-operating-temperature limit of 90°C, in accordance with Institute of Electrical and Electronics Engineers (IEEE), electrical-insulation temperature standards (see 6.1). For purposes of this specification, the term "insulation" is used herein when referring to the paper, pressboard, electrical insulation sheet.

1.2 Classification. Insulation shall be of the following grades, and as specified (see 6.2):

Grade B - Moderate dielectric strength.
Grade C - High dielectric strength.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent specified herein:

SPECIFICATIONS

FEDERAL

NN-P-71	-	Pallets, Material Handling, Wood, Double Faced, Stringer Construction.
QQ-S-781	-	Strapping, Steel, Flat and Seals.
UU-P-31	-	Paper; General Specifications and Methods of Testing.
PPP-B-576	-	Boxes, Wood, Cleated, Veneer, Paper Overlaid.
PPP-B-585	-	Boxes, Wood, Wirebound.
PPP-B-591	-	Boxes, Shipping, Fiberboard, Wood-Cleated.
PPP-B-601	-	Boxes, Wood, Cleated-Plywood.
PPP-B-621	-	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-640	-	Boxes, Fiberboard, Corrugated, Triple-Wall.

MILITARY

MIL-P-116	-	Preservation-Packaging, Methods of.
MIL-C-45662	-	Calibration System Requirements.

FSC 5970

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:43Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED-STD-356 - Commercial Packaging of Supplies and Equipment.
FED-STD-406 - Plastics; Methods of Testing.

MILITARY

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 - Marking for Shipment and Storage.
MIL-STD-130 - Identification Marking of U.S. Military Property.
MIL-STD-147 - Palletized Unit Loads for 40" x 48" Pallets.

(Copies of specifications, standards, drawings, and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply:

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

D202 - Sampling and Testing Untreated Paper used for Electrical Insulation.
D1161- Total Chloride Content of Paper and Paper Products.

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103. Technical society and technical association specifications and standards are generally available for reference from libraries. They are also distributed among technical groups and using Federal Agencies.)

3. REQUIREMENTS

3.1 Material. The insulation shall contain no oil- or alcohol-soluble coloring matter which will reduce the insulating qualities of the paper. The insulation shall be substantially free from rubber or other material which is removable by oil or alcohol. The insulation shall be made by the so-called wet process; no pasteboard or similar material shall be used.

3.1.1 Grade B. Grade B insulation shall be made from undyed and unbleached coniferous (kraft) woodpulp.

3.1.2 Grade C. Grade C insulation shall be made up of cotton or linen rag stock. The insulation shall contain not more than 5 percent of jute or 5 percent of ground (mechanical) wood.

3.2 Dimensions.

3.2.1 Thicknesses. Unless otherwise specified (see 6.2), the insulation shall be furnished in the thicknesses and with the tolerances as specified in table I (see 4.6.2.1).

Source: https://assist.dla.mil -- Downloaded: 202610-16T07:43Z
Check the source to verify that this is the current version before use.

TABLE I. Thicknesses and tolerances.

Grade B		Grade C	
Inch		Inch	
0.0070	±0.0006	0.0100	±0.0010
0.0100	±0.0008	0.0150	±0.0015
0.0160	±0.0013	0.0200	±0.0020
0.0200	±0.0016	0.0250	±0.0025
0.0310	±0.0025	0.0300	±0.0030
0.0500	±0.0040	- - - -	
0.0630	±0.0051	- - - -	
0.0930	±0.0075	- - - -	
0.1250	±0.0100	- - - -	
0.1880	±0.0120	- - - -	

3.2.2 Width and length. Unless otherwise specified (see 6.2), the sheets shall be not less than 36 nor more than 60 inches in width, and not less than 36 nor more than 86 inches in length (see 4.6.2.2).

3.3 Bending. When insulation is tested as specified in 4.6.2.3, there shall be no evidence of cracks or creases along the fold or on either face of the insulation.

3.4 Shearing, blanking, and perforating. When insulation is tested as specified in 4.6.2.4, it shall remain flat, and there shall be no cracking or separation along the laminations.

3.5 Molding. When insulation is tested as specified in 4.6.2.5, the fibers on the outside corners of the bend shall not break nor shall there be delamination of plies. After molding, the channels shall retain the shape of the mold without evidence of breaking or spreading.

3.6 Finish. When insulation is tested as specified in 4.6.3.1, it shall have a smooth, glossy finish.

3.7 Property values. When insulation is tested as specified herein, the property values shall be as specified in table II.

TABLE II. Property values.

Property to be tested (see 4.6.1)	Value required			
	Grade B		Grade C	
	Min	Max	Min	Max
Apparent density, grams per cubic centimeter (g/cc)	1.07	---	1.30	1.40
Hydrogen-ion content (pH)	5.5	8.0	5.5	8.0
Conductivity of water extract, mhos per centimeter (mhos/cm) at 25°C:				
Up to 0.030 inch thick, incl	---	2.0×10^{-5}	---	2.0×10^{-5}
0.031 inch thick and over	---	4.0×10^{-5}	---	2.0×10^{-5}
Chlorides, percent	---	0.020	---	0.020
Dielectric strength, short-time test, volts per 0.001 inch:				
Up to 0.031 inch thick, incl	250	---	300	---
0.032 to 0.063 inch thick, incl	225	---	300	---
0.064 to 0.125 inch thick, incl	200	---	---	---
0.126 to 0.250 inch thick, incl	150	---	---	---
Moisture content, percent	---	7.0	---	7.0
Ash content, percent	---	2.0	---	2.0
Fiber-impurities content, percent	---	5.0	---	5.0

Source: https://assist.dla.mil -- Downloaded: 202610-16T07:43Z
Check the source to verify that this is the current version before use.

3.8 Marking. Full-size insulation, as furnished, shall be marked in accordance with MIL-STD-130, with the grade, thickness, and the manufacturer's code symbol. Such marking shall not be obliterated by normal processing, nor shall it affect the physical or electrical properties of the insulation.

3.9 Workmanship. The insulation shall be processed in such a manner as to be uniform in quality, compact, flat, uniformly dense, and free from metallic and carbon particles and other defects that will affect life, serviceability, or appearance.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Test equipment and inspection facilities. Test and measuring equipment and inspection facilities of sufficient accuracy, quality, and quantity to permit performance of the required inspection shall be established and maintained by the supplier. The establishment and maintenance of a calibration system to control the accuracy of the measuring and test equipment shall be in accordance with MIL-C-45662.

4.2 Classification of inspections. The inspections specified herein are classified as follows:

(a) Materials inspection (see 4.3).
(b) Quality conformance inspection (see 4.5).

4.3 Materials inspection. Material inspection shall consist of certification supported by verifying data that the materials used in fabricating the insulation are in accordance with the applicable requirements specified herein (see 3.1, 3.1.1, and 3.1.2).

4.4 Inspection conditions. Unless otherwise specified herein, all inspections shall be made at a temperature of 25° ±5°C, and room ambient relative humidity and pressure.

4.5 Quality conformance inspection.

4.5.1 Inspection of product for delivery. Inspection of product for delivery shall consist of groups A, B, and C inspections.

4.5.2 Inspection lot. An inspection lot shall consist of all insulation of the same grade and thickness, produced from the same batches of materials under essentially the same conditions, and offered for inspection at one time.

4.5.2.1 Group A inspection. Group A inspection shall consist of the examination specified in table III.

4.5.2.1.1 Sampling plan. Statistical sampling and inspection shall be in accordance with MIL-STD-105 for general inspection level II. The acceptable quality level (AQL) shall be as specified in table III. Major and minor defects shall be as defined in MIL-STD-105.

4.5.2.1.2 Rejected lots. If an inspection lot is rejected, the supplier may rework it to correct the defects, or screen out the defective units, and resubmit for reinspection. Resubmitted lots shall be inspected using tightened inspection. Such lots shall be separate from new lots, and shall be clearly identified as reinspected lots.

Source: https://assist.dla.mil -- Downloaded: 20260-16T07:43Z
Check the source to verify that this is the currentversion before use.

TABLE III. Group A inspection.

Examination	Requirement paragraph	Method paragraph	AQL (percent defective)	
			Major	Minor
Visual and mechanical examination - - - - - - - - -	3.2 to 3.5 incl, 3.8, and 3.9	4.6.2 to 4.6.2.5 incl	1.0	4.0

4.5.2.2 Group B inspection. Group B inspection shall consist of the test specified in table IV. Group B inspection shall be made on samples of insulation selected from inspection lots which have passed group A inspection.

TABLE IV. Group B inspection.

Test	Requirement paragraph	Method paragraph
Finish- - -	3.6	4.6.3.1

4.5.2.2.1 Sampling plan. The sampling plan shall be in accordance with MIL-STD-105 for special inspection level S-4. The sample size shall be based on the inspection lot size from which the sample was selected for group A inspection. The AQL shall be 6.5 percent defective.

4.5.2.2.2 Rejected lots. If an inspection lot is rejected, the supplier may rework it to correct the defects, or screen out the defective insulation and resubmit for reinspection. Resubmitted lots shall be inspected using tightened inspection. Such lots shall be separate from new lots, and shall be clearly identified as reinspected lots.

4.5.2.2.3 Disposition of samples of insulation. Unless otherwise specified (see 6.2), samples of insulation from which specimens have been cut and have passed group B inspection, shall be delivered on the contract or order, if the lot is accepted.

4.5.2.3 Periodic inspection. Periodic inspection shall consist of group C inspection. Except where the results of this inspection show noncompliance with the applicable requirements (see 4.5.2.3.1.4), delivery of products which have passed groups A and B inspections shall not be delayed pending the results of the periodic inspection.

4.5.2.3.1 Group C inspection. Group C inspection shall consist of the tests specified in table V, in the order shown. Group C inspection shall be made on samples of insulation selected from inspection lots which have passed groups A and B inspections.

TABLE V. Group C inspection.

Test (see 4.6.1)	Requirement paragraph	Method paragraph
Apparent density - - - - - - - - -

4.5.2.3.1.1 Sampling plan. Sample insulation shall be selected from the first lot, and thereafter, from each month's production of the same grade and thickness, in accordance with table VI.

TABLE VI. Sampling plan for group C inspection.

Total number of sheets produced during month	Sample size	Acceptance number
2 to 15 incl	2	0
16 to 40 incl	3	0
41 to 65 incl	5	1
66 to 110 incl	7	1
111 to 300 incl	10	2
301 to 500 incl	15	3
Over 500	25	5

4.5.2.3.1.2 Failures. If the number of failures exceeds the acceptance number specified in table VI, the sample shall be considered to have failed.

4.5.2.3.1.3 Disposition of samples of insulation. Unless otherwise specified (see 6.2), samples of insulation from which specimens have been cut and have passed group C inspection, shall be delivered on the contract or order, if the lot is accepted.

4.5.2.3.1.4 Noncompliance. If a sample fails to pass group C inspection, the supplier shall take corrective action on the materials or processes, or both, as warranted, and on all units of product which can be corrected and which were manufactured under essentially the same conditions, with essentially the same materials, processes, etc., and which are considered subject to the same failure. Acceptance of the product shall be discontinued until corrective action, acceptable to the Government, has been taken. After the corrective action has been taken, group C inspection shall be repeated on additional samples of insulation (all inspection, or the inspection which the original sample failed, at the option of the Government). Groups A and B inspection may be reinstituted; however, final acceptance shall be withheld until the group C reinspection has shown that the corrective action was successful. In the event of failure after reinspection, information concerning the failure and the corrective action taken shall be furnished to the cognizant inspection activity.

4.5.3 Inspection of preparation for delivery. Except for commercial packaging, the sampling and inspection of the preservation-packaging and interior package marking shall be in accordance with the group A and B quality conformance inspection requirements of MIL-P-116. The sampling and inspection of the packing and marking for shipment and storage shall be in accordance with the quality assurance provisions of the applicable container specification and the marking requirements of MIL-STD-129. The inspection of commercial packaging shall be as specified in the contract or purchase order (see 6.2).

4.6 Methods of examination and test.

4.6.1 Specimens. The number, form, dimensions, preparation, and conditioning, as applicable, of specimens shall be as described in the applicable test method as specified in table VII.

4.6.2 Visual and dimensional examination. The insulation shall be examined to verify that the materials, dimensions, bending, shearing, blanking, perforating, molding, marking, and workmanship are in accordance with the applicable requirements (see 3.2 to 3.5 inclusive, 3.8, and 3.9).

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:43Z
Check the source to verify that this is the current version before use.

4.7.1 Recovered materials. Unless otherwise specified herein, all materials

4.6.2.1 Thickness. Thickness shall be determined in accordance with method 173 of UU-P-31 (see 3.2.1).

4.6.2.2 Width and length. Width and length shall be determined in accordance with any method accurate to within ±1/64 inch (see 3.2.2).

4.6.2.3 Bonding (see 3.3).

4.6.2.3.1 Specimen. The specimen shall be 2 by 2 inches.

4.6.2.3.2 Conditioning. The specimen shall be conditioned in accordance with method 102 of UU-P-31.

4.6.2.3.3 Test procedure. Specimens up to and including 0.015 inch nominal thickness shall be folded in both the machine and cross directions. The initial fold shall be pressed at the middle by running a thumbnail or ruler along the fold. The specimen shall then be folded in the opposite direction along the same line and shall be similarly pressed. Specimens of insulation over 0.015 inch nominal thickness shall be folded only in the machine direction with the directional crease perpendicular to the machine direction. The specimen shall be examined with normal vision (20/20) for cracks or creases.

4.6.2.4 Shearing, blanking, and perforating. Four specimens shall be punched from each sample of insulation, using a punching die such as described in method 5031 of FED-STD-406. The specimens shall be punched in such a pattern as to assure that two specimens are taken perpendicular to the machine direction and two in the direction of the machine grain. The specimens shall be examined with normal vision (20/20) to determine that the edges are clean cut, allowing for only slight chipping or slight drag, neither exceeding one-half the thickness of the insulation. The holes shall be clean cut with no discernible bulging around the circumference. The surface of the specimen shall be unaffected, but allowing for microscopic cracks around the holes and at the edges which do not extend the distance between holes. Cracks that extend between the faces of the insulation shall be cause for rejection. When compared, all four specimens shall present uniform appearance as described above. The specimens shall then be immersed in a mineral-oil bath for $10^{+\frac{1}{2}}_{-0}$ hours at a temperature of 100° to 110°C inclusive, and examined for separation of the laminations (see 3.4).

4.6.2.5 Molding. The insulation shall be tested by molding, using a steam-heated press, into channels 12 inches or more in length by 0.25 inch wide (inside dimension) by 2 inches deep. The molds used shall have square corners, and the insulation shall be saturated with alcohol before being molded. The molded channels shall be immersed in a mineral-oil bath for $10^{+\frac{1}{2}}_{-0}$ hours at a temperature of 100° to 110°C inclusive. The molded channels shall be examined for breaks, spreading, or delamination of the plies (see 3.5).

4.6.3 Test methods. Methods of test shall be as specified in table VII.

TABLE VII. Methods of test.

Test (see 3.6, 3.7, and table II)	FED-STD-406 method No.	Spec UU-P-31 method No.	ASTM publication No.	Modified by paragraph
Finish	---	---	---	4.6.3.1
Apparent density	---	---	D202	---
Hydrogen-ion content (pH)	---	200	---	---
Conductivity of water extract	---	---	D202	---
Chlorides	---	---	D1161	4.6.3.2
Dielectric strength	4031	---	---	4.6.3.3
Moisture content	---	240	---	---
Ash content	---	202	---	---
Fiber-impurities content	---	300	---	---

Source: https://assist.dla.mil -- Downloaded: 202640-16T07:43Z
Check the source to verify that this is the currentversion before use.

4.6.3.1 Finish. Two specimens from each sample of insulation shall be given two coats of a baking, linseed-oil varnish, having a specific gravity of 0.880, applied with varnish rollers. The specimens shall be examined for smoothness and glossiness of finish (see 3.6).

4.6.3.2 Chlorides. The potassium-chromate ($K_2C_rO_4$) reagent shall be a solution of 2.5 grams in 100 milliliters of water.

4.6.3.3 Dielectric strength. The short-time test shall be made after the specimens have been dried for $2^{+\frac{1}{4}}_{-0}$ hours at a temperature of 105° to 110°C inclusive.

5. PREPARATION FOR DELIVERY

5.1 Preservation-packaging. Preservation-packaging shall be level A or C, or as specified (see 6.2).

5.1.1 Level A.

5.1.1.1 Cleaning. Insulation sheets shall be cleaned in accordance with MIL-P-116, process C-1.

5.1.1.2 Drying. Insulation sheets shall be dried in accordance with MIL-P-116.

5.1.1.3 Preservative application. Preservatives shall not be used.

5.1.1.4 Unit packaging. Insulation sheets shall be unit packaged in the quantity per unit package specified (see 6.2) in accordance with method IC of MIL-P-116 insuring compliance with the applicable requirements of that specification. Each unit package quantity shall be wrapped and sealed with waterproof barrier material and tape. Insulation sheets less than 6 feet in length by 4 feet in width shall be packaged flat and interlined with a suitable material to prevent adherence or creasing. Larger sheets may be rolled or folded, as necessary, providing this does not result in deformation of this material. Spools or cores shall be used when this material is rolled. Fold cores or soft fold separators shall be used for insulation sheets that are folded to prevent deformation.

5.1.1.5 Intermediate packaging. Not required.

5.1.2 Level C. Insulation sheets shall be clean, dry and packaged in a manner that will afford adequate protection against corrosion, deterioration and physical damage during shipment from supply source to the first receiving activity. This level may conform to the supplier's commercial practice when such meets the requirements of this level.

5.2 Packing. Packing shall be level A, B, or C, or as specified (see 6.2).

5.2.1 Level A. The packaged insulation sheets shall be packed in containers conforming to PPP-B-640, class 2, style optional; PPP-B-576, class 2, style optional; PPP-B-591, class 2, style optional; PPP-B-601, overseas type, style optional; or PPP-B-621, class 2, style optional. The closure and strapping requirements shall be in accordance with the applicable box specification for the class or type of container used.

5.2.2 Level B. The packaged insulation sheets shall be packed in containers conforming to PPP-B-640, class 1, style optional; PPP-B-576, class 1, style optional; PPP-B-591, class 1, style optional; PPP-B-601, domestic type, style optional; or PPP-B-621, class 1, style optional. The closure and strapping requirements shall be in accordance with the applicable box specification for the class or type of container used.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:43Z
Check the source to verify that this is the current version before use.

5.2.3 Level C. The packaged insulation sheets shall be packed in shipping containers in a manner that will afford adequate protection against damage during direct shipment from the supply source to the first receiving activity. These packs shall conform to the applicable carrier rules and regulations and may be the supplier's commercial practice when such meets the requirements of this level.

5.2.4 Unitized loads. Unitized loads, commensurate with the level of packing specified in the contract or order, shall be used whenever total quantities for shipment to one destination equal 40 cubic feet or more. Quantities less than 40 cubic feet need not be unitized. Unitized loads shall be uniform in size and quantities to the greatest extent practicable.

5.2.4.1 Level A. Insulation sheets, packed as specified in 5.2.1, shall be unitized on pallets in conformance with MIL-STD-147, load type 1, with a fiberboard cap (storage aid 4) positioned over the load.

5.2.4.2 Level B. Insulation sheets, packed as specified in 5.2.2, shall be unitized as specified in 5.2.4.1 except that the fiberboard caps shall be class domestic.

5.2.4.3 Level C. Insulation sheets, packed as specified in 5.2.3, shall be unitized with pallets and caps of the type, size and kind commonly used for this purpose. These unitized loads shall conform to the applicable carrier rules and regulations and may be the supplier's commercial practice when such meets the requirements of this level.

5.3 Marking. In addition to any special marking required by the contract or purchase order (see 6.2), each unit package, intermediate and exterior container shall be marked in accordance with MIL-STD-129.

5.4 General.

5.4.1 Exterior containers. Exterior containers (see 5.2.1, 5.2.2, and 5.2.3) shall be of a minimum tare and cube consistent with the protection required and shall contain equal quantities of identical stock numbered items to the greatest extent practicable.

5.4.2 Packaging inspection. The inspection of these packaging requirements shall be in accordance with 4.5.3.

5.4.3 Army procurements.

5.4.3.1 Level A (maximum military protection) packing. For level A packing; the containers shall conform to PPP-B-601, overseas type; PPP-B-621, class 2, style 4 or PPP-B-585, class 3, style 2 or 3. Closure and strapping shall be in accordance with applicable container specification except that metal strapping shall conform to QQ-S-781, type I, finish A. When the gross weight exceeds 200 pounds or the container length and width is 48 x 24 inches or more and the weight exceeds 100 pounds, 3 x 4 inch skids (laid flat) shall be applied in accordance with the requirements of the container specification. If not described in the container specification, the skids shall be applied in a manner which will adequately support the item and facilitate the use of material handling equipment.

5.4.3.2 Level A unitization. For level A unitization, the fiberboard caps shall be weather resistant and softwood pallets conforming to NN-P-71, type VI, size 2 shall be used. The loads shall be bonded to the pallets by strapping conforming to QQ-S-781, type I, finish A or shrink film (see 5.2.4.1 and 5.2.4.2).

5.4.3.3 Commercial packaging. Commercial packaging (including unit packaging, packing, and marking) shall be in accordance with FED-STD-356.

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:43Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The insulation covered by this specification is intended for use as layer insulation, spaces in coils, and for collars, shields, sleeves, and cells. Grade B is characterized by a hard finish and possesses moderate dielectric strength. Grade C is a dense insulation with a hard finish and possesses a high dielectric strength. (Grade A formerly covered by this specification has been deleted.) The insulation covered by this specification may be used, when combined with liquid dielectric, to form class A (IEEE) insulation with a continuous-operating-temperature limit of 105°C.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number, and date of this specification.
(b) Grade required (see 1.2).
(c) Insulation dimensions (see 3.2).
(d) Disposition of sample sheets of insulation (see 4.5.2.2.3 and 4.5.2.3.1.3).
(e) Inspection of commercial packaging (see 4.5.3).
(f) Levels of preservation-packaging required (see 5.1 and 5.2).
(g) Special marking, if required (see 5.3).

6.3 International standardization agreements. Certain provisions of this specification are the subject of international standardization agreement (ABC-NAVY-STD-17D). When amendment, revision, or cancellation of this specification is proposed which will affect or violate the international agreement concerned, the preparing activity will take appropriate reconciliation action through international standardization channels including departmental standardization offices, if required.

Custodians:
Army - EL
Navy - SH
Air Force - 85

Review activities:
Army - MU, MI
Navy - SH
Air Force -
DSA - ES

User activities:
Army -
Navy -
Air Force -

Preparing activity:
Army - EL

Agent:
DSA - ES

(Project 5970-0481)

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:43Z
Check the source to verify that this is the current version before use.

SPECIFICATION ANALYSIS SHEET

Form Approved
Budget Bureau No. 22-R255

INSTRUCTIONS: This sheet is to be filled out by personnel, either Government or contractor, involved in the use of the specification in procurement of products for ultimate use by the Department of Defense. This sheet is provided for obtaining information on the use of this specification which will insure that suitable products can be procured with a minimum amount of delay and at the least cost. Comments and the return of this form will be appreciated. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments and suggestions submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or serve to amend contractual requirements.

SPECIFICATION MIL-I-5458 INSULATION SHEET, ELECTRICAL, PAPER, PRESSBOARD

ORGANIZATION

CITY AND STATE

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE SPECIFICATION CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY SPECIFICATION REQUIREMENT CONSIDERED TOO RIGID

3. IS THE SPECIFICATION RESTRICTIVE?

☐ YES ☐ NO *(If "yes", in what way?)*

4. REMARKS *(Attach any pertinent data which may be of use in improving this specification. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity)*

SUBMITTED BY *(Printed or typed name and activity - Optional)*

DATE

DD FORM 1 JAN 66 1426

REPLACES EDITION OF 1 OCT 64 WHICH MAY BE USED.

ESC-FM 1068-68

Source: https://assist.dla.mil -- Downloaded: 2026-10-16T07:43Z
Check the source to verify that this is the current version before use.

FOLD

Department of the Army
Headquarters
U.S.Army Electronics Command
Fort Monmouth, New Jersey 07703

POSTAGE AND FEES PAID

OFFICIAL BUSINESS

Commanding General
U.S.Army Electronics Command
ATTN: [redacted] DRSEL-[redacted]D-TS
Fort Monmouth, New Jersey 07703

FOLD

To detach this form, cut along this line

Source: https://assist.dla.mil -- Downloaded: 202610-16T07:43Z
Check the source to verify that this is the current version before use.