MIL-W-36369A
10 December 1975
SUPERSEDING
MIL-W-36369 (DM)
26 January 1965

# MILITARY SPECIFICATION

# WIRE FABRIC

This specification is approved for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 This specification covers wire fabric suitable for use in surgical splints.

## 2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposal, form a part of the specification to the extent specified herein.

SPECIFICATIONS

FEDERAL

| | | |
|---|---|---|
| PPP-B-566 | - | Box, Folding, Paperboard. |
| PPP-B-636 | - | Boxes, Shipping, Fiberboard. |
| PPP-B-676 | - | Boxes, Setup. |

STANDARDS

MILITARY

| | | |
|---|---|---|
| MIL-STD-105 | - | Sampling Procedures and Tables for Inspection by Attributes. |
| MIL-STD-129 | - | Marking for Shipment and Storage. |

(Copies of specifications, standards, drawings, and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)



Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:29Z
Check the source to verify that this is the current version before use.

## 3. REQUIREMENTS

3.1 Material.

3.1.1 Wire. The wire for the wire fabric shall be annealed low-carbon steel wire of 0.0348 inch ± 0.001 inch diameter (Steel Wire Gage 20) before galvanizing. The wire shall be of the best commercial quality, cold-drawn, round, and be free from kinks, splits, laps, seams, scale, segregation, decarburization, or other defects which might impair the serviceability of the finished wire fabric.

* 3.2 Design and construction. The wire shall be woven to form a fabric with a uniform square mesh, four wires to the inch each way. The wire fabric shall be 5-1/4 ± 1/8 inches wide and 36 ± 1/2 inches long. The edges of the long borders shall be made of a double wire to form selvage edges.

3.3 Bending. The wire fabric shall be capable of being easily bent by hand as required for the test of 4.4.1. The fabric shall withstand the test without cracking.

3.4 Finish. The wire fabric shall be heavily galvanized with molten virgin zinc, prime western grade or better, by the hot-dipped process so that all joints of the warp and filler wires are securely locked. The galvanized wire fabric shall be free from drippings, dross, cracks, flakes, sharp points and edges, etc., which may interfere with its function as a splint. Ends of wire cut to form the 36 inch lengths, may be free of galvanizing.

3.5 Workmanship. Workmanship shall be first class throughout. Wire fabric shall be free from defects which detract from its appearance or may impair its serviceability.

## 4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.



Source: https://assist.dla.mil -- Downloaded: 202610-21T08:29Z
Check the source to verify that this is the current version before use.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of quality. Certificates of quality supplied by the manufacturer of the wire may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the National Stock Number (NSN), the item identification, the name of the component, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be conducted in accordance with MIL-STD-105 and as indicated in table I. The unit of product for examination purposes shall be one 36 inch length of wire fabric.

TABLE I. Sampling for examination.

| Type defect | Inspection level | AQL (percent defective) |
|---|---|---|
| Major | II | 1.0 |

* 4.2.2 For tests. Five lengths of wire fabric shall be taken from each lot (batch) and subjected to the required test. The unit of product for test purposes shall be a 5-1/2 inch minimum length of wire fabric. No two samples shall be taken from adjacent locations in the production run of fabric. Acceptance number shall be zero.



Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:29Z
Check the source to verify that this is the current version before use.

4.3 Examination.

4.3.1 Wire fabric. Examination of the wire fabric shall be conducted as specified in table II. Examination, however, shall not be restricted to defects listed in table II.

TABLE II. Classification of defects.

| Classification | Defect |
|---|---|
| Major | |
| 101 | Wire not correct diameter. |
| 102 | Wire fabric not correct size. |
| 103 | Mesh openings non-uniform. |
| 104 | Wire not galvanized. |
| 105 | Wire cross-joints not securely locked. |
| 106 | Wire not free from kinks, splits, laps, seams and scale. |
| 107 | Wire fabric not free from drippings, dross, cracks, flakes, sharp points, and edges. |

4.3.2 Examination of preparation for delivery. An examination shall be made to determine whether the packaging, packing, and marking comply with the requirements of Section 5. Defects shall be scored as specified in table III. Sampling shall be in accordance with MIL-STD-105. The sample unit shall be one container fully prepared for delivery. The lot shall be the number of containers offered for inspection at one time. The inspection level shall be S-2 and the acceptable quality level shall be 4.0 defects per hundred units.

TABLE III. Examination of preparation for delivery.

| Examination | Defect |
|---|---|
| Containers | |
| Quantity | Not as specified. |
| | Quantity in interior packages and shipping containers not as specified. |
| Packaging & packing materials | Any component missing or damaged. |
| Workmanship | Inadequate application of components, such as incomplete closure of container flaps, tape improperly applied, or containers distorted. |
| Markings | Omitted, incorrect, illegible, improper location, sequence, or method of application. |



Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:29Z
Check the source to verify that this is the current version before use.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Bend test. The sample length of wire fabric shall be bent, parallel with the long dimension, through 180° around a 1/2 ± 1/16 inch diameter mandrel and then flattened to full size. This procedure shall be repeated a second time. In like manner, the fabric shall be twice bent flattened perpendicular to the long dimension. The fabric shall be inspected for compliance with 3.3. Failure of any sample during this test shall be cause for rejection of the lot.

5. PACKAGING

5.1 Preservation - packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Unit of issue. One roll of wire fabric, as specified, constitutes one unit of issue.

5.1.2 Level A.

5.1.2.1 Unit package. Each piece of wire fabric 5-1/4 by 36 inches shall be formed into a roll of an appropriate size and the roll secured by tieing. The roll shall be further packaged in an snug fitting box constructed in accordance with PPP-B-566 or PPP-B-676. Closure of the box shall be adequate to prevent accidental opening.

5.1.2.2 Intermediate package. Six units shall be packaged in a snug fitting box constructed in accordance with PPP-B-566, PPP-B-676 or PPP-B-636, class domestic. Closure of the box shall be adequate to prevent accidental opening.

5.1.3 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose within the continental limits of the United States of America.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A. Ninety-six units shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-636, class weather-resistant. Closure and strapping shall be as specified in the appendix of the box specification. Waterproofing shall conform to paragraph 30.4.2 of PPP-B-636.



Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:29Z
Check the source to verify that this is the current version before use.

5.2.2 Level B. Ninety-six units shall be packed in an exterior container designed for a type 2 load and constructed in accordance with PPP-B-636, class domestic. Closure shall conform to method I or II as specified in PPP-B-636.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. Contract or purchase order number and name of contractor shall be shown.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129.

6. NOTES

6.1 Intended use. The wire fabric covered by this specification is intended for use in surgical splints.

6.2 Ordering data. Procurement documents should specify the following:

a. Title, number, and date of this specification.
b. National Stock Number (NSN)
c. Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

6.3 This specification is intended to cover the following item appearing in the Federal Supply Catalog.

| National Stock Number | Item Identification |
|---|---|
| 5335-00-373-2800 | WIRE, FABRIC, 5-1/4 x 36 INCHES |



Source: https://assist.dla.mil -- Downloaded: 202610-21T08:29Z
Check the source to verify that this is the current version before use.

6.4 Marginal notations. The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 5335-0131
cs



Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:29Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:29Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE
MIL-W-36369A WIRE FABRIC (FOR SURGICAL USE)

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

**DD FORM 1 JAN 72 1426** REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

☆ GPO 1974—603-680/6126 2-1

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:29Z
Check the source to verify that this is the current version before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 South 20th Street
Philadelphia, PA. 19101

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD • 304

U.S. MAIL

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T08:29Z
Check the source to verify that this is the current version before use.