MILITARY SPECIFICATION

DRAIN, SURGICAL, RUBBER, WHISTLE TIP, RIGHT ANGLE, 13 INCHES LONG, 3 1/2 INCH LEG

This specification is mandatory for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 This specification covers right angle rubber surgical drains with whistle tips and one eye.

1.2 Classification. The surgical drains shall be of the following sizes:

40 Fr
45 Fr

2. APPLICABLE DOCUMENTS

2.1 Specifications and standards. The following documents of the issue in effect on date of invitation for bids or request for proposals, form a part of this specification to the extent specified herein:

SPECIFICATIONS

Federal

PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-585	Box, Wood, Wirebound.
PPP-B-601	Box, Wood, Cleated-plywood.
PPP-B-621	Box, Wood, Nailed and Lock-corner.
PPP-B-636	Box, Fiberboard.
PPP-B-676	Box, Set-up.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

Military

MIL-L-10547 Liners, Case and Sheet, Overwrap; Water-Vaporproof or Waterproof.

STANDARDS

Federal

FED-STD-601 Rubber, Sampling and Testing.

Military

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes.
MIL-STD-129 Marking for Shipment and Storage.

DRAWING

Defense Personnel Support Center

No. 23272 DRAIN SURGICAL, ANGULATED WHISTLE TIP, 40 Fr.

(Copies of specifications, standards, and drawing required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply:

AMERICAN SOCIETY FOR TESTING AND MATERIALS

D412 Tension Testing of Vulcanized Rubber.

(Applications for copies should be addressed to American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pa. 19103).

3. REQUIREMENTS

3.1 Material. Shall be made of highest grade natural rubber latex and be free from coloring matter or fillers. Shall be suitable in all respects for the purpose intended.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

3.2 Style, design and construction. Shall be molded or dip formed in one piece to have one long leg of approximately 13 inches in length and one short leg at a right angle to the long leg and approximately 3-1/2 inches in length. There shall be a whistle tip having approximately a 45° angle. The eye shall be approximately 3/8 inch x 1/4 inch. Shall be in accordance with DPSC Drawing No. 23272.

3.2.1 Additional dimensions.

French size	Nominal ID
40	0.313 inch
45	0.344 inch

3.2.2 Physical requirements. The physical properties shall be as shown below when tested in accordance with 4.4.1:

Tensile strength	4,500 psi
Ultimate elongation	750%

3.3 Sterilization. When tested as specified in 4.4.2, the surgical drains shall show no signs of deterioration.

3.4 Resistance to aging. The tensile strength and ultimate elongation of the surgical drains shall not decrease by more than 25% of the values before aging, nor shall be rubber latex become tacky or brittle when tested as described in 4.4.3.

3.5 Animal implantation. The surgical drains shall meet the requirements of the animal implantation test as described in 4.4.4.

3.6 Certificates of animal implantation tests. A certificate listing all lot or control numbers shall state that representative samples from each lot or control have been tested and have passed the animal implantation test. This certificate shall include the specific tests performed and the tests results. The record of the animal implantation test and its results shall be certified by the pathologist who performed or supervised performance of the animal implantation test. For destination inspection, certificates shall be submitted by the contractor directly to Defense Personnel Support Center, Directorate of Medical Materiel, Technical Operations Division, 2800 South 20th Street, Philadelphia, Pa. 19101, attention: Quality Assurance Branch, and one copy of each shall be forwarded with each shipment to the consignee. For source inspection, certificates shall be furnished to the procuring activity via the Government inspector.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

3.7 Marking. Shall be permanently and legibly marked with name or trademark of manufacturer, date of manufacture, angle leg size, and French size.

3.8 Workmanship. Workmanship shall be first class throughout. The surgical drains shall be free from defects which detract from their appearance or may impair their serviceability.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.2 Sampling.

4.2.1 For examination. Sampling for examination shall be in accordance with MIL-STD-105 and as indicated in Table I.

Table I. Sampling for Examination

Type of defect	Inspection level	AQL (percent defective)*
Major	S-2	1.5
Minor	S-1	1.5

* If acceptance number is not exceeded, lot shall be accepted. If rejection number is equaled or exceeded, inspection at Level I shall be performed to determine final acceptance or rejection.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

4.2.2 For tests. Sampling for tests shall be in accordance with MIL-STD-105 and as shown in Table II.

Table II. Sampling for Tests

Characteristic	Requirement	Test procedure	Inspection level	AQL (percent defective)
Tensile strength	3.2.2	4.4.1	S-1	2.5
Ultimate elongation	3.2.2	4.4.1	S-1	2.5
Sterilization	3.3	4.4.2	S-1	2.5
Aging	3.4	4.4.3	S-1	1.5
Animal implantation	3.5	4.4.4	S-1	*

* Acceptance number shall be zero for all sample sizes.

4.2.3 Test samples. Where feasible, the same sample shall be used for the determination of two or more test characteristics.

4.3 Examination. The surgical drains shall be examined to determine compliance with all the requirements contained in the specification. Examination shall be conducted as specified in Tables I and III. Examination, however, shall not be restricted to the defects listed in Table III. Any surgical drain in the sample, containing one or more defects shall be rejected, and if the number of defective surgical drains in any sample exceeds the acceptance number for that sample, the lot represented by that sample shall be rejected (see 4.2.1).

Table III. Classification of Defects

Categories	Defects
Major	
101	Roughness at whistle tip and eye.
102	Surface of drain not smooth.
103	Presence of foreign material.
104	Tackiness.
Minor	
201	Presence of bubbles in rubber.
202	Eye not symmetrically located.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

4.4 Tests. Tests shall be conducted to determine compliance with specification requirements.

4.4.1 Physical properties. Testing for tensile strength and ultimate elongation shall be in accordance with ASTM Method D 412.

4.4.2 Sterilization. The surgical drains shall be steam autoclaved for 20 minutes at 250° Fahrenheit (F) and 15 pounds per square inch gage (psig). They shall be removed and examined after having cooled to room temperature.

4.4.3 Resistance to aging. The accelerated aging test shall be performed in accordance with Method 7221, Air Heat Test, Air Heating Medium of Federal Test Method Standard No. 601.

4.4.4 Animal implantation test. Samples of the surgical drains shall be tested in accordance with the U.S.P. for Implantation Test, Plastic Containers, for class VI plastic, except after "72 hours" add "and not to exceed 144 hours"; and delete "Examine macroscopically the area of the tissue surrounding the center portion of each implant strip. Use a magnifying lens if necessary," and substitute: "The muscle tissue surrounding the implants shall be examined, both grossly and microscopically, by a pathologist certified by the American Board of Pathology or the American College of Veterinary Pathologists."

5. PREPARATION FOR DELIVERY

5.1 Packaging. Packaging shall be level A or C as specified (see 6.2).

5.1.1 Unit of issue. One surgical drain, as specified, constitutes one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in Table IV shall be packaged in each unit, intermediate, and exterior container, as applicable, for the required level of protection specified in the procurement document.

Table IV. Packaging Quantities

Unit package	Intermediate package	Exterior container
1 unit	12 units	288 units

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

5.1.2.1 Packing variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units may be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

5.1.3 Level A.

5.1.3.1 Unit package. Unit package shall be packaged in a clear polyethylene bag of appropriate size. Closure shall be adequate to prevent spilling of contents under normal handling.

5.1.3.2 Intermediate package. Intermediate package shall be a box of appropriate size constructed in accordance with PPP-B-566 or PPP-B-676 except that commercial colors are acceptable. Closure shall be adequate to prevent spilling of contents under normal handling.

5.1.4 Level C. Units shall be packaged in standard commercial containers of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing. Packing shall be level A, B or C as specified (see 6.2).

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, grade V3c. Fiberboard boxes shall conform to the special requirements specified in PPP-B-636.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes.

5.2.1.3 Closure. Closure of wood boxes shall be in accordance with appendix of applicable box specification. Closure of each fiberboard box shall be as specified in the appendix, and waterproofing shall conform with 30.4 of PPP-B-636.

5.2.1.4 Strapping. Strapping, when required, shall be in accordance with appendix of applicable box specification.

NOTE: Strapping shall not be required for shipments forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure of wood boxes shall be as specified in the appendix of the applicable box specification. Closure of fiberboard boxes shall conform to method II of PPP-B-636. Fiberboard boxes shall conform to the special requirements specified in PPP-B-636.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Interior packages. Each unit package and each intermediate package shall be marked in accordance with MIL-STD-129. When labels are utilized, waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Contract or purchase order number and name of contractor shall be shown. As an alternate, marking of unit packages may be accomplished by use of a label inserted in the bag in such a manner as to permit ready identification. Date of manufacture shall be shown in lieu of date packed.

5.3.2 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129. Date of manufacture shall be shown in lieu of date packed.

6. NOTES

6.1 Intended use . The drains are intended for use in surgical procedures.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Selection of applicable levels of packaging and packing (see 5.1 and 5.2).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

6.3 This specification is applicable to the following Federal Supply Catalog items:

Federal Stock Number	Item Identification
6515-131-6985	DRAIN, SURGICAL, Rubber, Whistle Tip, Right Angle, 40 Fr.
6515-131-6991	DRAIN, SURGICAL, Rubber, Whistle Tip, Right Angle, 45 Fr.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 6515-1641

Review activities:
Army - MD
Navy - MS
Air Force - 03

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 South 20th Street
Philadelphia, Pa. 19101

Defense Supply Agency

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY

DOD-304

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/ vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

MIL-D-36847

NAME OF ORGANIZATION AND ADDRESS	CONTRACT NUMBER
	MATERIAL PROCURED UNDER A ☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?
   A. GIVE PARAGRAPH NUMBER AND WORDING.

   B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

   ☐ YES. ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*	TELEPHONE NO.
	DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:27Z
Check the source to verify that this is the current version before use.