MILITARY SPECIFICATION

PAD, NONADHERENT

This interim amendment is issued for use by the Defense Personnel Support Center, with Military Specification MIL-P-36861 dated 10 July 1972.

Page 2

3.1.1 Absorbent filler. Delete entirely and substitute:

"3.1.1 Absorbent filler. The absorbent filler shall be nontoxic and shall be composed of absorbent cotton, absorbent rayon or absorbent cellulose or a combination thereof. The weight per square yard shall be 75 grams minimum. The absorbency rate of the filler shall not exceed 15 seconds and the filler shall not disintegrate nor fray after standing in water for 24 hours. The thickness shall be 30 mils minimum."

Page 3

3.1.2 Film. Delete entirely and substitute:

"3.1.2 Cover. The cover shall be a foraminous plastic film having a minimum thickness of 0.2 mils or a foraminous nonwoven fabric having a weight not less than 0.85 ounces per square yard. The cover shall be smooth, inert, nontoxic, insoluble in the wound and shall not adhere to the wound. The cover shall have a minimum open area of 15 percent with openings closely spaced and uniformly distributed and the cover shall allow wound exudates to pass readily through the cover without puddling to be absorbed by the absorbent filler."

3.1.3 In line 2, delete "25 pounds" and substitute: "22 pounds", and, in line 4, delete "18 points" and substitute "15 points".

3.1.4 Envelope. Delete the last three sentences and substitute:

"The maximum overall dimensions of the envelope shall be 4-1/8 by 3 inches for size I and 5-3/8 by 4-5/16 inches for size II. Envelopes shall be sealed with an adhesive in such a way as to maintain sterility until envelopes are manually opened. Once opened, the envelopes shall

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

not be capable of being resealed. Envelopes shall have "pull-apart" tabs on one edge allowing the two sheets of paper to separate upon opening or shall have a rip seal. The envelope shall meet the requirements of the Federal Food, Drug and Cosmetic Act and shall be of such compatibility that neither the contents nor the container are altered in any way by each other."

3.2 Construction. With the exception of table I delete this paragraph and substitute:

"3.2 Construction. The absorbent filler shall be completely enclosed by the cover except that two opposite edges may be cut. The cover shall be attached to the absorbent filler in such a way as to prevent the filler from sliding out of its cover during use. The finished pads shall be capable of absorbing a minimum 4.7 grams of water for Size I and a minimum 8.0 grams of water for Size II. The seam joining the cover to itself shall run the full length of the pad and shall not have a loose edge. The finished pads shall be of the dimensions and weights shown in table I."

In table I, after "thickness (mils)" add "minimum".

Page 5

4.1.3 Certificates of quality. Line 2, delete "non-woven fabric, film" and substitute: "absorbent filler, cover".

Page 6

4.3.1 Classification of defects. In table III, Major 102, delete "non-woven" and substitute: "absorbent filler".

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:28Z
Check the source to verify that this is the currentversion before use.

Page 7

4.5.1 Components and Pads. Delete entirely and substitute:

"4.5.1 Components and pads. Pad components and completed pads shall be tested and examined as specified in table IV. Acceptance number shall be zero for all sample sizes.

TABLE IV. Component or completed pad.

Component (or pad)	Characteristic	Requirement	Test procedure	Inspection level
Paper	Basis Weight	3.1.3	4.5.2.1	S-2
	Tensile strength	3.1.3	4.5.2.2	S-2
	Bursting strength	3.1.3	4.5.2.3	S-2
Absorbent filler	Weight per square yard	3.1.1	4.5.2.4	S-2
	Thickness	3.1.1	4.5.2.5	S-2
	Absorbency rate	3.1.1	4.5.2.6	S-2
	Disintegration	3.1.1	4.5.2.17	S-2
Cover	Thickness	3.1.2	4.5.2.7	S-2
	Weight	3.1.2	4.5.2.18	S-2
	Open area	3.1.2	4.5.2.8	S-1
Completed Pad	Dimensions	3.2	1/	S-2
	Thickness	3.2	4.5.2.12	S-2
	Weight	3.2	4.5.2.13	S-2
	Adhesion of cover to absorbent filler	3.2	4.5.2.14	S-2
	Sterility	3.3	4.5.2.15	S-4
	Absorbent capacity	3.2	4.5.2.16	S-1

1/ Use ruler graduated in at least 1/16 inch."

Page 8

4.5.2.4 Weight per square yard, non-woven fabric. Delete title and substitute: "Weight per square yard, absorbent filler."

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

4.5.2.6 Absorbency. Delete title and substitute: "Absorbency rate."

4.5.2.7 Thickness of the plastic film. Delete the title and substitute: "thickness of the cover." Delete the last sentence and substitute: "Not less than 10 determinations shall be made on the cover material. The thickness may be measured on the material in its foraminous form."

4.5.2.8 Perforation of the Plastic film. Delete entirely and substitute:

"4.5.2.8 Open area of cover. The open area shall be determined by means of an optical comparitor or other suitable means."

4.5.2.9 Melting point, plastic film. Delete entirely.

4.5.2.10 Tensile strength, plastic film. Delete entirely.

4.5.2.11 Solubility of plastic film material. Delete entirely.

Page 9

4.5.2.14 Adhesion area, nonwoven material. Delete title and substitute: "Adhesion area, absorbent filler."

Add the following:

"4.5.2.16 Absorbent capacity. Weigh each of 5 dry pads, then immerse the pads in distilled water for 20 seconds. Pick the pads up by one corner with tweezers and allow to drain for 20 seconds. Reweigh the pads. The difference in weight is the amount of water absorbed. The test result is the average of the individual results of the 5 pads.

"4.5.2.17 Disintegration. Immerse the absorbent filler in distilled water for 24 hours, remove and examine for signs of deterioration and fraying.

"4.5.2.18 Weight per square yard of cover. The weight of the nonwoven fabric cover shall be determined by method 5041 of FED-TEST METHOD STD-191."

Page 11

5.1.3.1 Unit package. In line 4, following "acceptable.", insert: "The box may be fabricated of .018 inch board." Delete the last sentence and substitute: "Closure shall be as specified in the appendix of the applicable box specification."

Source: https://assist.dla.mil -- Downloaded: 202640-21T09:28Z
Check the source to verify that this is the currentversion before use.

5.1.3.2 Intermediate package. Delete the last sentence and substitute: "Closure shall be as specified in the box specification."

Page 12

5.2.2.1 Exterior container. Delete the 2nd and 3rd sentences and substitute: "Closure shall be as specified in the appendix of the applicable box specification."

5.3.1 Immediate container. Delete and substitute:

"5.3.1 Immediate container. In addition to any commercial markings, each immediate container shall be marked in accordance with the requirements of the Federal Food, Drug and Cosmetic Act. In addition, marking shall include the item identification, manufacturer's name and address, sterility lot or control number and the legend or similar statement 'STERILITY GUARANTEED UNLESS PACKAGE IS DAMAGED OR OPENED'."

5.3.4 Exterior container. At end of the paragraph add: "The method of sterilization as specified in 5.3.2 shall be shown."

Page 13

Add the following:

6.5 This specification covers the following items listed in the Federal Supply Catalog:

NSN	Item Identification	Size 1
6510-00-018-6184	PAD, NONADHERENT, 2 by 3 inches, 100's	I
6510-00-111-0708	PAD, NONADHERENT, 3 by 4 inches, 100's	II

Custodians:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
DLA - DM

Project No. 6510-0642

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.