MILITARY SPECIFICATION

PAD, NONADHERENT

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers the following sizes of sterile, nonadherent, absorbent, surgical dressing pads, suitable for use as a dry dressing for wounds:

1.2 Classification. The pads shall be of the following sizes, as specified (see 6.2):

Size I - 2 by 3 inches.

Size II - 3 by 4 inches.

2. APPLICABLE DOCUMENTS

2.1 The following documents of the issue in effect on date of invitation for bids or request for proposals, form a part of the specification to the extent specified herein:

SPECIFICATIONS

Federal

UU-P-31	Paper, General Specifications and Methods of Testing.
MMM-A-250	Adhesive, Water-Resistant (For Sealing Fiberboard Boxes).
PPP-B-566	Boxes, Folding, Paperboard.
PPP-B-585	Boxes, Wood, Wirebound.
PPP-B-601	Boxes, Wood, Cleated-Plywood.
PPP-B-621	Boxes, Wood, Nailed and Lock-Corner.
PPP-B-636	Box, Fiberboard.
PPP-B-676	Box, Setup.
PPP-T-76	Tape, Pressure-sensitive Adhesive Paper, Water-Resistant, (For Carton Sealing).

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

Military

MIL-S-36586 Sterilization Test Strip Set, Bacterial Spore.

STANDARDS

Federal

FED-TEST-METHOD STD NO. 191 Textile Test Methods.

FED-TEST-METHOD STD NO. 406 Plastic, Methods of Testing.

Military

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes.

MIL-STD-129 Marking for Shipment and Storage.

(Copies of specifications and standards required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer).

2.2 Other publications. The following document forms a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposals shall apply.

UNITED STATES PHARMACOPEIAL CONVENTION, INC.

(Pharmacopeia of the United States)

(Application for copies should be addressed to the Mack Publishing Company, Easton, Pennsylvania).

3. REQUIREMENTS

3.1 Material.

3.1.1 Absorbent filler. Absorbent filler shall be a non-woven fabric. Fabric shall be made of cotton and rayon fiber; or the fiber shall be all cotton or all rayon. The weight per square yard shall be 75 grams minimum. The thickness shall be 30 mils minimum. Absorbency shall be 15 seconds maximum.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

3.1.2 Film. The non-adherent transparent plastic film shall be ethylene-glycol terephthalate, having minimum thickness of 0.2 mils. One pound of the plastic film shall contain an average of 61 square yards. Film shall be perforated. Perforations shall be 325 to 335 perforations per square inch. Diameter of holes shall be 0.025 ± 0.005 inches. Film shall have a melting point of 480°F. minimum and a tensile strength of 15,000 pounds per square inch, prior to perforation. Film shall be soluble in methyl salicylate, when tested according to 4.5.2.11

3.1.3 The paper for packaging the individual pads shall have a basis weight of 25 pounds per ream, minimum (500 sheets 24 inches by 36 inches). The tensile strength (minimum average) shall be 13 pounds in the machine direction. The bursting strength, Mullen, shall be a minimum of 18 points.

3.1.4 Envelope. Envelope for pad shall be made of two rectangular sheets of paper, in accordance with 3.1.3. The sheets of paper shall be joined to each other by a seal, which completely surrounds the pad and maintains the sterility of the contents. Overall dimensions shall be 3-13/16 inches by 2-11/16 inches for the Size I and 4-5/16 inches by 6-1/16 inches for the Size II. One narrow end of the envelope shall have "pull-apart" tabs. The Size I envelope shall be sealed with a gum adhesive and the Size II envelope shall be sealed with adhesive giving an effective rip seal, and not capable of being resealed.

3.2 Construction. The components shall be assembled so that the absorbent filler (3.1.1) is enclosed by the plastic film (3.1.2). Prior to assembly, the plastic film shall be fabricated into short "sleeves" by means of lamination and cutting. The inner surface of the film shall be adhered to at least 75% of the area of the pad. Finished pads shall be open along the long edges. Finished pads shall be of the dimensions and weights as indicated in Table I, below.

Table I. Dimensions and Weight

Characteristic	Size I	Size II
Dimensions, overall		
Length (in.)	3 ± 1/8	4 ± 1/8
Width (in.)	2 ± 1/8	3 ± 1/8
Thickness (mils)	30.4	30.4
Weight (gms) (minimum)	0.45	0.85

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:28Z
Check the source to verify that this is the currentversion before use.

3.2.1 Immediate container. Each pad shall be sealed in an envelope as described in 3.1.4.

3.3 Sterility. The nonadherent pads shall be sterile when tested with a biological indicator as specified in 4.5.2.15. Each pad shall be sterilized by means other than steam.

3.3.1 Certificate of sterility. A certificate of sterility, stating that samples from each sterilizer lot have been tested and found to be sterile, shall be submitted to the procuring activity. The certificate of sterility shall include:

a. Item identification.
b. Federal stock number.
c. Contract or purchase order number.
d. Sterility lot or control number.
e. Date of sterilization.
f. Quantity of product in sterilizer lot.
g. Type of sterilization (gas, radiation, dry heat, etc.).
h. Form of biological indicator (i.e., inoculated paper spore strip or carrier, inoculated product, or inoculated simulated product).
i. Test organism(s) and population density used.
j. Test medium, incubation temperature, incubation time, and dates of tests.
k. Number of test units.
l. Statement that samples comply with sterility tests.
m. Signature of head of laboratory or a designated qualified alternate.

When inspection is made at destination, the certificate of sterility shall be submitted by the contractor to the Directorate of Medical Materiel, ATTN: DPSC-ATQ, Defense Personnel Support Center, 2800 South 20th Street, Philadelphia, Pa., 19101, and a copy forwarded with each shipment to the consignee. When inspection is made at source, certificate of sterility shall be furnished to the cognizant Government Quality Assurance Representative for submission to the procuring activity.

3.3.2 Sterility lot. A sterility lot is that single quantity of product subjected to the same manufacturing operation and simultaneously sterilized in the same sterilizer chamber. Each unit package shall be clearly marked with a sterility lot (control) number and date of sterilization as specified in 5.3.2. Each sterility lot shall be traceable to the pertinent manufacturing lot(s).

3.4 Workmanship. Workmanship shall be first class throughout. The finished pads shall be clean, well made, and free from defects which detract from their appearance or may impair their serviceability.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract or order, the supplier may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.1.1 Records. Records of examinations and tests performed by or for the contractor shall be maintained by the contractor and made available to the Government, upon the Government's request, at any time, or from time to time, during the performance of the contract and for a period of 3 years after delivery of the supplies to which such records relate.

4.1.2 Inspection. Inspection, as used in this specification, is defined as both examination (such as visual or auditory investigation without the use of special laboratory appliances or procedures) and testing (determination by technical means of physical and chemical properties) of the item.

4.1.3 Certificates of Quality. Certificates of quality, supplied by the manufacturer of the non-woven fabric, film, and paper, may be furnished in lieu of actual performance of such testing by the contractor, provided lot identity has been maintained and can be demonstrated to the Government. The Certificate shall include the name of the contractor, the contract number, the name of the manufacturer or supplier, the FSN, the Item Identification, the name of the component/material, the lot number, the lot size, the sample size, the date of testing, the test method, individual test results, and the specification requirements.

4.2 Quality conformance inspection. The examinations and tests required to assure conformance of those items or lots of items to be offered for acceptance are classified as specified in Tables II and III (see 4.3 and 4.3.1) and table IV (see 4.5.1).

4.2.1 Sampling for examination. Sampling for examination shall be conducted in accordance with MIL-STD-105. The inspection levels and acceptable quality levels shall be as indicated in table II. Unit of product for examination purposes shall be 1 pad.

Source: https://assist.dla.mil -- Downloaded: 202610-21T09:28Z
Check the source to verify that this is the currentversion before use.

4.2.2 Sampling for tests. Sampling for tests shall be conducted in accordance with MIL-STD-105, except that the acceptance number shall be zero for all sample sizes. Unit of product for test purpose shall be 1 pad.

4.3 Examination. The pads shall be examined for defects including, but not limited to, those listed in table III.

Table II. Sampling for examination

	Inspection level	AQL (Percent defective)
For visual examination		
Major defects	S-3	1.0
Minor defects	S-3	4.0

4.3.1 Classification of defects. Examination shall be conducted in accordance with the classification of defects specified in Table III. Examination shall not be restricted to the classified possible defects listed.

Table III. Categories and Defects

Categories	Defects
Major	
101	Number or size of nonadherent pad is incorrect.
102	Non-woven material of pad poorly made, i.e., not uniform in thickness, dirty.
103	Holes or non-sealed area in envelopes.
Minor	
201	Finished pad not cleanly cut and free of folds or wrinkles.
202	Finished pad not free of dirt, spots, stains, foreign matter or debris.
203	Marking on unit package incomplete, incorrect, or difficult to read.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

4.4 Examination. The pads shall be examined to determine compliance with all requirements contained in this specification.

4.5 Tests. Tests shall be conducted to determine compliance with specification requirements. Where possible, the same sample unit shall be used for the determination of two or more tests.

4.5.1 Components and Pads. Pad components and completed pads shall be tested and examined as specified in table IV.

Table IV. Component or Complete Pad

Component (of pad)	Characteristic	Requirement	Test procedure	Inspection level	AQL
Paper	Basis Weight	3.1.3	4.5.2.1	S-2	(2)
	Tensile strength	3.1.3	4.5.2.2	S-2	(2)
	Bursting strength	3.1.3	4.5.2.3	S-2	(2)
Non-woven fabric	Weight per square yard	3.1.1	4.5.2.4	S-2	(2)
	Thickness	3.1.1	4.5.2.5	S-2	(2)
	Absorbency	3.1.1	4.5.2.6	S-2	(2)
Film	Thickness	3.1.2	4.5.2.7	S-2	(2)
	Perforations per square inch	3.1.2	4.5.2.8		
	Diameter of Perforations	3.1.2	4.5.2.8		
	Melting Point	3.1.2	4.5.2.9	S-2	(2)
	Tensile strength	3.1.2	4.5.2.10	S-2	(2)
	Solubility	3.1.2	4.5.2.11	S-2	(2)
Completed Pad	Dimensions	3.2	(1)	S-2	(2)
	Thickness	3.2	4.5.2.12	S-2	(2)
	Weight	3.2	4.5.2.13	S-2	(2)
	Adhesion area non-woven material	3.2	4.5.2.14	S-2	(2)
	Sterility	3.3	4.5.2.15	S-4	(2)

(1) Use ruler graduated in at least 1/16 inch.
(2) Acceptance number shall be zero for all sample sizes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

4.5.2 Test methods. The following tests shall be conducted in accordance with the method designated.

4.5.2.1 Paper basis weight. Basis weight shall be determined in accordance with Method No. 110 of Fed. Spec. UU-P-31.

4.5.2.2 Tensile strength of paper, machine direction. Tensile strength of paper, machine direction, shall be determined in accordance with Method No. 171 of Fed. Spec. UU-P-31.

4.5.2.3 Bursting strength of paper. Bursting strength of paper shall be determined in accordance with Method No. 112 of Fed. Spec. UU-P-31.

4.5.2.4 Weight per square yard, non-woven fabric. Weight per square yard shall be determined in accordance with Method 5041 of Fed. Test Method Standard No. 191. Result shall be reported in grams per square yard.

4.5.2.5 Thickness, non-woven fabric. Thickness of the non-woven fabric shall be determined in accordance with Method 5030 of Fed. Test Method Std. No. 191.

4.5.2.6 Absorbency. Absorbency of the non-woven fabric shall be determined in accordance with U.S.P. for cotton.

4.5.2.7 Thickness of the plastic film. The thickness of the plastic film shall be determined by using a micrometer or other suitable thickness gage, reading to at least 0.0001 inch or less. The pressure exerted by the gage on the specimen shall be between 23 and 27 pounds per square inch. The thickness shall be read to an accuracy of 0.0001 inch or less. Not less than 10 determinations shall be made on each lot of unperforated film used in the manufacture of the pads.

4.5.2.8 Perforation of the Plastic film. Film shall be examined by means of a microscope for compliance with number of perforations per square inch, and the diameter of holes.

4.5.2.9 Melting point, plastic film. The melting point of the plastic film shall be determined by means of the Fisher Johns Melting Point Apparatus.

4.5.2.10 Tensile strength, plastic film. Tensile strength of the plastic film shall be determined in accordance with Method 1013 of Fed. Test Method Std. No. 406, for isotropic materials.

4.5.2.11 Solubility of plastic film material. A one inch square of plastic film material, when boiled with 20 cc of methyl salicylate, shall dissolve completely.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

4.5.2.12 Thickness, completed pad. Thickness of the completed pad shall be determined in accordance with Method 5030 of Fed. Test Method Std. No. 191.

4.5.2.13 Weight, completed pad. Weight of completed pads shall be determined by means of a gram scale, accurate to at least 1/100 of a gram.

4.5.2.14 Adhesion area, non-woven material. The pads shall be slit through one thickness of plastic, at right angles to the open ends, opened up, and examined for adhered area of non-woven material to the plastic.

4.5.2.15 Sterility test. The nonadherent pads shall be tested for sterility in accordance with the method specified in the USP for Purified cotton, gauze, surgical dressings and related material using inoculated product, inoculated simulated product, or paper spore strip (carrier). Product containing a biological indicator shall be marked or labeled so that it clearly differentiates from product intended for distribution. The incubation medium and minimum time in each case shall be soybean casein digest for 7 days for inoculated product, inoculated simulated product, or paper spore strip (carrier). The incubation temperature shall be as indicated in paragraph 4.5.2.15.1. The minimum number of test units, regardless of lot size, shall be 10, except for inoculated carrier which shall be 20 for Type I Sterilization and 30 for Type II Sterilization including inoculated carrier and product test units. The inspection level shall be as indicated in Table IV, Sampling Criteria for Tests.

4.5.2.15.1 Inoculated product or simulated product. For each type of sterilization, the organism used shall be as listed below:

Type of Sterilization	Organism	Incubation Temperature
Dry Heat	B. stearothermophilus, or	55° - 65° C
	B. subtilis var. niger (or globigii)	30° - 35° C
Gas	B. subtilis var. niger (or globigii)	30° - 35° C
Radiation	B. pumilus	30° - 35° C

The number of viable cells shall be sufficient to provide assurance that the product has been sterilized.

4.5.2.15.2 Inoculated carrier. Inoculated carriers (paper spore strips) if used shall be in accordance with MIL-S-36586. Other paper carriers shall be inoculated to be of equivalent resistance. The method of incubation and number of test units shall be as indicated in 4.5.2.15 Sterility test and 4.5.2.15.1 Inoculated product or simulated product. The method of sterilization will control the organism in the spore strip to be tested for as shown in 4.5.2.15.1. NOTE: When an inoculated carrier is chosen, product samples must also be tested as required by the USP.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

4.5.2.15.3 Alternate method. Suppliers conducting sterility tests or designating lots in a manner other than that indicated herein shall submit proof that the alternate method provides equal assurance concerning the sterility of the product. However, all sterility tests shall be conducted using biological indicators. Requests for approval of any alternate method of testing for sterility shall be made to the Contracting Officer, and approval obtained before employment of the alternate method on a government contract.

4.5.2.15.4 Product testing. Testing for sterility of the product after receipt by the government shall be without a biological indicator and in accordance with the U.S.P.

5. PREPARATION FOR DELIVERY

5.1 Packaging.

5.1.1 Unit of issue One package containing 100 pads of the size specified, constitutes one unit of issue.

5.1.2 Packaging quantities. The number of units of issue indicated in table V shall be packaged in each unit, intermediate, and exterior container, as applicable for the required level of protection specified in the procurement document.

Table V. Packaging Quantities

Size	Unit package	Intermediate package	Exterior container
I	1 unit	12 units	48 units
II	1 unit	12 units	24 units

5.1.2.1 Variation permitted. If the required number of units in the entire shipment is less than the number of units specified to be overpacked in an exterior container, such units shall be packed in an exterior container of suitable size and design, acceptable to a common carrier, which shall insure safe delivery to destination.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

5.1.3 Level A.

5.1.3.1 Unit package. One hundred pads of one size, individually packaged as specified in 3.1.4, shall be further packaged in a box of appropriate size and design constructed in accordance with PPP-B-566 or PPP-B-676 except that commercial colors are acceptable. Closure shall be adequate to prevent spilling of contents under normal handling.

5.1.3.2 Intermediate package. Intermediate package shall be a box of appropriate size and design constructed in accordance with PPP-B-636, type CF, class domestic. Closure shall be adequate to prevent spilling of contents under normal handling.

5.1.4 Level C. Units shall be packaged in standard commercial containers, of the size and kind commonly used, which will afford the degree of protection required for shipment and use of the product for its intended purpose.

5.2 Packing.

5.2.1 Level A.

5.2.1.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 3, style 3; PPP-B-601, overseas type; PPP-B-621, class 2; or PPP-B-636, class weather-resistant, Fiberboard boxes shall conform to the special requirements specified in PPP-B-636.

5.2.1.2 Case liner. Each level A wood box shall be lined with a waterproof case liner conforming to MIL-L-10547. Closure and sealing shall conform to applicable paragraphs of appendix thereto. Case liner shall not be required for fiberboard boxes.

5.2.1.3 Closure. Closure of wood boxes shall be in accordance with appendix of applicable box specification. Closure of each fiberboard box shall be as specified in the appendix, and waterproofing shall conform with 30.4 of PPP-B-636.

5.2.1.4 Strapping. Strapping, when required, shall be in accordance with appendix of applicable box specification.

NOTE: Strapping shall not be required for shipments forwarded to a receiving activity within the continental limits of the United States for storage and redistribution.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

5.2.2 Level B.

5.2.2.1 Exterior container. Exterior container shall be designed for a type 2 load and constructed in accordance with PPP-B-585, class 1, style 3; PPP-B-601, domestic type; PPP-B-621, class 1; or PPP-B-636, class domestic. Closure of wood boxes shall be as specified in the appendix of the applicable box specification. Closure of fiberboard boxes shall conform to method II of PPP-B-636. In addition, fiberboard boxes shall conform to the special requirements specified in PPP-B-636.

5.2.3 Level C. The subject commodity shall be packed in substantial commercial containers of the type, size, and kind commonly used for the purpose, so constructed as to insure acceptance and safe delivery by common or other carriers, at the lowest rate, to point of delivery called for in the contract or purchase order.

5.3 Marking.

5.3.1 Immediate container. In addition to any commercial markings, each immediate container shall be marked with the item identification, the legend: "STERILE", name of manufacturer, and the legend (or similar): "STERILITY GUARANTEED UNLESS PACKAGE IS DAMAGED OR OPENED".

5.3.2 Unit package. Each unit package shall be marked in accordance with MIL-STD-129 and the requirements of the Federal Food, Drug, and Cosmetics Act. In addition, marking shall include the sterility lot (control) number, contract or purchase order number, name and address of manufacturer, when the manufacturer is not the contractor, the name and address of the contractor shall also appear. Marking shall include the method of sterilization (G-Gas, R-Radiation, C-Cold, S-Steam, D-Dry Heat Sterilization) shall be shown following the level of packaging and the date of packaging. Example: "A-9/69-G".

5.3.3 Intermediate package. Each intermediate package shall be marked in accordance with Military Standard MIL-STD-129. When labels are utilized waterproofing shall be required only when applicable carton is fabricated of water-resistant material. Sterility lot (control) number, contract or purchase order number, and name of contractor shall be shown. The method of sterilization as specified in 5.3.2 shall also be shown.

5.3.4 Exterior container. Exterior container shall be marked in accordance with MIL-STD-129. Sterility lot (control) number shall be shown.

NOTE: Final sterilization shall be on or after indicated packaging date.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use. The nonadherent pads covered by this specification are intended for use by Military Medical Services.

6.2 Ordering data. Procurement documents should specify the following:

(a) Title, number and date of this specification.
(b) Size required (see 1.2).
(c) Selection of applicable levels of packing (see 5.1 and 5.2).

6.3 This specification does not include all types, classes, grades or sizes of the commodity indicated by the title of the specification, or which are commercially available, but is intended to cover the types which are normally procured to meet Military requirements.

6.4 Supersession Data. This specification includes the requirements of Defense Medical Purchase Description No. 1, dated 10 November 1970 and Modification No. 3, dated 3 November 1971.

Custodians:
Army - MD
Navy - MS
Air Force - 03

Review activities:
Army - MD
Navy - MS
Air Force - 03

Preparing activity:
Defense Supply Agency - DM

Project No. 6510-0577

Review information is current as of the date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

OMB Approval
No. 22-R255

INSTRUCTIONS: The purpose of this form is to solicit beneficial comments which will help achieve procurement of suitable products at reasonable cost and minimum delay, or will otherwise enhance use of the document. DoD contractors, government activities, or manufacturers/vendors who are prospective suppliers of the product are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity.

DOCUMENT IDENTIFIER AND TITLE

MIL-P-36861

NAME OF ORGANIZATION AND ADDRESS

CONTRACT NUMBER

MATERIAL PROCURED UNDER A

☐ DIRECT GOVERNMENT CONTRACT ☐ SUBCONTRACT

1. HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE?

A. GIVE PARAGRAPH NUMBER AND WORDING.

B. RECOMMENDATIONS FOR CORRECTING THE DEFICIENCIES

2. COMMENTS ON ANY DOCUMENT REQUIREMENT CONSIDERED TOO RIGID

3. IS THE DOCUMENT RESTRICTIVE?

☐ YES ☐ NO *(If "Yes", in what way?)*

4. REMARKS

SUBMITTED BY *(Printed or typed name and address - Optional)*

TELEPHONE NO.

DATE

DD FORM 1 JAN 72 1426 REPLACES EDITION OF 1 JAN 66 WHICH MAY BE USED

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.

FOLD

DEFENSE PERSONNEL SUPPORT CENTER
2800 South 20th Street
Philadelphia, Pa. 19101

Defense Supply Agency

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

POSTAGE AND FEES PAID
DEFENSE SUPPLY AGENCY
DoD - 304

U.S.MAIL

HEADQUARTERS, DEFENSE PERSONNEL SUPPORT CENTER
ATTN: DIRECTORATE OF MEDICAL MATERIEL, CODE ATT
2800 SOUTH 20TH STREET
PHILADELPHIA, PA. 19101

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-21T09:28Z
Check the source to verify that this is the current version before use.