A-A-160D
December 12, 1989
SUPERSEDING
A-A-160C
February 10, 1984

COMMERCIAL ITEM DESCRIPTION

SACK, SHIPPING, PAPER (CUSHIONED)

The General Services Administration has authorized the use of this Commercial Item Description in preference to Federal Specification PPP-S-30, Type I.

This description covers cushioned paper sacks for shipping items weighing not more than 10 pounds.

1. SALIENT CHARACTERISTICS:

A. Construction. The walls of the sack shall consist of 2 layers of kraft paper with a cushioning medium such as macerated paper inserted between the layers. The outer layer of kraft paper shall be water resistant. The fabricated sacks shall pass the water resistance test and the impact resistance test. The edge of the inside seam shall be located not more than 1 inch from the side of the sack.

B. Dimensions. Dimensions of the sacks shall be outside measurements, expressed as width by length. Dimensions shall be as specified with a tolerance of ± 1/4 inch. Sack opening shall be on the short side.

C. Workmanship. Sacks shall be uniformly constructed and free from holes, tears, cuts, splits, or other defects which might impair their usefulness.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.

3. QUALITY ASSURANCE.

A. Examination of the end item for dimensions and workmanship. The sample unit shall be one sack. The Inspection Level shall be S-2 with an Acceptable Quality Level (AQL) of 2.5 percent defective, in accordance with MIL-STD-105.

B. Testing of the end item for water resistance and impact resistance. The sample unit shall be one sack. The Inspection Level shall be S-1 with an Acceptable Quality Level (AQL) of 2.5 percent defective, in accordance with MIL-STD-105.

1. Water resistance test. Two drops of water shall be placed on the outside of the sack and covered with a watchglass. The water shall remain on the outside of the sack without being absorbed for not less than 30 minutes.

2. Impact resistance test. Determine the cubic capacity of the sack by multiplying the three factors F1, F2, and F3, together:

Cubic capacity = F1 x F2 x F3
F1 = specified length
F2 = 90% of specified width
F3 = 10% of specified width

Fill a graduated cylinder or similar volumetric device to 75 percent of the cubic capacity of the sack with dry, unpopped, popcorn. Transfer the popcorn to the sack and seal the open end of the sack with packaging tape. Drop each sack six times from a height of 36 inches onto a hard, unyielding surface such as uncarpeted concrete. The sack shall be dropped once on each face and once on each side. If any popcorn spills from the sack, the sack does not pass the impact resistance test.

C. Examination of packaging, packing and marking. The sample unit for this examination shall be one fully prepared shipping container. The Inspection Level shall be S-2 with an Acceptable Quality Level (AQL) of 4.0 percent defective, in accordance with MIL-STD-105.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.

3. REGULATORY REQUIREMENTS:

The offeror/contractor shall certify that the kraft paper used to make the sacks contains not less than 5 percent post consumer recovered material. The Government reserves the right to require proof of such content prior to the first delivery and thereafter as may be provided for under the provisions of the contract. Post consumer recovered material is defined as paper, paperboard and fibrous wastes from factories, retail stores, office buildings, homes, etc., which has passed through an end use as a consumer item, including: used corrugated boxes, old newspapers, old magazines, mixed waste paper, tabulating cards, used cordage; and all paper, paperboard, or fibrous waste collected from municipal solid waste.

4. PACKAGING, PACKING, AND MARKING:

Packaging, packing, and marking shall be as specified in the contract or order.

5. REFERENCED DOCUMENT:

Military Standard

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

The issue of MIL-STD-105 in effect on the date of the solicitation for offers or request for proposals shall be used to determine conformance with the requirements of this Commercial Item Description. MIL-STD-105 is available from the Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

6. NOTES:

Purchasers shall specify:

(1) Dimensions, expressed as width by length,
(2) Packaging, packing and marking required.

MILITARY INTERESTS:

No official DOD interest in this Commercial Item Description has been registered.

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:05Z
Check the source to verify that this is the current version before use.