[METRIC]

A-A-2106A
June 17, 1993
SUPERSEDING
A-A-2106
September 14, 1982

COMMERCIAL ITEM DESCRIPTION
PAPER, PROTECTIVE, ADHESIVE

The General Services Administration has authorized the use of this commercial item description, for all Federal agencies.

1. SCOPE. This description covers protective adhesive paper which is used on the exterior aluminum skins on aircraft to prevent scratches during fabrication.

2. SALIENT CHARACTERISTICS:

A. Construction. The protective adhesive paper shall be made from kraft paper impregnated with synthetic latex. Adhesive coating shall be covered with a liner which has been treated to assure easy release from adhesive surface.

B. Dimensions. The length and thickness of the roll shall be not less than specified (see 7a). The width of the roll shall be as specified with the tolerances of 6.35 mm (+1/4"), 3.2 mm (-1/8") (see 7a).

C. Paper. The paper shall meet the requirements of Table I, when tested with the appropriate test methods.

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document, should be sent to: General Services Administration, Federal Supply Service, 26 Federal Plaza, New York N.Y. 10278
ATTN: Engineering Branch (2FYEE).

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited

FSC 8135

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:19Z
Check the source to verify that this is the current version before use.

TABLE I

PAPER	REQUIREMENTS	TEST METHODS
Basis Weight (minimum)	114 g/m^2 +/- 5% (70 lbs +/- 5 % based on 24" x 36" - 500 sheets) (Including Adhesive)	TAPPI T 410
Thickness	0.127 mm minimum (0.005" minimum)	TAPPI T 411
	0.177 mm maximum (0.007" maximum)	TAPPI T 411
Adhesive strength	15.3 N/100 mm minimum (14 oz / inch, minimum)	ASTM D 1000
	25.2 N/100 mm maximum (23 oz / inch, maximum)	ASTM D 1000

D. Workmanship. The protective adhesive paper shall be free from any defects adversely affecting its appearance or serviceability.

3. QUALITY ASSURANCE:

A. Responsibility for Inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the Commercial Item Description, where such inspection are deemed necessary to assure that supplies and services conform to prescribed requirements.

B. Sampling. Samples shall be in accordance with MIL-STD-105 using the plan as specified in Table II, unless stated otherwise.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:19Z
Check the source to verify that this is the current version before use.

TABLE II

Inspection	Inspection Level	AQL (%) defective	Sample Unit	Requirements Paragraph/s
Construction & Adhesive Test	S-3	4.0	1 ROLL	2A Table I
Dimensions	S-3	4.0	1 ROLL	2B
Workmanship	S-3	4.0	1 ROLL	2D
Packaging, Packing & Marking	S-3	4.0	1 ROLL	5

TAPPI TESTS (see Table I, for individual TAPPI'S which provide specific sampling instructions).

4. REGULATORY REQUIREMENTS: The offeror/contractor is encouraged to use recovered materials in accordance with Paragraph 23.403 of the Federal Acquisition Regulation.

5. PACKAGING, PACKING AND MARKING: Packaging, packing and marking shall be as specified in the contract or purchase order.

6. REFERENCED DOCUMENTS: The issue of the referenced documents in effect on the date of the solicitation for offers or request for proposals shall be used to determine conformance with the requirements of this Commercial Item Description.

A. Federal Regulations:

Federal Acquisition Regulation. Paragraph 23.403

Copies of the U.S. Code may be obtained through the Congressional Sales Office, U.S. Government Printing Office, Washington D.C. 20402.

B. Military Standard:

MIL-STD-105 - Sampling Procedures and Tables for Inspection by Attributes

MIL-STD-105 is available from Naval Publication and Forms Center; 5801 Tabor Avenue; and Materials; Philadelphia, PA 19120.

Source: https://assist.dla.mil -- Downloaded: 202610-26T08:19Z
Check the source to verify that this is the current version before use.

C. American Society for Testing and Materials (ASTM):

ASTM D 1000 - Standard Test Method for Pressure-Sensitive Adhesive-Coated Tapes for Electric and Electronic Applications

ASTM standards test method can be obtained from the American Society for Testing and Materials; 1916 Race Street; Philadelphia, PA 191103.

D. Technical Association of the Pulp and Paper Industry (TAPPI):

T 410 - Weight Per Unit Area (Basic Weight or Substance) of Paper and Paperboard
T 411 - Thickness (Caliper) of Paper and Paperboard and liningboard
T 400 - Sampling and accepting a single lot of paper, paperboard, fiberboard, or related product

TAPPI standard T test methods can be obtained from Technical Association of the Pulp and Paper Industry; Technology Park/Atlanta P.O. Box 105113; Atlanta, GA 30348.

7. ORDERING DATA:

Purchasers shall specify the following in the contract or purchase order.

(a) The thickness, width, and length of the roll.
(b) Packaging, packing, labeling and marking requirements.

MILITARY INTERESTS:

NONE: DoD has no interest and waives coordination interest for the subject document.

PREPARING ACTIVITY:

GSA-FSS

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:19Z
Check the source to verify that this is the current version before use.