COMMERCIAL ITEM DESCRIPTION

CUP, DISPOSABLE: LID, DISPOSABLE CUP

The General Services Administration has authorized the use of this commercial item description in preference to Federal Specification UU-C-806.

This commercial item description covers disposable paper cups and paper or plastic lids.

Salient characteristics.

The paper cups shall be of the following types, styles of construction, classes of coatings, capacities (see table I), and forms, as specified.

CUPS:

Type I - Hot Drink
  Style A - Round, Two-piece
    Class 3 - Plastic lined
    Color - Green (9 oz. only) outer surface
    Form - 6 and 8 ounce with or without handles,
           9, 12, and 16 ounce without handles

Type II - Hot Food
  Style A - Round, Two-piece
    Class 1 - Uncoated (moisture resistant stock)
    Class 3 - Plastic lined

Type III - Cold Drink
  Style A - Round, Two-piece
    Class 2 - Wax coated
    Class 4 - Plastic coated, both sides
    Form - Sizes 10, 12, 16, 20 and 24 ounce available in squat or tall shape. Squat cups have a height less than twice the diameter of the base and tall cups have a height more than twice the diameter of the base.

Type IV - Cold Food, Light Duty (ice cream, condiments)
  Style A - Round, Two-piece
    Class 2 - Wax coated

Type V - Water
  Style A - Round, Two-piece
    Class 1 - Uncoated (moisture resistant stock)
    Class 2 - Wax coated

Beneficial comments, recommendations, additions, deletions, clarifications, etc. and any data which may improve this document should be sent to: General Services Administration, Engineering Group (7FXEE), 819 Taylor St., Fort Worth, TX 76102

DISTRIBUTION STATEMENT A: Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

Style C - Conical
Class 1 - Uncoated (moisture resistant stock)

Style E - Flat, not nested
Class 1 - Uncoated (moisture resistant stock)

Type VI - Portion Control
Style B - Pleated
Class 1 - Uncoated (moisture resistant stock)
Class 3 - Plastic lined

LIDS - Paper or Plastic Coverall

Part Numbering System for Commercial Item Description A-A-2577

```
Example - AA2577- I A 3 W 1 S 08    (AA2577-IA3W1S08)
                  | | | | | |  |---Size: 8 ounce
                  | | | | | |---Form (shape): S - squat,
                  | | | | |      R - regular, T - tall
                  | | | | |---Form, handle: 1 - not provided
                  | | | |                 2 - provided
                  | | | |---Color: W - white, G - green
                  | | |---Class: 3 - Plastic coated
                  | |---Style: A - Round, Two-piece
                  |---Type: I - Hot Drink
```

The cups shall be made from paper or paperboard. The lids shall be either paperboard, which may be white-lined on both sides or may be solid stock, or shall be plastic or any combination of paper or plastic.

All cup, lid, and coating materials shall conform in all aspects to the Code of Federal Regulations (CFR), Subpart B of 21 CFR 176, as applicable. Cups shall conform to 21 CFR 176.170 for paper and paperboard in contact with aqueous and fatty foods. Plastic lid and lid components shall conform to 21 CFR 177. Reclaimed fiber shall conform to 21 CFR 176.260.

The cups shall be round, nestable construction except type V, style E, which shall be flat, not nested (rectangular). Flat cups (type V, style E) shall be made of one piece of paper formed in a rectangular or tapered shape with a gummed lip. The rolled or crimped top brim shall be sufficiently tight to prevent release of the pleats when filling or handling. Conical cups (type V, style C) shall be made from a single sheet of paper formed into a conical shape, with a straight or rolled edge.

Round two-piece cups (types I, II, III, IV, V) shall have smooth sidewalls with reinforced or rolled top edges and flat bottoms. The outer surface of the type I, style A, class 3, 9-ounce cup, exclusive of the rolled edge, shall be green and approximate one of the following colors of FED-STD-595; 34373, 34441, 34491, 34504, 34516, 34518, 34558, or 34670. The capacities and material thicknesses of the cups shall be as specified in Table I.

When specified, handles shall be paperboard and may be either integral with the cup or adhered to the cup. The handles shall be sufficiently strong, shall not tear or separate from the cup body when subjected to the rigidity test.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

TABLE I. Cups

Style	Class	Rated capacity	Required capacity minimum	Minimum thickness	
				Wall	Bottom
		ounces	ounces	inch	inch
Type I, Hot drink					
A	3	6 1/	5-3/4	0.0120	0.0090
		8 1/	7-3/4	0.0120	0.0090
		9 2/	8-3/4	0.0150	0.0115
		12	11-3/4	0.0160	0.0110
		16	15-3/4	0.0160	0.0110
Type II, Hot food					
A	1	8	7-3/4	0.0152	0.0171
		10	9-3/4	0.0170	0.0171
		12	11-3/4	0.0093	0.0171
		16	15-3/4	0.0093	0.0171
		32	31-3/4	0.0093	0.0189
A	3	8	7-3/4	0.0087	0.0120
		12	11-3/4	0.0170	0.0124
		16	15-3/4	0.0170	0.0171
		32	31-3/4	0.0180	0.0180
Type III, Cold Drink					
A	2, 4	5	4-3/4	0.0058	0.0070
		6	5-3/4	0.0068	0.0070
		7	6-3/4	0.0068	0.0070
		8	7-3/4	0.0068	0.0070
		9	8-3/4	0.0068	0.0070
		10 3/	9-3/4	0.0068	0.0070
		12 3/	11-3/4	0.0077	0.0070
		16 3/	15-3/4	0.0099	0.0070
		20 3/	19-3/4	0.0099	0.0070
		24 3/	23-3/4	0.0099	0.0085
Type IV, Cold Food					
A	2	8	7-3/4	0.0084	0.0070
Type V, Water					
A	1	4	3-3/4	0.0070	0.0077
	2	4	3-3/4	0.0058	0.0074
C	1	3-1/4 4/	3	0.0036	
		3-1/2 4/	3-1/4	0.0036	
		4 4/	3-3/4	0.0036	
E	1	4	3-1/2	0.0040	
Type VI, Portion Control					
B	1	1	1	0.0036	
	3	1	1	0.0040	

1/ Handles available in these sizes only
2/ Known in industry as 8-1/4 ounce vending cup
3/ Available in either squat or tall shape. When the overall height is less than two times the diameter of the base, the cup is considered squat. When the overall height is greater than two times the diameter of the base, the cup is considered tall. This applies to type III, cold drink cups only.
4/ Available in either straight or rolled edge

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

The lids shall be a coverall design with a skirt or flange which extends over the brim of the cup. Plastic lids may be either clear or opaque. The lids shall be supplied by the same manufacturer of the cups to ensure a snug fit.

The cups shall not leak when tested as specified. The cups shall have sufficient rigidity so that they will not collapse when filling and handling or when tested as specified. The cups and lids shall not impart an objectionable odor when tested as specified.

Workmanship. The cups and lids shall be clean and free from foreign matter, holes, tears, lumps, or blisters. Lids shall fit snugly.

Quality Assurance:

Responsibility for inspection: Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Government. Inspection records of the examinations or tests shall be kept complete and available to the Government as specified in the contract or purchase order. The Government reserves the right to perform any of the inspections set forth in the Commercial Item Description where such inspections are deemed necessary to assure that supplies and services conform to prescribed requirements.

Inspection of the end item: Sampling shall be in accordance with MIL-STD-105, Sampling Procedures and Tables for Inspection by Attributes. The inspection lot shall consist of all cups and lids offered for inspection at one time. The sample unit shall be one cup and lid, if applicable.

Visual inspection. The visual examination of the cups and lids shall be for construction and workmanship defects in accordance with Table II. The inspection level shall be level S-4 with an acceptable quality level (AQL) of 2.5 expressed in defects per hundred units.

Table II - Classification of Defects

Examine	Defect
Cups, and lids	Not type, style, class, color or form specified
Appearance of Cups and lids	Any disagreeable odor Surface not clean; presence of any foreign matter, dirt, sand, grit, or glue spots Any hole, tear, cut, puncture, wrinkle, crease, or fold that is not required by style of construction Visibly and detrimentally out of round or misshaped Top not sufficiently tight, allows pleats to open Top brim not smooth, uniform, or sturdy Color not as specified
Construction (where applicable)	Not capable of being nested Does not have pleated side, reinforced, or rolled brim Bottom not flat or recessed Lid seat missing or does not encircle cup in its entirety Not squat or tall, as specified Handle missing or damaged Handle prohibits nesting or adheres to sidewall preventing forward folding Handle tears or separates from sidewall when full cup is lifted by handle Lid does not fit matching cup snugly

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

Table II - Cont.

Examine	Defect
Workmanship	Poorly glued, as applicable Not waxed or plastic coated, as applicable Torn, crushed, or distorted

Inspection for preparation and delivery. An inspection shall be made to determine whether the packaging, packing, and marking comply with the requirements of the contract or purchase order. Examination for defects shall be in accordance with Table III. For examination of interior packaging, the sample unit shall be one shipping container fully prepared for delivery. Sampling shall be in accordance with MIL-STD-105. The lot size shall be the number of shipping containers in the end item inspection lot. The inspection level shall be S-2 with an AQL of 4.0 defects per hundred units.

Table III - Preparation for delivery defects

Examine	Defects
Markings	Omitted; incorrect; illegible; improper size, location, sequence, or method of application.
Material	Any component missing, damaged, or not conforming to applicable requirements stated herein.
Workmanship	Inadequate application of components such as incomplete closure of container flaps, loose strapping, or distortion of container.
Contents	Quantity of container is more or less than required. Gross weight exceeds requirements of the box specification.

Testing of the end item. The end item shall be tested for the applicable characteristics. A sample unit shall consist of four cups of the same type, style, class, color, capacity and form. No more than one sample unit randomly selected shall be drawn from any one shipping container. The lot size for the purpose of determining the sample size shall be expressed in units of 1000 cups of the same type, style, class, color, capacity, or form in the inspection lot. The inspection level shall be S-3 and the AQL shall be 2.5 percent defective for all tests except leakage. For the leakage test, 20 cups shall be drawn from each lot. Failure of 2 cups shall be cause for rejection of the lot.

Thickness test. For determining the thickness of the sidewall, cut two specimens approximately 2 inches square from the sidewalls of two of the cups constituting the sample unit and determine the thickness in accordance with the procedure of method T 411 om-83 TAPPI Standard. For the thickness of the cup bottom, trim away the sidewalls of two cups to produce a circle of material approximating the diameter of the cup bottom. Determine the thickness as described above. For one-piece pleated cups, the thickness shall be determined on the bottom portion of the cup, after trimming away the sidewalls.

Capacity test. The capacity of the paper cup shall be determined on two cups from each sample unit. Measure to the nearest milliliter the quantity of tap water, at room temperature, required to fill the cup to the brim. The cup shall rest on a smooth level surface. This test shall be performed on cups to be used for the leakage test.

Leakage test.

Types I and II. Twenty cups shall be filled with distilled water having a pouring temperature of 180 to 200 degrees Fahrenheit and placed on an irregular or ventilated surface to permit air circulation under the recessed bottom and prevent accumulation of moisture condensation which is not leakage. The cups shall be examined for leakage at the end of 15 minutes.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

Types III through VI. Twenty cups shall be filled with distilled water at a temperature range of 70 to 75 degrees Fahrenheit. Place a sheet of clean, white bond paper between the cup and the supporting surface. All above types shall be examined for leakage at the end of 15 minutes except type V, styles C and E which shall be examined at the end of 5 minutes while suspended from the top.

Rigidity test. The rigidity of the cups shall be determined on the filled cups used for the leakage test at the end of the time specified for the leakage test. The rigidity shall be observed while holding the cup in the normal position for use. The cups shall not collapse when handled or when being filled for the leakage test.

Odor and taste. A minimum of 60 milliliters distilled water used in the leakage test shall be collected and allowed to stand in a stoppered flask or bottle for 2 hours. The odor and taste of the sample water shall be compared with that of freshly distilled water contained in a stoppered flask for the same length of time and at the same temperature.

Regulatory requirements: In accordance with Section 23.403 of the Federal Acquisition Regulations, the Government's policy is to acquire items composed of the highest percentage of recovered materials practicable, consistent with maintaining a satisfactory level of competition without adversely affecting performance requirements or exposing suppliers' employees to undue hazards from the recovered materials.

Preservation, packaging, packing and marking (Civil Agencies): Preservation, packaging, packing, and marking shall be as specified in the contract or purchase order.

Packaging (DOD): Packaging shall be in accordance with ASTM Standard D 3951.

Notes:

Copies of military standards may be obtained from the Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

Application for copies of American Society for Testing and Materials (ASTM) Standards should be addressed to the American Society for Testing and Materials, 1916 Race Street,
Philadelphia, PA 19103.

Application for copies of TAPPI test methods should be addressed to TAPPI, Technology Park/Atlanta, P.O. Box 105113, Atlanta, GA 30348.

The standards referenced in this document shall be the issues in effect on the date of the invitation for bids or request for quotation and shall be used to determine compliance with these requirements. In the event that there is a conflict between this document and a standard referenced herein, this document shall take precedence.

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.

MILITARY INTERESTS:

MILITARY COORDINATING ACTIVITY:

Army - GL

CIVIL AGENCY COORDINATING ACTIVITY:

VA - OSS
NASA

Custodians:

Army - GL
Navy - SA
Air Force - 99

PREPARING ACTIVITY:

GSA - FSS

Review Activities:

Army - MD, TS
Navy - MS
Air Force - 84

Source: https://assist.dla.mil -- Downloaded: 2026-10-26T08:24Z
Check the source to verify that this is the current version before use.