MILITARY SPECIFICATION

CASTINGS, CLASSIFICATION AND INSPECTION OF

This specification is approved for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope - This specification prescribes the requirements for the classification and inspection of ferrous and non-ferrous metal castings. This specification supplements detail casting specifications when specified.

* 1.2 Classification - Castings shall be classified by classes and as applicable grades.

* 1.2.1 The classification designations have been changed to conform to the "Defense Standardization Manual" 4120.3-M by keeping the class designation limited to numbers only.

MIL-C-6021H Classification designation	MIL-C-6021G Classification designation
Class 1	Class 1, Class 1A
Class 2	Class 1, Class 1B
Class 3	Class 2, Class 2A
Class 4	Class 2, Class 2B

* 1.2.2 Classes - Castings shall be classified as follows:

* 1.2.1.1 Class 1 - A casting, the single failure of which would cause significant danger to operating personnel or would result in a significant operational penalty. In the case of missiles, aircraft and other vehicles; this includes loss of major components, loss of control, unintentional release or inability to release armament stores, or failure of weapon installation components.

1.2.1.2 Class 2 - A casting not included in Class 1.

* 1.2.1.3 Class 3 - Castings having a margin of safety of 200 percent or less.

* 1.2.1.4 Class 4 - Castings having a margin of safety greater than 200 percent, or for which no stress analysis is required. All

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

target drone castings and aerospace ground support equipment fall in this category, except for such critical parts, the failure of which would make the equipment unsatisfactory and cause the vehicles which they are intended to support to be inoperable.

1.2.2 Grades - Castings shall be of Grades A, B, C, and D as shown in Tables III, IIIa, IV, and V and shall be in accordance with the radiograph reference specified in the tables.

2. APPLICABLE DOCUMENTS

2.1 The following documents, of the issue in effect on date of invitation for bids or request for proposal, form a part of this specification to the extent herein:

SPECIFICATIONS

Military

MIL-I-6866	Inspection, Penetrant Method of
MIL-I-6868	Inspection Process, Magnetic Particle

STANDARDS

Military

* MIL-STD-139	Radiographic Inspection: Soundness Requirements for Aluminum and Magnesium Castings (For Small Arms Parts)
MIL-STD-271	Nondestructive Testing Requirements for Metals
MIL-STD-410	NONDESTRUCTIVE TESTING PERSONNEL QUALIFICATION AND CERTIFICATION (Eddy Current, Liquid Penetrant, Magnetic Particle, Radiographic and Ultrasonic).
MIL-STD-453	Inspection, Radiographic

Naval Air Systems Command

NAVWEPS-00-15PK-500	Weapons Technical Inspection Manual - Reference Radiographs for Inspection of Thin Wall Castings

(Copies of specifications, standards, drawings and publications required by suppliers in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

* 2.2 Other publications - The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

American Society for Testing and Materials

E155	Reference Radiographs for Inspection of Aluminum and Magnesium Castings (Series II)
E186	Standard Reference Radiographs for Heavy Walled (2- to 4-1/2-inch) Steel Castings
E192	Reference Radiographs of Investment Steel Castings for Aerospace Applications
E446	Reference Radiographs for Steel Castings Up to 2 in. (51mm) in Thickness

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

3. REQUIREMENTS

3.1 Classification option - The contractor may elect to classify castings in a manner requiring greater frequency of inspection tests than the minimum requirements specified herein.

* 3.2 Determination of classes and grades - The contractor's design activity shall establish the class and grade by critical areas and stress levels for each casting design. The classification(s) and critical area(s) shall be indicated on the applicable drawing.

* 3.2.1 All areas of a Class 1 casting shall be of a quality equivalent to or better than Grade C, except that all critical areas of a Class 1 casting shall be of a quality equivalent to or better than Grade B (See Tables III, IIIa, IV, V and VI).

* 3.2.2 Radiographic grades - The contractor's design activity shall specify on the drawing or other document the (quality level) radiographic grade(s) for Classes 1, 2 and 3 casting designs. The design activity may specify radiographic grade(s) for Class 4 casting designs. Castings shall be of Grades A, B, C or D as shown in Tables III, IIIa, IV, V and VI and shall be in accordance with the reference radiographs specified in the tables unless the design activity has information substantiating the suitability of castings with more extensive defects.

* 3.3 Inspection - Castings shall be inspected as specified herein unless the contractor's design activity has information substantiating the suitability of other inspection plans.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

* 3.3.1 For all castings for which radiographic inspection is specified, the contractor shall prepare either photographs, X-ray film, sketches, documents, or drawings containing:

(a) Classification of casting.

(b) Alloy and heat treatment.

(c) Grade(s) of defect limits as applicable.

(d) Deviations from this specification if not covered by the purchase order, procurement specification, or standard.

3.4 Workmanship - Castings shall be free of the presence of discontinuities such as cracks, evidence of shrinkage, etc. and potential stress raisers, such as tool marks, recesses, inadequate fillets, sharp corners, etc., not specifically permitted on the drawing.

4. QUALITY ASSURANCE PROVISIONS

* 4.1 Responsibility for inspection - Unless otherwise specified in the contract or purchase order, the supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own facilities or any commercial laboratory acceptable to the Procuring Activity. The Procuring Activity reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

* 4.1.1 Laboratories and personnel performing radiographic, magnetic particle and penetrant inspection shall be qualified in accordance with MIL-STD-410, MIL-STD-453 and MIL-STD-271 as applicable.

4.2 Lot definition -

4.2.1 Inspection lot - Unless otherwise specified, a lot shall consist of all castings of a specific design, of one alloy produced at one facility by the same production technique and submitted for inspection at one time.

4.2.1.1 Casting for small arms parts (except sand castings) - When individual production melts are used, the first 10 lots shall consist of all castings from each consecutive individual production melt. Increase of lot size to 50 consecutive individual production melts shall be permitted provided that the preceding 10 consecutive lots were acceptable.

4.2.1.1.1 Inspection shall revert to the number of consecutive castings specified in 4.3.3.1 and lot size for investment and shell molded castings shall revert back to the first 10 lot individual production melt basis, in the event that any of the following conditions occur:

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

(a) Failure of samples from a lot to meet the sampling inspection acceptance criteria.

(b) Any pattern change or new pattern.

(c) Any major change of foundry technique, such as risering, chilling, sand mix or pouring temperatures.

(d) Start of a new foundry or furnace. (Includes lapse of production of 3 months or more).

4.3 Sampling -

4.3.1 Visual inspection - Each casting shall be examined visually.

4.3.2 Magnetic particle and penetrant inspection - Each casting shall be subjected either to magnetic particle or penetrant inspection, as may be appropriate, except that Class 4 castings shall be sample inspected in accordance with Table I.

4.3.3 Radiographic inspection -

* 4.3.3.1 Castings, for small arms parts - Unless otherwise specified, sampling inspection for castings for small arms parts shall be in accordance with MIL-STD-139.

* 4.3.3.2 Castings, general - Except as specified in 4.3.3.1, sampling inspection shall be as indicated below:

Class 1 Castings - Each casting shall be completely examined.

Class 2 Castings - Casting shall be selected in accordance with Table I and completely examined.

Class 3 Castings - Castings shall be selected in accordance with Table II and completely examined.

Class 4 Castings - Radiographic examination is not required unless otherwise specified.

4.3.4 Inspection during manufacture - Appropriate tests shall be performed as necessary during manufacture or assembly to assure freedom from harmful discontinuities, which due to their nature, degree or extent, are detrimental to the indicated usage of the finished part or assembly.

* 4.3.4.1 When processing operations such as heat treating, machining, cold grinding, plating or welding are involved which may in any way adversely affect the material or the part, inspection shall be performed after completion of the operation(s).

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

4.3.4.2 When processing operations are involved which may in any way interfere with the inspection process, such as certain types of electroplates or surface treatments as grit blasting and shot peening, inspection shall be performed both before and after such operations.

4.4 Tests -

* 4.4.1 Visual inspection - Unless otherwise specified, each casting shall be 100 percent visually inspected for surface defects and irregularities, particularly in critical areas. Attention shall be given to the presence of discontinuities such as cracks, evidence of shrinkage, etc., and potential stress raiser, such as tool marks, recesses, inadequate fillets, sharp corners, etc., not specifically permitted on the drawing. Where advisable, a magnifiying glass (up to 12X) shall be used to aid visual inspection.

4.4.2 Magnetic particle and penetrant inspection -

* 4.4.2.1 Ferromagnetic materials - Castings of ferromagnetic materials shall be magnetic particle inspected or penetrant inspected. Magnetic particle inspection shall be in accordance with MIL-I-6868. Penetrant inspection shall be in accordance with MIL-I-6866. When applicable, either method of inspection may be conducted in accordance with MIL-STD-271.

* 4.4.2.2 Nonferromagnetic materials - Castings of nonferromagnetic materials shall be penetrant inspected in accordance with MIL-I-6866 or MIL-STD-271 as applicable.

4.4.3 Radiographic inspection -

4.4.3.1 Castings, for small arms parts - Radiographic inspection shall be in accordance with standards acceptable to the procuring activity.

4.4.3.2 Castings, general - Except as specified in 4.4.3.1, radiographic inspection shall be in accordance with MIL-STD-453 or MIL-STD-271 as applicable except that nonfilm method may be used as follows:

(a) Castings of any class may be screened, using 100 percent radiographic inspection by nonfilm methods. All castings found acceptable by nonfilm methods shall then be inspected by a film method in accordance with the sampling requirements applicable to the specific class.

(b) When authorized by the procuring activity, Class 3 castings may be radiographically inspected, using 100 percent nonfilm methods in lieu of the sampling methods permitted for such castings by a film method. However, the disclosure of a single rejectable or borderline discontinuity

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

shall be cause for reinspection of the lot in accordance with the sampling requirements of 4.3.3.2 using a film method.

4.4.3.2.1 Nonfilm radiographic procedures - The procedure used shall be sufficiently sensitive to discriminate between parts in a borderline category which are considered to be rejectable using film methods, and parts representing the worst condition acceptable as specified in Tables III, IIIa, IV, V and VI as applicable. To assure compliance therewith, at least two castings representing each of the two conditions shall be introduced periodically into the test lot to serve as a control on the inspection process.

4.5 Standards -

4.5.1 Visual standards - Specific standards, using sample parts wherever necessary, should be prepared. Where approved specified standards are not available, evaluations of discontinuities shall be based on a review of the radiographic film, past experience, and sound engineering criteria. Dissection as an aid in establishing acceptance criteria is recommended.

* 4.5.2 Radiographic standards - Radiographic standard grades shall be established for each casting design for which radiographic inspection is specified (see 3.2.1). Such standards shall be in terms of ASTM E155 for aluminum and magnesium alloys and ASTM E192, ASTM E186, and ASTM E446 for steel. Maximum acceptable defects shall be in accordance with Paragrpah 3.2.

5. RESUBMITTED INSPECTION LOTS

* 5.1 Rejection - Defects and/or discontinuities which are so aligned as to cause stress concentration are caused for rejection. When an inspection lot is rejected on the basis of a sampling plan, it may be resubmitted for 100 percent inspection. If more than 25% of any lot of Type I Aircraft or Type II Guided Missile castings given 100 percent inspection are rejected because of discontinuities in highly stressed areas, the entire lot shall be submitted to review procedures. Castings not conforming to this specification shall be rejected and submitted to review procedures.

5.1.1 In performing the review of the rejected lot, the cognizant engineering member of the review board may detail a technique for the subjection of a casting to a destructive test, either by loading as in service use or by dissection, as practicable. This consideration shall be predicated on the size of the rejected lot, the size of the castings and criticality of the casting application.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

6. NOTES

6.1 Intended use - Inspection operations required by this specification are intended to assure the quality of the castings to which they are applicable.

* 6.2 Producibility warning - The class assigned to the casting should represent a realistic value for the functional requirement; i.e., do not assign a Type I Casting for a Type II function. Casting design coupled with foundry practice can make too severe soundness requirements impractical for a manufacturer to satisfy. Caution should be exercised in specifying the grade of maximum permissible radiographic discontinuity level to be met in a casting.

* For Information:

Radiographic Grade A - A highly stressed casting or area for critical application.

Radiographic Grade B - A premium grade of casting for critical applications or specified area of a casting with low margins of safety.

Radiographic Grade C - A high quality grade of casting for general applications or area of a casting with average margin of safety.

Radiographic Grade D - This grade was included for less important low-stressed castings, or area of castings.

6.3 Correlation of radiographic standards - ASTM E155 replaces ASTM E98 and NAVAIR-00-15PC-504 referenced in previous issues. For information purposes only, the correlation between ASTM E98 Reference Radiographs for Inspection of Aluminum and Magnesium or NAVAIR-00-15PC-504, Aeronautical Technical Inspection Manual, Volume 3, Section 5; Reference Radiographs for Inspection of Aluminum and Magnesium Castings and E155 is presented in Table VIII.

6.4 Changes from previous issues - The margins of this specification are marked with an asterisk to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

TABLE I

SAMPLE SIZE

Lot Size	Sample Size	Lot Size	Sample Size
2-5	All	27-36	10
6-8	5	37-51	11
9-11	6	52-82	12
12-15	7	83-162	13
16-20	8	163-971	14
21-26	9	972 and over	15

Acceptance number is 0

TABLE II

SAMPLE SIZE

Lot Size	Sample Size	Lot Size	Sample Size
2-4	All	18-27	7
5-6	4	28-48	8
7-11	5	49 and over	9
12-17	6		

Acceptance number is 0

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

TABLE III

DISCONTINUITY - SEVERITY LEVEL REQUIREMENTS FOR ALUMINUM CASTINGS PER ASTM E155

Discontinuity	Radiograph	Grade A		Grade B		Grade C		Grade D	
		Inch		Inch		Inch		Inch	
		1/4	3/4	1/4	3/4	1/4	3/4	1/4	3/4
Gas holes	1.1	None		1	1	2	2	5	5
Gas porosity (round)	1.21	None		1	1	3	3	7	7
Gas porosity (elongated)	1.22	None		1	2	3	4	5	5
Shrinkage cavity cavity	2.1	None		1	NA 1/	2	NA 1/	3	NA 1/
Shrinkage porosity or sponge	2.2	None		1	1	2	2	4	3
Foreign material (less dense material)	3.11	None		1	1	2	2	4	4
Foreign material (more dense material)	3.12	None		1	1	2	1	4	3
Segregation	3.2	None		None		None		None	
Cracks	NA 1/	None		None		None		None	
Cold shuts	NA 1/	None		None		None		None	
Surface irregularity	NA 1/	Not to exceed drawing tolerance							
Core shift	NA 1/	Not to exceed drawing tolerance							

1/ Not available

NOTES: See TABLE V

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

TABLE IIIa

DISCONTINUITY - SEVERITY LEVEL REQUIREMENTS FOR MAGNESIUM CASTINGS PER ASTM E155

Discontinuity	Radiograph Reference	Grade A		Grade B		Grade C		Grade D	
		Inch		Inch		Inch		Inch	
		1/4	3/4	1/4	3/4	1/4	3/4	1/4	3/4
Gas holes	1.1	None		1	1	3	2	5	4
Segregation	3.2	None		1	1	2	2	4	4
Shrinkage cavity	2.1	Not available							
Microshrinkage (feathery)	2.31	None		1	1	4	4	7	7
Microshrinkage (sponge)	2.32	None		1	1	3	4	7	8
Foreign material (less dense material)	3.11	None		2	2	3	3	4	4
Foreign material (more dense material)	3.12	None		1	1	2	2	3	3
Cracks	NA 1/	None		None		None		None	
Cold shuts	NA 1/	None		None		None		None	
Surface irregularity	NA 1/	Not to exceed drawing tolerance							
Core shift	NA 1/	Not to exceed drawing tolerance							

NOTES: See TABLE V 1/ Not Available

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

TABLE IV

DISCONTINUITIES - SEVERITY LEVEL REQUIREMENTS FOR THIN WALL STEEL CASTINGS (1-INCH WALL OR LESS) PER NAVWEPS 00-15PK-500 OR ASTM E192

Discontinuity	Grade A			Grade B			Grade C			Grade D		
	Inch			Inch			Inch			Inch		
	1/8	3/8	3/4	1/8	3/8	3/4	1/8	3/8	3/4	1/8	3/8	3/4
Gas holes	1	1	1	3	3	3	5	5	5	7 1/	7 2/	7
Foreign material (more dense)	Not to exceed sample radiograph in any grade											
Shrinkage cavity	None	None	None	None	None	1	2	2	3	3	4	5
Shrinkage sponge	1	1	1	2 3/	1	1	5	4	5	6	6	7
Shrinkage dendritic	1	1	1	2	2	NA 4/	4	4	4	6	6	6
Shrinkage filamentary	None	None	None	NA 4/	NA 4/	1	NA 4/	NA 4/	2	NA 4/	NA 4/	3
Foreign material (less dense)	1	1	1	3	3	3	5	6	6	6	7	7
Cold shut	None allowed											
Hot tear	None allowed											
Cold crack	None allowed											
Misrun	None allowed											
Coreshift	Not to exceed drawing tolerance											
Mold buckle, positive	Not to exceed drawing tolerance											
Mold buckle, negative	Not to exceed drawing tolerance											
Mold ridge	Not to exceed drawing tolerance											
Excess metal in cracked core	Not to exceed drawing tolerance											
Surface irregularity	Not to exceed drawing tolerance											

1/ Excluding the single largest gas hole. 2/ Excluding the crack-like discontinuities emitting from the gas holes. 3/ Excluding bottom half of the standard reference film. 4/ NA - Not available.

NOTES: See TABLE V.

Source: https://assist.dla.mil/ Downloaded: 2016-10-27T06:03Z
Check the source to verify that this is the current version before use.

TABLE V

DISCONTINUITIES - SEVERITY LEVEL REQUIREMENTS FOR THICK WALL STEEL CASTINGS (2-4.5 INCHES) PER ASTM E186

(Standards apply to all three radiographic techniques)

Category		Grade A	Grade B	Grade C	Grade D
A	Gas porosity	0	1	2	3
B	Sand/slag inclusions	0	1	2	4
C	Shrinkage A	0	2	3	5
C	Shrinkage B	0	2	3	4
C	Shrinkage C	0	2	3	4
E	Inserts A	1	2	3	4
E	Inserts B	0	1	3	4

TABLE VI

MAXIMUM ACCEPTABLE DEFECTS IN STEEL CASTINGS (1-2 INCHES)

Defect	Maximum permissible radiograph per ASTM E446				
	Radiographic reference	Grade A	Grade B	Grade C	Grade D
Gas and blowholes	A	None	1	2	3
Sand spots and inclusions	B	None	1	2	3
Internal shrinkage	C	None	1	2	3
Hot tears	D	None	None	None	None
Cracks	E	None	None	Dwg. Tol.	Dwg. Tol.
Unfused chaplets	F	None	None	1	2
Internal chills	G	None	None	None	1

NOTES: For Tables III, IIIa, IV and V

(1) When two or more types of defects are present to an extent equal to or not significantly better than the acceptance standards for respective defects, the parts shall be rejected.

(2) When two or more types of defects are present and the predominating defect is not significantly better than the acceptance standard, the part shall be considered borderline.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

TABLE VI (Continued)

NOTES: (Continued)

(3) Borderline castings will be considered acceptable, upon review by competent engineering personnel.

(4) Gas holes or sand spots and inclusions allowed by this table shall be cause for rejection when closer than twice their maximum dimension to an edge or extremity of a casting.

(5) Dwg. tol. is defined as minimum thickness of material after defect is removed by machining.

TABLE VIII

REFERENCE RADIOGRAPHS FOR INSPECTION OF ALUMINUM AND MAGNESIUM CASTINGS

	NAVAER 00-15PC-504 and ASTM E98	ASTM E155	
		1/4 in.	3/4 in.
Aluminum - Gas holes	1	1	1
	2	1	1
	3	2	2
	4	3	3
	5	5	5
	6	5	5
	7	7	7
	8	8+	8+
Aluminum - Shrinkage cavity	1	1	-
	2	1	-
	3	1	-
	4	3	-
	5	3	-
	6	4	-
	7	5	-
	8+	8+	-
Aluminum - Round porosity	1	1	1
	2	3	3
	3	6	6
	4	7	7
	5	7	7
	6	7	7
	7	7	8
	8	8+	8+

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

TABLE VIII (Continued)

	NAVAER 00-15PC-504 and ASTM E98	ASTM E155	
		1/4 in.	3/4 in
Aluminum - Elongated porosity	1	1	1
	2	2	2
	3	2	2
	4	3	4
	5	4	4
	6	7	7
	7	8	8
	8	8	8
Aluminum - Foreign material (less dense)	1	1	1
	2	1	1
	3	2	2
	4	3	3
	5	3	3
	6	5	3
	7	6	5
	8	7	6
Aluminum - Foreign material (more dense)	1	2	1
	2	4	2
	3	6	4
	4	6	4
Aluminum - Sponge shrinkage	1	1	1
	2	1	1
	3	2	2
	4	3	3
	5	4	3
	6	7	6
Magnesium - Gas holes	1	1	1
	2	3	2
	3	5	4
	4	7	6
	5	8+	8+
	6	8+	8+
Magnesium - Foreign material (less dense)	1	1	1
	2	2	2
	3	3	3
	4	4	4
	5	7	7
	6	7	7
	7	8	8+

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.

TABLE VIII (Continued)

	NAVAER 00-15PC-504 and ASTM E98	ASTM E155	
		1/4 in.	3/4 in.
Magnesium - Foreign material (more dense)	1	3	2
	2	3	3
	3	5	4
	4	8+	8+
Magnesium - Microshrinkage sponge	1	1	1
	2	2	3
	3	3	4
	4	3	4
	5	3	4
	6	5	6
	7	6	8
	8	8	8+
Magnesium - Microshrinkage feathery	1	1	1
	2	2	3
	3	3	4
	4	3	4
	5	4	5
	6	7	7
	7	7	8
	8	8	8+

Custodians:
Army - MR
Navy - AS
Air Force - 11

Preparing activity:
Navy - AS

Project No. NDTI-0012

Review activities:
Army - MR, MI, MU
Navy - AS, OS
Air Force - 23,

User activities:
Army -
Navy -
Air Force - 69, 79, 99

Review/user information is current as of date of this document. For future coordination of changes to this document, draft circulation should be based on the information in the current DODISS.

Source: https://assist.dla.mil -- Downloaded: 2026-10-17T06:03Z
Check the source to verify that this is the current version before use.