INCH-POUND

MIL-C-82827(OS)
29 December 1989
SUPERSEDING
WS 21848
8 November 1983

MILITARY SPECIFICATION

COMPOUND, ANTIOXIDANT

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification defines the requirements for one type of antioxidant compound, referred to herein as the antioxidant (see 6.1).

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards and handbooks. The following specifications, standards and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commanding Officer, Naval Ordnance Station, Standardization Branch (3730), Indian Head, MD 20640-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 1340

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

STANDARDS

FEDERAL

FED-STD-313 Material Safety Data, Transportation Data and Disposal Data for Hazardous Materials Furnished to Government Activities

MILITARY

MIL-STD-129 Marking for Shipment and Storage

(Unless otherwise indicated, copies of federal and military specifications, standards, and handbooks are available from: Military Specifications and Standards, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094).

2.1.2 **Other Government documents, drawings, and publications.** The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

CODE OF FEDERAL REGULATIONS (CFR)

49 CFR 100-199 Transportation

(Application for copies of CFRs should be addressed to the Superintendent of Documents, U. S. Government Printing Office, Washington, D.C. 20402-0001.)

2.2 **Non-Government publications.** The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN TRUCKING ASSOCIATION, INC.

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Asso-ciation, Inc., Attn: Traffic Dept., 2200 Mill Road, Alexandria, VA 22314-4677.)

NATIONAL RAILROAD FREIGHT COMMITTEE

Uniform Freight Classification (UFC) 6000

(Application for copies should be addressed to the National Railroad Freight Committee, 222 South Riverside Plaza, Suite 1120, Chicago, IL 60606-5945.)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample shall be subjected to first article inspection (see 6.3) in accordance with 4.3.

3.2 Material. The material shall be 2,2-methylene bis (4-methyl, 6-tert-butylphenol) antioxidant compound.

3.3 Chemical and physical properties. Chemical and physical properties of the antioxidant shall conform to the requirements specified in table I.

TABLE I. Chemical and physical properties.

Property	Limits	
	Minimum	Maximum
Melting point range, degrees Celsius (^{o}C)	120	130
Hydroxyl content, equivalent/100 grams (eq/100g)	0.55	0.62

3.4 Shelf life. The antioxidant shall have an unlimited shelf life after date of acceptance.

3.5 Safety.

3.5.1 Toxic products and formulations. The material shall have no adverse effect on the health of personnel when used for its intended purpose. Questions pertinent to this effect shall be referred by the contracting activity to the appropriate departmental medical service who will act as an advisor to the contracting agency (see 4.1.2).

3.5.2 Material Safety Data Sheet (MSDS). The contractor shall prepare and submit a MSDS in accordance with FED-STD-313 as specified in the contract (see 6.4).

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

3.6 Workmanship. Workmanship shall be such that the antioxidant is uniform in appearance and free from visible contamination.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.1.2 Toxicological product formulations. The contractor shall have the toxicological product formulations and associated information available for review by the contracting activity to evaluate the safety of the material for the proposed use.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

a. First article inspection (see 4.3).

b. Quality conformance inspection (see 4.4).

4.3 First article inspection. First article inspection shall consist of the quality conformance inspections (see 4.4). Failure to meet all of the requirements specified herein shall be cause for rejection of the first article sample.

4.4 Quality conformance inspection. Quality conformance inspection shall consist of the examination and tests specified in table II.

4.4.1 Sampling for inspection.

4.4.1.1 Lot. For inspection purposes, a lot shall consist of all the antioxidant subject to inspection at one time from one of the following:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

a. A single batch (see 6.5.1).

b. A continuous process (see 6.5.2).

c. A uniform blend of batches or a uniform blend of portions from a continuous process.

TABLE II. First article and quality conformance inspections.

Examination and tests	Requirement	Test method
Visual examination	3.6 and section 5	4.5.1
Melting point test	3.3	4.5.2
Hydroxyl equivalent test	3.3	4.5.3

4.4.1.2 Selection of sample containers. Sample containers of the antioxidant shall be selected at random from each lot in accordance with table III.

TABLE III. Sampling for inspection.

Number of containers in the lot	Number of sample containers to be selected for inspection
1-3	All
4-40	3
41-65	4
66-110	5
111-180	7

4.4.1.3 Sample material. Sufficient samples shall be selected at random from each sample container to perform all the inspections specified in 4.5.1 through 4.5.3. Samples shall be combined and blended to form three composite samples. An individual single sample shall not be split between composites, except where a lot consists of less than three containers. A single determination of each quality characteristic listed in table I shall be performed on each of the three composite samples independently. When a lot consists of less than three containers, three samples shall be taken from each container. The sample portions thus obtained shall be grouped and blended to form three composite samples. The results of each test shall meet the requirements of table I. Failure of any composite sample to meet any requirement shall be cause for rejection of the lot.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

4.5 Methods of inspection. The following inspection methods shall be used. Unless otherwise specified in the method, all weights, volumes, temperatures, and times shall be measured to the nearest specified unit or decimal.

NOTE: Reagent grade chemicals shall be used for chemical reactions in the conduct of all inspections defined herein. Solvents and indicators may be commercial nonreagent grade materials.

4.5.1 Visual examination. Each sample shall be visually examined for conformance to the requirements specified in 3.6 and section 5.

4.5.2 Melting point test. Melting point shall be determined in accordance with the following:

a. Force a small amount of sample into a clean, dry, melting point capillary tube (closed at one end). Pack sample into lower 3 millimeters (mm) of tube.

b. Place capillary tube in transparent mineral oil or silicone oil bath equipped with suitable thermometer.

c. Rapidly heat bath to about 10°C below expected melting point, then adjust heating rate to 1°C per minute until melting point is reached.

d. Record melting point to nearest °C.

4.5.3 Hydroxyl content test. Hydroxyl content shall be determined in accordance with the following:

a. Prepare acetylating reagent by adding 3.2 milliliters (ml) of 72 percent perchloric acid to 200 ml of ethyl acetate in 250-ml glass-stoppered flask; pipet 8.0 ml of acetic anhydride into flask and allow it to stand at room temperature for at least 30 minutes. Cool contents of flask to 5°C, and add 40 ml of cold acetic anhydride. Keep flask at 5°C for 1 hour, then allow reagent to come to room temperature. This material is stable for at least 2 weeks.

b. Weigh, to nearest 0.1 mg, a 0.8 to 1.2 g sample in a 125-ml Erlenmeyer flask, and pipet into it exactly 5 ml of acetylating reagent. Swirl flask until sample is dissolved.

c. Allow reaction to proceed for 10 minutes at room temperature. Add 2 ml of water, and swirl mixture; then add 25 ml of 3:1 pyridine-water solution. Allow flask to stand for 10 minutes at room temperature.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

d. Titrate with standard 0.5 normal (N) potassium hydroxide (KOH) in methanol, using thymol blue indicator. Run at least three blank determinations.

e. Calculation: $OH = \frac{(B - V) \times N}{10 w}$

Where: OH = hydroxyl content (equivalent/100 g)

B = volume of KOH to titrate blank, ml

V = volume of KOH to titrate sample, ml

N = normality of KOH

w = sample weight, g

10 = conversion factor (milliequivalents/gram to equivalents/100 g)

g. Record hydroxyl content to nearest 0.01 equivalent/100 g.

4.6 **Inspection of packaging.** The antioxidant containers and container markings shall be visually examined to verify conformance to section 5.

5. PACKAGING

5.1 **Level C.** Unless otherwise specified in the contract or order (see 6.2), packaging shall be level C as specified herein.

5.1.1 **Level C.** The antioxidant shall be packaged conforming to Uniform Freight Classification, National Motor Freight Classification, 49 CFR 171-178, or to other carrier rules and regulations as applicable to the mode of transportation. Containers in the same shipment shall be of the same size and of such construction and materials that the antioxidant will be adequately protected against loss, contamination, deterioration and damage during shipment from the supply source to the first receiving activity..

5.2 **Marking.**

5.2.1 **Standard marking.** In addition to any special marking required by the contract or order (see 6.2), interior and exterior containers shall be marked in accordance with MIL-STD-129.

5.2.2 **Special marking.** In addition to the marking requirements of 5.2.1, each container marking shall include the following information:

a. Title, number and date of this specification.

b. Manufacturer's name and address.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

c. Material trade name and identification.

d. Net weight of contents.

e. Shelf life expiration date.

f. Lot number and date of quality conformance inspection (see 3.4).

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The antioxidant specified herein is intended for use in the manufacture of propellant and liner for the Standard Missile Mark 104 Dual Thrust Rocket Motor.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number and date of this specification.

b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1, 2.1.2 and 2.2).

c. Whether first article is required (see 3.1 and 6.3).

d. Material Safety Data Sheets (see 3.5.2 and 6.6).

e. Packaging required if other than as specified in 5.1.

f. Special marking if other than as specified in 5.2.2.

6.3 First article. When first article inspection is required, the contracting officer should provide specific guidance to offerors on the material to be inspected. The material should be a first article sample and should consist of a quantity of the release compound sufficient to perform all of the inspections specified in 4.3. The first article sample should be packaged and marked as specified in section 5. The contracting officer should include specific instructions in acquisition documents regarding arrangements for examinations, approval of first article test results and disposition of first articles. Invitations for bids should provide that the Government reserves the right to waive the requirement for samples for first article inspection to those bidders offering a product which has been previously acquired or tested by the Government, and that bidders offering such products, who wish to rely on such production or test, must furnish evidence with the bid that prior Government approval is presently appropriate for the pending contract.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

6.4 Material Safety Data Sheet (MSDS). MSDS requirements are applicable to this specification and should be specified in the contract as required by the Federal Acquisition Regulation (FAR), Part 23, Subpart 23.3. Contracting officers will identify those activities requiring copies of completed MDSDs prepared in accordance with FED-STD-313. The pertinent Government mailing addresses for submission of data are listed in FED-STD-313.

6.5 Definitions.

6.5.1 Batch. A batch is that amount of antioxidant made as one unit in the manufacturing process.

6.5.2 Continuous process. A continuous process is an uninterrupted process of manufacture from which, in one unbroken flow, the material is accumulated for a lot.

6.6 Subject term (key word) listing.

Rocket Motor, Dual Thrust, Mk 104
Standard Missile

Preparing Activity:
NAVY-OS
(Project 1340-N805)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-A-82827	2. DOCUMENT DATE (YYMMDD) 29 December 1989

3. DOCUMENT TITLE
ANTIOXIDANT COMPOUND

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME *(Last, First, Middle Initial)*	b. ORGANIZATION	
c. ADDRESS *(Include Zip Code)*	d. TELEPHONE *(Include Area Code)* (1) Commercial (2) AUTOVON *(If applicable)*	7. DATE SUBMITTED *(YYMMDD)*

8. PREPARING ACTIVITY NAVAL ORDNANCE STATION (CODE 3730) INDIAN HEAD, MD 20640-5000

a. NAME	b. TELEPHONE *(Include Area Code)* (1) Commercial (2) AUTOVON
c. ADDRESS *(Include Zip Code)*	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 2026-10-23 07:282
Check the source to verify that this is the current version before use.