INCH-POUND

MIL-R-82844(OS)
5 February 1990
SUPERSEDING
WS 25354
16 August 1985

MILITARY SPECIFICATION

RUBBER, POLYISOPRENE (NON-ASBESTOS)

This specification is approved for use by the Naval Sea Systems Command, Department of the Navy and is available for use by all Departments and Agencies of the Department of Defense.

1. SCOPE

1.1 Scope. This specification covers four types of Kevlar filled polyisoprene rubber (non-asbestos) material in the uncured state.

1.2 Classification. The polyisoprene rubber shall be of the following types as specified (see 6.2):

Type I:	0.030-inch-thick material, calendered (see 6.5.1)
Type II:	0.060-inch-thick material, calendered
Type III:	0.100-inch-thick material, calendered
Type IV:	Extruded (see 6.5.2)

2. APPLICABLE DOCUMENTS

2.1 Government documents.

2.1.1 Specifications, standards and handbooks. The following specifications, standards and handbooks form a part of this document to the extent specified herein. Unless otherwise specified, the issues of these documents are those listed in the issue of the Department of Defense Index of Specifications and Standards (DODISS) and supplement thereto, cited in the solicitation (see 6.2).

Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commanding Officer, Naval Ordnance Station, Standardization Branch (3730), Indian Head, MD 20640-5000, by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.

AMSC N/A FSC 9320

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

SPECIFICATIONS

FEDERAL

L-P-378 Plastic Sheet and Strip, Thin Gage, Polyolefin

STANDARDS

FEDERAL

FED-STD-601 Rubber: Sampling and Testing

MILITARY

MIL-STD-129 Marking for Shipment and Storage

(Unless otherwise indicated, copies of federal and military specifications, standards and handbooks are available from: Military Specifications and Standards, Bldg. 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.)

2.1.2 Other Government documents, drawings, and publications. The following other Government documents, drawings, and publications form a part of this document to the extent specified herein. Unless otherwise specified, the issues are those cited in the solicitation.

CODE OF FEDERAL REGULATIONS (CFR)

49 CFR 100-199 Transportation

(Application for copies of CFRs should be addressed to the Superintendent of Documents, U.S. Government Printing Office, Washington, D.C. 20402-0001.)

2.2 Non-Government publications. The following documents form a part of this document to the extent specified herein. Unless otherwise specified, the issues of the documents which are DoD adopted are those listed in the issue of the DODISS cited in the solicitation. Unless otherwise specified, the issues of documents not listed in the DODISS are the issues of the documents cited in the solicitation (see 6.2).

AMERICAN TRUCKING ASSOCIATION, INC.

National Motor Freight Classification

(Application for copies should be addressed to the American Trucking Association, Inc., Attn: Traffic Dept., 2200 Mill Road, Alexandria, VA 22314-4677.)

NATIONAL RAILROAD FREIGHT COMMITTEE

Uniform Freight Classification (UFC) 6000

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

(Application for copies should be addressed to the National Railroad Freight Committee, 222 South Riverside Plaza, Suite 1120,Chicago, IL 60606-5945.)

AMERICAN SOCIETY FOR TESTING AND MATERIALS (ASTM)

ASTM D 412 Rubber Properties in Tension (DoD adopted)

(Application for copies should be addressed to the American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103-1187.)

(Non-Government standards and other publications are normally available from the organizations that prepare or distribute the documents. These documents also may be available in or through libraries or other informational services.)

2.3 Order of precedence. In the event of a conflict between the text of this document and the references cited herein, the text of this document takes precedence. Nothing in this document, however, supersedes applicable laws and regulations unless a specific exemption has been obtained.

3. REQUIREMENTS

3.1 First article. When specified (see 6.2), a sample of the polyisoprene rubber shall be subjected to first article inspection (see 6.4) in accordance with 4.3.

3.2 Product characteristics.

3.2.1 Dimensions and tolerances.

3.2.1.1 Types I, II and III. The width of Types I, II, and III polyisoprene rubber shall be as specified in the contract or order (see 6.2). The thickness of the three types of material shall be as specified in 1.2. Thickness tolerance of each type of material shall be $\pm$ 10 percent of the specified thickness, except that the thickness tolerance shall not apply within 1.5 inches of each edge of the roll and within 2 yards of each end of the roll.

3.2.1.2 Type IV. Dimensions and tolerances for Type IV polyisoprene rubber shall be as specified in the contract or order (see 6.2).

3.2.2 Release agent. The polyisoprene rubber, during processing and packaging, shall be kept free from any type of release agent, except that a commercially available, color contrasted polyethylene film conforming to L-P-378, Type I, Class 1, Grade C, Finish 1 (0.003 inch thick), with a smooth surface (not embossed) shall be used to separate layers in the roll or layers between stacked coils of Type IV polyisoprene rubber.

3.2.3 Defects. The cumulative area of Type I, II, or III polyisoprene rubber in any roll containing defects such as wrinkles, voids, delaminations,

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

and nonhomogeneous material shall be not more than 10 percent of the area of the material in the roll. The area within 1.50 inches of each edge of the roll and within 2 yards of each end of the roll shall be excluded. The Type IV polyisoprene rubber may have a rough and ragged appearance which shall be acceptable, but it shall not contain defects such as nonhomogeneous material in more than 10 percent of the material in the roll or coil. Any defects within 24 inches of each other, measure parallel to the edge of the roll or coil, shall be considered as one continuous defect when determining percentage of defective area in the roll or coil.

3.3 Chemical and physical properties.

3.3.1 Chemical properties. Chemical properties of polyisoprene rubber (all types) shall conform to table I.

TABLE I. Chemical properties of unvulcanized polyisoprene rubber.

Property	Minimum	Maximum
Volatile content, percent (%)	---	3.3
Ash content, %	24.2	26.8
Flow index, inches @ 4000 pound-force per square inch (psi) @ 2500 psi	 3.2 2.2	 --- ---

3.3.2 Physical properties. Physical properties of vulcanized polyisoprene rubber (all types) shall conform to table II. A sample from each batch (see 6.5.3) of the Type IV polyisoprene rubber shall be debulked by forming or calendering as applicable prior to vulcanization for the testing of physical properties.

3.3.3 Storage and shipment. The polyisoprene rubber material shall be protected from contamination and direct sunlight at all times. Storage and shipment of the polyisoprene rubber material shall be at a temperature below 10°C except that after cure agent addition and before calendering or extruding, the storage temperature may be as high as 32°C for as long as 1 week. Caution shall be exercised to prevent contamination to unpackaged (not enclosed in waterproof liner) polyisoprene rubber upon removal from storage temperatures below 4°C.

3.3.4 Shelf life. When stored in accordance with 3.3.3, the polyisoprene rubber shall have a shelf life of not less than 6 months from date of calendering or extruding. The shelf life may be extended for 6-month intervals after retesting for conformance to flow index requirements in table I. Unless otherwise specified in the contract or purchase order (see 6.2), the polyisoprene rubber submitted to the Government for acceptance shall have not less than 5 months shelf life remaining.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

TABLE II. Physical properties of vulcanized polyisoprene rubber at 25 ± 3°C.

Property	Types I, II, and III		Type IV	
	Min	Max	Min	Max
Specific gravity, 25°/4°C	1.14	1.18	1.14	1.18
Hardness, Shore A	69	96	69	96
Tensile strength, w/grain (see 6.5.5), psi	1000	---	---	---
Tensile strength, across grain (see 6.5.6), psi	820	---	---	---
Tensile strength ratio (see 6.5.7)	0.8	---	---	---
Ultimate elongation, across grain, %	250	---	---	---

3.4 Workmanship. Workmanship shall be such that the polyisoprene rubber is uniform in appearance, clean and free from the defects as specified in 3.2.3.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection. Unless otherwise specified in the contract or purchase order, the contractor is responsible for the performance of all inspection requirements (examinations and tests) specified herein. Except as otherwise specified in the contract or purchase order, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to ensure supplies and services conform to prescribed requirements.

4.1.1 Responsibility for compliance. All items shall meet all requirements of sections 3 and 5. The inspection set forth in this specification shall become a part of the contractor's overall inspection system or quality program. The absence of any inspection requirements in the specification shall not relieve the contractor of the responsibility of ensuring that all products or supplies submitted to the Government for acceptance comply with all requirements of the contract. Sampling inspection, as part of manufacturing operations, is an acceptable practice to ascertain conformance to requirements, however, this does not authorize submission of known defective material, either indicated or actual, nor does it commit the Government to accept defective material.

4.2 Classification of inspections. The inspection requirements specified herein are classified as follows:

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

a. First article inspection (see 4.3).

b. Quality conformance inspection (see 4.4).

4.3 First article inspection. First article inspection shall consist of the inspections specified in 4.4 except for the inspection of packaging (see 4.5.10). Failure to meet all of the requirements specified herein shall be cause for rejection of the first article sample.

4.4 Quality conformance inspection. Quality conformance inspection shall consist of the inspections specified in table III.

TABLE III. Quality conformance inspection.

Requirement	Requirement Paragraph	Inspection Method
Dimensions and tolerances	3.2.1	4.5.2
Release agent	3.2.2	4.5.1
Defects	3.2.3	4.5.1
Chemical properties:		
Volatile content	3.3.1	4.5.3
Ash content	3.3.1	4.5.4
Flow index	3.3.1	4.5.5
Physical properties:		
Specific gravity	3.3.2	4.5.6
Hardness	3.3.2	4.5.7
Tensile strength & ratio	3.3.2	4.5.8
Ultimate elongation	3.3.2	4.5.9
Storage and shipment	3.3.3	4.5.1 & 4.5.10
Shelf life	3.3.4	4.5.5
Workmanship	3.4	4.5.1
Packaging	Section 5	4.5.10

4.4.1 Sampling.

4.4.1.1 Method. Selection of samples shall be in accordance with random sampling methods specified in the "Sampling and Acceptance Procedures" section of FED-STD-601. Samples shall be taken from each lot of material, packaged, and identified as follows:

a. Samples:

(1) Types I, II, and III: Beginning not less than 2 yards from the end of the roll, remove sufficient material for tests on samples as specified in 4.4. Indicate direction of the grain on the sample.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

(2) Type IV, Chemical properties: Beginning not less than 2 yards from end of roll or coil, remove sufficient material for tests on samples specified in 4.4.

(3) Type IV, Physical properties: A sufficient amount of material shall be taken from a single batch for tests on samples as specified in 4.4. The sample shall be taken before or after extruding and debulked by forming or calendering into a flat sheet.

b. Wrap the samples in a clean waterproof wrapper that will provide protection from heat and light.

c. The following information shall accompany the sample:

(1) Title, number, and revision letter of this specification.
(2) Material name or identification designation.
(3) Lot number.
(4) Date and time sample taken.
(5) Identity of sample taken.
(6) Roll or coil number.

4.4.1.2 Vulcanized samples. For tests requiring vulcanized specimens, the samples shall be vulcanized at a pressure of 100 ± 10 pound-force per square inch gage (psig) for 2 to 2.5 hours at 107 ± 3°C. Any deviation from these conditions shall require prior approval of the contracting activity.

4.5 Methods of inspection. Inspections shall be performed using apparatus, reagents, and procedures specified herein or equivalents. Alternate inspection methods may be proposed by the contractor but must be approved by the contracting activity prior to use in inspection.

4.5.1 Visual examination. Visual examination shall be made to verify conformance to the requirements of 3.2.2, 3.2.3, 3.3.3 and 3.4.

4.5.2 Dimensional examination. The dimensions of the unvulcanized polyisoprene rubber (all types) shall be determined at a material temperature of 25 ± 6°C. The thickness shall be determined by a micrometer or comparator graduated to 0.001 inch, having an anvil or pressure foot of 0.375-inch diameter, and exerting a total force of 3 ± 1 ounces.

4.5.3 Volatile content. Volatile content shall be determined in accordance with the following:

a. Weigh duplicate specimens of from 10 to 15 grams to the nearest 0.001 gram.

b. Place the specimens in a vacuum oven at 107 ± 3°C with an absolute pressure not greater than 74 millimeters of mercury. The specimens shall remain in the oven for not less than 4 hours.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

c. Remove and reweigh each specimen.

d. Calculate the volatile content of each specimen as follows:

$$\text{Percent volatile} = \frac{(B - A) \times 100}{B}$$

Where: A = weight of specimen after heating, g

B = weight of specimen prior to heating, g

e. Record the average volatile content of the duplicate specimens to the nearest 0.1 percent.

4.5.4 Ash content. Ash content shall be determined in accordance with the following:

a. Weight duplicate specimens of from 6 to 8 grams to the nearest 0.001 gram.

b. Place the specimens in a muffle furnace at 816 ± 28°C for not less than 60 minutes.

c. Remove and reweigh each specimen.

d. Calculate the ash content of each specimen as follows:

$$\text{Percent ash} = \frac{A \times 100}{B}$$

Where: A = weight of specimen after heating, g

B = weight of specimen prior to heating, g

e. Record the average ash content of the duplicate specimens to the nearest 0.1 percent.

4.5.5 Flow index.

4.5.5.1 Apparatus. Garlock Flow Index Machine, or equivalent, with a 0.25-inch-diameter orifice sprue shall be used to perform the test.

4.5.5.2 Flow index measurements. Flow index shall be determined in accordnace with the following:

a. Prepare duplicate specimens of the polyisoprene rubber to a diameter of 1.12 ± 0.22 inches and a thickness of 0.5 ± 0.1 inch.

b. Test one specimen at 4000 psi and one specimen at 2500 psi.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

b. Test one specimen at 4000 psi and one specimen at 2500 psi.

c. Place specimen in the pressure changer of the flow index machine and test at applicable pressure for 5 minutes ± 15 seconds at 149 ± 6°C.

d. Measure each of the 4 legs of the tested specimen to the nearest 0.05 inch. Repeat test if the four readings on a single specimen do not agree within 20 percent.

e. Record the average value of the four readings on each specimen to the nearest 0.05 inch.

4.5.6 Specific gravity. Specific gravity shall be determined in accordance with FED-STD-601, method 14011. The average specific gravity at 25°C/4°C shall be recorded to the nearest 0.01.

4.5.7 Hardness. Hardness shall be determined in accordance with FED-STD-601, method 3021.

4.5.8 Tensile strength. Tensile strength shall be determined in accordance with FED-STD-601, method 4111, die Type III, with the exception that the average of values obtained shall be recorded to the nearest 10 psi, and that two types of specimens shall be prepared from the calendered samples. One type shall be such that the material grain direction is oriented in the length direction of the specimen for with-grain testing. The other type shall be such that the material grain direction is oriented in the width direction of the specimen for across-grain testing.

4.5.9 Ultimate elongation. Using the same specimens that were used in determining tensile strength (see 4.5.8), ultimate elongation shall be determined in accordance with ASTM D 412, except that the test temperature shall be 25 ± 3°C and the average shall be recorded to the nearest 10 percent. The elongation shall be measured by an electrical extensometer with provisions for indicating 10 percent strain increments on the load versus crosshead displacement chart.

4.6 Inspection of packaging. The containers and container markings shall be visually examined to verify compliance with section 5.

5. PACKAGING

5.1 Preservation. Unless otherwise specified in the contract or order (see 6.2), preservation shall be level C as specified herein.

5.1.1 Level C. The calendered or extruded polyisoprene rubber shall be rolled on a spool or in a flat coil with a separator as specified in 3.2.2. Polyisoprene rubber shall be unit packed so the weight of the material is supported to prevent distortion during shipment and storage. The inside diameter of the roll or coil shall not be less than 3 inches. The roll or coil

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

shall be individually unit packed in a sealed waterproof liner such as polyethylene. The maximum weight of the roll or coil shall be 100 pounds.

5.2 Packing. Unless otherwise specified in the contract or order (see 6.2), packing shall be level C as specified herein.

5.2.1 Level C. The polyisoprene rubber shall be packed to afford adequate protection against loss, contamination, deterioration, and damage during shipment from the supply source to the first receiving activity and during storage under the shelf life period and conditions specified in 3.3.3 and 3.3.4. Containers in the same shipment shall be of the same size. The packing shall conform to UFC 6000, National Motor Freight Classification, 49 CFR 171-178, or to other carrier rules and regulations as applicable to the mode of transportation.

5.3 Marking.

5.3.1 Standard marking. In addition to any special marking required by the contract or order (see 6.2) or herein, interior and exterior containers shall be marked in accordance with MIL-STD-129.

5.3.2 Special marking.

5.3.2.1 Roll or coil marking. Unless otherwise specified in the contract or order (see 6.2), each roll or coil shall have a tag attached to it showing the contractor's lot and roll or coil numbers.

5.3.2.2 Container marking. In addition to the marking requirements of 5.3.1, each container marking shall include the following applied in accordance with MIL-STD-129.

a. Title, number, and date of this specification.

b. Shelf life and shelf life extension (see 3.3.4).

e. Storage and shipment conditions (see 3.3.3).

6. NOTES

(This section contains information of a general or explanatory nature that may be helpful, but is not mandatory.)

6.1 Intended use. The polyisoprene rubber is intended for use in the manufacture of the nozzle components of the Mk 104 Standard Missile Dual Thrust Rocket Motor.

6.2 Acquisition requirements. Acquisition documents must specify the following:

a. Title, number and date of this specification.

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

b. Issue of DODISS to be cited in the solicitation, and if required, the specific issue of individual documents referenced (see 2.1.1 2.1.2 and 2.2).

c. Type(s) of polyisoprene rubber required (see 1.2).

d. Whether first article inspection is required (see 3.1 and 6.4).

e. Width of Types I, II, and III calendered sheet (see 3.2.1.1).

f. Dimensions and tolerances of Type IV extrusions (see 3.2.1.2).

g. Remaining shelf life if other than as specified in 3.3.4.

h. Preservation, if other than as specified in 5.1.

i. Packing, if other than as specified in 5.2.

j. Special marking (see 5.3.1).

6.3 Consideration of data requirements. The following data requirements should be considered when this specification is applied on a contract. The applicable Data Item Descriptions (DID's) should be reviewed in conjunction with the specific acquisition to ensure that only essential data are requested/ provided and that the DID's are tailored to reflect the requirements of the specific acquisition. To ensure correct contractual application of the data requirements, a Contract Data Requirements List (DD Form 1423) must be prepared to obtain the data, except where DOD FAR Supplement 27.475-1 exempts the requirement for a DD Form 1423.

Reference paragraph	DID Number	DID Title	Suggested Tailoring
Appendix, 10.1	DI-MISC-80678	Certified/Data Report	See appendix

The above DID was cleared as of the date of this specification. The current issue of DOD 5010.12-L, Acquisition Management Systems and Data Requirements Control List (AMSDL), must be researched to ensure that only current, cleared DID's are cited on the DD Form 1423.

6.4 First article. When first article inspection is required, the contracting officer should provide specific guidance to offerors whether the item(s) should be a preproduction sample, a first article sample, a first production item, a sample selected from the first production items, or a standard production item from the contractor's current inventory (see 3.1), and the number of items to be tested as specified in 4.3. The contracting officer should also include specific instructions in acquisition documents regarding arrangements for examinations, approval of first article test results, and disposition of first articles. Invitations for bids should provide that the

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

Government reserves the right to waive the requirement for samples for first article inspection to those bidders offering a product which has been previously acquired or tested by the Government, and that bidders offering such products, who wish to rely on such production or test, must furnish evidence with the bid that prior Government approval is presently appropriate for the pending contract. Bidders should not submit alternate bids unless specifically requested to do so in the solicitation.

6.5 Definitions.

6.5.1 Calender. Calender is the process by which the material from a single batch is rolled or pressed into sheets for the required width and thickness.

6.5.2 Extrude. Extrude is the process by which the polyisoprene rubber is formed through a die to specified dimensions.

6.5.3 Batch. A batch is that quantity of material produced in one operation when all ingredients are combined, but before calendering or extruding into finished sheets or shapes. More than one lot may be made from a single batch.

6.5.4 Lot. A lot is that quantity of material processed in a single batch (see 6.5.3), calendered or extruded in one continuous work period, and of one thickness.

6.5.5 With grain. With grain is the direction of rolling or calendering of the polyisoprene rubber.

6.5.6 Across grain. Across grain is the perpendicular direction of rolling or calendering of the polyisoprene rubber.

6.5.7 Tensile strength ratio. Tensile strength ratio is the tensile strength with grain direction divided by the tensile strength across grain direction.

6.6 Suggested source of supply. The following material has been found to meet the requirements of this specification. This is given for information only and is not restrictive. Rubber Insulation No. 44765 manufactured by Uniroyal Plastics Products (Commercial and Government Entity (CAGE) Code 00333) has met the requirements of this specification.

6.7 Subject term (key word) listing.

Rocket Motor, Dual Thrust, Mk 104
Standard Missile

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

APPENDIX

CERTIFICATION DATA/REPORT

TECHNICAL CONTENT REQUIREMENTS

10. SCOPE

10.1 Scope. This appendix details the technical content and procedures for the control of certification data/report covering the contractor's material and process control for the manufacture of the polyisoprene rubber. This appendix is a mandatory part of the specification when DI-MISC-80678 is cited in the contract or order (see 6.3).

20. APPLICABLE DOCUMENTS

This section is not applicable to this appendix.

30. TECHNICAL CONTENT REQUIREMENTS

30.1 Material and process control.

30.1.1 Material and process certification data. The contractor shall prepare certification data, defining the preparation of the polyisoprene rubber. The data shall include, but not be limited to, composition, procedures and methods for handling and weighout of ingredients, mix cycle, calendering, extruding, transfer and storage of unvulcanized polyisoprene rubber, time, temperature and humidity limits, equipment used, and process and quality controls. Acceptability of the process and equipment shall be determined by conformity of the polyisoprene rubber to the requirements of this specification.

30.1.2 Process approval. The data defining the composition and detailed process selected by the contractor shall be identified with an assigned number. Any change to the identified process, after first article inspection with 4.3 shall be submitted to the contracting activity for written approval as specified in the contract or order (see 6.3). Upon receipt of written approval, the contractor shall incorporate the approved changes and reidentify the data reflecting the changes. Request for changes shall be accompanied by supporting data.

Preparing Activity:
NAVY-OS
(Project 9320-N007)

Source: https://assist.dla.mil -- Downloaded: 2026-10-23T07:28Z
Check the source to verify that this is the current version before use.

STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

INSTRUCTIONS

1. The preparing activity must complete blocks 1, 2, 3, and 8. In block 1, both the document number and revision letter should be given.
2. The submitter of this form must complete blocks 4, 5, 6, and 7.
3. The preparing activity must provide a reply within 30 days from receipt of the form.

NOTE: This form may not be used to request copies of documents, nor to request waivers, or clarification of requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

I RECOMMEND A CHANGE:	1. DOCUMENT NUMBER MIL-R-82844	2. DOCUMENT DATE (YYMMDD) 5 February 1990

3. DOCUMENT TITLE
RUBBER, POLYISOPRENE (NON-ASBESTOS)

4. NATURE OF CHANGE *(Identify paragraph number and include proposed rewrite, if possible. Attach extra sheets as needed.)*

5. REASON FOR RECOMMENDATION

6. SUBMITTER

a. NAME (Last, First, Middle Initial)	b. ORGANIZATION	
c. ADDRESS (Include Zip Code)	d. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON (If applicable)	7. DATE SUBMITTED (YYMMDD)

8. PREPARING ACTIVITY NAVAL ORDNANCE STATION (CODE 3730) INDIAN HEAD, MD 20640-5000

a. NAME	b. TELEPHONE (Include Area Code) (1) Commercial (2) AUTOVON
c. ADDRESS (Include Zip Code)	IF YOU DO NOT RECEIVE A REPLY WITHIN 45 DAYS, CONTACT: Defense Quality and Standardization Office 5203 Leesburg Pike, Suite 1403, Falls Church, VA 22041-3466 Telephone (703) 756-2340 AUTOVON 289-2340

Source: https://assist.dla.mil -- Downloaded: 2020-10-29T07:28Z
Check the source to verify that this is the current version before use.