MIL-P-46230C(AR)
5 November 1981
SUPERSEDING
MIL-P-46230B (AR)
6 November 1972

MILITARY SPECIFICATION

# PROPELLANT M6 FOR USE IN CHARGE PROPELLING, 175MM, M199 AND M86A2B1

This specification is approved by the U.S. Army Armament Research and Development Command, and is available for use by all Departments and Agencies of the Department of Defense.

## 1. SCOPE

1.1 This specification covers M6 Propellant for use in the M199 and M86A2B1 propelling charges employed with the M437 series projectiles.

1.2 Classification. The propellant shall be Type I, cylindrical multi-perforated grains.

## 2. APPLICABLE DOCUMENTS

2.1 Issues of documents. The following documents of the issue in effect on date of invitation for bids, or request for proposal, form a part of this specification to the extent specified herein.

SPECIFICATIONS

MILITARY

MIL-C-45463 - Charge, Propelling, 175MM, M86A2B1, Loading, Assembling and Packing

MIL-A-48078 - Ammunition, Standard Quality Assurance Provisions, General Specification for

STANDARDS

MILITARY

MIL-STD-414 - Sampling Procedures and Tables for Inspection by Variables for Percent Defective

FSC: 1376

**Beneficial comments (recommendations, additions, deletions) and any pertinent data which may be of use in improving this document should be addressed to: Commander, US Army Armament Research and Development Command, Attn. DRDAR-QA, Dover, New Jersey 07801 by using the self-addressed Standardization Document Improvement Proposal (DD Form 1426) appearing at the end of this document or by letter.**

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

MIL-STD-652 - Propellants, Solid, for Cannons, Requirements and Packing

DRAWINGS (see 6.3)

U.S. ARMY ARMAMENT RESEARCH AND DEVELOPMENT COMMAND

8837906 - Zone No. 2 Loading Assembly
8837908 - Zone No. 3 Loading Assembly
9276581 - Increment No. 1 Loading Assembly
9276582 - Increment No. 2 Loading Assembly

2.2 Other publications. The following documents form a part of this specification to the extent specified herein. Unless otherwise indicated, the issue in effect on date of invitation for bids or request for proposal shall apply.

AMC PAMPHLET 706-114

Experimental Statistics, Section 5, Tables

(Copies of specifications, standards, drawings and publications required by contractors in connection with specific procurement functions should be obtained from the procuring activity or as directed by the contracting officer.)

3. REQUIREMENTS

3.1 Material. The propellant shall be M6 Type I, conforming to the requirements of MIL-STD-652. The data obtained from zone 2 of the M86A2B1 charge shall be used for the assessment of the M199 charge.

3.2 Ballistic assessment requirements. The propellant, when fired in the M113A1 cannon and with the projectile (M437A2) for which the propellant was manufactured, shall comply with the requirements of Table I when tested at 70°F and standard weapon conditions.

3.3 Ballistic uniformity requirements. The propellant, when fired in the M113A1 cannon at the established charge weight, with the projectile (M437A2) for which it was manufactured, shall comply with the following requirements when tested as specified in 4.5.1. All M86A2B1 charges shall be manufactured in accordance with MIL-C-45463.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

3.3.1 Uniformity of velocity - The standard deviation of velocity for the lot at 70°F shall not exceed the requirements of Table II.

TABLE I

Velocity and Pressure at 70°F

| Zone | 2 | 3 |
|---|---|---|
| Charge | M199/M86A2B1 | M86A2B1 |
| Velocity, fps | 2310 | 3000 |
| Pressure, psi | N/A | 48,400 |

TABLE II

Velocity Uniformity at 70°F

| Zone | 2 | 3 |
|---|---|---|
| Charge | M199/M86A2B1 | M86A2B1 |
| Uniformity of Velocity, fps | N/A | 7.9 |

3.3.2 Average pressure. At standard weapon conditions, the propellant shall not exceed the average pressure specified in Table III.

TABLE III

Maximum Average Pressure at 70°F

| Zone | 2 | 3 |
|---|---|---|
| Charge | M199/M86A2B1 | M86A2B1 |
| Average pressure, psi | N/A | 48,400 |

3.3.3 Individual maximum pressure (IMP). The propellant shall not produce an individual pressure greater than 58,000 psi at 145°F.

3.4 Initial production. This specification contains provisions for initial production inspection. Requirements for the submission of initial production inspection samples by the contractor shall be as specified in 4.5.1.2.1.

3.5 Preproduction inspection. This specification contains provisions for preproduction inspection. Requirements for the submission of preproduction inspection samples by the contractor shall be as specified in 4.3.1.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

3.6 Workmanship. The best commercial practices shall be used in the formulation of propellant furnished under this specification, and all other applicable documents. The propellant and its standard ingredients shall be protected from the action of direct sunlight and acid fumes. Unless otherwise specified, no reground propellant or nitrocellulose shall be used in the manufacture of propellant procured under this specification.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for inspection and standard quality assurance provisions. Unless otherwise specified herein or in the contract, the provisions of MIL-A-48078 shall apply and are hereby made a part of this detail specification. Unless otherwise specified in the contract, the contractor is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified in the contract, the contractor may use his own or any other facilities suitable for the performance of the inspection requirements specified herein, unless disapproved by the Government. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements.

4.2 Classification of inspections. The following types of inspection shall be conducted on the unit of product:

a. Preproduction Sample Inspection
b. Quality Conformance Inspection

4.3 Preproduction sample (pilot lots). The preproduction sample is intended to provide the necessary information to establish the propellant granulation needed to meet the required ballistic parameters.

4.3.1 Submission. The Contractor shall select three (3) propellant granulations which, from experience, should best fit the requirements of this specification. The contractor shall submit a preproduction sample as designated by the Contracting Officer for evaluation in accordance with 4.3.2, consisting of three (3) pilot lots of 2200 lbs to 2500 lbs each representing the three (3) candidate granulations.

4.3.2 Inspections to be performed. Each of the pilot lots comprising the preproduction sample and submitted in accordance with 4.3.1 may be subjected by the Government to any or all of the requirements of the applicable drawings and specifications.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

4.3.3 Rejection. Government Engineering and Product Assurance personnel and the Contractor shall review the pilot lot test data and shall select a granulation size which best fits the requirements of this specification. The Technical Agency shall notify the Contracting Officer of the selected granulation. The Contractor shall request approval from the Contracting Officer to produce the selected granulation. If none of the pilot lots submitted meets the requirements of this specification, a new preproduction sample shall be submitted in accordance with 4.3.1. All future production lots should be of the same basic granulation.

4.4 Quality conformance inspection

4.4.1 Inspection lot formation. Inspection lots shall comply with the lot formation provisions of MIL-A-48078.

4.4.2 Examination and testing

PRECAUTION - This specification covers sampling and testing of chemical, toxic or explosive materials which are potentially hazardous to personnel. Accordingly, it is emphasized that all applicable safety rules, regulations and procedures must be followed in handling and processing these materials.

4.4.2.1 Sampling for laboratory testing (see 3.1). Each lot of propellant shall be sampled and tested for composition, form, dimensions and chemical/physical properties in accordance with MIL-STD-652.

4.4.2.2 Sampling for ballistic testing (see 3.2). Each lot of propellant shall be sampled for Proving Ground tests in accordance with MIL-STD-652.

4.4.2.3 Charge establishment (see 3.2). If the lot does not meet the applicable requirements, testing shall cease and the Test Director shall immediately notify the procuring activity and US Army Armament Research and Development Command, Dover, NJ 07801, ATTN: DRDAR-LCA-G and DRDAR-QAR-R.

4.4.2.4 Velocity uniformity (70°F) (see 3.3.1). If the product of the factor times the velocity standard deviation of the rounds tested in accordance with 4.5.1.2 exceeds the applicable requirement, apply referral criteria in accordance with 4.5.1.4. If the referral criteria cited do not apply, the lot shall be rejected. The factor, as taken from Table A-21 of



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

AMC Pamphlet 706-114 using the 95 percent upper confidence limits (A.05) and n-1 degrees of freedom, makes allowance for the probability that a standard deviation from a small sample size exceeds the true standard deviation by chance alone. The standard deviation shall be calculated with (n-1) as the devisor in a standard statistical technique equivalent to that shown in MIL-STD-414, Section B, Example B-1.

4.4.2.5 Average pressure (see 3.3.2). If the average pressure obtained exceeds the applicable requirements, apply referral criteria in accordance with 4.5.1.4. If the referral criteria cited do not apply, the lot shall be rejected.

4.4.2.6 Individual maximum pressure (IMP)

4.4.2.6.1 Initial production. If any individual pressure observed during uniformity firings at 145°F after correction for difference between as fired and recommended service charge weight exceeds 58,000 psi, the lot shall be rejected.

4.4.2.6.2 Subsequent production. If any individual pressure observed during the 70°F uniformity series when corrected to standard conditions and recommended charge weight exceeds 58,000 psi minus 75 times the pressure temperature coefficient established during initial production testing, the lot shall be tested at +145°F in accordance with 4.5.1.2.2.

4.5 Test methods and procedures

4.5.1 Proving ground assessments. This test shall be performed at a Government Proving Ground in accordance with the applicable acceptance test procedure using M437A2 projectiles inert loaded within 0.01 lb of an as fired weight of 147.75 lb and fired in an M113A1 cannon with a tube wear no greater than 0.147 inches when measured 64.5 inches from the rear face of the tube. All charges shall be temperature conditioned in a large conditioning box, with adequate air circulation to assure uniform conditioning, at the required temperature for a minimum of 24 hours and assurance will be made that, when fired, the charges are at the conditioning temperature (as indicated by thermocoupled control charges or liquid crystal gages). The following tolerances shall apply to all temperature conditionings: -50°F, + 5°F; 70°F, + 2.5°F; 145°F, -5°F. Copper crusher gages (2) shall be used to measure the maximum chamber pressure of each charge. Velocity coils will be used to measure the muzzle velocity of each charge. Test charges shall be assembled in accordance with MIL-C-45463.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

4.5.1.1 Charge establishment (see Table IV)

4.5.1.1.1 Charge slope method. Three or more groups of charges loaded with selected charge weights of propellant (weights selected should bracket expected service charge weight) shall be conditioned and fired at 70°F. Three calibration charges at each zone shall also be conditioned and fired at 70°F, with the test charges. From the data obtained, a charge weight shall be calculated which will yield the prescribed service velocity (see 3.2). This calculated charge weight shall then be loaded into charges for the uniformity series (see 4.5.1.2.1). The difference between the corrected velocity obtained during the uniformity series and the service velocity shall be compensated for by a final adjustment in charge weight using the slope of the velocity charge weight curve previously established. The resultant will be the recommended charge weight.

4.5.1.1.2 Constant slope method. After ten (10) lots of a given production series have been fired to provide a good knowledge of the propellant characteristics, the charge slope method of assessment may be discontinued and the charge weight determined by the constant slope method. A composite charge weight versus velocity curve can be established from test results generated. This curve can then be used as in 4.5.1.1.1 to calculate the charge weight needed to achieve service velocity. This calculated charge weight is then to be loaded into charges for the uniformity series and final adjustment is to be made as indicated above for the charge slope method (see 4.5.1.1.1). The resultant will be the recommended charge weight.

4.5.1.2 Uniformity (see Table IV)

4.5.1.2.1 Initial production. Thirty (30) charges shall be assembled with the calculated charge weight (see 4.5.1.1.1) of propellant at zone 3 and ten (10) charges at the calculated charge weight (see 4.5.1.1.1) at zone 2. Ten zone 3 charges each shall be conditioned to -50°F, 70°F and 145°F and 10 zone 2 charges at 70°F (as indicated by thermocoupled control charge). Charges fired at 70°F shall be fired alternately with calibration charges and shall be corrected to standard weapon/firing conditions (i.e., the difference between calibration performance under test conditions and standard conditions). Firing results at all temperatures shall be corrected to standard projectile weight (see 4.5.1) and to recommended charge weight conditions (i.e., the difference



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

between calculated (as fired) charge weight and recommended charge weight). The means and standard deviations of the velocities and pressures at all firing temperatures shall be calculated using corrected results. The initial production lots represent the first ten consecutive lots from each manufacturer which have been produced and met the acceptance criteria of this specification.

4.5.1.2.2 Subsequent production. Seven (7) charges each shall be assembled with the calculated charge weight (see 4.5.1.1.2) of propellant at zone 2 and 3. All charges shall be conditioned at 70°F (as indicated by thermocoupled control charge). Charges fired at 70°F shall be fired alternately with calibration charges and shall be corrected to standard weapon/firing conditions (i.e., the difference between calibration performance under test conditions and standard conditions). Firing results shall be corrected to standard projectile weight (see 4.5.1) and to recommended charge weight conditions (i.e., the difference between as fired charge weight and recommended charge weight). The means and standard deviations of the velocities and pressures shall be calculated using corrected results. Throughout production, if 3 consecutive lots fail on first test, testing shall revert back to the initial production plan (see 4.5.1.2.1). If any individual pressures observed at 70°F when corrected to standard conditions and recommended charge weight exceeds 58,000 psi minus 75 times the pressure temperature coefficient established during Initial Production Testing, ten additional charges shall be conditioned and fired at 145°F. If any individual charge at 145°F exceeds 58,000 psi, the lot shall be rejected.

4.5.1.3 Retest criteria. A lot shall be retested whenever any of the following conditions exist or whenever the proving ground deems it necessary.

a. The final adjustment in charge weight exceeds 8.0 ozs of the charge weight used in uniformity firings, retest for uniformity in accordance with 4.5.1.2.

b. If for any reason the Proving Ground considers that test conditions have detrimentally affected the test results, additional charges as required shall be tested.

4.5.1.4 Referral criteria. A test lot shall be referred to the procuring activity for disposition whenever any of the following conditions exist or whenever the proving ground deems it necessary.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

a. Calibration charges fired in any test phase fail to comply with Section 3 of this specification.

b. Calibration correction applied exceeds two percent of the expected muzzle velocity.

c. Calibration components are not available.

d. Number of test or calibration results utilized in calculations is less than specified.

e. Any unusual occurrences during ballistic testing, such as excessive delays between rounds, poor projectile flights, etc. Each such event shall be reported in detail on the applicable firing record.

f. Test lot fails velocity standard deviation or average pressure requirement at 70°F and any extreme test value is an outlier. The following test shall be performed to determine if a single test result is an outlier. With a sample size of 10 at a significance level of 0.05, the critical value ($T_c$) is 0.477. Calculate a test value ($T_t$) as follows:

For Low Outlier

$$T_t = \frac{(X_2 - X_1)}{(X_9 - X_1)}$$

For High Outlier

$$T_t = \frac{(X_{10} - X_9)}{(X_{10} - X_2)}$$

Where:

$X_1$ = test result being tested as low outlier
$X_2$ = test result adjacent to $X_1$, after all the test results are ordered from smallest to largest
$X_9$ = test result adjacent to the largest test result
$X_{10}$ = test result being tested as high outlier

$X_1$ or $X_{10}$ is an outlier if $T_t$ is greater than $T_c$.

With a sample size of 7 at a significance level of 0.05, the critical value ($T_c$) is 0.507. Calculate ($T_t$) as follows:

For Low Outlier

$$T_t = \frac{(X_2 - X_1)}{(X_7 - X_1)}$$

For High Outlier

$$T_t = \frac{(X_7 - X_6)}{(X_7 - X_1)}$$

Where:
$X_1$ = test result being tested as low outlier
$X_2$ = test result adjacent to $X_1$, after all the test results are ordered from smallest to largest
$X_6$ = test result adjacent to the largest test result
$X_7$ = test result being tested as high outlier

$X_1$ or $X_7$ is an outlier if $T_t$ is greater than $T_c$.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

5. PACKAGING

5.1 Packing and marking. Packing and marking shall be in accordance with MIL-STD-652, except that all propellant designated for use as reference shall be packed level A.

6. NOTES

6.1 Ordering data. Ordering data shall be in accordance with MIL-A-48078 with the following exceptions:

6.1.1 Acquisition requirements. Acquisition requirements of MIL-A-48078 shall apply.

6.1.2 Contract data requirements. One copy each of the Propellant Description Sheet and the Acceptance Test Summary shall be forwarded to each office designated by the contracting officer. Copies of data item descriptions required by the contractor in connection with specific procurement functions should be obtained from the procuring activity.

6.2 Proving ground test summary (see Table IV).

6.3 Drawings. Drawings listed in Section 2 of this specification under the heading US Army Armament Research and Development Command (ARRADCOM) may also include drawings prepared by, and identified as, Edgewood Arsenal, Frankford Arsenal, Rock Island Arsenal or Picatinny Arsenal drawings. Technical data originally prepared by these activities is now under the custodianship of ARRADCOM.

6.4 Surveillance sample. Samples shall be forwarded to US Army Armament Research and Development Command, Dover, NJ 07801, ATTN: DRDAR-LCE-MP for the propellant surveillance test program in accordance with MIL-STD-652.

6.5 Initial production lots. The initial production lots represent the first ten consecutive lots from each manufacturer which have been produced and met the acceptance criteria of the specification. Throughout production, if 3 consecutive lots fail on first test, testing shall revert back to the initial production plan. Lapse in production of 90 days or more shall cause testing to revert back to initial production plan.

6.6 Changes from previous issue. Asterisks are not used in this revision to identify changes with respect to the previous issue due to the extensiveness of the changes.



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

TABLE IV
PROVING GROUND TEST SUMMARY

| Test Phase | Test Parameter | Zone | Temperature (°F) | Sample Size Cal | Sample Size Test | Velocity Reqts service Vel (fps) | Velocity Reqts Std Dev (fps) | Pressure Reqts IMP (psi) | Pressure Reqts Avg press (psi) |
|---|---|---|---|---|---|---|---|---|---|
| Charge Establishment | | 2 | 70 | 3 | 9 | 2310 | N/A | N/A | N/A |
| | | 3 | 70 | 3 | 9 | 3000 | N/A | N/A | N/A |
| Uniformity | | 3 | -50* | N/A | 10 | N/A | N/A | N/A | N/A |
| | | 2 | 70* | 10 | 10 | 2310 | N/A | N/A | N/A |
| | | 3 | 70* | 10 | 10 | 3000 | 7.9 | N/A | 48,400 |
| | | 2 | 70** | 7 | 7 | 2310 | N/A | N/A | N/A |
| | | 3 | 70** | 7 | 7 | 3000 | 7.9 | N/A | 48,400 |
| | | 3 | 145*** | N/A | 10 | N/A | N/A | 58,000 | N/A |

*Initial production
**Subsequent production
***Initial production or when required by paragraph 4.5.1.2.2





Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

Custodian:
Army-AR

Preparing Activity:
Army-AR
Project Number 1376-A173



Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

FOLD

DEPARTMENT OF THE ARMY

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE $300

NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

**BUSINESS REPLY CARD**

FIRST CLASS PERMIT NO. 12062 WASHINGTON D. C.

POSTAGE WILL BE PAID BY THE DEPARTMENT OF THE ARMY

COMMANDER
US ARMY ARMAMENT RESEARCH & DEVELOPMENT COMMAND
ATTN: DRDAR-QAR
DOVER, NJ 07801

FOLD

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.

# STANDARDIZATION DOCUMENT IMPROVEMENT PROPOSAL

**INSTRUCTIONS:** This form is provided to solicit beneficial comments which may improve this document and enhance its use. DoD contractors, government activities, manufacturers, vendors, or other prospective users of the document are invited to submit comments to the government. Fold on lines on reverse side, staple in corner, and send to preparing activity. Attach any pertinent data which may be of use in improving this document. If there are additional papers, attach to form and place both in an envelope addressed to preparing activity. A response will be provided to the submitter, when name and address is provided, within 30 days indicating that the 1426 was received and when any appropriate action on it will be completed.
**NOTE:** This form shall not be used to submit requests for waivers, deviations or clarification of specification requirements on current contracts. Comments submitted on this form do not constitute or imply authorization to waive any portion of the referenced document(s) or to amend contractual requirements.

DOCUMENT IDENTIFIER *(Number)* AND TITLE

MIL-P-46230C PROPELLANT M6

NAME OF ORGANIZATION AND ADDRESS OF SUBMITTER

☐ VENDOR ☐ USER ☐ MANUFACTURER

1. ☐ HAS ANY PART OF THE DOCUMENT CREATED PROBLEMS OR REQUIRED INTERPRETATION IN PROCUREMENT USE? ☐ IS ANY PART OF IT TOO RIGID, RESTRICTIVE, LOOSE OR AMBIGUOUS? PLEASE EXPLAIN BELOW.

A. GIVE PARAGRAPH NUMBER AND WORDING

B. RECOMMENDED WORDING CHANGE

C. REASON FOR RECOMMENDED CHANGE(S)

2. REMARKS

SUBMITTED BY *(Printed or typed name and address — Optional)*

TELEPHONE NO.

DATE

DD FORM 1 OCT 76 1426 EDITION OF 1 JAN 72 WILL BE USED UNTIL EXHAUSTED.

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:17Z
Check the source to verify that this is the current version before use.