INCH-POUND

MIL-P-46235A (AR)
AMENDMENT 2
23 March 1993
SUPERSEDING
AMENDMENT 1
30 March 1964

MILITARY SPECIFICATION

PROPELLANT, M26 (T28) FOR USE IN CARTRIDGES M344 AND M346, IN 106MM RIFLES

This Amendment forms a part of Military Specification MIL-P-46235A (MU) dated 1 March 1964, and is approved for use within the US Army Armament Munitions and Chemical Command and is available for use by all Departments and Agencies of the Department of Defense.

PAGE 1

* 2.1: Add the following:

"MIL-STD-286-Propellants, Solids: Sampling, Examination and Testing"

PAGE 2

3.1: Delete "Type II" and substitute "Type I".

* Add paragraph: "3.4 Total graphite. The total graphite content shall not exceed 0.55 percent when determined as specified in paragraph 4.3.2.1."

PAGE 3

4.2.2.1: Delete "115 pounds" and substitute "350 pounds".

* Add the following new paragraphs:

"4.3.2 Graphite content determination.

4.3.2.1 Total graphite content. The total graphite content shall be determined in accordance with Method 308.1 of MIL-STD-286.

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 202610-22T05:18Z
Check the source to verify that this is the current version before use.

4.3.2.2 Graphite determination in propellant composition. The percent graphite in the propellant composition shall be calculated as follows:

Total graphite percent, minus percent graphite added (glazed, equals percent graphite in propellant composition."

PAGE 4

* 6.4: Delete paragraphs 6.4, 6.4.1 and 6.4.2 in their entirety and substitute the following:

"6.4 Reliability testing. The following tests shall be performed on the first five lots which have been submitted for acceptance and have been accepted. If any of the lots fail, additional lots shall be tested until information is obtained on a total of five accepted lots. The tests shall be for informational purposes only.

6.4.1 A uniformity series shall be performed on seven rounds which were conditioned for a minimum of 24 hours at minus 65 degrees F. Firing shall be performed at ambient conditions. The shells shall be inert loaded.

6.4.2 A uniformity series shall be performed on seven rounds which were conditioned for a minimum of 15 days at 160 degrees F. Firing shall be performed at ambient conditions. The shells shall be inert loaded.

6.4.3 A uniformity series shall be performed on seven rounds which were conditioned for a minimum of 24 hours at 140 degrees F. Firing shall be conducted at 140 degrees F".

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:18Z
Check the source to verify that this is the current version before use.

The margins of this amendment are marked with an asterisk or vertical lines to indicate where changes (additions, modifications, corrections, deletions) from the previous amendment were made. This was done as a convenience only, and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evaluate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous amendment.

Custodian:
Army-AR

Preparing activity:
Army-AR

(Project 1375-A495)

Source: https://assist.dla.mil -- Downloaded: 2026-10-22T05:18Z
Check the source to verify that this is the current version before use.