INCH-POUND

MIL-DTL-22529D
AMENDMENT 1
30 APRIL 1997

MILITARY SPECIFICATION

GROMMET, EDGING

This amendment forms a part of MIL-DTL-22529D, dated 6 JUNE 1996, and is approved for use by all Departments and Agencies of the Department of Defense.

PAGE 3

Add paragraph 3.2.6.

3.2.6 Salt spray (corrosion). This requirement is for MIL-DTL-22529/2 only. The grommet shall show no evidence of corrosion after subjection to salt spray (corrosion) test specified in 4.2.10.

PAGE 8

Add paragraph 4.2.10.

4.2.10 Salt spray (corrosion)test. Grommets shall be tested in accordance with MIL-STD-202 Method 101. The following details and exceptions shall apply.

a. Test samples shall be prepared by cutting approximately a seven inch length of grommet using MFE 100 shears. Then cut approximately one inch off the opposite end from the first cut, so that both ends are freshly cut.

b. The samples shall not be mounted, but shall be suspended from the top of the chamber using waxed twine or string, glass rod or glass cord.

c. The samples shall be tested for 96 hours.

Custodians:
Navy - AS
Air Force - 99

Preparing Activity:
DLA-IS

(Project 5325-0374)

Review activity:
Air Force - 82

AMSC N/A FSC 5325

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-19T12:53Z
Check the source to verify that this is the current version before use.