MIL-M-14F
AMENDMENT-4
15 August 1961
SUPERSEDING
Amendment-3
29 June 1961

MILITARY SPECIFICATION

MOLDING PLASTICS AND MOLDED PLASTIC PARTS: THERMOSETTING

This amendment forms a part of Military Specification MIL-M-14F, dated 15 January 1960, has been approved by the Department of Defense and is mandatory for use by the Departments of the Army, the Navy, and the Air Force.

Pages 1 and 2, paragraph 1.2: Add the following type under "Diallyl phthalate resin":

"Type SDG-F - Glass fiber filler, flame resistant."

Page 2, paragraph 3.1.1, last sentence: Delete.

Page 2, second paragraph numbered 3.1.2: Delete.

Page 3, footnote 1 at bottom of page, line 1: After "MAI-30" insert "MAI-60".

Page 3, paragraph 4.1: Delete and substitute:

"4.1 The supplier is responsible for the performance of all inspection requirements as specified herein. Except as otherwise specified, the supplier may utilize his own or any other inspection facilities and services acceptable to the Government. Inspection records of the examination and tests shall be kept complete and available to the Government as specified in the contract or order. The Government reserves the right to perform any of the inspections set forth in the specification where such inspections are deemed necessary to assure supplies and services conform to prescribed requirements."

Page 3, paragraph 4.2: Delete "(Not required for Army Ordnance Corps procurement.)" and "Statement of identity values (by the manufacturer (see 6.3.1)). (For Army Ordnance Corps procurement only.)"

Page 8, table II, Type MAI-30: Delete "175" for "Arc resistance" and substitute "160".

Page 9, table II, Type MAI-30: Delete "7,500" for "Tensile strength" and substitute "6,000".

FSC 9330

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:55Z
Check the source to verify that this is the current version before use.

Pages 12 and 13, table III: Add the following column for type SDG-F:

Property to be tested	"Type SDG-F
Arc resistance	-----
Compressive strength, endwise	-----
Dielectric constant:	
At 1 kilocycle	-----
At 1 megacycle	-----
Dielectric strength:	
Short-time test	-----
Step-by-step test	-----
Short-time test	-----
Step-by-step test	-----
Dielectric breakdown:	
Short-time test	-----
Step-by-step test	-----
Short-time test	-----
Step-by-step test	-----
Flame resistance:	
Ignition time	90
Burning time	90
Flexural strength face	-----
Heat-distortion temperature, side	-----
Impact strength:	
Face	-----
Side	-----
Tensile strength	-----
Water absorption	-----
Heat resistance	-----
Dimensional stability (high temperature)	-----
Volume resistance	5,000
Surface resistance	5,000"

Page 21: Add the following new paragraph:

"4.6 Flame resistance.- Flame resistance shall be determined in accordance with method 2032.2 of Specification L-P-406. Specimens 1/2 inch by 1/2 inch by 5 inches shall be tested."

Pages 23 and 24, paragraph 6.3.1: Delete.

Page 26, paragraph 10.1: Delete "not applicable for Army Ordnance Corps procurements)."

Custodians:
Army - SigC
Navy - Ships

Preparing activity:
Navy - Ships
(Project 9330-0138)

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:55Z
Check the source to verify that this is the current version before use.