INCH-POUND

MIL-M-14H
AMENDMENT 2
28 May 1991
SUPERSEDING
AMENDMENT 1
7 November 1990

MILITARY SPECIFICATION SHEET

MOLDING COMPOUNDS, THERMOSETTING

This amendment forms a part of MIL-M-14H, dated 2 April 1990, and is approved for use by all Department and Agencies of the Department of the Defense.

PAGE 4

Para. 3.2.1, first line: Delete "every 5 years".

PAGE 5

Para. 3.6: Delete and substitute:

"3.6 Compound. The compound shall consist of a filler impregnated or intimately combined with a thermosetting condensation or polymerization product binder, processed to conform to this specification. Unless otherwise specified herein, all material incorporated in the products covered by this specification shall be new and may be fabricated using materials produced from recovered materials to the maximum extent practicable without jeopardizing the intended use. The term "recovered materials" means materials which have been collected or recovered from solid waste and reprocessed to become a source of raw materials, as opposed to virgin raw materials. Material shall be free from foreign substances. None of the above shall be interpreted to mean that the use of used products is allowed under this specification unless otherwise specifically specified."

AMSC N/A FSC 9330
DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:54Z
Check the source to verify that this is the current version before use.

PAGE 7

Para. 4.5.1.3, second line: Delete "post-core", and substitute "postcure".

PAGE 8

* Table I, under "Impact strength..": Delete and substitute:

Property to be tested-mechanical/physical	Test method		Specimens		Conditioning procedure (see 4.5.1.5)	Unit of value
	ASTM	Modified by	Form and dimension	Number tested		
Impact Strength						
Side 2/	D256	-	As per ASTM D256	5	E-48/50 + C-96/23/50	ft-lb/in notch (min. average)
Face 3/ 4/	D256	-	As per ASTM D256	5	E-48/50 + C-96/23/50	ft-lb/in notch (min. average)

* Table I, Footnotes: Add the following:

3/ The face of the test specimen is that area formed by the top or bottom force plug.

4/ When specified.

PAGE 9

Table II, "Dielectric constant" and "Dissipation factor", under column "Form and dimension": Delete "4-inch disc, 1/8 inch", and substitute "2-inch disc, 1/8 inch".

PAGE 10

Table II, "Comparative track index", under "Form and dimension": Delete "4-inch disc, 1/8", and substitute "2-inch disc, 1/8 inch".

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:54Z
Check the source to verify that this is the current version before use.

PAGE 11

Table III, "Flame resistance: Burning time", under column "Unit of value": Delete "minimum", and substitute "maximum".

PAGE 12

Table IV, "Comparative track index", under column "Form and dimension": Delete "4-inch disk, 1/8 inch", and substitute "2-inch disk, 1/8 inch".

Table IV, "Dielectric strength," under column "Number tested": Delete "3", and substitute "5".

Table IV, "Water extract conductance", last line, under column "Conditioning procedure": Add "E144/71".

PAGE 13

Para. 4.5.2.4, third line: Delete "ASTM D 290", and substitute "ASTM D 790".

PAGE 14

* Under "Temperature": Delete and substitute:

Type	Temperature °C
SDG & SDG-F	100
GDI-30 & GDI-30F	130
MDG & MDG-F	90
SIG & SIG-F	140
GII-30 & GII-30F	160
MIG & MIG-F	120

All other materials for heat resistance temperature are to be determined by individual laboratories and returned to NAVSEA for consideration.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:54Z
Check the source to verify that this is the current version before use.

PAGE 16

* Para. 4.5.2.8: Add a third line, "Example:"

PAGE 18

* Para. 4.5.2.10, second line: Delete and substitute "using the vertical or horizontal burning test and either 1/16-, 1/8- or 1/4-inch thick specimens. Record as"

PAGE 20

Table VI: Delete and substitute (page 5 attached)

PAGE 21

Table VI: Delete and substitute (page 6 attached)

PAGE 22

Table VI, fifth column, title: Delete "1879A", and substitute "18794A"

NOTE: The margins of this amendment are marked with asterisks to indicate where changes (additions, modifications, corrections, deletions) from the previous issue were made. This was done as a convenience only and the Government assumes no liability whatsoever for any inaccuracies in these notations. Bidders and contractors are cautioned to evalutate the requirements of this document based on the entire content irrespective of the marginal notations and relationship to the last previous issue.

Custodians:
Army - ME
Navy - SH
Air Force - 20

Review activities:
Army - ER, MI, MR, AR, EA
Navy - AS, OS
DLA - GS

User activities:
Navy - YD, EC

Preparing activity:
Navy - SH
(Project 9330-1213)

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:54Z
Check the source to verify that this is the current version before use.

TABLE VI. *Supersession data.*

Resin	Compound type	Specification sheets of MIL-M-14H	MIL-M-14G	MIL-M-18794A	MIL-M 19061	MIL-M 19536A	MIL-M-19833A	MIL-M-21556	MIL-M-21699	MIL-M-24325
Phenolic	CFG	MIL-M-14/1	X							
"	CFI-5	"	X							
"	CFI-10	"	X							
"	CFI-20	"	X							
"	CFI-30	"	X							
"	CFI-40	"	X							
"	MFA-30[1]	"	X					X		
"	MFE	MIL-M-14/2	X							
"	MFG[1]	"	X							
"	MFH	"	X							
"	MFI-10[1]	"	X							
"	MFI-20[1]	"	X							
"	GPG	"	X							
"	GPI-5	"	X							
"	GPI-10	"	X							
"	GPI-20	"	X							
"	GPI-30	"	X							
"	GPI-50	"	X							
"	GPI-100	"	X			X				
Melamine	CMG	MIL-M-14/3	X							
"	CMI-5	"	X							
"	CMI-10	"	X							
"	MME	"	X							
"	MMI-5	"	X		X					
"	MMI-30	"	X							

See footnote at end of table.

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:54Z
Check the source to verify that this is the current version before use.

TABLE VI. *Supersession data – Continued.*

Resin	Compound type	Specification sheets of MIL-M-14H	MIL-M-14G	MIL-M-18794A	MIL-M-19061	MIL-M 19536A	MIL-M-19833A	MIL-M-21556	MIL-M-21699	MIL-M-24325
Polyester	MAG	MIL-M-14H/4	X							
"	MAI-30	"	X						X	
"	MAI-60	"	X							
"	MAT-30	"	X							
Diallyl	GII-30	MIL-M-14H/5								
iso-	GII-30F	"								
phthalate										
"	MIG	"								
"	MIG-F	"								
"	SIG	"								
"	SIG-F	"								
Diallyl	GDI-30	MIL-M-14H/6	X				X			
ortho-										
phthalate	GDI-30F	"	X				X			
"	GDI-300	"								
"	GDI-300F	"								
"	MDG	"	X							
"	MDG-F	"	X							
"	SDG	"	X	X						
"	SDG-F	"	X							
"	SDI-5	"	X	X						
"	SDI-30	"	X	X						
Silicone	MSG	MIL-M-14H/7	X							
"	MSI-30	"	X							

Source: https://assist.dla.mil -- Downloaded: 2026-10-15T15:54Z
Check the source to verify that this is the current version before use.